

ASX Announcement

Hatches Creek Tungsten Gold Copper Project Exceptional Final RC Drilling Results

Highlights

- Assay results for an additional 14 RC drill holes (HCRC038 to 50) received from the 33 hole program completed in August 2017
- All results for the drilling program completed in August 2017 have now been received
- Significant intercepts include;
 - High grade intercepts from HCRC049 (Pioneer) of 1 m at 10.37% WO₃, 0.59 g/t Au and 1.41% Cu from 46 m and 1 m at 6.6% WO₃, 0.29 g/t Au and 0.29% Cu from 86 m
 - HCRC041 (Black Diamond) of 10 m at 0.48% WO₃, from 29 m, including 3 m at 1.42% WO₃ from 36 m
 - HCRC042 (Black Diamond) of 4 m at 0.53% WO₃, from 17 m, including 1 m at 1.64% WO₃ from 19 m
 - HCRC044 (Green Diamond) of 1 m at 3.90% WO₃ from 93 m
 - Mineralised zone in HCRC045 (Bonanza) of 14 m at 0.39% WO₃ from 32 m including 1 m at 1.23% WO₃ from 32 m and 1 m at 2.11% WO₃ from 42 m
 - HCRC047 (Pioneer) of 7 m at 1.16% WO₃ and 0.81 g/t Au from 38 m, including 1 m at 3.36% WO₃ and 5.32 g/t Au
- These results are in addition to the 19 holes previously reported
- 9 of these 14 holes have intersected high grade (>1% WO₃) tungsten mineralisation
- Initial drilling results at the Black Diamond, Green Diamond and Bonanza prospects are highly encouraging as most holes have hit multiple mineralised structures
- Results for the entire program will now be compiled and maiden Mineral Resource estimates will be undertaken for the Pioneer, Treasure and Hit or Miss prospects

GWR Group Limited (ASX: GWR) ("GWR" or "the Company") is pleased to announce that it has received assay results for an additional 14 RC holes from the 33 hole program completed at the Hatches Creek Polymetallic (tungsten, gold, copper) Project in the Northern Territory (Figures 1 and 2).

The Company is now compiling all data from the entire program completed in August 2017 and this ASX release has been made on the basis that the results achieved since the announcement on 12th October 2017 are considered to be material.

Table 1 lists all of the holes completed in August 2017 and the results in this ASX release are from the Black Diamond, Green Diamond, Bonanza, Pioneer (Figure 3) and Treasure prospects (Figure 4). All significant intercepts are listed in Table 2 and all assay results are provided in Appendix 1. The significant intercepts achieved at Black Diamond, Green Diamond and Bonanza clearly demonstrate that widespread mineralisation is present.

In addition to the significant tungsten mineralisation intersected, anomalous and significant copper is also present with sporadic molybdenite confirming the polymetallic nature of the mineralisation and at Pioneer, gold mineralisation is also present.

A total of 4 RC drill holes (HCRC046 to HCRC049) were completed at Pioneer and this combined with the RC drilling completed in 2016 has tested the mineralisation over a strike length of approximately 250 m with four lines of holes on an approximate 60 m line spacing (Figure 2). With the exception of HCRC048, which intersected old mine workings all holes from the current program intersected significant tungsten gold and copper with HCRC047 and HCRC049 obtaining high grade intercepts.

- **HCRC047, 7 m at 1.16% WO₃ and 0.81 g/t Au from 38 m, including 1 m at 3.36% WO₃ and 5.32 g/t Au**
- **HCRC049, 1 m at 10.37% WO₃, 0.59 g/t Au and 1.41% Cu from 46 m and 1 m at 6.6% WO₃, 0.29 g/t Au and 0.29% Cu from 8 6m**

At Treasure significant mineralisation has now been confirmed over a strike length of 350 m and this is currently open especially to the south where multiple mineralised structures were intersected in HCRC050 over a down hole width of 105 m or estimated true width of approximately 40 m. This corresponds with similar widths obtained in HCRC013, HCRC014, HCRC034 and HCRC035.

At Black Diamond a single line of RC drill holes was completed with all holes obtaining significant results and individual high grade intercepts of >1% WO₃. HCRC041 and HCRC043 also intersected multiple mineralised structures.

A single hole HCRC044 was completed at Green Diamond and this hole yielded high grade WO₃ (>1%), Cu (>1%) and significant Mo intercepts again over multiple mineralised structures.

A single hole was also drilled at Bonanza and this also identified multiple mineralised structures with high grade mineralisation (>1% WO₃) also intersected.

Results for the entire program are now being compiled and a maiden Mineral Resource estimate will be undertaken at the Hit or Miss, Treasure and Pioneer prospects




Figure 1 - Hatches Creek location plan

**Table 1
Drill Hole Collar Summary**

Prospect	Hole #	East (MGA)	North (MGA)	RL	Depth	Azimuth	Dip	ASX Release
Hit or Miss	HCRC019	519574.80	7685741.90	430.11	102	90	-60	14/09/2017
Hit or Miss	HCRC020	519535.12	7685739.81	430.12	102	90	-60	14/09/2017
Hit or Miss	HCRC021	519495.10	7685741.48	430.38	132	90	-60	12/10/2017
Hit or Miss	HCRC022	519655.66	7685698.75	426.89	102	90	-60	12/10/2017
Hit or Miss	HCRC023	519613.59	7685707.58	427.99	102	90	-60	12/10/2017
Hit or Miss	HCRC024	519580.81	7685711.60	428.63	102	90	-60	14/09/2017
Hit or Miss	HCRC025	519703.25	7685689.10	432.90	144	90	-60	14/09/2017
Hit or Miss	HCRC026	519640.62	7685799.18	444.07	102	90	-60	12/10/2017
Hit or Miss	HCRC027	519598.20	7685798.88	442.17	108	90	-60	12/10/2017
Hit or Miss	HCRC028	519561.51	7685800.72	444.66	102	90	-60	14/09/2017
Hit or Miss	HCRC029	519517.84	7685797.46	441.13	86	90	-60	12/10/2017
Hit or Miss	HCRC030	519473.00	7685815.74	432.78	108	90	-60	12/10/2017
Silver Granite	HCRC031	519317.15	7685614.37	447.74	102	180	-60	12/10/2017
Kangaroo	HCRC032	518978.30	7685958.33	458.30	90	180	-60	12/10/2017
Kangaroo	HCRC033	518778.81	7685913.75	456.38	84	180	-60	12/10/2017
Treasure	HCRC034	519833.38	7686824.30	431.28	138	70	-60	12/10/2017
Treasure	HCRC035	519849.83	7686863.12	425.06	102	90	-50	12/10/2017
Treasure	HCRC036	519909.12	7686897.43	424.59	132	270	-60	12/10/2017
Treasure	HCRC037	519835.37	7687002.85	427.04	138	90	-60	12/10/2017
Treasure	HCRC038	519830.63	7687099.08	440.71	132	90	-60	08/11/2017
Treasure	HCRC039	519790.70	7687098.19	436.06	138	90	-60	08/11/2017
Treasure	HCRC040	519820.21	7687060.71	439.98	57	90	-60	08/11/2017
Black Diamond	HCRC041	519537.83	7690603.53	433.69	54	360	-60	08/11/2017
Black Diamond	HCRC042	519570.20	7690574.89	432.51	102	360	-60	08/11/2017
Black Diamond	HCRC043	519569.73	7690539.22	430.30	132	360	-60	08/11/2017
Green Diamond	HCRC044	519621.54	7690285.45	414.26	96	360	-60	08/11/2017
Bonanza	HCRC045	519329.65	7690389.98	460.96	108	360	-60	08/11/2017
Pioneer	HCRC046	518571.78	7692110.52	398.22	72	360	-60	08/11/2017
Pioneer	HCRC047	518569.30	7692091.04	398.77	102	360	-60	08/11/2017
Pioneer	HCRC048	518671.23	7692137.03	403.48	11	360	-60	08/11/2017
Pioneer	HCRC048A	518670.96	7692131.56	403.23	12	360	-60	08/11/2017
Pioneer	HCRC049	518683.55	7692100.45	401.59	114	360	-60	08/11/2017
Treasure	HCRC050	519929.09	7686849.60	431.43	180	230	-50	08/11/2017
TOTAL					3388			

Table 2
Significant RC Drill Hole Intercepts

Prospect	Hole#	East (MGA 94)	North (MGA 94)	RL	Dip/Azi	From (m)	To (m)	Interval (m)	Au (ppm)	WO ₃ (%)	Cu (%)	Mo (ppm)	
Treasure	HCRC038	519830.63	7687099.08	440.71	-60/90	4	6	2	N/A	0.66	0.01	26	
						25	27	2		0.12	0.02	32	
						68	69	1		0.58	0.01	38	
	HCRC039	519790.70	7687098.19	436.06	-60/90	NO SIGNIFICANT INTERCEPT							
	HCRC040	519820.21	7687060.71	439.98	-60/90	44	45	1		0.27	0.03	20	
				HIT MINE WORKINGS AT 51.5 M AND ABANDONED									
Black Diamond	HCRC041	519537.83	7690603.53	433.69	-60/360	0	2	2		0.32	0.02	11	
						2	3	1	NO SAMPLE				
						3	4	1		0.34	0.06	19	
						8	11	3		0.20	0.06	13	
						13	14	1		0.21	0.03	11	
						19	23	4		0.14	0.02	4	
						29	39	10		0.48	0.03	12	
					INCLUDING		36	39	3		1.42	0.01	31
						46	47	1		0.01	0.52	12	
	HCRC042	519570.20	7690574.89	432.51	-60/360	17	21	4		0.53	0.10	9	
					INCLUDING		19	20	1		1.64	0.08	16
	HCRC043	519569.73	7690539.22	430.30	-60/360	7	9	2		0.26	0.08	19	
						15	18	3		0.13	0.11	9	
						51	52	1		0.36	0.01	7	
						60	62	2		0.95	0.05	19	
					INCLUDING		60	61	1		1.62	0.09	27
						113	115	2		0.33	0.10	5	
				INCLUDING		113	114	1		0.51	0.09	8	
					119	120	1		0.37	0.00	13		
Green Diamond	HCRC044	519621.54	7690285.45	414.26	-60/360	0	1	1		1.49	0.06	151	
						19	25	6		0.08	0.36	20	
						45	46	1		0.49	0.18	45	
						54	63	9		0.07	0.65	36	
					INCLUDING		57	58	1		0.49	0.24	59
					INCLUDING		59	60	1		0.02	2.55	22
						68	70	2		0.56	1.68	275	
					INCLUDING		68	69	1		0.02	3.09	48
					INCLUDING		69	70	1		1.10	0.27	501
						90	91	1		1.24	0.09	1040	
					93	94	1		3.90	0.06	3650		
Bonanza	HCRC045	519329.65	7690389.98	460.96	-60/360	6	11	5		0.10	0.00	8	
						32	37	5		0.49	0.02	14	
					INCLUDING		32	33	1		1.23	0.00	33
						42	46	4		0.69	0.04	8	
					INCLUDING		42	43	1		2.11	0.03	19
				MINERALISED ZONE		32	46	14		0.39	0.02	9	

Prospect	Hole#	East (MGA 94)	North (MGA 94)	RL	Dip/Azi	From (m)	To (m)	Interval (m)	Au (ppm)	WO ₃ (%)	Cu (%)	Mo (ppm)	
Pioneer	HCRC046	518571.78	7692110.52	398.22	-60/360	0	3	3	0.13	0.13	0.13	42	
						5	6	1	0.68	0.05	0.07	8	
	HCRC047	518569.30	7692091.04	398.77	-60/360	0	1	1	1.05	0.27	0.09	38	
						38	45	7	0.81	1.16	0.06	97	
				INCLUDING		38	39	1	0.09	4.00	0.28	152	
				INCLUDING		43	44	1	5.32	3.36	0.02	429	
						59	60	1	0.93	0.27	0.09	49	
						66	68	2	0.02	0.39	0.20	13	
						77	79	2	0.02	0.19	0.02	4	
						86	87	1	0.01	1.92	0.10	44	
	HCRC048	518670.96	7692131.56	403.23	-60/360	7	8	1	0.82	0.05	0.00	3	
					HIT MINE WORKINGS AT 12 M AND ABANDONED								
	HCRC049	518683.55	7692100.45	401.59	-60/360	24	28	4	1.88	0.34	0.04	41	
				INCLUDING		24	25	1	4.52	0.07	0.07	107	
						26	28	2	1.36	0.64	0.03	18	
						46	47	1	0.59	10.37	1.41	22	
						72	76	4	0.13	0.27	0.44	46	
				INCLUDING		75	76	1	0.26	0.54	1.14	26	
						86	87	1	0.29	6.60	0.29	419	
						95	97	2	0.30	1.16	0.10	272	
			ZONE		86	97	11	0.10	0.87	0.09	96		
Treasure	HCRC050	519929.09	7686849.60	431.43	-50/230	0	3	3		0.18	0.08	43	
						38	39	1		0.34	0.03	66	
						63	65	2		0.34	0.15	90	
				INCLUDING		64	65	1		0.56	0.22	102	
						74	76	2		1.07	0.01	234	
				INCLUDING		74	75	1		1.75	0.01	232	
						86	90	4		0.55	0.03	53	
				INCLUDING		88	90	2		0.99	0.05	61	
						114	119	5		0.15	0.06	42	
						124	129	5		0.35	0.10	244	
						137	139	2		0.19	0.16	565	
						152	158	6		0.43	0.09	349	
				INCLUDING		152	153	1		0.77	0.09	25	
				INCLUDING		156	158	2		0.72	0.08	644	




Figure 2 - Hatches Creek prospect locations




Figure 3 - Pioneer prospect drill hole collars




Figure 4 - Treasure prospect drill hole collars

For further information:

Craig Ferrier

Chief Executive Officer

Ph: +61 8 9322 6666

E: craigf@gwrgroup.com.au

Competent Persons Statement

The information in this report which relates to Exploration Targets, Exploration Results and Mineral Resources or Ore Reserves is based on information compiled by Mr Allen Maynard, who is a Member of the Australian Institute of Geosciences ("AIG"), a Corporate Member of the Australasian Institute of Mining & Metallurgy ("AusIMM") and independent consultant to the Company. Mr Maynard is the Director and principal geologist of Al Maynard & Associates Pty Ltd and has over 35 continuous years of exploration and mining experience in a variety of mineral deposit styles. Mr Maynard has sufficient experience which is relevant to the style of mineralisation and type of deposit under consideration and to the activity which he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the "Australasian Code for reporting of Exploration Results, Exploration Targets, Mineral Resources and Ore Reserves" (JORC Code). Mr Maynard consents to inclusion in the report of the matters based on this information in the form and context in which it appears.

Appendix 1
Assay Results

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC038	0	1		0.03	0.01	3
Treasure	HCRC038	1	2		0.02	0.01	2
Treasure	HCRC038	2	3		0.01	0.01	X
Treasure	HCRC038	3	4		0.01	0.01	3
Treasure	HCRC038	4	5		0.36	0.01	16
Treasure	HCRC038	5	6		0.97	0.01	37
Treasure	HCRC038	6	7		0.06	0.01	9
Treasure	HCRC038	7	8		0.05	0.01	5
Treasure	HCRC038	8	9		0.03	0.01	5
Treasure	HCRC038	9	10		0.02	0.01	5
Treasure	HCRC038	10	11		0.02	0.01	5
Treasure	HCRC038	11	12		0.01	0.01	5
Treasure	HCRC038	12	13		0.00	0.00	2
Treasure	HCRC038	13	14		0.01	0.00	3
Treasure	HCRC038	14	15		0.02	0.00	3
Treasure	HCRC038	15	16		0.02	0.01	7
Treasure	HCRC038	16	17		0.01	0.01	4
Treasure	HCRC038	17	18		0.02	0.01	4
Treasure	HCRC038	18	19		0.02	0.01	9
Treasure	HCRC038	19	20		0.01	0.01	4
Treasure	HCRC038	20	21		0.02	0.02	7
Treasure	HCRC038	21	22		0.02	0.04	11
Treasure	HCRC038	22	23		0.01	0.03	6
Treasure	HCRC038	23	24		0.02	0.02	5
Treasure	HCRC038	24	25		0.03	0.03	3
Treasure	HCRC038	25	26		0.13	0.02	38
Treasure	HCRC038	26	27		0.11	0.01	26
Treasure	HCRC038	27	28		0.04	0.01	36
Treasure	HCRC038	28	29		0.03	0.01	42
Treasure	HCRC038	29	30		0.02	0.01	4
Treasure	HCRC038	30	31		0.04	0.01	9
Treasure	HCRC038	31	32		0.07	0.01	6
Treasure	HCRC038	32	33		0.04	0.01	8
Treasure	HCRC038	33	34		0.04	0.01	18
Treasure	HCRC038	34	35		0.03	0.01	10
Treasure	HCRC038	35	36		0.06	0.01	6
Treasure	HCRC038	36	37		0.03	0.02	11
Treasure	HCRC038	37	38		0.04	0.02	9
Treasure	HCRC038	38	39		0.02	0.01	5
Treasure	HCRC038	39	40		0.02	0.02	4
Treasure	HCRC038	40	41		0.03	0.01	4
Treasure	HCRC038	41	42		0.01	0.01	2
Treasure	HCRC038	42	43		0.02	0.02	2
Treasure	HCRC038	43	44		0.03	0.01	2
Treasure	HCRC038	44	45		0.02	0.01	2
Treasure	HCRC038	45	46		0.02	0.01	X
Treasure	HCRC038	46	47		0.01	0.01	2
Treasure	HCRC038	47	48		0.02	0.02	2
Treasure	HCRC038	48	49		0.01	0.01	2
Treasure	HCRC038	49	50		0.02	0.01	4

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC038	50	51		0.02	0.01	3
Treasure	HCRC038	51	52		0.05	0.02	3
Treasure	HCRC038	52	53		0.01	0.00	4
Treasure	HCRC038	53	54		0.01	0.00	5
Treasure	HCRC038	54	55		0.01	0.00	3
Treasure	HCRC038	55	56		0.01	0.00	3
Treasure	HCRC038	56	57		0.01	0.01	3
Treasure	HCRC038	57	58		0.03	0.01	8
Treasure	HCRC038	58	59		0.02	0.01	3
Treasure	HCRC038	59	60		0.02	0.02	5
Treasure	HCRC038	60	61		0.02	0.01	6
Treasure	HCRC038	61	62		0.02	0.02	4
Treasure	HCRC038	62	63		0.02	0.02	5
Treasure	HCRC038	63	64		0.03	0.03	5
Treasure	HCRC038	64	65		0.02	0.01	7
Treasure	HCRC038	65	66		0.01	0.00	4
Treasure	HCRC038	66	67		0.01	0.00	3
Treasure	HCRC038	67	68		0.02	0.01	8
Treasure	HCRC038	68	69		0.58	0.01	38
Treasure	HCRC038	69	70		0.03	0.00	6
Treasure	HCRC038	70	71		0.02	0.00	8
Treasure	HCRC038	71	72		0.01	0.02	4
Treasure	HCRC038	72	73		0.02	0.03	5
Treasure	HCRC038	73	74		0.01	0.01	3
Treasure	HCRC038	74	75		0.01	0.00	3
Treasure	HCRC038	75	76		0.01	0.01	4
Treasure	HCRC038	76	77		0.01	0.00	7
Treasure	HCRC038	77	78		0.00	0.00	8
Treasure	HCRC038	78	79		0.00	0.00	5
Treasure	HCRC038	79	80		0.01	0.00	5
Treasure	HCRC038	80	81		0.01	0.00	8
Treasure	HCRC038	81	82		0.01	0.01	4
Treasure	HCRC038	82	83		0.02	0.00	5
Treasure	HCRC038	83	84		0.01	0.00	5
Treasure	HCRC038	84	85		0.01	0.00	4
Treasure	HCRC038	85	86		0.08	0.00	16
Treasure	HCRC038	86	87		0.01	0.00	4
Treasure	HCRC038	87	88		0.01	0.00	3
Treasure	HCRC038	88	89		0.01	0.00	4
Treasure	HCRC038	89	90		0.01	0.01	4
Treasure	HCRC038	90	91		0.01	0.00	6
Treasure	HCRC038	91	92		0.01	0.00	6
Treasure	HCRC038	92	93		0.01	0.00	5
Treasure	HCRC038	93	94		0.02	0.00	6
Treasure	HCRC038	94	95		0.01	0.00	3
Treasure	HCRC038	95	96		0.01	0.00	4
Treasure	HCRC038	96	97		0.01	0.00	5
Treasure	HCRC038	97	98		0.06	0.00	5
Treasure	HCRC038	98	99		0.01	0.00	3
Treasure	HCRC038	99	100		0.01	0.00	3

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC038	100	101		0.01	0.00	4
Treasure	HCRC038	101	102		0.02	0.01	7
Treasure	HCRC038	102	103		0.08	0.02	19
Treasure	HCRC038	103	104		0.02	0.00	7
Treasure	HCRC038	104	105		0.01	0.00	2
Treasure	HCRC038	105	106		0.01	0.00	X
Treasure	HCRC038	106	107		0.01	0.00	2
Treasure	HCRC038	107	108		0.01	0.00	2
Treasure	HCRC038	108	109		0.02	0.00	2
Treasure	HCRC038	109	110		0.03	0.01	7
Treasure	HCRC038	110	111		0.07	0.08	17
Treasure	HCRC038	111	112		0.03	0.02	11
Treasure	HCRC038	112	113		0.01	0.01	X
Treasure	HCRC038	113	114		0.01	0.00	2
Treasure	HCRC038	114	115		0.01	0.00	3
Treasure	HCRC038	115	116		0.01	0.00	7
Treasure	HCRC038	116	117		0.04	0.00	4
Treasure	HCRC038	117	118		0.01	0.00	2
Treasure	HCRC038	118	119		0.03	0.00	11
Treasure	HCRC038	119	120		0.01	0.00	2
Treasure	HCRC038	120	121		0.04	0.01	5
Treasure	HCRC038	121	122		0.01	0.00	1
Treasure	HCRC038	122	123		0.01	0.01	X
Treasure	HCRC038	123	124		0.01	0.01	X
Treasure	HCRC038	124	125		0.01	0.00	3
Treasure	HCRC038	125	126		0.01	0.00	2
Treasure	HCRC038	126	127		0.01	0.00	3
Treasure	HCRC038	127	128		0.01	0.01	5
Treasure	HCRC038	128	129		0.03	0.00	5
Treasure	HCRC038	129	130		0.00	0.00	1
Treasure	HCRC038	130	131		0.01	0.01	3
Treasure	HCRC038	131	132		0.02	0.00	6
Treasure	HCRC039	0	1		0.02	0.00	3
Treasure	HCRC039	1	2		0.01	0.00	3
Treasure	HCRC039	2	3		0.00	0.00	4
Treasure	HCRC039	3	4		0.01	0.01	3
Treasure	HCRC039	4	5		0.01	0.01	5
Treasure	HCRC039	5	6		0.01	0.01	3
Treasure	HCRC039	6	7		0.01	0.01	3
Treasure	HCRC039	7	8		0.01	0.00	5
Treasure	HCRC039	8	9		0.01	0.01	5
Treasure	HCRC039	9	10		0.01	0.01	8
Treasure	HCRC039	10	11		0.01	0.01	4
Treasure	HCRC039	11	12		0.01	0.01	4
Treasure	HCRC039	12	13		0.01	0.01	5
Treasure	HCRC039	13	14		0.01	0.01	6
Treasure	HCRC039	14	15		0.01	0.01	4
Treasure	HCRC039	15	16		0.00	0.01	4
Treasure	HCRC039	16	17		0.01	0.01	5
Treasure	HCRC039	17	18		0.01	0.00	5

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC039	18	19		0.00	0.00	4
Treasure	HCRC039	19	20		0.00	0.00	5
Treasure	HCRC039	20	21		0.01	0.00	3
Treasure	HCRC039	21	22		0.01	0.00	3
Treasure	HCRC039	22	23		0.02	0.01	4
Treasure	HCRC039	23	24		0.01	0.01	3
Treasure	HCRC039	24	25		0.01	0.00	2
Treasure	HCRC039	25	26		0.01	0.00	3
Treasure	HCRC039	26	27		0.01	0.00	4
Treasure	HCRC039	27	28		0.01	0.00	4
Treasure	HCRC039	28	29		0.01	0.01	4
Treasure	HCRC039	29	30		0.01	0.01	4
Treasure	HCRC039	30	31		0.01	0.01	3
Treasure	HCRC039	31	32		0.01	0.01	5
Treasure	HCRC039	32	33		0.01	0.01	5
Treasure	HCRC039	33	34		0.01	0.02	5
Treasure	HCRC039	34	35		0.01	0.01	3
Treasure	HCRC039	35	36		0.01	0.00	3
Treasure	HCRC039	36	37		0.01	0.01	8
Treasure	HCRC039	37	38		0.01	0.01	2
Treasure	HCRC039	38	39		0.01	0.01	2
Treasure	HCRC039	39	40		0.01	0.01	3
Treasure	HCRC039	40	41		0.01	0.01	2
Treasure	HCRC039	41	42		0.00	0.01	2
Treasure	HCRC039	42	43		0.00	0.01	2
Treasure	HCRC039	43	44		0.01	0.00	4
Treasure	HCRC039	44	45		0.01	0.01	4
Treasure	HCRC039	45	46		0.00	0.00	4
Treasure	HCRC039	46	47		0.00	0.00	2
Treasure	HCRC039	47	48		0.01	0.00	2
Treasure	HCRC039	48	49		0.01	0.00	3
Treasure	HCRC039	49	50		0.02	0.00	3
Treasure	HCRC039	50	51		0.01	0.00	4
Treasure	HCRC039	51	52		0.01	0.00	3
Treasure	HCRC039	52	53		0.01	0.00	3
Treasure	HCRC039	53	54		0.03	0.00	10
Treasure	HCRC039	54	55		0.04	0.01	4
Treasure	HCRC039	55	56		0.01	0.00	3
Treasure	HCRC039	56	57		0.01	0.00	2
Treasure	HCRC039	57	58		0.02	0.01	4
Treasure	HCRC039	58	59		0.01	0.01	3
Treasure	HCRC039	59	60		0.01	0.00	4
Treasure	HCRC039	60	61		0.00	0.00	3
Treasure	HCRC039	61	62		0.01	0.01	3
Treasure	HCRC039	62	63		0.00	0.00	4
Treasure	HCRC039	63	64		0.00	0.01	3
Treasure	HCRC039	64	65		0.00	0.00	2
Treasure	HCRC039	65	66		0.00	0.00	2
Treasure	HCRC039	66	67		0.00	0.00	3
Treasure	HCRC039	67	68		0.00	0.00	36

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC039	68	69		0.00	0.00	24
Treasure	HCRC039	69	70		0.00	0.00	9
Treasure	HCRC039	70	71		0.00	0.00	10
Treasure	HCRC039	71	72		0.00	0.00	5
Treasure	HCRC039	72	73		0.00	0.00	4
Treasure	HCRC039	73	74		0.00	0.00	2
Treasure	HCRC039	74	75		0.00	0.00	3
Treasure	HCRC039	75	76		0.00	0.00	2
Treasure	HCRC039	76	77		0.00	0.00	4
Treasure	HCRC039	77	78		0.00	0.00	5
Treasure	HCRC039	78	79		0.00	0.00	6
Treasure	HCRC039	79	80		0.02	0.01	7
Treasure	HCRC039	80	81		0.01	0.01	5
Treasure	HCRC039	81	82		0.01	0.01	4
Treasure	HCRC039	82	83		0.01	0.00	7
Treasure	HCRC039	83	84		0.02	0.01	12
Treasure	HCRC039	84	85		0.01	0.01	6
Treasure	HCRC039	85	86		0.00	0.01	4
Treasure	HCRC039	86	87		0.01	0.01	10
Treasure	HCRC039	87	88		0.00	0.01	3
Treasure	HCRC039	88	89		0.00	0.01	3
Treasure	HCRC039	89	90		0.00	0.00	2
Treasure	HCRC039	90	91		0.00	0.00	5
Treasure	HCRC039	91	92		0.00	0.00	7
Treasure	HCRC039	92	93		0.01	0.00	4
Treasure	HCRC039	93	94		0.00	0.00	5
Treasure	HCRC039	94	95		0.01	0.01	5
Treasure	HCRC039	95	96		0.01	0.01	4
Treasure	HCRC039	96	97		0.01	0.00	3
Treasure	HCRC039	97	98		0.00	0.00	3
Treasure	HCRC039	98	99		0.00	0.00	2
Treasure	HCRC039	99	100		0.00	0.00	3
Treasure	HCRC039	100	101		0.00	0.00	4
Treasure	HCRC039	101	102		0.01	0.01	5
Treasure	HCRC039	102	103		0.01	0.00	5
Treasure	HCRC039	103	104		0.00	0.01	7
Treasure	HCRC039	104	105		0.01	0.01	5
Treasure	HCRC039	105	106		0.01	0.01	5
Treasure	HCRC039	106	107		0.00	0.00	4
Treasure	HCRC039	107	108		0.00	0.00	2
Treasure	HCRC039	108	109		0.00	0.00	5
Treasure	HCRC039	109	110		0.00	0.00	5
Treasure	HCRC039	110	111		0.00	0.00	14
Treasure	HCRC039	111	112		0.01	0.00	5
Treasure	HCRC039	112	113		0.01	0.00	22
Treasure	HCRC039	113	114		0.00	0.00	6
Treasure	HCRC039	114	115		0.01	0.01	8
Treasure	HCRC039	115	116		0.02	0.01	17
Treasure	HCRC039	116	117		0.01	0.02	9
Treasure	HCRC039	117	118		0.01	0.02	10

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC039	118	119		0.00	0.02	9
Treasure	HCRC039	119	120		0.01	0.01	6
Treasure	HCRC039	120	121		0.01	0.01	17
Treasure	HCRC039	121	122		0.01	0.01	8
Treasure	HCRC039	122	123		0.01	0.02	9
Treasure	HCRC039	123	124		0.01	0.01	6
Treasure	HCRC039	124	125		0.00	0.01	4
Treasure	HCRC039	125	126		0.00	0.00	3
Treasure	HCRC039	126	127		0.00	0.00	4
Treasure	HCRC039	127	128		0.00	0.01	6
Treasure	HCRC039	128	129		0.00	0.01	6
Treasure	HCRC039	129	130		0.01	0.01	7
Treasure	HCRC039	130	131		0.01	0.01	5
Treasure	HCRC039	131	132		0.01	0.01	13
Treasure	HCRC039	132	133		0.01	0.01	13
Treasure	HCRC039	133	134		0.01	0.01	6
Treasure	HCRC039	134	135		0.02	0.00	7
Treasure	HCRC039	135	136		0.01	0.00	6
Treasure	HCRC039	136	137		0.00	0.00	3
Treasure	HCRC039	137	138		0.00	0.01	4
Treasure	HCRC040	0	1		0.01	0.01	3
Treasure	HCRC040	1	2		0.01	0.01	2
Treasure	HCRC040	2	3		0.01	0.01	2
Treasure	HCRC040	3	4		0.00	0.01	3
Treasure	HCRC040	4	5		0.00	0.01	2
Treasure	HCRC040	5	6		0.01	0.01	3
Treasure	HCRC040	6	7		0.01	0.01	4
Treasure	HCRC040	7	8		0.00	0.01	6
Treasure	HCRC040	8	9		0.01	0.02	6
Treasure	HCRC040	9	10		0.00	0.03	4
Treasure	HCRC040	10	11		0.01	0.02	12
Treasure	HCRC040	11	12		0.02	0.01	8
Treasure	HCRC040	12	13		0.02	0.02	5
Treasure	HCRC040	13	14		0.01	0.01	14
Treasure	HCRC040	14	15		0.01	0.02	7
Treasure	HCRC040	15	16		0.01	0.02	12
Treasure	HCRC040	16	17		0.01	0.02	20
Treasure	HCRC040	17	18		0.01	0.03	12
Treasure	HCRC040	18	19		0.01	0.03	3
Treasure	HCRC040	19	20		0.03	0.05	3
Treasure	HCRC040	20	21				
Treasure	HCRC040	21	22		0.01	0.02	3
Treasure	HCRC040	22	23		0.03	0.02	4
Treasure	HCRC040	23	24		0.01	0.01	9
Treasure	HCRC040	24	25		0.02	0.02	4
Treasure	HCRC040	25	26		0.02	0.02	5
Treasure	HCRC040	26	27		0.03	0.03	8
Treasure	HCRC040	27	28		0.02	0.01	9
Treasure	HCRC040	28	29		0.17	0.02	5
Treasure	HCRC040	29	30		0.04	0.01	5

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC040	30	31		0.01	0.01	8
Treasure	HCRC040	31	32		0.01	0.01	4
Treasure	HCRC040	32	33		0.02	0.01	5
Treasure	HCRC040	33	34		0.01	0.02	11
Treasure	HCRC040	34	35		0.01	0.01	17
Treasure	HCRC040	35	36		0.01	0.01	14
Treasure	HCRC040	36	37		0.03	0.01	7
Treasure	HCRC040	37	38		0.00	0.00	13
Treasure	HCRC040	38	39		0.01	0.01	2
Treasure	HCRC040	39	40		0.01	0.00	4
Treasure	HCRC040	40	41		0.01	0.02	1
Treasure	HCRC040	41	42		0.02	0.03	2
Treasure	HCRC040	42	43		0.02	0.01	6
Treasure	HCRC040	43	44		0.01	0.01	5
Treasure	HCRC040	44	45		0.27	0.03	20
Treasure	HCRC040	45	46		0.03	0.02	5
Treasure	HCRC040	46	47		0.02	0.01	28
Treasure	HCRC040	47	48		0.03	0.00	4
Treasure	HCRC040	48	49		0.01	0.00	6
Treasure	HCRC040	49	50		0.01	0.00	8
Treasure	HCRC040	50	51		0.01	0.00	7
Treasure	HCRC040	51	52		0.02	0.01	3
Treasure	HCRC040	52	53		0.03	0.02	7
Treasure	HCRC040	53	54		0.01	0.02	2
Treasure	HCRC040	54	55		0.01	0.01	4
Treasure	HCRC040	55	56		0.01	0.01	5
Treasure	HCRC040	56	57		0.02	0.01	8
Black Diamond	HCRC041	0	1		0.34	0.01	9
Black Diamond	HCRC041	1	2		0.31	0.03	12
Black Diamond	HCRC041	2	3		NO SAMPLE		
Black Diamond	HCRC041	3	4		0.34	0.06	19
Black Diamond	HCRC041	4	5		0.09	0.01	10
Black Diamond	HCRC041	5	6		0.04	0.01	3
Black Diamond	HCRC041	6	7		0.06	0.01	4
Black Diamond	HCRC041	7	8		0.03	0.01	3
Black Diamond	HCRC041	8	9		0.13	0.05	8
Black Diamond	HCRC041	9	10		0.31	0.07	11
Black Diamond	HCRC041	10	11		0.16	0.05	21
Black Diamond	HCRC041	11	12		0.04	0.01	7
Black Diamond	HCRC041	12	13		0.04	0.01	5
Black Diamond	HCRC041	13	14		0.21	0.03	11
Black Diamond	HCRC041	14	15		0.04	0.09	5
Black Diamond	HCRC041	15	16		0.05	0.10	3
Black Diamond	HCRC041	16	17		0.02	0.05	3
Black Diamond	HCRC041	17	18		0.01	0.07	2
Black Diamond	HCRC041	18	19		0.04	0.17	6
Black Diamond	HCRC041	19	20		0.10	0.04	3
Black Diamond	HCRC041	20	21		0.16	0.01	3
Black Diamond	HCRC041	21	22		0.10	0.01	4
Black Diamond	HCRC041	22	23		0.22	0.01	5

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC041	23	24		0.05	0.02	2
Black Diamond	HCRC041	24	25		0.02	0.00	X
Black Diamond	HCRC041	25	26		0.02	0.00	2
Black Diamond	HCRC041	26	27		0.02	0.02	2
Black Diamond	HCRC041	27	28		0.02	0.00	3
Black Diamond	HCRC041	28	29		0.02	0.01	2
Black Diamond	HCRC041	29	30		0.11	0.04	5
Black Diamond	HCRC041	30	31		0.05	0.04	3
Black Diamond	HCRC041	31	32		0.07	0.06	3
Black Diamond	HCRC041	32	33		0.13	0.05	4
Black Diamond	HCRC041	33	34		0.05	0.04	6
Black Diamond	HCRC041	34	35		0.06	0.02	6
Black Diamond	HCRC041	35	36		0.04	0.01	5
Black Diamond	HCRC041	36	37		2.30	0.02	40
Black Diamond	HCRC041	37	38		0.74	0.01	23
Black Diamond	HCRC041	38	39		1.22	0.00	29
Black Diamond	HCRC041	39	40		0.05	0.00	8
Black Diamond	HCRC041	40	41		0.01	0.01	5
Black Diamond	HCRC041	41	42		0.01	0.00	3
Black Diamond	HCRC041	42	43		0.02	0.00	5
Black Diamond	HCRC041	43	44		0.01	0.00	19
Black Diamond	HCRC041	44	45		0.01	0.00	8
Black Diamond	HCRC041	45	46		0.01	0.00	3
Black Diamond	HCRC041	46	47		0.01	0.52	12
Black Diamond	HCRC041	47	48		0.01	0.46	6
Black Diamond	HCRC041	48	49		0.02	0.12	6
Black Diamond	HCRC041	49	50		0.01	0.03	4
Black Diamond	HCRC041	50	51		0.00	0.00	5
Black Diamond	HCRC041	51	52		0.00	0.00	4
Black Diamond	HCRC041	52	53		0.02	0.23	9
Black Diamond	HCRC041	53	54		0.01	0.06	4
Black Diamond	HCRC042	0	1		0.11	0.03	7
Black Diamond	HCRC042	1	2		0.02	0.01	2
Black Diamond	HCRC042	2	3		0.01	0.01	2
Black Diamond	HCRC042	3	4		0.06	0.02	7
Black Diamond	HCRC042	4	5		0.04	0.11	3
Black Diamond	HCRC042	5	6		0.05	0.05	2
Black Diamond	HCRC042	6	7		0.05	0.05	7
Black Diamond	HCRC042	7	8		0.07	0.03	6
Black Diamond	HCRC042	8	9		0.07	0.01	5
Black Diamond	HCRC042	9	10		0.08	0.04	15
Black Diamond	HCRC042	10	11		0.09	0.05	20
Black Diamond	HCRC042	11	12		0.04	0.01	8
Black Diamond	HCRC042	12	13		0.06	0.01	12
Black Diamond	HCRC042	13	14		0.03	0.01	7
Black Diamond	HCRC042	14	15		0.04	0.01	7
Black Diamond	HCRC042	15	16		0.06	0.02	6
Black Diamond	HCRC042	16	17		0.07	0.01	5
Black Diamond	HCRC042	17	18		0.17	0.07	9
Black Diamond	HCRC042	18	19		0.15	0.18	9

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC042	19	20		1.64	0.08	16
Black Diamond	HCRC042	20	21		0.15	0.05	3
Black Diamond	HCRC042	21	22		0.05	0.03	5
Black Diamond	HCRC042	22	23		0.04	0.01	8
Black Diamond	HCRC042	23	24		0.03	0.00	2
Black Diamond	HCRC042	24	25		0.09	0.01	4
Black Diamond	HCRC042	25	26		0.07	0.01	6
Black Diamond	HCRC042	26	27		0.04	0.01	4
Black Diamond	HCRC042	27	28		0.03	0.00	4
Black Diamond	HCRC042	28	29		0.02	0.00	13
Black Diamond	HCRC042	29	30		0.02	0.00	4
Black Diamond	HCRC042	30	31		0.03	0.00	3
Black Diamond	HCRC042	31	32		0.04	0.00	5
Black Diamond	HCRC042	32	33		0.04	0.00	9
Black Diamond	HCRC042	33	34		0.05	0.00	6
Black Diamond	HCRC042	34	35		0.02	0.00	3
Black Diamond	HCRC042	35	36		0.01	0.00	3
Black Diamond	HCRC042	36	37		0.01	0.00	3
Black Diamond	HCRC042	37	38		0.08	0.00	17
Black Diamond	HCRC042	38	39		0.15	0.00	15
Black Diamond	HCRC042	39	40		0.03	0.00	7
Black Diamond	HCRC042	40	41		0.01	0.00	6
Black Diamond	HCRC042	41	42		0.01	0.01	3
Black Diamond	HCRC042	42	43		0.01	0.00	4
Black Diamond	HCRC042	43	44		0.01	0.00	3
Black Diamond	HCRC042	44	45		0.01	0.00	4
Black Diamond	HCRC042	45	46		0.00	0.00	3
Black Diamond	HCRC042	46	47		0.11	0.00	4
Black Diamond	HCRC042	47	48		0.02	0.01	2
Black Diamond	HCRC042	48	49		0.01	0.00	2
Black Diamond	HCRC042	49	50		0.01	0.00	2
Black Diamond	HCRC042	50	51		0.01	0.00	4
Black Diamond	HCRC042	51	52		0.01	0.00	3
Black Diamond	HCRC042	52	53		0.11	0.00	5
Black Diamond	HCRC042	53	54		0.01	0.00	2
Black Diamond	HCRC042	54	55		0.02	0.00	2
Black Diamond	HCRC042	55	56		0.01	0.01	2
Black Diamond	HCRC042	56	57		0.01	0.06	3
Black Diamond	HCRC042	57	58		0.02	0.09	3
Black Diamond	HCRC042	58	59		0.02	0.00	3
Black Diamond	HCRC042	59	60		0.01	0.01	X
Black Diamond	HCRC042	60	61		0.00	0.01	1
Black Diamond	HCRC042	61	62		0.01	0.01	1
Black Diamond	HCRC042	62	63		0.01	0.01	2
Black Diamond	HCRC042	63	64		0.01	0.01	2
Black Diamond	HCRC042	64	65		0.01	0.01	1
Black Diamond	HCRC042	65	66		0.00	0.00	2
Black Diamond	HCRC042	66	67		0.00	0.00	2
Black Diamond	HCRC042	67	68		0.00	0.00	3
Black Diamond	HCRC042	68	69		0.01	0.01	4

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC042	69	70		0.00	0.00	3
Black Diamond	HCRC042	70	71		0.00	0.00	3
Black Diamond	HCRC042	71	72		0.01	0.00	X
Black Diamond	HCRC042	72	73		0.01	0.00	2
Black Diamond	HCRC042	73	74		0.00	0.00	2
Black Diamond	HCRC042	74	75		0.00	0.00	1
Black Diamond	HCRC042	75	76		0.01	0.00	X
Black Diamond	HCRC042	76	77		0.01	0.00	2
Black Diamond	HCRC042	77	78		0.00	0.00	2
Black Diamond	HCRC042	78	79		0.01	0.00	1
Black Diamond	HCRC042	79	80		0.00	0.00	2
Black Diamond	HCRC042	80	81		0.00	0.00	1
Black Diamond	HCRC042	81	82		0.00	0.00	2
Black Diamond	HCRC042	82	83		0.01	0.00	3
Black Diamond	HCRC042	83	84		0.03	0.01	3
Black Diamond	HCRC042	84	85		0.02	0.01	3
Black Diamond	HCRC042	85	86		0.02	0.01	2
Black Diamond	HCRC042	86	87		0.03	0.01	7
Black Diamond	HCRC042	87	88		0.02	0.01	3
Black Diamond	HCRC042	88	89		0.02	0.05	11
Black Diamond	HCRC042	89	90		0.02	0.03	8
Black Diamond	HCRC042	90	91		0.02	0.02	3
Black Diamond	HCRC042	91	92		0.02	0.02	2
Black Diamond	HCRC042	92	93		0.01	0.01	X
Black Diamond	HCRC042	93	94		0.01	0.01	2
Black Diamond	HCRC042	94	95		0.00	0.00	1
Black Diamond	HCRC042	95	96		0.00	0.00	2
Black Diamond	HCRC042	96	97		0.01	0.00	3
Black Diamond	HCRC042	97	98		0.00	0.00	2
Black Diamond	HCRC042	98	99		0.00	0.00	X
Black Diamond	HCRC042	99	100		0.01	0.00	2
Black Diamond	HCRC042	100	101		0.01	0.00	12
Black Diamond	HCRC042	101	102		0.01	0.01	2
Black Diamond	HCRC043	0	1		0.14	0.08	10
Black Diamond	HCRC043	1	2		0.06	0.08	6
Black Diamond	HCRC043	2	3		0.06	0.09	7
Black Diamond	HCRC043	3	4		0.07	0.05	7
Black Diamond	HCRC043	4	5		0.08	0.10	9
Black Diamond	HCRC043	5	6		0.06	0.09	10
Black Diamond	HCRC043	6	7		0.10	0.06	12
Black Diamond	HCRC043	7	8		0.16	0.09	25
Black Diamond	HCRC043	8	9		0.36	0.07	12
Black Diamond	HCRC043	9	10		0.04	0.03	6
Black Diamond	HCRC043	10	11		0.05	0.02	6
Black Diamond	HCRC043	11	12		0.05	0.02	5
Black Diamond	HCRC043	12	13		0.03	0.01	4
Black Diamond	HCRC043	13	14		0.05	0.02	7
Black Diamond	HCRC043	14	15		0.09	0.05	8
Black Diamond	HCRC043	15	16		0.11	0.07	10
Black Diamond	HCRC043	16	17		0.13	0.14	13

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC043	17	18		0.14	0.13	4
Black Diamond	HCRC043	18	19		0.05	0.12	6
Black Diamond	HCRC043	19	20		0.03	0.04	4
Black Diamond	HCRC043	20	21		0.05	0.01	3
Black Diamond	HCRC043	21	22		0.20	0.01	7
Black Diamond	HCRC043	22	23		0.07	0.03	5
Black Diamond	HCRC043	23	24		0.01	0.01	3
Black Diamond	HCRC043	24	25		0.01	0.01	2
Black Diamond	HCRC043	25	26		0.02	0.03	4
Black Diamond	HCRC043	26	27		0.04	0.08	3
Black Diamond	HCRC043	27	28		0.03	0.04	3
Black Diamond	HCRC043	28	29		0.02	0.03	3
Black Diamond	HCRC043	29	30		0.01	0.02	3
Black Diamond	HCRC043	30	31		0.03	0.02	4
Black Diamond	HCRC043	31	32		0.02	0.01	3
Black Diamond	HCRC043	32	33		0.02	0.01	4
Black Diamond	HCRC043	33	34		0.03	0.01	4
Black Diamond	HCRC043	34	35		0.07	0.06	14
Black Diamond	HCRC043	35	36		0.05	0.11	3
Black Diamond	HCRC043	36	37		0.03	0.06	3
Black Diamond	HCRC043	37	38		0.02	0.07	2
Black Diamond	HCRC043	38	39		0.02	0.04	2
Black Diamond	HCRC043	39	40		0.01	0.03	3
Black Diamond	HCRC043	40	41		0.01	0.05	2
Black Diamond	HCRC043	41	42		0.01	0.02	2
Black Diamond	HCRC043	42	43		0.18	0.08	5
Black Diamond	HCRC043	43	44		0.04	0.04	4
Black Diamond	HCRC043	44	45		0.03	0.02	5
Black Diamond	HCRC043	45	46		0.01	0.00	4
Black Diamond	HCRC043	46	47		0.01	0.01	5
Black Diamond	HCRC043	47	48		0.00	0.00	4
Black Diamond	HCRC043	48	49		0.00	0.00	2
Black Diamond	HCRC043	49	50		0.01	0.00	7
Black Diamond	HCRC043	50	51		0.01	0.00	4
Black Diamond	HCRC043	51	52		0.36	0.01	7
Black Diamond	HCRC043	52	53		0.05	0.07	6
Black Diamond	HCRC043	53	54		0.01	0.01	3
Black Diamond	HCRC043	54	55		0.01	0.01	3
Black Diamond	HCRC043	55	56		0.00	0.00	3
Black Diamond	HCRC043	56	57		0.01	0.02	2
Black Diamond	HCRC043	57	58		0.00	0.01	3
Black Diamond	HCRC043	58	59		0.01	0.01	3
Black Diamond	HCRC043	59	60		0.02	0.01	3
Black Diamond	HCRC043	60	61		1.62	0.08	27
Black Diamond	HCRC043	61	62		0.28	0.02	10
Black Diamond	HCRC043	62	63		0.01	0.01	3
Black Diamond	HCRC043	63	64		0.01	0.04	4
Black Diamond	HCRC043	64	65		0.01	0.01	3
Black Diamond	HCRC043	65	66		0.02	0.00	5
Black Diamond	HCRC043	66	67		0.01	0.01	4

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC043	67	68		0.01	0.09	13
Black Diamond	HCRC043	68	69		0.01	0.08	43
Black Diamond	HCRC043	69	70		0.02	0.02	37
Black Diamond	HCRC043	70	71		0.03	0.16	14
Black Diamond	HCRC043	71	72		0.04	0.11	12
Black Diamond	HCRC043	72	73		0.02	0.04	4
Black Diamond	HCRC043	73	74		0.04	0.01	5
Black Diamond	HCRC043	74	75		0.01	0.01	5
Black Diamond	HCRC043	75	76		0.01	0.02	4
Black Diamond	HCRC043	76	77		0.01	0.01	6
Black Diamond	HCRC043	77	78		0.00	0.01	2
Black Diamond	HCRC043	78	79		0.02	0.01	3
Black Diamond	HCRC043	79	80		0.01	0.00	1
Black Diamond	HCRC043	80	81		0.01	0.00	X
Black Diamond	HCRC043	81	82		0.01	0.00	1
Black Diamond	HCRC043	82	83		0.01	0.00	2
Black Diamond	HCRC043	83	84		0.00	0.00	3
Black Diamond	HCRC043	84	85		0.00	0.00	4
Black Diamond	HCRC043	85	86		0.00	0.00	1
Black Diamond	HCRC043	86	87		0.00	0.00	2
Black Diamond	HCRC043	87	88		0.00	0.00	2
Black Diamond	HCRC043	88	89		0.00	0.00	X
Black Diamond	HCRC043	89	90		0.00	0.00	2
Black Diamond	HCRC043	90	91		0.00	0.00	4
Black Diamond	HCRC043	91	92		0.00	0.00	1
Black Diamond	HCRC043	92	93		0.00	0.00	3
Black Diamond	HCRC043	93	94		0.00	0.00	21
Black Diamond	HCRC043	94	95		0.00	0.00	5
Black Diamond	HCRC043	95	96		0.01	0.01	1
Black Diamond	HCRC043	96	97		0.01	0.00	2
Black Diamond	HCRC043	97	98		0.01	0.00	5
Black Diamond	HCRC043	98	99		0.00	0.00	4
Black Diamond	HCRC043	99	100		0.02	0.05	8
Black Diamond	HCRC043	100	101		0.01	0.16	5
Black Diamond	HCRC043	101	102		0.00	0.01	4
Black Diamond	HCRC043	102	103		0.00	0.14	6
Black Diamond	HCRC043	103	104		0.00	0.35	9
Black Diamond	HCRC043	104	105		0.00	0.01	3
Black Diamond	HCRC043	105	106		0.01	0.01	3
Black Diamond	HCRC043	106	107		0.01	0.27	9
Black Diamond	HCRC043	107	108		0.01	0.03	1
Black Diamond	HCRC043	108	109		0.00	0.00	2
Black Diamond	HCRC043	109	110		0.01	0.00	1
Black Diamond	HCRC043	110	111		0.01	0.00	6
Black Diamond	HCRC043	111	112		0.01	0.00	10
Black Diamond	HCRC043	112	113		0.08	0.00	5
Black Diamond	HCRC043	113	114		0.51	0.09	8
Black Diamond	HCRC043	114	115		0.15	0.11	2
Black Diamond	HCRC043	115	116		0.01	0.00	1
Black Diamond	HCRC043	116	117		0.07	0.01	5

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Black Diamond	HCRC043	117	118		0.01	0.00	18
Black Diamond	HCRC043	118	119		0.01	0.00	12
Black Diamond	HCRC043	119	120		0.37	0.00	13
Black Diamond	HCRC043	120	121		0.01	0.00	4
Black Diamond	HCRC043	121	122		0.01	0.00	2
Black Diamond	HCRC043	122	123		0.00	0.01	2
Black Diamond	HCRC043	123	124		0.00	0.00	4
Black Diamond	HCRC043	124	125		0.00	0.01	5
Black Diamond	HCRC043	125	126		0.00	0.01	2
Black Diamond	HCRC043	126	127		0.01	0.01	3
Black Diamond	HCRC043	127	128		0.00	0.01	3
Black Diamond	HCRC043	128	129		0.00	0.01	3
Black Diamond	HCRC043	129	130		0.00	0.00	5
Black Diamond	HCRC043	130	131		0.00	0.00	4
Black Diamond	HCRC043	131	132		0.00	0.00	12
Green Diamond	HCRC044	0	1		1.49	0.06	151
Green Diamond	HCRC044	1	2		0.03	0.01	7
Green Diamond	HCRC044	2	3		0.09	0.07	23
Green Diamond	HCRC044	3	4		0.08	0.30	50
Green Diamond	HCRC044	4	5		0.02	0.13	13
Green Diamond	HCRC044	5	6		0.01	0.08	9
Green Diamond	HCRC044	6	7		0.03	0.16	22
Green Diamond	HCRC044	7	8		0.04	0.18	34
Green Diamond	HCRC044	8	9		0.06	0.35	35
Green Diamond	HCRC044	9	10		0.05	0.30	25
Green Diamond	HCRC044	10	11		0.05	0.19	14
Green Diamond	HCRC044	11	12		0.04	0.19	13
Green Diamond	HCRC044	12	13		0.08	0.43	20
Green Diamond	HCRC044	13	14		0.02	0.40	10
Green Diamond	HCRC044	14	15		NO SAMPLE		
Green Diamond	HCRC044	15	16		0.07	0.26	11
Green Diamond	HCRC044	16	17		0.02	0.07	11
Green Diamond	HCRC044	17	18		0.01	0.05	6
Green Diamond	HCRC044	18	19		0.03	0.14	13
Green Diamond	HCRC044	19	20		0.09	0.45	24
Green Diamond	HCRC044	20	21		0.11	0.37	42
Green Diamond	HCRC044	21	22		0.10	0.30	17
Green Diamond	HCRC044	22	23		0.08	0.24	15
Green Diamond	HCRC044	23	24		0.06	0.22	11
Green Diamond	HCRC044	24	25		0.05	0.56	14
Green Diamond	HCRC044	25	26		0.04	0.29	15
Green Diamond	HCRC044	26	27		0.01	0.06	8
Green Diamond	HCRC044	27	28		0.03	0.15	50
Green Diamond	HCRC044	28	29		0.02	0.09	40
Green Diamond	HCRC044	29	30		0.01	0.04	10
Green Diamond	HCRC044	30	31		0.00	0.01	5
Green Diamond	HCRC044	31	32		0.01	0.01	6
Green Diamond	HCRC044	32	33		0.11	0.01	15
Green Diamond	HCRC044	33	34		0.01	0.01	46
Green Diamond	HCRC044	34	35		0.00	0.03	7

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Green Diamond	HCRC044	35	36		0.00	0.00	10
Green Diamond	HCRC044	36	37		0.01	0.01	14
Green Diamond	HCRC044	37	38		0.13	0.01	135
Green Diamond	HCRC044	38	39		0.01	0.00	90
Green Diamond	HCRC044	39	40		0.01	0.00	27
Green Diamond	HCRC044	40	41		0.06	0.07	14
Green Diamond	HCRC044	41	42		0.01	0.17	17
Green Diamond	HCRC044	42	43		0.01	0.03	9
Green Diamond	HCRC044	43	44		0.00	0.01	6
Green Diamond	HCRC044	44	45		0.04	0.04	11
Green Diamond	HCRC044	45	46		0.49	0.18	45
Green Diamond	HCRC044	46	47		0.06	0.07	14
Green Diamond	HCRC044	47	48		0.01	0.18	21
Green Diamond	HCRC044	48	49		0.01	0.14	11
Green Diamond	HCRC044	49	50		0.10	0.09	11
Green Diamond	HCRC044	50	51		0.05	0.02	14
Green Diamond	HCRC044	51	52		0.00	0.02	8
Green Diamond	HCRC044	52	53		0.00	0.01	5
Green Diamond	HCRC044	53	54		0.03	0.33	44
Green Diamond	HCRC044	54	55		0.03	0.65	70
Green Diamond	HCRC044	55	56		0.03	0.73	68
Green Diamond	HCRC044	56	57		0.02	0.22	27
Green Diamond	HCRC044	57	58		0.49	0.24	59
Green Diamond	HCRC044	58	59		0.02	0.19	15
Green Diamond	HCRC044	59	60		0.02	2.55	22
Green Diamond	HCRC044	60	61		0.01	0.49	21
Green Diamond	HCRC044	61	62		0.01	0.10	8
Green Diamond	HCRC044	62	63		0.01	0.66	33
Green Diamond	HCRC044	63	64		0.01	0.07	28
Green Diamond	HCRC044	64	65		0.01	0.08	94
Green Diamond	HCRC044	65	66		0.01	0.25	183
Green Diamond	HCRC044	66	67		0.02	0.04	67
Green Diamond	HCRC044	67	68		0.06	0.04	101
Green Diamond	HCRC044	68	69		0.02	3.09	48
Green Diamond	HCRC044	69	70		1.10	0.27	501
Green Diamond	HCRC044	70	71		0.03	0.10	70
Green Diamond	HCRC044	71	72		0.01	0.03	130
Green Diamond	HCRC044	72	73		0.32	0.17	320
Green Diamond	HCRC044	73	74		0.01	0.09	708
Green Diamond	HCRC044	74	75		0.01	0.05	30
Green Diamond	HCRC044	75	76		0.01	0.01	12
Green Diamond	HCRC044	76	77		0.00	0.01	10
Green Diamond	HCRC044	77	78		0.00	0.00	10
Green Diamond	HCRC044	78	79		0.16	0.02	20
Green Diamond	HCRC044	79	80		0.07	0.35	19
Green Diamond	HCRC044	80	81		0.12	0.37	13
Green Diamond	HCRC044	81	82		0.01	0.09	4
Green Diamond	HCRC044	82	83		0.01	0.06	5
Green Diamond	HCRC044	83	84		0.01	0.00	4
Green Diamond	HCRC044	84	85		0.01	0.01	5

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Green Diamond	HCRC044	85	86		0.14	0.08	360
Green Diamond	HCRC044	86	87		0.13	0.10	19
Green Diamond	HCRC044	87	88		0.01	0.02	9
Green Diamond	HCRC044	88	89		0.02	0.04	8
Green Diamond	HCRC044	89	90		0.04	0.07	26
Green Diamond	HCRC044	90	91		1.24	0.09	1039
Green Diamond	HCRC044	91	92		0.04	0.05	24
Green Diamond	HCRC044	92	93		0.07	0.02	51
Green Diamond	HCRC044	93	94		3.90	0.06	3647
Green Diamond	HCRC044	94	95		0.03	0.04	15
Green Diamond	HCRC044	95	96		0.10	0.15	395
Bonanza	HCRC045	0	1		0.18	0.00	15
Bonanza	HCRC045	1	2		0.02	0.00	5
Bonanza	HCRC045	2	3		0.02	0.00	3
Bonanza	HCRC045	3	4		0.02	0.00	3
Bonanza	HCRC045	4	5		0.04	0.00	8
Bonanza	HCRC045	5	6		0.03	0.00	5
Bonanza	HCRC045	6	7		0.14	0.00	14
Bonanza	HCRC045	7	8		0.06	0.00	9
Bonanza	HCRC045	8	9		0.12	0.00	10
Bonanza	HCRC045	9	10		0.09	0.00	5
Bonanza	HCRC045	10	11		0.10	0.00	4
Bonanza	HCRC045	11	12		0.02	0.00	3
Bonanza	HCRC045	12	13		0.01	0.00	2
Bonanza	HCRC045	13	14		0.02	0.00	4
Bonanza	HCRC045	14	15		0.02	0.01	4
Bonanza	HCRC045	15	16		0.03	0.00	3
Bonanza	HCRC045	16	17		0.04	0.01	7
Bonanza	HCRC045	17	18		0.02	0.00	3
Bonanza	HCRC045	18	19		0.01	0.00	2
Bonanza	HCRC045	19	20		0.01	0.00	4
Bonanza	HCRC045	20	21		0.01	0.00	2
Bonanza	HCRC045	21	22		0.01	0.00	2
Bonanza	HCRC045	22	23		0.02	0.00	3
Bonanza	HCRC045	23	24		0.02	0.00	2
Bonanza	HCRC045	24	25		0.02	0.00	3
Bonanza	HCRC045	25	26		0.03	0.00	2
Bonanza	HCRC045	26	27		0.04	0.00	4
Bonanza	HCRC045	27	28		0.03	0.00	4
Bonanza	HCRC045	28	29		0.05	0.01	3
Bonanza	HCRC045	29	30		0.03	0.00	3
Bonanza	HCRC045	30	31		0.02	0.00	2
Bonanza	HCRC045	31	32		0.02	0.00	2
Bonanza	HCRC045	32	33		1.23	0.01	33
Bonanza	HCRC045	33	34		0.47	0.02	13
Bonanza	HCRC045	34	35		0.32	0.04	8
Bonanza	HCRC045	35	36		0.16	0.02	5
Bonanza	HCRC045	36	37		0.30	0.02	9
Bonanza	HCRC045	37	38		0.07	0.02	10
Bonanza	HCRC045	38	39		0.02	0.01	3

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Bonanza	HCRC045	39	40		0.02	0.01	2
Bonanza	HCRC045	40	41		0.02	0.01	3
Bonanza	HCRC045	41	42		0.08	0.01	5
Bonanza	HCRC045	42	43		2.11	0.03	19
Bonanza	HCRC045	43	44		0.33	0.03	4
Bonanza	HCRC045	44	45		0.18	0.04	4
Bonanza	HCRC045	45	46		0.14	0.05	5
Bonanza	HCRC045	46	47		0.06	0.03	3
Bonanza	HCRC045	47	48		0.02	0.07	2
Bonanza	HCRC045	48	49		0.04	0.06	2
Bonanza	HCRC045	49	50		0.02	0.08	2
Bonanza	HCRC045	50	51		0.02	0.05	2
Bonanza	HCRC045	51	52		0.01	0.01	2
Bonanza	HCRC045	52	53		0.02	0.04	1
Bonanza	HCRC045	53	54		0.04	0.07	1
Bonanza	HCRC045	54	55		0.02	0.09	2
Bonanza	HCRC045	55	56		0.01	0.04	2
Bonanza	HCRC045	56	57		0.02	0.06	1
Bonanza	HCRC045	57	58		0.03	0.02	2
Bonanza	HCRC045	58	59		0.02	0.01	2
Bonanza	HCRC045	59	60		0.02	0.04	1
Bonanza	HCRC045	60	61		0.02	0.03	1
Bonanza	HCRC045	61	62		0.14	0.01	2
Bonanza	HCRC045	62	63		0.04	0.00	2
Bonanza	HCRC045	63	64		0.02	0.00	1
Bonanza	HCRC045	64	65		0.02	0.00	2
Bonanza	HCRC045	65	66		0.02	0.00	2
Bonanza	HCRC045	66	67		0.02	0.00	2
Bonanza	HCRC045	67	68		0.05	0.01	5
Bonanza	HCRC045	68	69		0.03	0.01	4
Bonanza	HCRC045	69	70		0.03	0.00	5
Bonanza	HCRC045	70	71		0.17	0.01	7
Bonanza	HCRC045	71	72		0.03	0.01	5
Bonanza	HCRC045	72	73		0.03	0.01	4
Bonanza	HCRC045	73	74		0.04	0.00	5
Bonanza	HCRC045	74	75		0.01	0.00	2
Bonanza	HCRC045	75	76		0.01	0.00	3
Bonanza	HCRC045	76	77		0.01	0.00	3
Bonanza	HCRC045	77	78		0.02	0.00	2
Bonanza	HCRC045	78	79		0.01	0.00	2
Bonanza	HCRC045	79	80		0.01	0.00	4
Bonanza	HCRC045	80	81		0.00	0.00	2
Bonanza	HCRC045	81	82		0.01	0.00	3
Bonanza	HCRC045	82	83		0.02	0.01	3
Bonanza	HCRC045	83	84		0.01	0.00	2
Bonanza	HCRC045	84	85		0.01	0.01	8
Bonanza	HCRC045	85	86		0.02	0.01	4
Bonanza	HCRC045	86	87		0.02	0.01	2
Bonanza	HCRC045	87	88		0.01	0.00	3
Bonanza	HCRC045	88	89		0.01	0.00	2

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Bonanza	HCRC045	89	90		0.01	0.00	1
Bonanza	HCRC045	90	91		0.01	0.00	3
Bonanza	HCRC045	91	92		0.02	0.00	4
Bonanza	HCRC045	92	93		0.01	0.02	3
Bonanza	HCRC045	93	94		0.01	0.01	3
Bonanza	HCRC045	94	95		0.00	0.00	1
Bonanza	HCRC045	95	96		0.01	0.00	3
Bonanza	HCRC045	96	97		0.01	0.00	X
Bonanza	HCRC045	97	98		0.05	0.00	2
Bonanza	HCRC045	98	99		0.06	0.00	3
Bonanza	HCRC045	99	100		0.03	0.01	8
Bonanza	HCRC045	100	101		0.01	0.00	2
Bonanza	HCRC045	101	102		0.01	0.01	3
Bonanza	HCRC045	102	103		0.01	0.01	2
Bonanza	HCRC045	103	104		0.01	0.00	3
Bonanza	HCRC045	104	105		0.02	0.00	2
Bonanza	HCRC045	105	106		0.01	0.01	X
Bonanza	HCRC045	106	107		0.02	0.00	X
Bonanza	HCRC045	107	108		0.01	0.00	X
Pioneer	HCRC046	0	1	0.20	0.19	0.05	19
Pioneer	HCRC046	1	2	0.10	0.09	0.17	34
Pioneer	HCRC046	2	3	0.10	0.12	0.15	74
Pioneer	HCRC046	3	4	0.02	0.01	0.02	5
Pioneer	HCRC046	4	5	0.04	0.03	0.04	7
Pioneer	HCRC046	5	6	0.68	0.05	0.07	8
Pioneer	HCRC046	6	7	0.03	0.02	0.09	2
Pioneer	HCRC046	7	8	0.01	0.00	0.01	X
Pioneer	HCRC046	8	9	0.01	0.00	0.00	X
Pioneer	HCRC046	9	10	X	0.00	0.01	X
Pioneer	HCRC046	10	11	0.01	0.00	0.01	5
Pioneer	HCRC046	11	12	0.01	0.00	0.01	10
Pioneer	HCRC046	12	13	0.02	0.01	0.02	X
Pioneer	HCRC046	13	14	0.04	0.02	0.10	6
Pioneer	HCRC046	14	15	0.02	0.01	0.04	1
Pioneer	HCRC046	15	16	0.05	0.01	0.02	2
Pioneer	HCRC046	16	17	0.05	0.03	0.03	3
Pioneer	HCRC046	17	18	0.02	0.03	0.09	3
Pioneer	HCRC046	18	19	0.02	0.02	0.05	3
Pioneer	HCRC046	19	20	0.01	0.01	0.04	6
Pioneer	HCRC046	20	21	0.12	0.03	0.16	49
Pioneer	HCRC046	21	22	0.05	0.03	0.03	16
Pioneer	HCRC046	22	23	0.04	0.02	0.02	3
Pioneer	HCRC046	23	24	0.03	0.01	0.02	3
Pioneer	HCRC046	24	25	0.06	0.05	0.03	8
Pioneer	HCRC046	25	26	0.04	0.04	0.09	21
Pioneer	HCRC046	26	27	0.13	0.06	0.27	21
Pioneer	HCRC046	27	28	0.04	0.02	0.07	12
Pioneer	HCRC046	28	29	0.02	0.01	0.02	13
Pioneer	HCRC046	29	30	0.03	0.01	0.01	2
Pioneer	HCRC046	30	31	0.01	0.00	0.01	2

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC046	31	32	0.04	0.14	0.02	11
Pioneer	HCRC046	32	33	0.03	0.01	0.01	5
Pioneer	HCRC046	33	34	0.01	0.00	0.00	2
Pioneer	HCRC046	34	35	0.11	0.02	0.03	22
Pioneer	HCRC046	35	36	0.01	0.00	0.01	3
Pioneer	HCRC046	36	37	0.01	0.00	0.00	4
Pioneer	HCRC046	37	38	0.02	0.00	0.00	1
Pioneer	HCRC046	38	39	X	0.00	0.00	3
Pioneer	HCRC046	39	40	0.01	0.00	0.00	5
Pioneer	HCRC046	40	41	0.02	0.00	0.00	1
Pioneer	HCRC046	41	42	0.01	0.00	0.00	2
Pioneer	HCRC046	42	43	0.01	0.00	0.01	1
Pioneer	HCRC046	43	44	0.01	0.00	0.00	3
Pioneer	HCRC046	44	45	0.01	0.00	0.00	10
Pioneer	HCRC046	45	46	0.01	0.00	0.00	7
Pioneer	HCRC046	46	47	0.01	0.00	0.00	1
Pioneer	HCRC046	47	48	0.01	0.00	0.00	1
Pioneer	HCRC046	48	49	0.01	0.01	0.00	2
Pioneer	HCRC046	49	50	0.01	0.01	0.00	X
Pioneer	HCRC046	50	51	0.01	0.00	0.00	X
Pioneer	HCRC046	51	52	0.02	0.00	0.00	4
Pioneer	HCRC046	52	53	0.01	0.00	0.00	X
Pioneer	HCRC046	53	54	0.01	0.01	0.00	X
Pioneer	HCRC046	54	55	0.01	0.00	0.00	1
Pioneer	HCRC046	55	56	0.01	0.01	0.00	X
Pioneer	HCRC046	56	57	0.02	0.01	0.00	X
Pioneer	HCRC046	57	58	0.01	0.00	0.00	X
Pioneer	HCRC046	58	59	0.01	0.03	0.02	1
Pioneer	HCRC046	59	60	0.02	0.02	0.03	2
Pioneer	HCRC046	60	61	0.01	0.01	0.02	X
Pioneer	HCRC046	61	62	0.01	0.00	0.01	4
Pioneer	HCRC046	62	63	0.01	0.00	0.00	X
Pioneer	HCRC046	63	64	0.01	0.00	0.00	3
Pioneer	HCRC046	64	65	0.01	0.00	0.02	1
Pioneer	HCRC046	65	66	0.01	0.00	0.02	X
Pioneer	HCRC046	66	67	X	0.00	0.01	X
Pioneer	HCRC046	67	68	0.01	0.00	0.01	X
Pioneer	HCRC046	68	69	0.01	0.00	0.01	X
Pioneer	HCRC046	69	70	0.01	0.00	0.01	4
Pioneer	HCRC046	70	71	0.01	0.00	0.01	X
Pioneer	HCRC046	71	72	0.01	0.02	0.02	X
Pioneer	HCRC047	0	1	1.05	0.27	0.09	38
Pioneer	HCRC047	1	2	0.06	0.03	0.01	2
Pioneer	HCRC047	2	3	0.01	0.01	0.00	X
Pioneer	HCRC047	3	4	0.02	0.01	0.00	X
Pioneer	HCRC047	4	5	0.01	0.01	0.01	X
Pioneer	HCRC047	5	6	X	0.00	0.01	X
Pioneer	HCRC047	6	7	0.02	0.04	0.01	X
Pioneer	HCRC047	7	8	0.01	0.01	0.00	X
Pioneer	HCRC047	8	9	0.08	0.00	0.00	X

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC047	9	10	0.02	0.01	0.00	X
Pioneer	HCRC047	10	11	0.01	0.01	0.01	X
Pioneer	HCRC047	11	12	0.01	0.01	0.00	X
Pioneer	HCRC047	12	13	0.01	0.01	0.00	X
Pioneer	HCRC047	13	14	0.01	0.02	0.00	X
Pioneer	HCRC047	14	15	X	0.01	0.00	X
Pioneer	HCRC047	15	16	X	0.02	0.01	X
Pioneer	HCRC047	16	17	0.01	0.02	0.00	2
Pioneer	HCRC047	17	18	0.01	0.01	0.01	X
Pioneer	HCRC047	18	19	0.01	0.02	0.00	11
Pioneer	HCRC047	19	20	0.01	0.04	0.02	19
Pioneer	HCRC047	20	21	0.01	0.00	0.00	2
Pioneer	HCRC047	21	22	0.01	0.01	0.01	2
Pioneer	HCRC047	22	23	0.01	0.02	0.03	7
Pioneer	HCRC047	23	24	0.01	0.01	0.03	4
Pioneer	HCRC047	24	25	0.03	0.02	0.17	18
Pioneer	HCRC047	25	26	0.01	0.01	0.06	7
Pioneer	HCRC047	26	27	0.01	0.01	0.02	X
Pioneer	HCRC047	27	28	0.03	0.02	0.06	X
Pioneer	HCRC047	28	29	0.03	0.01	0.03	19
Pioneer	HCRC047	29	30	0.01	0.01	0.03	12
Pioneer	HCRC047	30	31	0.01	0.04	0.03	13
Pioneer	HCRC047	31	32	0.23	0.01	0.09	769
Pioneer	HCRC047	32	33	0.01	0.01	0.01	28
Pioneer	HCRC047	33	34	X	0.00	0.01	5
Pioneer	HCRC047	34	35	0.02	0.08	0.04	10
Pioneer	HCRC047	35	36	0.02	0.04	0.03	6
Pioneer	HCRC047	36	37	0.01	0.02	0.14	7
Pioneer	HCRC047	37	38	0.01	0.01	0.03	1
Pioneer	HCRC047	38	39	0.09	4.00	0.28	152
Pioneer	HCRC047	39	40	0.02	0.13	0.03	34
Pioneer	HCRC047	40	41	0.02	0.14	0.05	13
Pioneer	HCRC047	41	42	0.03	0.06	0.01	22
Pioneer	HCRC047	42	43	0.13	0.21	0.02	22
Pioneer	HCRC047	43	44	5.32	3.36	0.02	429
Pioneer	HCRC047	44	45	0.08	0.19	0.01	10
Pioneer	HCRC047	45	46	0.06	0.01	0.01	27
Pioneer	HCRC047	46	47	0.04	0.01	0.01	2
Pioneer	HCRC047	47	48	0.01	0.01	0.01	3
Pioneer	HCRC047	48	49	0.01	0.01	0.01	X
Pioneer	HCRC047	49	50	X	0.01	0.06	2
Pioneer	HCRC047	50	51	0.01	0.00	0.03	28
Pioneer	HCRC047	51	52	0.01	0.01	0.01	5
Pioneer	HCRC047	52	53	0.14	0.20	0.02	9
Pioneer	HCRC047	53	54	0.02	0.00	0.01	2
Pioneer	HCRC047	54	55	X	0.01	0.02	3
Pioneer	HCRC047	55	56	X	0.00	0.03	3
Pioneer	HCRC047	56	57	0.01	0.01	0.05	2
Pioneer	HCRC047	57	58	0.01	0.01	0.03	10
Pioneer	HCRC047	58	59	0.01	0.01	0.03	7

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC047	59	60	0.93	0.27	0.09	49
Pioneer	HCRC047	60	61	0.02	0.03	0.14	28
Pioneer	HCRC047	61	62	0.07	0.01	0.52	197
Pioneer	HCRC047	62	63	0.03	0.00	0.07	24
Pioneer	HCRC047	63	64	0.04	0.02	0.26	24
Pioneer	HCRC047	64	65	0.01	0.00	0.04	3
Pioneer	HCRC047	65	66	0.01	0.01	0.03	2
Pioneer	HCRC047	66	67	0.01	0.26	0.13	3
Pioneer	HCRC047	67	68	0.03	0.52	0.28	23
Pioneer	HCRC047	68	69	0.01	0.09	0.10	7
Pioneer	HCRC047	69	70	0.01	0.01	0.04	2
Pioneer	HCRC047	70	71	X	0.00	0.03	2
Pioneer	HCRC047	71	72	0.01	0.21	0.04	2
Pioneer	HCRC047	72	73	0.01	0.05	0.04	4
Pioneer	HCRC047	73	74	0.02	0.00	0.02	1
Pioneer	HCRC047	74	75	X	0.01	0.02	2
Pioneer	HCRC047	75	76	0.01	0.01	0.04	2
Pioneer	HCRC047	76	77	X	0.00	0.02	X
Pioneer	HCRC047	77	78	0.02	0.12	0.02	2
Pioneer	HCRC047	78	79	0.01	0.26	0.02	6
Pioneer	HCRC047	79	80	0.01	0.01	0.03	15
Pioneer	HCRC047	80	81	0.01	0.01	0.03	2
Pioneer	HCRC047	81	82	0.03	0.02	0.19	10
Pioneer	HCRC047	82	83	0.01	0.01	0.02	3
Pioneer	HCRC047	83	84	0.01	0.00	0.07	16
Pioneer	HCRC047	84	85	0.01	0.01	0.02	20
Pioneer	HCRC047	85	86	0.02	0.01	0.04	6
Pioneer	HCRC047	86	87	0.01	1.92	0.10	44
Pioneer	HCRC047	87	88	0.01	0.07	0.10	3
Pioneer	HCRC047	88	89	X	0.02	0.03	2
Pioneer	HCRC047	89	90	0.47	0.01	0.02	14
Pioneer	HCRC047	90	91	0.01	0.00	0.02	2
Pioneer	HCRC047	91	92	0.01	0.04	0.03	3
Pioneer	HCRC047	92	93	0.01	0.01	0.01	16
Pioneer	HCRC047	93	94	0.02	0.00	0.01	2
Pioneer	HCRC047	94	95	X	0.00	0.01	1
Pioneer	HCRC047	95	96	X	0.00	0.01	3
Pioneer	HCRC047	96	97	0.01	0.13	0.02	36
Pioneer	HCRC047	97	98	X	0.01	0.02	16
Pioneer	HCRC047	98	99	0.09	0.01	0.35	40
Pioneer	HCRC047	99	100	X	0.01	0.02	7
Pioneer	HCRC047	100	101	X	0.00	0.01	2
Pioneer	HCRC047	101	102	0.01	0.00	0.01	57
Pioneer	HCRC048	0	1	0.16	0.19	0.08	36
Pioneer	HCRC048	1	2	0.04	0.04	0.03	8
Pioneer	HCRC048	2	3	0.01	0.02	0.01	1
Pioneer	HCRC048	3	4	0.02	0.02	0.00	2
Pioneer	HCRC048	4	5	0.01	0.01	0.00	X
Pioneer	HCRC048	5	6	0.05	0.01	0.01	6
Pioneer	HCRC048A	6	7	0.18	0.01	0.00	3

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC048A	7	8	0.82	0.05	0.00	3
Pioneer	HCRC048A	8	9	0.03	0.01	0.00	2
Pioneer	HCRC048A	9	10	0.02	0.00	0.00	2
Pioneer	HCRC048A	10	11	0.02	0.01	0.00	2
Pioneer	HCRC048A	11	12	0.11	0.13	0.17	11
Pioneer	HCRC049	0	1	0.72	0.48	0.14	165
Pioneer	HCRC049	1	2	0.09	0.39	0.07	7
Pioneer	HCRC049	2	3	0.03	0.01	0.10	X
Pioneer	HCRC049	3	4	0.01	0.01	0.04	X
Pioneer	HCRC049	4	5	0.01	0.01	0.04	X
Pioneer	HCRC049	5	6	0.04	0.01	0.05	X
Pioneer	HCRC049	6	7	0.02	0.02	0.11	X
Pioneer	HCRC049	7	8	0.02	0.04	0.06	5
Pioneer	HCRC049	8	9	0.05	0.06	0.10	X
Pioneer	HCRC049	9	10	0.01	0.02	0.01	X
Pioneer	HCRC049	10	11	0.01	0.03	0.01	X
Pioneer	HCRC049	11	12	0.04	0.01	0.05	1
Pioneer	HCRC049	12	13	0.04	0.00	0.03	2
Pioneer	HCRC049	13	14	0.02	0.00	0.01	X
Pioneer	HCRC049	14	15	0.02	0.01	0.03	1
Pioneer	HCRC049	15	16	0.06	0.01	0.03	1
Pioneer	HCRC049	16	17	0.01	0.00	0.01	X
Pioneer	HCRC049	17	18	0.02	0.01	0.02	X
Pioneer	HCRC049	18	19	0.12	0.02	0.02	6
Pioneer	HCRC049	19	20	0.02	0.01	0.03	1
Pioneer	HCRC049	20	21	0.01	0.00	0.00	X
Pioneer	HCRC049	21	22	X	0.01	0.04	4
Pioneer	HCRC049	22	23	0.01	0.00	0.01	3
Pioneer	HCRC049	23	24	0.02	0.00	0.02	X
Pioneer	HCRC049	24	25	4.52	0.07	0.07	107
Pioneer	HCRC049	25	26	0.29	0.03	0.04	22
Pioneer	HCRC049	26	27	0.57	0.59	0.03	8
Pioneer	HCRC049	27	28	2.16	0.69	0.03	27
Pioneer	HCRC049	28	29	0.10	0.04	0.02	2
Pioneer	HCRC049	29	30	0.03	0.01	0.02	X
Pioneer	HCRC049	30	31	0.25	0.02	0.00	1
Pioneer	HCRC049	31	32	0.05	0.02	0.02	3
Pioneer	HCRC049	32	33	0.01	0.01	0.00	X
Pioneer	HCRC049	33	34	0.02	0.02	0.04	3
Pioneer	HCRC049	34	35	0.38	0.05	0.21	10
Pioneer	HCRC049	35	36	0.07	0.09	0.22	16
Pioneer	HCRC049	36	37	0.03	0.06	0.10	5
Pioneer	HCRC049	37	38	0.29	0.00	0.00	22
Pioneer	HCRC049	38	39	0.01	0.00	0.00	2
Pioneer	HCRC049	39	40	0.02	0.03	0.00	5
Pioneer	HCRC049	40	41	0.29	0.10	0.00	20
Pioneer	HCRC049	41	42	0.03	0.04	0.00	X
Pioneer	HCRC049	42	43	X	0.00	0.00	X
Pioneer	HCRC049	43	44	0.02	0.00	0.00	2
Pioneer	HCRC049	44	45	0.04	0.27	0.19	X

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC049	45	46	X	0.03	0.01	5
Pioneer	HCRC049	46	47	0.59	10.37	1.41	22
Pioneer	HCRC049	47	48	0.01	0.10	0.01	X
Pioneer	HCRC049	48	49	0.01	0.03	0.01	X
Pioneer	HCRC049	49	50	0.02	0.11	0.03	4
Pioneer	HCRC049	50	51	0.01	0.01	0.00	4
Pioneer	HCRC049	51	52	0.01	0.04	0.01	16
Pioneer	HCRC049	52	53	0.09	0.01	0.16	263
Pioneer	HCRC049	53	54	0.04	0.02	0.02	42
Pioneer	HCRC049	54	55	0.07	0.04	0.09	93
Pioneer	HCRC049	55	56	0.01	0.00	0.01	4
Pioneer	HCRC049	56	57	0.01	0.00	0.00	2
Pioneer	HCRC049	57	58	0.01	0.00	0.00	2
Pioneer	HCRC049	58	59	0.01	0.00	0.00	2
Pioneer	HCRC049	59	60	0.30	0.01	0.01	27
Pioneer	HCRC049	60	61	0.13	0.02	0.03	30
Pioneer	HCRC049	61	62	0.01	0.02	0.02	4
Pioneer	HCRC049	62	63	0.01	0.01	0.01	2
Pioneer	HCRC049	63	64	0.01	0.00	0.01	5
Pioneer	HCRC049	64	65	0.02	0.06	0.07	19
Pioneer	HCRC049	65	66	0.02	0.01	0.14	2
Pioneer	HCRC049	66	67	0.06	0.01	0.03	15
Pioneer	HCRC049	67	68	0.01	0.01	0.02	9
Pioneer	HCRC049	68	69	0.03	0.01	0.02	10
Pioneer	HCRC049	69	70	0.01	0.00	0.01	2
Pioneer	HCRC049	70	71	0.01	0.00	0.01	2
Pioneer	HCRC049	71	72	0.03	0.00	0.04	6
Pioneer	HCRC049	72	73	0.20	0.42	0.46	122
Pioneer	HCRC049	73	74	0.06	0.13	0.13	34
Pioneer	HCRC049	74	75	0.01	0.01	0.02	3
Pioneer	HCRC049	75	76	0.26	0.54	1.14	26
Pioneer	HCRC049	76	77	0.05	0.01	0.23	9
Pioneer	HCRC049	77	78	0.03	0.04	0.03	7
Pioneer	HCRC049	78	79	0.07	0.17	0.06	31
Pioneer	HCRC049	79	80	0.02	0.01	0.01	3
Pioneer	HCRC049	80	81	0.01	0.01	0.01	4
Pioneer	HCRC049	81	82	0.01	0.01	0.01	X
Pioneer	HCRC049	82	83	0.03	0.09	0.06	8
Pioneer	HCRC049	83	84	0.02	0.07	0.03	4
Pioneer	HCRC049	84	85	0.01	0.01	0.01	2
Pioneer	HCRC049	85	86	0.01	0.01	0.01	2
Pioneer	HCRC049	86	87	0.29	6.60	0.29	419
Pioneer	HCRC049	87	88	0.01	0.12	0.02	7
Pioneer	HCRC049	88	89	0.01	0.02	0.02	2
Pioneer	HCRC049	89	90	0.04	0.01	0.01	3
Pioneer	HCRC049	90	91	0.02	0.13	0.07	17
Pioneer	HCRC049	91	92	0.04	0.24	0.13	49
Pioneer	HCRC049	92	93	0.03	0.04	0.18	4
Pioneer	HCRC049	93	94	0.05	0.07	0.10	9
Pioneer	HCRC049	94	95	0.01	0.03	0.02	2

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Pioneer	HCRC049	95	96	0.37	1.44	0.11	308
Pioneer	HCRC049	96	97	0.24	0.89	0.10	235
Pioneer	HCRC049	97	98	0.03	0.10	0.08	20
Pioneer	HCRC049	98	99	0.75	0.04	0.07	9
Pioneer	HCRC049	99	100	0.04	0.02	0.03	2
Pioneer	HCRC049	100	101	0.01	0.00	0.02	1
Pioneer	HCRC049	101	102	0.01	0.00	0.02	1
Pioneer	HCRC049	102	103	0.04	0.05	0.06	2
Pioneer	HCRC049	103	104	0.01	0.01	0.02	1
Pioneer	HCRC049	104	105	0.01	0.01	0.01	X
Pioneer	HCRC049	105	106	0.02	0.08	0.03	X
Pioneer	HCRC049	106	107	0.01	0.01	0.03	X
Pioneer	HCRC049	107	108	0.01	0.01	0.02	X
Pioneer	HCRC049	108	109	0.01	0.01	0.01	X
Pioneer	HCRC049	109	110	0.01	0.00	0.01	1
Pioneer	HCRC049	110	111	0.01	0.01	0.01	1
Pioneer	HCRC049	111	112	X	0.00	0.01	1
Pioneer	HCRC049	112	113	0.01	0.02	0.01	8
Pioneer	HCRC049	113	114	0.01	0.01	0.01	1
Treasure	HCRC050	0	1		0.15	0.14	36
Treasure	HCRC050	1	2		0.27	0.07	64
Treasure	HCRC050	2	3		0.12	0.04	30
Treasure	HCRC050	3	4		0.03	0.02	11
Treasure	HCRC050	4	5		0.02	0.03	21
Treasure	HCRC050	5	6		0.01	0.03	12
Treasure	HCRC050	6	7		0.04	0.10	16
Treasure	HCRC050	7	8		0.20	0.08	43
Treasure	HCRC050	8	9		0.04	0.08	41
Treasure	HCRC050	9	10		0.03	0.04	34
Treasure	HCRC050	10	11		0.05	0.04	51
Treasure	HCRC050	11	12		0.03	0.03	33
Treasure	HCRC050	12	13		0.03	0.04	43
Treasure	HCRC050	13	14		0.01	0.06	31
Treasure	HCRC050	14	15		0.04	0.08	24
Treasure	HCRC050	15	16		0.01	0.19	23
Treasure	HCRC050	16	17		0.01	0.12	20
Treasure	HCRC050	17	18		0.03	0.08	22
Treasure	HCRC050	18	19		0.05	0.02	24
Treasure	HCRC050	19	20		0.03	0.01	40
Treasure	HCRC050	20	21		0.01	0.02	40
Treasure	HCRC050	21	22		0.01	0.04	5
Treasure	HCRC050	22	23		0.03	0.08	27
Treasure	HCRC050	23	24		0.03	0.16	44
Treasure	HCRC050	24	25		0.05	0.22	126
Treasure	HCRC050	25	26		0.04	0.18	68
Treasure	HCRC050	26	27		0.02	0.12	35
Treasure	HCRC050	27	28		0.03	0.15	59
Treasure	HCRC050	28	29		0.03	0.18	82
Treasure	HCRC050	29	30		0.01	0.11	48
Treasure	HCRC050	30	31		0.04	0.13	129

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC050	31	32		0.06	0.10	64
Treasure	HCRC050	32	33		0.09	0.06	50
Treasure	HCRC050	33	34		0.06	0.07	53
Treasure	HCRC050	34	35		0.18	0.11	78
Treasure	HCRC050	35	36		0.02	0.09	46
Treasure	HCRC050	36	37		0.01	0.06	30
Treasure	HCRC050	37	38		0.02	0.06	31
Treasure	HCRC050	38	39		0.34	0.03	66
Treasure	HCRC050	39	40		0.03	0.03	18
Treasure	HCRC050	40	41		0.03	0.02	17
Treasure	HCRC050	41	42		0.02	0.01	19
Treasure	HCRC050	42	43		0.03	0.03	21
Treasure	HCRC050	43	44		0.03	0.03	18
Treasure	HCRC050	44	45		0.02	0.04	37
Treasure	HCRC050	45	46		0.03	0.04	31
Treasure	HCRC050	46	47		0.02	0.05	49
Treasure	HCRC050	47	48		0.20	0.03	68
Treasure	HCRC050	48	49		0.04	0.03	35
Treasure	HCRC050	49	50		0.02	0.02	37
Treasure	HCRC050	50	51		0.01	0.01	30
Treasure	HCRC050	51	52		0.02	0.00	33
Treasure	HCRC050	52	53		0.01	0.01	40
Treasure	HCRC050	53	54		0.01	0.01	36
Treasure	HCRC050	54	55		0.01	0.01	40
Treasure	HCRC050	55	56		0.08	0.01	61
Treasure	HCRC050	56	57		0.01	0.01	33
Treasure	HCRC050	57	58		0.02	0.01	38
Treasure	HCRC050	58	59		0.02	0.01	26
Treasure	HCRC050	59	60		0.01	0.01	18
Treasure	HCRC050	60	61		0.19	0.01	47
Treasure	HCRC050	61	62		0.03	0.01	33
Treasure	HCRC050	62	63		0.01	0.01	42
Treasure	HCRC050	63	64		0.13	0.07	78
Treasure	HCRC050	64	65		0.56	0.22	102
Treasure	HCRC050	65	66		0.03	0.09	26
Treasure	HCRC050	66	67		0.10	0.14	40
Treasure	HCRC050	67	68		0.02	0.06	17
Treasure	HCRC050	68	69		0.01	0.05	16
Treasure	HCRC050	69	70		0.06	0.01	25
Treasure	HCRC050	70	71		0.02	0.00	42
Treasure	HCRC050	71	72		0.08	0.01	42
Treasure	HCRC050	72	73		0.04	0.01	26
Treasure	HCRC050	73	74		0.04	0.00	46
Treasure	HCRC050	74	75		1.75	0.01	232
Treasure	HCRC050	75	76		0.38	0.02	236
Treasure	HCRC050	76	77		0.06	0.02	27
Treasure	HCRC050	77	78		0.02	0.01	31
Treasure	HCRC050	78	79		0.01	0.00	37
Treasure	HCRC050	79	80		0.01	0.01	24
Treasure	HCRC050	80	81		0.01	0.00	32

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC050	81	82		0.01	0.01	53
Treasure	HCRC050	82	83		0.12	0.01	80
Treasure	HCRC050	83	84		0.04	0.02	43
Treasure	HCRC050	84	85		0.02	0.01	14
Treasure	HCRC050	85	86		0.09	0.01	28
Treasure	HCRC050	86	87		0.10	0.01	46
Treasure	HCRC050	87	88		0.11	0.01	45
Treasure	HCRC050	88	89		0.94	0.04	43
Treasure	HCRC050	89	90		1.04	0.06	79
Treasure	HCRC050	90	91		0.04	0.03	37
Treasure	HCRC050	91	92		0.02	0.06	209
Treasure	HCRC050	92	93		0.02	0.00	24
Treasure	HCRC050	93	94		0.02	0.16	13
Treasure	HCRC050	94	95		0.04	0.01	19
Treasure	HCRC050	95	96		0.01	0.06	25
Treasure	HCRC050	96	97		0.02	0.04	49
Treasure	HCRC050	97	98		0.13	0.06	195
Treasure	HCRC050	98	99		0.01	0.08	19
Treasure	HCRC050	99	100		0.02	0.03	40
Treasure	HCRC050	100	101		0.01	0.04	36
Treasure	HCRC050	101	102		0.01	0.06	78
Treasure	HCRC050	102	103		0.04	0.04	54
Treasure	HCRC050	103	104		0.02	0.04	15
Treasure	HCRC050	104	105		0.00	0.02	50
Treasure	HCRC050	105	106		0.00	0.07	22
Treasure	HCRC050	106	107		0.00	0.01	24
Treasure	HCRC050	107	108		0.00	0.01	15
Treasure	HCRC050	108	109		0.02	0.09	12
Treasure	HCRC050	109	110		0.04	0.11	54
Treasure	HCRC050	110	111		0.17	0.06	76
Treasure	HCRC050	111	112		0.01	0.06	25
Treasure	HCRC050	112	113		0.03	0.03	64
Treasure	HCRC050	113	114		0.06	0.12	19
Treasure	HCRC050	114	115		0.19	0.21	24
Treasure	HCRC050	115	116		0.03	0.01	22
Treasure	HCRC050	116	117		0.22	0.00	34
Treasure	HCRC050	117	118		0.03	0.03	34
Treasure	HCRC050	118	119		0.30	0.05	97
Treasure	HCRC050	119	120		0.05	0.05	90
Treasure	HCRC050	120	121		0.03	0.02	37
Treasure	HCRC050	121	122		0.06	0.00	17
Treasure	HCRC050	122	123		0.09	0.01	35
Treasure	HCRC050	123	124		0.03	0.05	35
Treasure	HCRC050	124	125		0.80	0.27	605
Treasure	HCRC050	125	126		0.38	0.06	58
Treasure	HCRC050	126	127		0.03	0.04	70
Treasure	HCRC050	127	128		0.28	0.05	188
Treasure	HCRC050	128	129		0.26	0.06	299
Treasure	HCRC050	129	130		0.03	0.01	20
Treasure	HCRC050	130	131		0.06	0.01	41

Prospect	Hole#	From	To	Au (ppm)	WO3 (%)	Cu (%)	Mo (ppm)
Treasure	HCRC050	131	132		0.05	0.06	70
Treasure	HCRC050	132	133		0.02	0.21	47
Treasure	HCRC050	133	134		0.01	0.13	12
Treasure	HCRC050	134	135		0.04	0.14	113
Treasure	HCRC050	135	136		0.02	0.04	85
Treasure	HCRC050	136	137		0.09	0.08	514
Treasure	HCRC050	137	138		0.27	0.16	1058
Treasure	HCRC050	138	139		0.10	0.16	72
Treasure	HCRC050	139	140		0.07	0.11	1922
Treasure	HCRC050	140	141		0.03	0.12	96
Treasure	HCRC050	141	142		0.03	0.02	37
Treasure	HCRC050	142	143		0.01	0.01	25
Treasure	HCRC050	143	144		0.01	0.01	55
Treasure	HCRC050	144	145		0.01	0.11	23
Treasure	HCRC050	145	146		0.00	0.04	22
Treasure	HCRC050	146	147		0.01	0.01	26
Treasure	HCRC050	147	148		0.01	0.01	9
Treasure	HCRC050	148	149		0.04	0.00	14
Treasure	HCRC050	149	150		0.01	0.01	9
Treasure	HCRC050	150	151		0.00	0.03	17
Treasure	HCRC050	151	152		0.02	0.18	43
Treasure	HCRC050	152	153		0.77	0.09	25
Treasure	HCRC050	153	154		0.09	0.06	420
Treasure	HCRC050	154	155		0.05	0.13	244
Treasure	HCRC050	155	156		0.20	0.12	115
Treasure	HCRC050	156	157		0.88	0.11	1157
Treasure	HCRC050	157	158		0.57	0.06	130
Treasure	HCRC050	158	159		0.04	0.19	41
Treasure	HCRC050	159	160		0.04	0.20	68
Treasure	HCRC050	160	161		0.01	0.06	9
Treasure	HCRC050	161	162		0.01	0.28	7
Treasure	HCRC050	162	163		0.02	0.17	19
Treasure	HCRC050	163	164		0.02	0.30	12
Treasure	HCRC050	164	165		0.03	0.15	16
Treasure	HCRC050	165	166		0.00	0.03	8
Treasure	HCRC050	166	167		0.08	0.14	14
Treasure	HCRC050	167	168		0.12	0.13	416
Treasure	HCRC050	168	169		0.01	0.17	241
Treasure	HCRC050	169	170		0.00	0.02	53
Treasure	HCRC050	170	171		0.08	0.00	21
Treasure	HCRC050	171	172		0.03	0.01	20
Treasure	HCRC050	172	173		0.00	0.00	21
Treasure	HCRC050	173	174		0.00	0.00	19
Treasure	HCRC050	174	175		0.04	0.01	28
Treasure	HCRC050	175	176		0.00	0.00	14
Treasure	HCRC050	176	177		0.04	0.00	17
Treasure	HCRC050	177	178		0.01	0.00	13
Treasure	HCRC050	178	179		0.01	0.00	12
Treasure	HCRC050	179	180		0.00	0.00	11

Appendix 2
JORC 2012 Table 1

JORC 2012 TABLE 1

Section 1: Sampling Techniques and Data

Criteria	JORC Code explanation	Commentary
Sampling techniques	<p><i>Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling.</i></p>	<p>The Black Diamond, Bonanza, Green Diamond, Hit or Miss, Kangaroo, Pioneer, Silver Granite, and Treasure prospect areas at the Hatches Creek project were sampled using Reverse Circulation (“RC”) drilling. A total of 33 holes for an aggregate of 3388 m were completed.</p> <p>This ASX release reports upon results from 14 RC drill holes located at the Pioneer, Black Diamond, Green Diamond, Bonanza and Treasure prospects, as defined in Table 1 in the body of the report</p>
	<p><i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used</i></p>	<p>The drill holes were located to intersect the mineralisation at representative points to help with the overall understanding of the geology and distribution of the mineralisation.</p> <p>All the sample recoveries were visually estimated and logged as they were collected and all the samples were consistently logged as approximately 100%.</p> <p>All the drill samples as well as QA/QC samples including duplicates and Certified Standards were submitted to an independent, ISO certified laboratory for chemical analysis.</p> <p>No measurement tools or systems were used that required calibration.</p>
	<p><i>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where ‘industry standard’ work has been done this would be relatively simple (e.g. ‘reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay’). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information</i></p>	<p>Samples were collected at 1 m intervals using cyclone and passed through a cone splitter. Duplicate (A and B sample) sub samples were collected of approximately 2 to 4 kg in pre-numbered and barcoded calico sample bags and the residue stored in a plastic bag. The “A” calico bag sample was submitted to Intertek Genalysis Laboratory in Alice Springs where the following was carried out;</p> <ul style="list-style-type: none"> • Dried and pulverized • WO₃ (2ppm) , Al₂O₃ (0.02%), As (20 ppm), Bi (0.1 ppm), CaO (0.2%), Cu (20 ppm), Fe (0.01%), MgO (0.02%), MnO (40 ppm), Mo (1 ppm), S (0.05%) ,Sb (0.5 ppm), SiO₂ (0.3%), Sn (0.01%), and TiO₂ (0.02%) were all analysed using the Intertek Genalysis sodium peroxide fusion zirconium crucible followed by ICP technique with detection limits as listed with each analyte. • Samples at the Pioneer prospect were also analysed for Au using a 50 g fire assay technique

Criteria	JORC Code explanation	Commentary
Drilling techniques	<i>Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i>	A total of 33 RC holes for an aggregate of 3388 m were completed at depths ranging from 11 to 180 m, averaging 103 m. All of the drilling was undertaken using a 146 mm face sampling RC hammer
Drill sample recovery	<i>Method of recording and assessing core and chip sample recoveries and results assessed</i>	The sample recovery was visually assessed and recorded on drill logs and is considered to be acceptable.
	<i>Measures taken to maximise sample recovery and ensure representative nature of the samples</i>	The samples were visually checked for recovery, moisture and contamination. A cyclone and cone splitter were utilised to provide a representative sample and were regularly cleaned. The drilling contractor blew out the hole at the beginning of each rod to remove any water.
	<i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i>	The ground conditions were good and the drilling returned consistent sized dry samples and the possibility of sample bias through selective recoveries is considered negligible.
Logging	<i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i>	All samples were geologically logged with lithology and mineralisation recorded. This logging was of sufficient detail to support the findings of this report and, after further drilling is completed, included in later Mineral Resource estimation.
	<i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i>	The drill sample logging was qualitative.
	<i>The total length and percentage of the relevant intersections logged</i>	All the drill samples were logged.
Sub-sampling techniques and sample preparation	<i>If core, whether cut or sawn and whether quarter, half or all core taken.</i>	This section is not applicable as there were no core samples collected.
	<i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i>	The RC drilling chip samples were collected using a cyclone and then duplicate sub samples of 2- 4 kg in size collected using a cone splitter attached to the cyclone. All samples were dry.
	<i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i>	<p>Samples were submitted to Intertek Genalysis in Alice Springs where the following sample preparation procedures were carried out;</p> <ul style="list-style-type: none"> • The sample was dried and crushed • Samples in excess of 3 kg are riffle split • The crushed sample is pulverized <p>These sample preparation procedures followed by the laboratory meet industry standards and are appropriate for the sample type and mineralisation being analysed.</p>

Criteria	JORC Code explanation	Commentary
	<p><i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i></p>	<p>Certified Standards and duplicate samples were routinely inserted into the sample sequences submitted for chemical analysis according to GWR Group Limited ("GWR") QA/QC procedures. Results from the QA/QC were found to be acceptable. Intertek Genalysis also carried out internal QA/QC as per their operating procedures</p>
	<p><i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i></p>	<p>Field duplicates of the drilling samples were routinely collected and these were all found to agree within acceptable limits with the original samples.</p>
	<p><i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i></p>	<p>The sample size is considered appropriate to the grain size of the material being sampled.</p>
<p>Quality of assay data and laboratory tests</p>	<p><i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i></p>	<p>Sodium Peroxide Fusion has proven to be a very accurate analytical technique for samples in which the elements of interest are hosted in minerals that may resist acid digestions. ICP is utilised for assaying, since it provides good accuracy and precision; it is suitable for analysis across appropriate grade ranges.</p> <p>Fire Assay techniques are considered appropriate and industry standard for the elements analysed using this technique with the detection limits as stated</p> <p>The assaying techniques used are total analyses.</p>
	<p><i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></p>	<p>Since this equipment was not used, this section is not applicable.</p>
	<p><i>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</i></p>	<p>Certified Standards and duplicate samples were routinely inserted into the sample sequences submitted for chemical analysis according to GWR Group Limited ("GWR") QA/QC procedures. Results from the QA/QC indicate that the assays met acceptable levels of accuracy without significant bias. Intertek Genalysis also carried out internal QA/QC as per their operating procedures.</p> <p>No blanks were used for QA/QC checking. The risk of contamination during sample preparation was considered minimal because of the mineralogy of the samples being tested.</p> <p>At this early stage of the exploration program no external laboratory checks have been undertaken.</p>

Criteria	JORC Code explanation	Commentary
Verification of sampling and assaying	<i>The verification of significant intersections by either independent or alternative company personnel.</i>	Brian Varndell of Al Maynard and Associates, who are consultants to GWR, has checked and verified the data pertaining to the significant intercepts. Final check will be undertaken once all results are in.
	<i>The use of twinned holes.</i>	At this early stage of the exploration program no twin holes have been drilled.
	<i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i>	All field data is recorded on log sheets as per GWR operating procedures. Drill data is entered into a digital database and is also stored in hard copy in Perth office. The digital data was checked against the field logs by the geologist after the data entry was completed and also checked visually on cross sections.
	<i>Discuss any adjustment to assay data.</i>	No adjustments to the assay data were made.
Location of data points	<i>Accuracy and quality of surveys used to locate drillholes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i>	All 33 drill holes have collars surveyed by Southern Cross Surveys Pty Ltd using GNSS (mmGPS) with manufacturers Specifications of +/- 10 mm North & East and +/- 15 mm RL All holes were down hole surveyed by Wireline Services Group using a Surface Reference MEMS gyroscope.
	<i>Specification of the grid system used.</i>	The grid system is MGA GDA94 Zone 53.
	<i>Quality and adequacy of topographic control.</i>	High resolution aerial photogrammetry was collected using an unmanned aerial vehicle (UAV) survey undertaken in August 2015 with an accuracy of +/-40 mm in all 3 dimensions.
Data spacing and distribution	<i>Data spacing for reporting of Exploration Results.</i>	The drilling is of a first pass nature to test the overall geology and indicative style and extent of the mineralisation only.
	<i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i>	No resource estimation was undertaken using the drilling data so this section is not applicable
	<i>Whether sample compositing has been applied.</i>	Only 1 m RC drill samples were collected and no sample compositing was undertaken.

Criteria	JORC Code explanation	Commentary
<p>Orientation of data in relation to geological structure</p>	<p><i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i></p> <hr/> <p><i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i></p>	<p>The drilling with the exception of HCRC050 was designed to intersect mineralisation approximately perpendicular to the mineralisation and not biased towards any special grade areas. However since the orientation of the mineralisation has not been determined accurately at this early stage, the intersection widths may be appreciably longer than the true width of the mineralisation intersected and some mineralised structures intersected at sub-optimal angles.</p> <p>In respect to HCRC050 located at the Treasure prospect because of terrain issues this hole was drilled oblique to the interpreted mineralisation orientation</p> <hr/> <p>Since the drilling to date has been exploratory and not at a sufficient density to properly determine the orientation and grade of the mineralisation, it cannot be determined at this early stage if the orientation of the drilling has introduced a sampling bias. But the knowledge of the mineralisation gained so far from surface mapping and drilling indicates that the drilling has been properly oriented to test the mineralisation without undue bias.</p>
<p>Sample security</p>	<p><i>The measures taken to ensure sample security.</i></p>	<p>Samples were collected in calico sample bags, then placed in a polyweave bag and the bag sealed with a cable tie. The individual bags were then placed in a Bulka Bag and this bag was sealed with rope. The bulka bags were transported by trucking contractors to Intertek Genalysis in Alice Springs.</p>
<p>Audits or reviews</p>	<p><i>The results of any audits or reviews of sampling techniques and data.</i></p>	<p>Since the exploration program is only at an early stage there have been no audits or reviews of the sampling techniques. It is believed by GWR that the sampling procedures and techniques followed meet current international standards of quality.</p> <p>Independent geological consultants, Al Maynard & Associates, will audit the drilling data once all results are in.</p>

Section 2: REPORTING OF EXPLORATION RESULTS

Criteria	JORC Code explanation	Commentary
<p>Mineral tenement and land tenure status</p>	<p>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</p>	<p>The Hatches Creek project is located in the Northern Territory of Australia upon EL22912 and EL23463 covering a total area of approximately 31.8 km²</p> <p>The registered holder of the tenements is NT Tungsten Pty Ltd, which is a 100% owned subsidiary of GWR Group Limited.</p> <p>The tenements are located upon Aboriginal Freehold Land, which is owned by the Anurrete Aboriginal Trust and administered by the Central Land Council (CLC), with whom a Deed of Exploration has been executed</p> <p>NT Tungsten holds a 100% interest in the tenements and a 1.5% net smelter royalty is payable to Davenport Resources Limited.</p>
	<p>The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.</p>	<p>The tenements are in good standing.</p>
<p>Exploration done by other parties</p>	<p>Acknowledgment and appraisal of exploration by other parties.</p>	<p>Previous mining activities up to 1960 are well documented and are summarised in Bulletin No 6 "The Geology and Mineral Resources of the Hatches Creek Wolfram Field, Northern Territory", G. R Ryan 1961.</p> <p>Between 2008 and 2015 the ground was held by numerous companies associated with Davenport Resources Limited and Arunta Resources Limited. Their activities focused on sampling and mapping of the historical mine workings.</p>
<p>Geology</p>	<p>Deposit type, geological setting and style of mineralisation.</p>	<p>Tungsten mineralisation at Hatches Creek is associated with quartz veins in shear zones within a variety of Proterozoic host rocks forming part of the Davenport Province. Wolframite and Scheelite are the dominant tungsten minerals present</p>
<p>Drill hole Information</p>	<p>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</p> <ul style="list-style-type: none"> • easting and northing of the drill hole collar • elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar • dip and azimuth of the hole • down hole length and interception depth • hole length. 	<p>All relevant data for GWR's RC drilling is summarised in Table 1 in the body of the report and all assay data in Appendix 1</p>

Criteria	JORC Code explanation	Commentary
<p>Data aggregation methods</p>	<p>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</p> <hr/> <p>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</p> <hr/> <p>The assumptions used for any reporting of metal equivalent values should be clearly stated.</p>	<p>Significant Intercept Significant intersections are reported for all intervals greater than 1m at 0.1% WO₃ and or greater than 0.5% Cu or greater than 2 m at 0.1% and or >0.5% Cu with up to 2 m of internal waste. At Pioneer Au intercepts of >0.5 g/t Au and greater than 1 m have also been reported.</p> <p>All composited intercept assays were weighted by sample length.</p> <p>No upper cut-off grades were applied,</p> <p>Mineralised Zone A mineralised zone has been reported for some drill holes which encompass the significant intercepts within defined structures that do contain multiple mineralised structures as reported in Table 2 of the body of the report.</p> <hr/> <p>All the drill samples are collected over consistent 1 m intervals and composited assays weighted by sample lengths.</p> <hr/> <p>No metal equivalents were calculated</p>
<p>Relationship between mineralisation widths and intercept lengths</p>	<p>These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known').</p>	<p>Based upon historical mine reports and surface observations; the geometry of the mineralisation is reasonably well understood. In most cases the drilling is close to perpendicular to the strike and as the mineralisation is steeply dipping, true widths of the mineralisation are considered to be greater than 60% of the intercept width. Plans and are provided in the body of the report for the Pioneer and Treasure prospects that show the relationship between the drill holes and the mineralisation.</p>
<p>Diagrams</p>	<p>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</p>	<p>The results of all 33 holes completed in the program are being compiled as summarised in Table 1 of the body of the report as such plans and sections are incomplete. These will be finalised and reported in detail.</p>
<p>Balanced reporting</p>	<p>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</p>	<p>All drilling results are provided in Appendix 1 of the report.</p>

Criteria	JORC Code explanation	Commentary
Other substantive exploration data	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	<p>The area was the subject of detailed study by the Bureau of Mineral Resources and this was published in Bulletin No 6 (1961). The geology of all the areas drilled are described in detail in this report.</p> <p>GWR has undertaken significant metallurgical test work on representative mineralised samples with the results of these tests reported in previous ASX announcements.</p>
Further work	The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling). Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive	Further RC drilling and possibly diamond drilling is planned to follow up on the results described in this report and also to evaluate the remaining prospect areas not tested in the current program.