

BONANZA GOLD INTERSECTION

*****173.2m @ 3.27 g/t Au and 11.8 g/t Ag*****

****103m @ 5.06 g/t Au and 13.4 g/t Ag****

inc. 1m @ 139 g/t Au and 24.0 g/t Ag from 154m

Highlights

- ★ UGA-30 intersected a thick, continuous mineralized zone of 173.2m @ 3.27 g/t Au and 11.8 g/t Ag from 0m (0.25g/t Au cut-off, downhole thickness) for 566 grams metres gold including:
 - 103m @ 5.06 g/t Au and 13.4 g/t Ag from 57m (1g/t Au cut-off, downhole thickness); including:
 - 8m @ 7.16g/t Au and 11.3 g/t Ag from 84m (3g/t Au cut-off, downhole thickness); and
 - 19m @ 11.35 g/t Au and 23.9 g/t Ag from 119m (3g/t Au cut-off, downhole thickness); including:
 - 2m @ 42.50 g/t Au and 53.3 g/t Ag from 119m (no Au cut-off, downhole thickness); and
 - 1m @ 67.90 g/t Au and 94.5 g/t Ag from 127m (no Au cut-off, downhole thickness);
 - 7m @ 23.30 g/t Au and 24.0 g/t Ag from 153m (3g/t Au cut-off, downhole thickness); including:
 - 1m @ 139 g/t Au and 24.0 g/t Ag from 154m (no Au cut-off, downhole thickness);

Cautionary Note: This intersection is not a true thickness as the drill hole was drilled at an acute angle to the mineralised zone due to the location of the underground drill site relative to the target zone. As this is an infill drill hole, resource modelling suggests the true thickness of mineralisation in this area is between 50-55m wide.

- ★ UGA-25 intersected a thick, continuous mineralized zone of 53m @ 0.86 g/t Au and 10.0 g/t Ag from 95m (0.25g/t Au cut-off, downhole thickness) including:
 - 23m @ 1.46 g/t Au and 15.1 g/t Ag from 104m (0.5g/t Au cut-off, downhole thickness); including:
 - 7m @ 2.75 g/t Au and 23.3 g/t Ag from 120m (1g/t Au cut-off, downhole thickness);
- ★ UGA-27 intersected a thick, continuous mineralized zone of 47m @ 0.61 g/t Au and 1.5 g/t Ag from 104m (0.25g/t Au cut-off, downhole thickness) including:
 - 12m @ 1.22 g/t Au and 2.0 g/t Ag from 139m (0.3g/t Au cut-off, downhole thickness); including:
 - 6m @ 2.09 g/t Au and 3.0 g/t Ag from 143m (0.5g/t Au cut-off, downhole thickness); including
 - 2m @ 5.14 g/t Au and 4.6 g/t Ag from 143m (1g/t Au cut-off, downhole thickness);

Cautionary Note: These intersections are not a true thickness as the drill hole was drilled at an angle to the mineralised zone due to the location of the underground drill site relative to the target zone. Further drilling is necessary to better constrain the interpretation in this area

- ★ Assay results from UGA-30 offers strong confidence to the existing Sturec Mineral Resource

** This announcement is authorised by the executive board on behalf of the Company **



Commenting on the recent assay results, MetalsTech Director, Gino D'Anna stated:

“The ore body at Sturec continues to deliver impressive zones of gold mineralisation. Our drilling has grown the confidence of the existing Sturec Mineral Resource and demonstrated that the mineralisation extends further to the south along strike of the existing resource and remains open down dip/plunge.”

MetalsTech Limited (ASX: MTC) (the Company or MTC) is pleased to provide stakeholders with an update on its Phase II diamond drilling program at the Company's 100% owned Sturec Gold Mine, located in Slovakia (Sturec). To date the Company has completed twelve diamond drill holes from Drill Chamber II within the Andrej Adit; and eight diamond drill holes from Drill Chamber III, with a ninth underway. This drill program has been designed to extend the mineralisation to the south along strike of the southern margin of the existing Sturec Mineral Resource; as well as increase the confidence of the southern extent of the existing Sturec Mineral Resource.

UGA-30

UGA-30 was stopped to a depth of 173.6m due to drilling issues but was still in variably argillic altered andesite host rock containing varying amounts of quartz filled vein / stockwork / breccia, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite). The drill hole collar details for drill holes from Phase II drill programme are set out in Table 1 and 2 below.

Table 1: drill holes from Drill Chamber II

Hole ID	Easting JTSK	Northing JTSK	Elevation (m)	Azimuth (°)	Dip (°)	Depth (m)
UGA-17	-435,852	-1,230,270	656.96	270	-70	109.35
UGA-18	-435,852	-1,230,270	656.96	230	-55	104.65
UGA-19	-435,852	-1,230,270	656.96	210	-30	101.6
UGA-20	-435,852	-1,230,270	656.96	205	-45	140.5
UGA-21	-435,852	-1,230,270	656.96	205	-65	178.2
UGA-22	-435,852	-1,230,270	656.96	200	-35	143.3
UGA-23	-435,852	-1,230,270	656.96	200	-42	179.5
UGA-24	-435,852	-1,230,270	656.96	195	-30	180.8
UGA-25	-435.852	-1.230.270	656.96	195	-37	180.8
UGA-26	-435.852	-1.230.270	656.96	300	-65	101.5
UGA-27	-435.852	-1.230.270	656.96	350	-65	214.3
UGA-28	-435.852	-1.230.270	656.96	335	-70	151.2

Table 2: drill holes from Drill Chamber III

Hole ID	Easting JTSK	Northing JTSK	Elevation (m)	Azimuth (°)	Dip (°)	Depth (m)
UGA-29	-435.851	-1.230.123	656.96	280	-80	84.7
UGA-30	-435.851	-1.230.123	656.96	008	-45	173.6
UGA-31	-435.851	-1.230.123	656.96	355	-60	106.45
UGA-32	-435.851	-1.230.123	656.96	325	-60	79.3
UGA-33	-435.851	-1.230.123	656.96	008	-70	109.2
UGA-34	-435.851	-1.230.123	656.96	270	-50	41.5

** This announcement is authorised by the executive board on behalf of the Company **



UGA-35	-435.851	-1.230.123	656.96	270	-70	64.2
UGA-36	-435.851	-1.230.123	656.96	270	-25	59.8
UGA-37	-435.851	-1.230.123	656.96	230	-40	In progress

UGA-30 was positioned as an infill drill hole above but parallel to UGA-03, which intersected a thick mineralized zone of 59m @ 2.3 g/t Au & 9.4 g/t Ag from 225m (0.3g/t Au cut-off, downhole thickness) including:

- 31.61m @ 3.76 g/t Au & 11 g/t Ag from 248m (0.5g/t Au cut-off)
- 24m @ 4.74 g/t Au & 13.4 g/t Ag from 252m (1g/t Au cut-off)
- 15m @ 6.70 g/t Au & 15.3 g/t Au from 252m (2g/t Au cut-off)
- 7m @ 11.65 g/t Au & 24.7 g/t Ag from 252m (5g/t Au cut-off)

See Figure 1 and 2 for the relative position of UGA-30 compared to UGA-03 and the existing Sturec Mineral Resource respectively (refer to MTC announcement dated 21 June 2021). UGA-30 was drilled from Drill Chamber III, which is 80m to the north of Drill Chamber I from which UGA-03 was drilled.

UGA-30 intersected variably argillic altered and brecciated andesite host rock containing varying amounts of quartz filled vein/ stockwork/ breccia, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) from approximately 0m to 173.6m down hole (*not true thickness).

Assay results from UGA-30 are interpreted to show a relatively continuous mineralised zone from 0m to 173.6m using a 0.25g/t Au cut-off. A summary of the significant intersections from UGA-30 are shown in Table 3 below.

See Figure 1 and 2 for the relative position of UGA-30 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (refer to MTC announcement dated 21 June 2021).

Table 3: Significant intersections in UGA-23 through to UGA-27 and UGA-30

Hole	Width (m) (Down hole depth)		Au g/t	Ag g/t	From (m) (Down hole depth)	To (m) (Down hole depth)	Cut-off
UGA-30	173.20	@	3.27	11.8	0.00	173.20	0.25g/t Au cut-off and max. 3m continuous internal dilution
	including						
	103.00	@	5.06	13.4	57.00	160.00	0.5g/t Au cut-off and max. 4m continuous internal dilution
	including						
	8.00	@	7.16	11.3	84.00	92.00	3g/t Au cut-off and 2m internal dilution
	and						
	19.00	@	11.35	23.9	119.00	138.00	3g/t Au cut-off and max. 4m continuous internal dilution
	including						
	2.00	@	42.50	53.3	119.00	121.00	no cut-off or dilution
	and						
	1.00	@	67.90	94.5	127.00	128.00	no cut-off or dilution
	and						
	7.00	@	23.30	24.0	153.00	160.00	3g/t Au cut-off and 4m continuous internal dilution
including							
1.00	@	139.00	87.3	154.00	155.00	no cut-off or dilution	

** This announcement is authorised by the executive board on behalf of the Company **



UGA-27	5.00	@	0.84	2.9	41.00	46.00	0.25g/t Au cut-off and no internal dilution
	including						
	2.00	@	1.51	5.7	78.00	80.00	0.5g/t Au cut-off and no internal dilution
	including						
	47.00	@	0.61	1.5	104.00	151.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
	including						
	5.00	@	1.26	2.4	104.00	109.00	0.5g/t Au cut-off and 3m internal dilution
	including						
	12.00	@	1.22	2.0	139.00	151.00	0.3g/t Au cut-off and 2m internal dilution
	including						
	6.00	@	2.09	3.0	143.00	149.00	0.5g/t Au cut-off and 2m internal dilution
including							
2.00	@	5.14	4.6	143.00	145.00	1g/t Au cut-off and no internal dilution	

UGA-26	2.00	@	2.27	13.0	22.00	24.00	0.25g/t Au cut-off and no internal dilution
	including						
	5.00	@	0.55	1.7	34.00	39.00	0.25g/t Au cut-off and 1m internal dilution
	including						
	32.00	@	0.91	16.3	56.00	88.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
	including						
10.00	@	1.50	22.5	69.00	79.00	0.75g/t Au cut-off and 3m internal dilution	

UGA-25	6.00	@	0.68	6.8	42.00	48.00	0.25g/t Au cut-off and 3m internal dilution
	including						
	53.00	@	0.86	10.0	95.00	148.00	0.25g/t Au cut-off and max. 3m continuous internal dilution
	including						
	23.00	@	1.46	15.1	104.00	127.00	0.5g/t Au cut-off and 2m continuous internal dilution
	including						
	7.00	@	2.75	23.3	120.00	127.00	1g/t Au cut-off and no internal dilution
including							
4.00	@	3.86	31.1	121.00	125.00	2g/t Au cut-off and no internal dilution	

UGA-24	15.00	@	1.30	6.8	27.00	42.00	0.25g/t Au cut-off and max. 1m continuous internal dilution
	including						
	11.00	@	1.67	8.5	30.00	41.00	0.5g/t Au cut-off and max. 2m continuous internal dilution
	including						
	2.00	@	5.53	17.5	35.00	37.00	1g/t Au cut-off and no internal dilution
	including						
	52.00	@	0.65	7.0	97.00	149.00	0.25g/t Au cut-off and max. 3m continuous internal dilution
	and						
	17.00	@	1.19	11.7	107.00	124.00	0.5g/t Au cut-off and max. 3m continuous internal dilution
	and						
3.00	@	3.13	16.9	109.00	112.00	1g/t Au cut-off and no internal dilution	

UGA-23	5.00	@	0.56	2.7	47.00	52.00	0.25g/t Au cut-off and no internal dilution
	including						
	3.00	@	0.72	2.7	49.00	52.00	0.5g/t Au cut-off and no internal dilution

** This announcement is authorised by the executive board on behalf of the Company **



53.00	@	0.77	5.9	65.00	118.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
including						
2.00	@	2.71	28.0	79.00	81.00	1g/t Au cut-off and no internal dilution
and						
3.00	@	1.19	2.9	88.00	91.00	0.5g/t Au cut-off and no internal dilution
and						
5.00	@	1.75	6.4	95.00	100.00	1g/t Au cut-off and 1m internal dilution
and						
5.00	@	0.94	7.9	131.00	136.00	0.5g/t Au cut-off and no internal dilution




Figure 1: Long-section showing the traces of holes from the current Phase 2 drill program from Drill Chamber II and III, as well as the previous Phase 1 drill program from Drill Chamber I; shown relative to mineralisation within the existing Sturec Mineral Resource displayed as a 3D point cloud (grade scale shown with pseudocolor spectrum). The position of Drill Chamber IV is also shown. This view is looking west.

** This announcement is authorised by the executive board on behalf of the Company **




Figure 2: Cross-section showing UGA-30 looking northwest and the interpretation of the extents of the mineralisation zone with the current Sturec Mineral Resource.

UGA-27

UGA-27 was completed to a depth of 214.3m. The drill hole collar details set out in Table 1.

Detailed geological logging identified quartz filled veins and locally stockwork/breccia zones, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) and hosted within variably argillic altered and brecciated andesite host rock from approximately 9m to 174m down hole (*not true thickness) in the drill core from hole UGA-27.

Assay results from UGA-27 are interpreted to show a relatively continuous mineralised zone from 104m to 151m using a 0.25g/t Au cut-off, with a central higher grade zone from 143-149m. A summary of the significant intersections from UGA-26 are shown in Table 3.

UGA-27 was positioned as a mineralisation extension drill hole below the existing Sturec Mineral Resource and under UGA-04 and UGA-08 from Drill Chamber I.

See Figure 1 and 3 for the relative position of UGA-27 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (*refer to MTC announcement dated 21 June 2021*).

** This announcement is authorised by the executive board on behalf of the Company **



UGA-26

UGA-26 was completed to a depth of 101.5m. The drill hole collar details set out in Table 1.

Detailed geological logging identified quartz filled veins and locally stockwork/breccia zones, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) and hosted within variably argillic altered and brecciated andesite host rock from approximately 4m to 96m down hole (*not true thickness) in the drill core from hole UGA-26.

Assay results from UGA-26 are interpreted to show a relatively continuous mineralised zone from 56m to 88m using a 0.25g/t Au cut-off, with a central higher grade zone from 69-79m. A summary of the significant intersections from UGA-26 are shown in Table 3.

UGA-26 was positioned as an infill drill hole into the existing Sturec Mineral Resource between UGA-05 and UGA-10 from Drill Chamber I.

See Figure 1 and 3 for the relative position of UGA-26 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (*refer to MTC announcement dated 21 June 2021*).




Figure 3: Cross-section showing UGA-26 and UGA-27 looking west-northwest and the interpretation of the extents of the mineralisation zone with the current Sturec Mineral Resource

** This announcement is authorised by the executive board on behalf of the Company **



UGA-25

UGA-25 was completed to a depth of 180.8m. The drill hole collar details set out in Table 1.

Detailed geological logging identified quartz filled veins and local stockwork/breccia zones, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) and hosted within variably argillic altered and brecciated andesite host rock from approximately 34m to 159m down hole (*not true thickness) in the drill core from hole UGA-25.

Assay results from UGA-25 are interpreted to show a relatively continuous mineralised zone from 95m to 148m using a 0.25g/t Au cut-off, with higher grade zone from 104-127m. A summary of the significant intersections from UGA-25 are shown in Table 3.

UGA-25 was positioned as a mineralisation extension drill hole above and along strike of UGA-14 (for significant assays intersected in UGA-14, refer to MTC announcement dated 1 June 2021 titled “Metalstech Hits Record Intercept At Sturec Gold Mine”).

See Figure 1 and 4 for the relative position of UGA-25 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (refer to MTC announcement dated 21 June 2021).




Figure 4: Cross-section showing UGA-23, UGA-24 and UGA-25 looking northwest and the interpretation of the extents of the mineralisation zone with the current Sturec Mineral Resource.

** This announcement is authorised by the executive board on behalf of the Company **



UGA-24

UGA-24 was completed to a depth of 180.8m. The drill hole collar details set out in Table 1.

Detailed geological logging identified quartz filled veins and local stockwork/breccia zones, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) and hosted within variably argillic altered and brecciated andesite host rock from approximately 24m to 155m down hole (*not true thickness) in the drill core from hole UGA-24.

Assay results from UGA-24 are interpreted to show two relatively continuous mineralised zones from 27-42m and 95-148m using a 0.25g/t Au cut-off, with central higher grade zones from 30-41m and 104-127m respectively. A summary of the significant intersections from UGA-24 are shown in Table 3.

UGA-24 was positioned as a mineralisation extension drill hole above and along strike of UGA-14 (for significant assays intersected in UGA-14, refer to MTC announcement dated 1 June 2021 titled "*Metalstech Hits Record Intercept At Sturec Gold Mine*").

See Figure 1 and 4 for the relative position of UGA-24 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (*refer to MTC announcement dated 21 June 2021*).

UGA-23

UGA-23 was completed to a depth of 179.5m. The drill hole collar details set out in Table 1.

Detailed geological logging identified quartz filled veins and local stockwork/breccia zones, variably rich in fine to very fine grained sulphides (mainly pyrite/marcasite) and hosted within variably argillic altered and brecciated andesite host rock from approximately 38m to 148m down hole (*not true thickness) in the drill core from hole UGA-23.

Assay results from UGA-23 are interpreted to show two relatively continuous mineralised zone from 65- 118m and 131-136m using a 0.25g/t Au cut-off. A summary of the significant intersections from UGA-23 are shown in Table 3.

UGA-23 was positioned as a infill drill hole above UGA-14 (for significant assays intersected in UGA-14, refer to MTC announcement dated 1 June 2021 titled "*Metalstech Hits Record Intercept At Sturec Gold Mine*").

See Figure 1 and 4 for the relative position of UGA-23 compared the current interpretation of the mineralised zone and to the existing Sturec Mineral Resource respectively (*refer to MTC announcement dated 21 June 2021*).

ENDS

For further information, contact:

Gino D'Anna
Director
M +61 400 408 878
gino@metalstech.net

Nathan Ryan
Investor Relations
M +61 420 582 887
nathan.ryan@nwrcommunications.com.au

** This announcement is authorised by the executive board on behalf of the Company **



Caution Regarding Forward-Looking Information

This document contains forward-looking statements concerning MetalsTech. Forward-looking statements are not statements of historical fact and actual events and results may differ materially from those described in the forward-looking statements as a result of a variety of risks, uncertainties and other factors. Forward-looking statements are inherently subject to business, economic, competitive, political and social uncertainties and contingencies. Many factors could cause the Company's actual results to differ materially from those expressed or implied in any forward-looking information provided by the Company, or on behalf of, the Company. Such factors include, among other things, risks relating to additional funding requirements, metal prices, exploration, development and operating risks, competition, production risks, regulatory restrictions, including environmental regulation and liability and potential title disputes.

Forward looking statements in this document are based on the company's beliefs, opinions and estimates of MetalsTech as of the dates the forward-looking statements are made, and no obligation is assumed to update forward looking statements if these beliefs, opinions and estimates should change or to reflect other future developments.

Competent Persons Statement

The information in this announcement that relates to Exploration Results is based on information compiled by Dr Quinton Hills Ph.D., M.Sc., B.Sc. Dr Hills is the technical advisor of MetalsTech Limited and is a member of the Australasian Institute of Mining and Metallurgy (No. 991225). Dr Hills has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Dr Hills consents to the inclusion in the report of the matters based on their information in the form and context in which it appears.

The information in the report to which this statement is attached that relates to Mineral Resources for the Sturec Gold Deposit is based on information compiled by Mr Chris Grove, who is a Member of The Australasian Institute of Mining and Metallurgy (No. 310106). Mr Grove is a full-time employee of Measured Group Pty Ltd and has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Mr Grove consents to the inclusion in the report of the matters based on his information in the form and context in which it appears.

**** This announcement is authorised by the executive board on behalf of the Company ****



Background: Sturec Gold Mine

The Sturec Gold Mine is located in central Slovakia between the town of Kremnica and the village of Lučky, 17km west of central Slovakia's largest city, Banská Bystrica, and 150km northeast of the capital, Bratislava.

Sturec is a low sulphidation epithermal system and contains a total Mineral Resource of 38.5Mt @ 1.23 g/t Au and 8.8 g/t Ag (1.30g/t AuEq¹), containing 1.522Moz of gold and 10.93Moz of silver (1.611Moz of gold equivalent) using a 0.26g/t Au cut-off within an optimised open pit shell; as well as 148kt @ 3.55 g/t Au and 12.6 g/t Ag (3.64g/t AuEq¹), containing 17koz of gold and 60koz of silver (18koz of gold equivalent) outside the optimised open pit shell on an underground mining basis; reported in accordance with JORC (2012).

Mineral Resource Estimate – Sturec Gold Project

Updated Sturec Mineral Resource Estimate							
Resource Estimate above 0.26 g/t Au cut-off and within an optimised open pit shell							
Resource Category	Tonnes (kt)	Au (g/t)	Ag (g/t)	AuEq (g/t) ¹	Au (koz)	Ag (koz)	AuEq (koz)
Measured	15,340	1.43	12.04	1.53	704	5,940	752
Indicated	18,438	1.20	6.74	1.25	709	3,995	742
Measured + Indicated	33,778	1.30	9.15	1.38	1413	9,935	1494
Inferred	4,717	0.72	6.56	0.77	109	995	117
TOTAL	38,495	1.23	8.83	1.30	1,522	10,930	1,611
Resource Estimate above 2 g/t Au cut-off: outside optimised open pit shell							
Resource Category	Tonnes (kt)	Au (g/t)	Ag (g/t)	AuEq (g/t) ¹	Au (koz)	Ag (koz)	AuEq (koz)
Measured	30	2.90	21.18	3.08	3	21	3
Indicated	114	3.75	10.5	3.81	14	38	14
Measured + Indicated	144	3.57	12.74	3.66	17	59	17
Inferred	4	2.73	8.0	2.80	0	1	1
TOTAL	148	3.55	12.62	3.64	17	60	18

¹ AuEq g/t = ((Au g/t grade*Met. Rec.*Au price/g) + (Ag g/t grade*Met. Rec.*Ag price/g)) / (Met. Rec.*Au price/g)

Long term Forecast Gold and Silver Price (source: Bank of America): \$1,785 USD/oz and \$27 USD/oz respectively.

Gold And silver recovery from the 2014 Thiosulphate Metallurgical test work: 90.5% and 48.9% respectively.

It is the Company's opinion that both gold and silver have a reasonable potential to be recovered and sold from the Sturec ore using Thiosulphate Leaching/Electrowinning as per the recoveries indicated.

** This announcement is authorised by the executive board on behalf of the Company **

APPENDIX A: JORC CODE, 2012 EDITION - TABLE 1

Section 1 - Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections)

Criteria	JORC Code Explanation	Details
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases, more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> Routine samples over prospective mineralised intervals from diamond drill core as determined by an experienced geologist are 1m half core; or quarter core for duplicates (routine ½ core sample sawn into two ¼ core samples). Entire sample sent to ALS laboratory in Romania for preparation and fire assay analysis, while the four-acid digest with ICPAES will be completed at the ALS laboratory in Ireland. 90% of sample crushed to <2mm. Sample is then dried and riffle split to produce a 1kg split. 1kg split then pulverised to 85% passing <75µm to produce a 50g charge for fire assay for gold analysis and a 0.25g sample for four acid digestion (near-total) with an ICPAES (inductively coupled plasma atomic emission spectroscopy) finish for 33 elements including Ag, Cu, Co, Pb, Zn, etc. If coarse-grained gold (visible gold) is encountered then Au will also be analysed by screen fire assay. The remaining sample from the 90% of the original routine sample that was crushed to <2mm and dried is then riffle split again to produce another 1kg split. This 1kg split is then dry screened to a nominal 106 micron. Duplicate 50g fire assays with AAS finish are then performed on the undersize, and fire assay with gravimetric finish is done on the entire oversize fraction. Then the total gold content is calculate and reported, using the individual assays and weight of the fractions.
Drilling techniques	<ul style="list-style-type: none"> Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc). 	<ul style="list-style-type: none"> The current program is utilising diamond drilling from multiple underground locations within the Andrej Adit. None of the diamond core is being oriented. UGA-23 was drilled with NQ (47.6mm core diameter) to EOH (179.5m). UGA-24 was drilled with NQ (47.6mm core diameter) to EOH (180.8m). UGA-25 was drilled with NQ (47.6mm core diameter) to EOH (180.8m). UGA-26 was drilled with NQ (47.6mm core diameter) to EOH (101.5m). UGA-27 was drilled with NQ (47.6mm core diameter) to EOH (214.3m). UGA-28 was drilled with NQ (47.6mm core diameter) to EOH (151.2m). UGA-29 was drilled with NQ (47.6mm core diameter) to EOH (84.7m). UGA-30 was drilled with NQ (47.6mm core diameter) to EOH (173.6m).
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature of the samples. 	<ul style="list-style-type: none"> Core recovery is measured as the length of core recovered versus the depth of the drill hole. In detail, the length of each 'run' of core recovered (between 0-3m) is measured and its length compared to the length the drillers measured from the drill rod advance. The core recovery for all drill holes so far has been excellent, greater than 90%.

Criteria	JORC Code Explanation	Details
	<ul style="list-style-type: none"> Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<ul style="list-style-type: none"> Historic drill records indicate that core recovery at the Sturec Project was consistently good, where historic mining voids have not been encountered. No relationship between sample recovery and grade has been interpreted in assay results received so far as recovery is excellent.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography. The total length and percentage of the relevant intersections logged. 	<ul style="list-style-type: none"> The core was geologically and geotechnically logged to a level to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Core is logged both qualitatively and quantitatively. All logging data is digitally captured via excel spreadsheets, which are then validated when they are imported into a resource modelling software package. Core photography is completed for all drill holes. The entire length of drill core is logged.
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> Routine samples over prospective mineralised intervals from diamond drill core as determined by an experienced geologist are sawn into 1m half core; or quarter core for duplicates. Same side of drill core sampled to ensure no selective sampling bias. The other half of the core was retained for geological reference and potential further sampling, such as metallurgical test work. Entire sample sent to ALS laboratory in Romania for preparation and fire assay analysis, while the four-acid digest with ICPAES is completed at the ALS laboratory in Ireland. 90% of sample crushed to <2mm. Sample then dried and riffle split. 1kg split then pulverised to 85% passing <75µm to produce a 50g charge for fire assay for gold analysis and a 0.25g sample for four acid digestion (near-total) with an ICPAES (inductively coupled plasma atomic emission spectroscopy) finish for 33 elements including Ag, Cu, Co, Pb, Zn, etc. The remainder of the material is retained as a coarse split for metallurgical test work. Remaining pulps are retained for analyses such as second laboratory check assays. Duplicate samples (routine 1m ½ core sample sawn in half to produce two ¼ core samples) taken every 30 samples or at least one per hole if less than 30 samples taken. A Certified Reference Material (CRM or 'Standard') is inserted into the routine sample sequence approximately every 30 samples or at least one per hole if less than 30 samples taken. A blank (material with no concentrations of economic elements under consideration) is inserted into the routine sample sequence approximately every 30 samples or at least one per hole if less than 30 samples taken. Sample prep techniques utilised are industry standard for Carpathian epithermal-style gold mineralisation and are considered appropriate. Samples sizes are considered appropriate for the grain-size of the material being sampled.
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including 	<ul style="list-style-type: none"> Analysis completed by using 50g charge for fire assay for gold analysis and a 0.25g sample for four acid digestion (near-total) with an ICPAES (inductively coupled plasma atomic emission spectroscopy) finish for 33 elements including Ag, Cu, Co, Pb, Zn, etc. If coarse-grained gold (visible gold) is encountered then Au will also be analysed by screen fire assay. The remaining sample from the 90% of the original routine sample that was

Criteria	JORC Code Explanation	Details
	<p><i>instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i></p> <ul style="list-style-type: none"> <i>Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established.</i> 	<p>crushed to <2mm and dried is then riffle split again to produce another 1kg split. This 1kg split is then dry screened to a nominal 106 micron. Duplicate 50g fire assays with AAS finish are then performed on the undersize, and fire assay with gravimetric finish is done on the entire oversize fraction. Then the total gold content is calculate and reported, using the individual assays and weight of the fractions.</p> <ul style="list-style-type: none"> Analysis techniques utilised are industry standard for Carpathian epithermal-style gold mineralisation and are considered appropriate. Laboratory Routine QC protocol for Au-AA26: 1 lab Blank, 2 lab CRM, 3 client duplicates, 1 PREP Duplicate per batch (up to 77 samples). Laboratory Routine QC protocol for ME-ICP61: 1 lab Blank, 2 lab CRM, 2 client duplicates, 1 PREP Duplicate per batch (up to 77 samples). Internal laboratory checks, as well as internal and external check assays such as repeats and check assays enable assessment of precision. Contamination between samples is checked for by the use of blank samples (laboratory and company inserted). Assessment of accuracy will be carried out by the analysis of the assay results of the CRMs. QAQC results are reviewed on a batch-by-batch basis. Any deviations from acceptable precision or indications of bias are acted upon prior to announcing any results with repeat and check assays.
Verification of sampling	<ul style="list-style-type: none"> <i>The verification of significant intersections by either independent or alternative company personnel.</i> <i>The use of twinned holes.</i> <i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i> <i>Discuss any adjustment to assay data.</i> 	<ul style="list-style-type: none"> On receipt of assay results from the laboratory, the results are verified by the Exploration Manager and by responsible geologists who compare the results with the geological logging and remaining drill core (or core photography if site access is not possible). No twins have been completed yet. All primary data (logging, sample intervals and assay results) is digitally captured via excel spreadsheets, which are then validated when they are imported into 3D modelling software package. Data is stored in a secure company owned Dropbox that has a 180 day file recovery and version history function. No adjustment to assay data.
Location of data points	<ul style="list-style-type: none"> <i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i> <i>Specification of the grid system used.</i> <i>Quality and adequacy of topographic control.</i> 	<ul style="list-style-type: none"> Locations of diamond drill hole collars, channel samples and mine workings are recorded using the Slovak National Datum: S-JTSK/Krovak Datum. As the location of the current drill hole is within the Andrej Adit, which has been surveyed, its location is very accurately known. High-resolution topography over the project was acquired using LiDAR.
Data spacing and distribution	<ul style="list-style-type: none"> <i>Data spacing for reporting of Exploration Results.</i> <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i> <i>Whether sample compositing has been applied.</i> 	<ul style="list-style-type: none"> Data spacing is highly variable across the prospect. UGA-30 was positioned as infill drill hole within the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021) holes above UGA-03. The area intersected by UGA-30 has been included in the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021) and therefore, the data spacing and distribution is interpreted to be sufficient to

Criteria	JORC Code Explanation	Details
		<p>establish the degree of geological and grade continuity appropriate for Mineral Resource and Ore Reserve estimation.</p> <ul style="list-style-type: none"> • UGA-26 and UGA-27 were positioned as mineralisation extension drill holes below the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021) holes; as well as below UGA-04 and UGA-08 from Drill Chamber I. • The area intersected by UGA-27 and UGA-26 is just below the southern extent of the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021). The data spacing and distribution is interpreted to be sufficient to establish the degree of geological and grade continuity appropriate for Mineral Resource and Ore Reserve estimation. • UGA-23, UGA-24 and UGA-25 were positioned as mineralisation extension drill holes along strike to the south of the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021) holes; as well as above and along strike of UGA-14. • The area intersected by UGA-23, UGA-24 and UGA-25 is just outside, along strike to the south of the Updated 2021 Sturec Mineral Resource Estimate constrained within an optimised pit (refer to MTC announcement dated 21 June 2021). The data spacing and distribution is interpreted to be sufficient to establish the degree of geological and grade continuity appropriate for Mineral Resource and Ore Reserve estimation. • No samples have been composited.
Orientation of data in relation to geological structure	<ul style="list-style-type: none"> • <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i> • <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i> 	<ul style="list-style-type: none"> • Due to only three (soon to be four) sites within the Andrej Adit being suitable for drilling currently, the drill holes fan out and are therefore drilled at various angles to the strike of the exploration target and the adjoining mineral resource. As the mineralisation zone strikes approximately north-south, the closer the hole azimuth is to north or south, the longer the intersection thickness. However, it is interpreted that this does not create a sampling bias as this actually provides more data points within the mineralisation zone and is therefore beneficial to estimating the grade of the mineralised zone. • Mineral Resource modelling suggests the Sturec ore body around UGA-30 is between 50-55m wide in true thickness. • 3D modelling of UGA-27, UGA-26, UGA-25, UGA-24 and UGA-23 assay results obtained so far, suggest that in this southern extent of the Sturec ore body, the true thickness of mineralisation is between 20-50m wide. The mineralisation is funnel shaped with the thicker zone towards the top and getting thinner at depth.
Sample security	<ul style="list-style-type: none"> • <i>The measures taken to ensure sample security.</i> 	<ul style="list-style-type: none"> • Samples were securely stored in company facilities prior to being completely sealed and couriered directly to the ALS laboratory in Romania.
Audits or reviews	<ul style="list-style-type: none"> • <i>The results of any audits or reviews of sampling techniques and data.</i> 	<ul style="list-style-type: none"> • No audits/reviews of the sampling techniques and assay data has been completed at this stage.

Section 2 - Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	JORC Code Explanation	Details																												
Mineral tenement and land tenure status	<ul style="list-style-type: none"> Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	<ul style="list-style-type: none"> Sturec Gold Project consists of the Kremnica Mining Territory (9.47 km²) owned by Slovakian limited liability company Ortac SK, which is a wholly-owned subsidiary of Ortac UK (a private limited company registered in England and Wales). Kremnica Mining Territory' and Mining Licence details: <p>'Kremnica Mining Territory'</p> <table border="1"> <tr> <td>Name:</td> <td>Mining Territory Kremnica Au-Ag</td> </tr> <tr> <td>Mining area No:</td> <td>MHD-D.P.- 12</td> </tr> <tr> <td>Date of Issuance:</td> <td>21 January 1961</td> </tr> <tr> <td>Metals:</td> <td>• Gold and Silver</td> </tr> <tr> <td>Duration:</td> <td>Indefinite</td> </tr> <tr> <td>Holder of the:</td> <td>Ortac, s.r.o</td> </tr> <tr> <td>Amendments:</td> <td>• No. 1037-1639/2009</td> </tr> </table> <p>ORTAC,s.r.o. Mining Licence details</p> <table border="1"> <tr> <td>Name:</td> <td>Ortac,s.r.o.</td> </tr> <tr> <td>Mining License No:</td> <td>1830-3359/2008</td> </tr> <tr> <td>Date of Issuance:</td> <td>13 November 2008</td> </tr> <tr> <td>Subject:</td> <td> <ul style="list-style-type: none"> Opening, preparation and exploitation of reserved mineral resource Installation, conservation and decommissioning of mining work Processing and refinement of mineral resources Installation and operation of unloading areas and dumps Opening the mining works to the public for museum purposes and related safety maintenance works </td> </tr> <tr> <td>Duration:</td> <td>Indefinite</td> </tr> <tr> <td>Responsible Person:</td> <td>Ing. Peter Čorej</td> </tr> <tr> <td>Amendments:</td> <td> <ul style="list-style-type: none"> No. 773-1398/2015 dated 11 May 2015 extending the subject of the Mining License No. 979-1401/2019 dated 11 June 2019 updating the information on statutory body </td> </tr> </table> <ul style="list-style-type: none"> The Kremnica Mining Licence is located in central Slovakia between the town of Kremnica and the village of Lučky, 17km west of central Slovakia's largest city, Banska Bystrica, and 150km northeast of the capital, Bratislava. Metals Tech owns 100% of the Sturec Gold Project by completing the acquisition of Ortac UK on 14 February 2020. 	Name:	Mining Territory Kremnica Au-Ag	Mining area No:	MHD-D.P.- 12	Date of Issuance:	21 January 1961	Metals:	• Gold and Silver	Duration:	Indefinite	Holder of the:	Ortac, s.r.o	Amendments:	• No. 1037-1639/2009	Name:	Ortac,s.r.o.	Mining License No:	1830-3359/2008	Date of Issuance:	13 November 2008	Subject:	<ul style="list-style-type: none"> Opening, preparation and exploitation of reserved mineral resource Installation, conservation and decommissioning of mining work Processing and refinement of mineral resources Installation and operation of unloading areas and dumps Opening the mining works to the public for museum purposes and related safety maintenance works 	Duration:	Indefinite	Responsible Person:	Ing. Peter Čorej	Amendments:	<ul style="list-style-type: none"> No. 773-1398/2015 dated 11 May 2015 extending the subject of the Mining License No. 979-1401/2019 dated 11 June 2019 updating the information on statutory body
Name:	Mining Territory Kremnica Au-Ag																													
Mining area No:	MHD-D.P.- 12																													
Date of Issuance:	21 January 1961																													
Metals:	• Gold and Silver																													
Duration:	Indefinite																													
Holder of the:	Ortac, s.r.o																													
Amendments:	• No. 1037-1639/2009																													
Name:	Ortac,s.r.o.																													
Mining License No:	1830-3359/2008																													
Date of Issuance:	13 November 2008																													
Subject:	<ul style="list-style-type: none"> Opening, preparation and exploitation of reserved mineral resource Installation, conservation and decommissioning of mining work Processing and refinement of mineral resources Installation and operation of unloading areas and dumps Opening the mining works to the public for museum purposes and related safety maintenance works 																													
Duration:	Indefinite																													
Responsible Person:	Ing. Peter Čorej																													
Amendments:	<ul style="list-style-type: none"> No. 773-1398/2015 dated 11 May 2015 extending the subject of the Mining License No. 979-1401/2019 dated 11 June 2019 updating the information on statutory body 																													

Criteria	JORC Code Explanation	Details
		<ul style="list-style-type: none"> • As a part of the acquisition, MetalsTech Limited has granted Arc Minerals Limited a royalty equal to A\$2 per ounce of resource that is delineated at the project above an open cut JORC (2012) Indicated and Measured Resources that exceeds 1.5million ounces at a grade greater than 2.5g/t AuEq after 2 years from the date of execution of the Terms Sheet but before the date that is 5 years after the date of execution of the Terms Sheet capped at 7 million ounces. • In 2013, Arc Minerals (named Ortac Resources Limited at this time) submitted a small-scale underground mining application, which was awarded by the Central Mining Bureau in 2014. Trial underground mining commenced in June 2014 and a 40t bulk sample was extracted from Sturec for metallurgical test work. • In 2016, the Regional Court in Banská Bystrica ruled against the Central Mining Bureau concerning the underground mining permit issued to Arc Minerals Limited in 2014 and revoked the decision to issue the mining permit. • In May 2017, the Central Mining Bureau issued Ortac SK with an amended underground mining permit that allowed for small-scale mining activities to recommence. • In July 2017, Ortac SK (Arc Minerals Limited) re-commenced the trial underground mining activities at Sturec, fulfilling the condition required by Slovak regulations to preserve its right to exploit the ore deposit in the Kremnica Mining Licence Area for a minimum period of at least three years. 500t of ore was extracted and used for metallurgical test work relating to alternative processing technologies to the conventional cyanide leaching. • Since 2017 (before selling the project to MetalsTech), Arc Minerals Limited has continued working with the local community and stakeholders to facilitate the development of the project. • In October 2019, the Central Mining Bureau issued Ortac SK with an underground mining permit that allowed for small-scale mining activities to recommence: Decision No. 827-2373 / 2019. This decision was appealed soon after being received. • In February 2020, the appeals against Decision No. 827-2373 / 2019 were rejected by the State Mining Administration and the underground mining authorisation was upheld. • In April 2020, MetalsTech Limited re-commenced the underground mining activities at Sturec, in order to fulfill the condition required by Slovak regulations to preserve its right to exploit the ore deposit in the Kremnica Mining Licence Area for a minimum period of at least three years. • Although Ortac SK is officially registered as the holder of the Kremnica Mining Territory, the validity of the allocation of the Kremnica Mining Territory has been repeatedly disputed. Arguments challenging the validity of the allocation of the Kremnica Mining Territory have been raised by third parties in licensing proceedings in respect of particular mining activities within the Kremnica Mining Territory. So far, the merits of such arguments have not been assessed by the court, as the respective court decisions were issued on procedural grounds in the past. Despite the existence of reasonable legal arguments defending the validity of the allocation of the Kremnica Mining Territory, it cannot be ruled out that the challenges to its validity will eventually prevail before the court. Even if the validity of the allocation of the Kremnica Mining Territory is successfully defended in principle, there is a risk that Ortac SK's entitlement to the Kremnica Mining Territory could be held to be limited to underground operations only. • There are no environmental protected areas in the vicinity of the project resource area, except a protected lime tree situated close to the Leopold Shaft, adjacent to the monument commemorating the visit by Emperor Joseph II to Kremnica. Permission can be obtained to fell the tree if necessary, from the Provincial Environmental Office in Banska Bystrica. • It appears that a significant part of the Kremnica Mining Licence is covered by a heritage conservation area. This is not surprising given the extensive mining history throughout this area. The previous owners Arc Minerals Ltd used this fact to their advantage by establishing the Andrej Kremnica Mining Museum, whose two main attractions are the Ludavika Shaft Building and the Andrej Adit, which was established in 1982 by the State to access the main quartz vein mineralisation. As a result, various requirements under the applicable regulations in the area of heritage

Criteria	JORC Code Explanation	Details
		<p>protection must be complied with. Further investigation needs to be completed to understand the effect this Heritage Protection will have on any proposed mining activities.</p> <ul style="list-style-type: none"> • There is one registered environmental burden located in the Kremnica Mining Territory with registration number SK/EZ/ZH/2129. This environmental burden relates to the processing facilities including the historic waste dumps that are situated immediately next to the Arc Minerals operation office/Andrej Kremnica Mining Museum. It is categorized "only" as a potential (probable) environmental burden as no significant contamination/acid rock drainage (ARD) effects have been reported concerning these historic mining remnants. • There is risk concerning the further development of the Sturec Gold Project due to the historic social and environmental opposition to the development of a mining operation in this area. The opposition is believed to be the result of two main factors: previous development plans utilised cyanide ore processing; and previous development plans involved digging a large open pit in relatively proximity to the township of Kremnica. <ul style="list-style-type: none"> ○ To minimise the first risk, MetalsTech is investigating alternative gold processing methods, especially Thiosulphate Leaching, which has previously been used quite successfully on Sturec ore samples during metallurgical test work in 2014. Also, in 2014 the CSIRO successfully collaborated with Barrick Gold Corp. to implement Thiosulphate ore processing technology on the Goldstrike Mine in Nevada, USA, which now produces approximately 350,000 ounces of gold per annum for Barrick and Newmont Goldcorp Corp; proving that this technology can be utilised economically and at significant scale. ○ To minimise the second risk, MetalsTech intends to put in place a comprehensive project stakeholder engagement programme to attempt to understand and mitigate their concerns about the development of a mining operation on the Sturec Gold Project. Also, the full suite of benefits to the country and local communities that will arise from the Sturec Gold Project (such as job creation, training, capital investment, revenue generation, procurement of goods and services locally, and community development initiatives) need to be properly communicated to project stakeholders, so that that they can use this to motivate/ justify the project in project-approval processes.
<p>Exploration done by other parties</p>	<p>• <i>Acknowledgment and appraisal of exploration by other parties.</i></p>	<ul style="list-style-type: none"> • Many exploration companies have previously explored the Sturec Gold Project and the surrounding areas. The details of the exploration history are outlined below: <ul style="list-style-type: none"> ○ The Slovak Geological Survey carried out extensive exploration in the Sturec area from 1981 to 1987, including extensive adit and cross-cut development within the Sturec zone. ○ Rudne Bane operated the open-pit mine at Sturec from 1987 to 1992 and produced 50,028t of ore averaging 1.54g/t Au. During this time, Rudne Bane conducted underground sampling of the larger mineralised portions of the Sturec deposit (40 channels for 3,149 individual samples) and 12 underground fan drill holes (for 425.3m) into the northern-most known limits of the deposit. A total of 266 sample intervals were assayed for gold and silver. ○ Kremnica Banská Spolocnost (KBS), an investment company composed of former mine managers, obtained the title to the Kremnica Mining Lease (MHD-D.P. 12) from the Slovak government on 1 April 1995. In 1995, Argosy Mining Corporation (Argosy) of Vancouver formed a 100% owned Slovak Subsidiary, Argosy Slovakia s.r.o., which entered into a joint venture with KBS on 6 October 1995. Argosy Slovakia purchased KBS's share of the joint venture on 24 April 1997 to control 100% of the mining licence through its subsidiary, Kremnica Gold a.s. Argosy completed a core drilling programme in 1996 and a combined core and reverse-circulation (RC) drilling programme in 1997. This core/RC program totalled 79 holes for 12,306m; 9,382.4m of which was into the Sturec Deposit area. ○ In July 2003, Tournigan Gold Corporation (Tournigan) acquired the rights to the Sturec Project by purchasing Kremnica Gold a.s. from Argosy. Tournigan then completed 104 diamond core and RC drill holes for

Criteria	JORC Code Explanation	Details
		<p>~14,000m over the period 2004 to 2008. The majority of these holes were into the Sturec Deposit, but adjacent areas were also explored. In the summer and autumn of 2005, Tournigan executed a 36-hole program of RC drilling as infill of Argosy's and Tournigan's earlier core drilling programs into the Sturec Deposit. Tournigan also drilled five additional holes as twins of Argosy's previous core holes. This drilling resulted in the deposit being drilled off on approximate 50-metre centres (earlier drilling had been on approximately 100 x 50 metre centres). The RC program results confirmed the geology and ore outlines that were previously established by core drilling (e.g., rock types and alteration, location of zones of oxidation, location of ore-bearing veins and stockworks, hanging walls, footwalls, thicknesses, strikes, dips, and grades). The holes and assay results were displayed on cross-sections and recorded on logs. Samples were collected at 1-meter intervals under the immediate supervision of a geologist, sealed in plastic bags, and submitted for analysis and check analyses according to the required formal protocols. The holes were logged on site by the drill geologists and again in the laboratory where qualitative samples were taken and inventoried as geological reference samples. The bulk rejects from these RC samples are stored at the operational offices at the Andrej Mining Museum. Tournigan also completed nine bench channel surveys incorporating a total of 317 sample intervals. In 2004, Tournigan also conducted an 11-hole diamond drilling programme north of Sturec at the Wolf and Vratislav prospects.</p> <ul style="list-style-type: none"> ○ Ortac Resources (now Arc Mineral Limited) acquired the project in 2009. Since 2009 till MetalsTech acquired the project from them in February 2020, Ortac drilled 13 core holes for 2,771.7m within the Sturec Deposit area.
Geology	<ul style="list-style-type: none"> • <i>Deposit type, geological setting and style of mineralisation.</i> 	<ul style="list-style-type: none"> • The Sturec Gold Project is located in the Central Slovakia Volcanic Area in the Kremnica Mountains of the Western Carpathians. The Central Slovakia Volcanic Field hosts several Ag–Au epithermal vein-type deposits including Banská Štiavnica, Kremnica, Hodruša-Hámre, and Nová Bana, which were important sources of precious and base metals in the past. The area is characterised by Tertiary pyroxene-amphibole andesite flows and tuffs of the Zlata Studna Formation. The andesites are underlain by Mesozoic limestone. Deep-seated structures and faults within the pre-Tertiary basement interpreted to be extensional Horst and Graben in style, focussed sub-volcanic intrusions of gabbrodiorite, diorite, diorite porphyry, and minor quartz-diorite porphyry at depth and associated mesothermal mineralising events, which were then overprinted by the epithermal precious metal mineralisation. In the Kremnica area, the structure is controlled by a 6-7km long, N-S trending horst, known as the Kremnica Horst Structure, which is interpreted to be the result of the sub-volcanic intrusions of gabbrodiorite, diorite, diorite porphyry, and minor quartz-diorite porphyry at depth causing this zone to be uplifted relative to the two graben structures to either side. • The Sturec Gold Project mineralisation is classified as a low-sulphidation epithermal Ag-Au deposit type and is interpreted to have formed from low-salinity fluids composed of a mixture of meteoric and magmatic waters at temperatures mostly between ~270 to 190 °C. The mineralisation is hosted by quartz–dolomite veins also containing adularia, sericite, illite and chalcedony that cut through Neogene propylitised (low pressure/low to medium temperature hydrothermal alteration) andesites of the Kremnica stratovolcano. The hydrothermal alteration from the veins outwards consists of silicification and potassic-metasomatism (adularia), propylitization and argillisation. Vein styles include large banded to massive quartz veins, smaller quartz veins and sheeted veins, quartz stockwork veining and silicified hydrothermal breccias.

Criteria	JORC Code Explanation	Details																																																																																																																																																																																								
Drill hole Information	<ul style="list-style-type: none"> A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: <ul style="list-style-type: none"> easting and northing of the drill hole collar elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar dip and azimuth of the hole down hole length and interception depth hole length. If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case. 	<ul style="list-style-type: none"> Drill collar details: <table border="1"> <thead> <tr> <th>Drill hole name</th> <th>Easting (m)</th> <th>Northing (m)</th> <th>RL (m)</th> <th>Datum</th> <th>Azi (°TN)</th> <th>Dip (°)</th> <th>EOH Depth (m)</th> </tr> </thead> <tbody> <tr><td>UGA-01</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>017</td><td>-53</td><td>346.05</td></tr> <tr><td>UGA-02</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>022</td><td>-46</td><td>293.46</td></tr> <tr><td>UGA-03</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>007</td><td>-45</td><td>287.25</td></tr> <tr><td>UGA-04</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>297</td><td>-80</td><td>140.90</td></tr> <tr><td>UGA-05</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>200</td><td>-60</td><td>140.46</td></tr> <tr><td>UGA-06</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>344</td><td>-60</td><td>116.50</td></tr> <tr><td>UGA-07</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>350</td><td>-70</td><td>130.1</td></tr> <tr><td>UGA-08</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>265</td><td>-85</td><td>151.1</td></tr> <tr><td>UGA-09</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>195</td><td>-80</td><td>190.2</td></tr> <tr><td>UGA-10</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>195</td><td>-50</td><td>164.5</td></tr> <tr><td>UGA-11</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>340</td><td>-85</td><td>250.80</td></tr> <tr><td>UGA-12</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>350</td><td>-50</td><td>106.00</td></tr> <tr><td>UGA-13</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>190</td><td>-30</td><td>288.04</td></tr> <tr><td>UGA-14</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>195</td><td>-35</td><td>165.50</td></tr> <tr><td>UGA-15</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>000/360</td><td>-40</td><td>134.40</td></tr> <tr><td>UGA-16</td><td>-435,852</td><td>-1,230,204</td><td>656</td><td>S-JTSK/ Krovak</td><td>000/360</td><td>-60</td><td>183.30</td></tr> <tr><td>UGA-17</td><td>-435,852</td><td>-1,230,270</td><td>656</td><td>S-JTSK/ Krovak</td><td>270</td><td>-70</td><td>109.35m</td></tr> <tr><td>UGA-18</td><td>-435,852</td><td>-1,230,270</td><td>656</td><td>S-JTSK/ Krovak</td><td>230</td><td>-55</td><td>104.65m</td></tr> <tr><td>UGA-19</td><td>-435,852</td><td>-1,230,270</td><td>656.96</td><td>S-JTSK/ Krovak</td><td>210</td><td>-30</td><td>101.6m</td></tr> <tr><td>UGA-20</td><td>-435,852</td><td>-1,230,270</td><td>656.96</td><td>S-JTSK/ Krovak</td><td>205</td><td>-45</td><td>140.5m</td></tr> <tr><td>UGA-21</td><td>-435,852</td><td>-1,230,270</td><td>656.96</td><td>S-JTSK/ Krovak</td><td>205</td><td>-65</td><td>178.2m</td></tr> <tr><td>UGA-22</td><td>-435,852</td><td>-1,230,270</td><td>656.96</td><td>S-JTSK/ Krovak</td><td>200</td><td>-35</td><td>143.3m</td></tr> </tbody> </table>	Drill hole name	Easting (m)	Northing (m)	RL (m)	Datum	Azi (°TN)	Dip (°)	EOH Depth (m)	UGA-01	-435,852	-1,230,204	656	S-JTSK/ Krovak	017	-53	346.05	UGA-02	-435,852	-1,230,204	656	S-JTSK/ Krovak	022	-46	293.46	UGA-03	-435,852	-1,230,204	656	S-JTSK/ Krovak	007	-45	287.25	UGA-04	-435,852	-1,230,204	656	S-JTSK/ Krovak	297	-80	140.90	UGA-05	-435,852	-1,230,204	656	S-JTSK/ Krovak	200	-60	140.46	UGA-06	-435,852	-1,230,204	656	S-JTSK/ Krovak	344	-60	116.50	UGA-07	-435,852	-1,230,204	656	S-JTSK/ Krovak	350	-70	130.1	UGA-08	-435,852	-1,230,204	656	S-JTSK/ Krovak	265	-85	151.1	UGA-09	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-80	190.2	UGA-10	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-50	164.5	UGA-11	-435,852	-1,230,204	656	S-JTSK/ Krovak	340	-85	250.80	UGA-12	-435,852	-1,230,204	656	S-JTSK/ Krovak	350	-50	106.00	UGA-13	-435,852	-1,230,204	656	S-JTSK/ Krovak	190	-30	288.04	UGA-14	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-35	165.50	UGA-15	-435,852	-1,230,204	656	S-JTSK/ Krovak	000/360	-40	134.40	UGA-16	-435,852	-1,230,204	656	S-JTSK/ Krovak	000/360	-60	183.30	UGA-17	-435,852	-1,230,270	656	S-JTSK/ Krovak	270	-70	109.35m	UGA-18	-435,852	-1,230,270	656	S-JTSK/ Krovak	230	-55	104.65m	UGA-19	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	210	-30	101.6m	UGA-20	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	205	-45	140.5m	UGA-21	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	205	-65	178.2m	UGA-22	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	200	-35	143.3m
		Drill hole name	Easting (m)	Northing (m)	RL (m)	Datum	Azi (°TN)	Dip (°)	EOH Depth (m)																																																																																																																																																																																	
		UGA-01	-435,852	-1,230,204	656	S-JTSK/ Krovak	017	-53	346.05																																																																																																																																																																																	
		UGA-02	-435,852	-1,230,204	656	S-JTSK/ Krovak	022	-46	293.46																																																																																																																																																																																	
		UGA-03	-435,852	-1,230,204	656	S-JTSK/ Krovak	007	-45	287.25																																																																																																																																																																																	
		UGA-04	-435,852	-1,230,204	656	S-JTSK/ Krovak	297	-80	140.90																																																																																																																																																																																	
		UGA-05	-435,852	-1,230,204	656	S-JTSK/ Krovak	200	-60	140.46																																																																																																																																																																																	
		UGA-06	-435,852	-1,230,204	656	S-JTSK/ Krovak	344	-60	116.50																																																																																																																																																																																	
		UGA-07	-435,852	-1,230,204	656	S-JTSK/ Krovak	350	-70	130.1																																																																																																																																																																																	
		UGA-08	-435,852	-1,230,204	656	S-JTSK/ Krovak	265	-85	151.1																																																																																																																																																																																	
		UGA-09	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-80	190.2																																																																																																																																																																																	
		UGA-10	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-50	164.5																																																																																																																																																																																	
		UGA-11	-435,852	-1,230,204	656	S-JTSK/ Krovak	340	-85	250.80																																																																																																																																																																																	
		UGA-12	-435,852	-1,230,204	656	S-JTSK/ Krovak	350	-50	106.00																																																																																																																																																																																	
		UGA-13	-435,852	-1,230,204	656	S-JTSK/ Krovak	190	-30	288.04																																																																																																																																																																																	
		UGA-14	-435,852	-1,230,204	656	S-JTSK/ Krovak	195	-35	165.50																																																																																																																																																																																	
		UGA-15	-435,852	-1,230,204	656	S-JTSK/ Krovak	000/360	-40	134.40																																																																																																																																																																																	
		UGA-16	-435,852	-1,230,204	656	S-JTSK/ Krovak	000/360	-60	183.30																																																																																																																																																																																	
		UGA-17	-435,852	-1,230,270	656	S-JTSK/ Krovak	270	-70	109.35m																																																																																																																																																																																	
		UGA-18	-435,852	-1,230,270	656	S-JTSK/ Krovak	230	-55	104.65m																																																																																																																																																																																	
		UGA-19	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	210	-30	101.6m																																																																																																																																																																																	
		UGA-20	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	205	-45	140.5m																																																																																																																																																																																	
		UGA-21	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	205	-65	178.2m																																																																																																																																																																																	
UGA-22	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	200	-35	143.3m																																																																																																																																																																																			

Criteria	JORC Code Explanation	Details																																													
		UGA-23	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	200	-42	179.5																																						
		UGA-24	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	195	-30	180.8																																						
		UGA-25	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	195	-37	180.8																																						
		UGA-26	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	300	-65	101.5																																						
		UGA-27	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	350	-65	214.3																																						
		UGA-28	-435,852	-1,230,270	656.96	S-JTSK/ Krovak	335	-70	151.2																																						
		UGA-29	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	280	-80	84.7																																						
		UGA-30	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	008	-45	173.6																																						
		UGA-31	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	355	-60	106.45																																						
		UGA-32	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	325	-60	79.3																																						
		UGA-33	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	8	-70	109.2																																						
		UGA-34	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	270	-50	41.5																																						
		UGA-35	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	270	-70	64.2																																						
		UGA-36	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	270	-25	59.8																																						
		UGA-37	-435,851	-1,230,123	656.96	S-JTSK/ Krovak	230	-40	In progress																																						
		<ul style="list-style-type: none"> Summary table of significant drill hole intersections so far: 																																													
		<table border="1"> <thead> <tr> <th>Hole</th> <th>Width (m) (Down hole depth)</th> <th></th> <th>Au g/t</th> <th>Ag g/t</th> <th>From (m) (Down hole depth)</th> <th>To (m) (Down hole depth)</th> <th>Cut-off</th> </tr> </thead> <tbody> <tr> <td rowspan="3">UGA-30</td> <td>173.20</td> <td>@</td> <td>3.27</td> <td>11.8</td> <td>0.00</td> <td>173.20</td> <td>0.25g/t Au cut-off and max. 4m continuous internal dilution</td> </tr> <tr> <td colspan="7">including</td> </tr> <tr> <td>103.00</td> <td>@</td> <td>5.06</td> <td>13.4</td> <td>57.00</td> <td>160.00</td> <td>0.5g/t Au cut-off and max. 4m continuous internal dilution</td> </tr> <tr> <td></td> <td colspan="7">including</td> </tr> </tbody> </table>								Hole	Width (m) (Down hole depth)		Au g/t	Ag g/t	From (m) (Down hole depth)	To (m) (Down hole depth)	Cut-off	UGA-30	173.20	@	3.27	11.8	0.00	173.20	0.25g/t Au cut-off and max. 4m continuous internal dilution	including							103.00	@	5.06	13.4	57.00	160.00	0.5g/t Au cut-off and max. 4m continuous internal dilution		including						
Hole	Width (m) (Down hole depth)		Au g/t	Ag g/t	From (m) (Down hole depth)	To (m) (Down hole depth)	Cut-off																																								
UGA-30	173.20	@	3.27	11.8	0.00	173.20	0.25g/t Au cut-off and max. 4m continuous internal dilution																																								
	including																																														
	103.00	@	5.06	13.4	57.00	160.00	0.5g/t Au cut-off and max. 4m continuous internal dilution																																								
	including																																														

Criteria	JORC Code Explanation	Details										
			8.00	@	7.16	11.3	84.00	92.00	3g/t Au cut-off and 2m internal dilution			
			and									
			19.00	@	11.35	23.9	119.00	138.00	3g/t Au cut-off and max. 4m continuous internal dilution			
			including									
			2.00	@	42.50	53.3	119.00	121.00	no cut-off or dilution			
			and									
			1.00	@	67.90	94.5	127.00	128.00	no cut-off or dilution			
			including									
			7.00	@	23.30	24.0	153.00	160.00	3g/t Au cut-off and 4m continuous internal dilution			
			including									
		1.00	@	139.00	87.3	154.00	155.00	no cut-off or dilution				
		UGA-27			5.00	@	0.84	2.9	41.00	46.00	0.25g/t Au cut-off and no internal dilution	
					and							
					2.00	@	1.51	5.7	78.00	80.00	0.5g/t Au cut-off and no internal dilution	
					and							
					47.00	@	0.61	1.5	104.00	151.00	0.25g/t Au cut-off and max. 5m continuous internal dilution	
					including							
					5.00	@	1.26	2.4	104.00	109.00	0.5g/t Au cut-off and 3m internal dilution	
					and							
					12.00	@	1.22	2.0	139.00	151.00	0.3g/t Au cut-off and 2m internal dilution	
including												
6.00	@	2.09	3.0	143.00	149.00	0.5g/t Au cut-off and 2m internal dilution						
including												
2.00	@	5.14	4.6	143.00	145.00	1g/t Au cut-off and no internal dilution						

Criteria	JORC Code Explanation	Details							
		UGA-26	2.00	@	2.27	13.0	22.00	24.00	0.25g/t Au cut-off and no internal dilution
			including						
			5.00	@	0.55	1.7	34.00	39.00	0.25g/t Au cut-off and 1m internal dilution
			including						
			32.00	@	0.91	16.3	56.00	88.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
			including						
		10.00	@	1.50	22.5	69.00	79.00	0.75g/t Au cut-off and 3m internal dilution	
		UGA-25	6.00	@	0.68	6.8	42.00	48.00	0.25g/t Au cut-off and 3m internal dilution
			including						
			53.00	@	0.86	10.0	95.00	148.00	0.25g/t Au cut-off and max. 3m continuous internal dilution
			including						
			23.00	@	1.46	15.1	104.00	127.00	0.5g/t Au cut-off and 2m continuous internal dilution
			including						
			7.00	@	2.75	23.3	120.00	127.00	1g/t Au cut-off and no internal dilution
		including							
		4.00	@	3.86	31.1	121.00	125.00	2g/t Au cut-off and no internal dilution	
		UGA-24	15.00	@	1.30	6.8	27.00	42.00	0.25g/t Au cut-off and max. 1m continuous internal dilution
			including						
			11.00	@	1.67	8.5	30.00	41.00	0.5g/t Au cut-off and max. 2m continuous internal dilution
			including						
			2.00	@	5.53	17.5	35.00	37.00	1g/t Au cut-off and no internal dilution

Criteria	JORC Code Explanation	Details								
			52.00	@	0.65	7.0	97.00	149.00	0.25g/t Au cut-off and max. 3m continuous internal dilution	
			and							
			17.00	@	1.19	11.7	107.00	124.00	0.5g/t Au cut-off and max. 3m continuous internal dilution	
			and							
			3.00	@	3.13	16.9	109.00	112.00	1g/t Au cut-off and no internal dilution	
		UGA-23		5.00	@	0.56	2.7	47.00	52.00	0.25g/t Au cut-off and no internal dilution
				including						
				3.00	@	0.72	2.7	49.00	52.00	0.5g/t Au cut-off and no internal dilution
				53.00	@	0.77	5.9	65.00	118.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
				including						
				2.00	@	2.71	28.0	79.00	81.00	1g/t Au cut-off and no internal dilution
				and						
				3.00	@	1.19	2.9	88.00	91.00	0.5g/t Au cut-off and no internal dilution
				and						
				5.00	@	1.75	6.4	95.00	100.00	1g/t Au cut-off and 1m internal dilution
			5.00	@	0.94	7.9	131.00	136.00	0.5g/t Au cut-off and no internal dilution	
		UGA-22		105.30	@	0.55	3.2	38.00	143.30	0.25g/t Au cut-off and max. 7m continuous internal dilution
				including						
				22.00	@	0.80	5.7	99.00	121.00	0.5g/t Au cut-off and 2m internal dilution
				and						
			13.00	@	1.28	2.4	130.00	143.30	0.3g/t Au cut-off and max. 4m continuous internal dilution	

Criteria	JORC Code Explanation	Details							
		and							
		3.00	@	4.42	5.2	130.00	133.00	0.5g/t Au cut-off and no internal dilution	
		UGA-21	98.00	@	0.55	3.4	60.00	158.00	0.25g/t Au cut-off and max. 10m continuous internal dilution
			including						
			2.00	@	3.37	6.1	60.00	62.00	1g/t Au cut-off and no internal dilution
			and						
			2.00	@	2.38	2.3	93.00	95.00	0.5g/t Au cut-off and no internal dilution
			and						
			6.00	@	1.10	5.6	110.00	116.00	0.5g/t Au cut-off and 2m internal dilution
			and						
			4.00	@	1.34	6.0	137.00	141.00	0.5g/t Au cut-off and 2m internal dilution
		and							
		9.00	@	1.03	4.1	149.00	158.00	0.5g/t Au cut-off and no internal dilution	
		UGA-20	61.00	@	0.97	12.3	55.00	116.00	0.25g/t Au cut-off and max. 5m continuous internal dilution
			including						
			19.00	@	2.07	29.1	77.00	96.00	1g/t Au cut-off and 4m internal dilution
			including						
			15.00	@	2.24	34.3	77.00	92.00	1.5g/t Au cut-off and max. 4m continuous internal dilution
			including						
			2.00	@	4.68	150.8	77.00	79.00	2g/t Au cut-off and no internal dilution
		and							
2.00	@	3.91	20.7	83.00	85.00	2g/t Au cut-off and no internal dilution			

Criteria	JORC Code Explanation	Details								
		UGA-19	68.00	@	0.43	4.3	19.00	87.00	0.26g/t Au cut-off and max. 6m continuous internal dilution	
			including							
			6.00	@	1.07	1.7	19.00	25.00	0.3g/t Au cut-off and 3m continuous internal dilution	
			and							
			3.00	@	1.23	15.4	33.00	36.00	0.3g/t Au cut-off and no internal dilution	
			and							
			2.00	@	0.93	8.0	49.00	51.00	0.3g/t Au cut-off and no internal dilution	
			and							
		1.00	@	4.08	46.4	77.00	78.00	1g/t Au cut-off and no internal dilution		
		UGA-18	38.00	@	17.72	17.6	44.00	82.00	0.26g/t Au cut-off, no top cut and max. 7m continuous internal dilution	
			including							
			18.00	@	36.96	30.6	64.00	82.00	0.5g/t Au cut-off, no top cut and max. 5m continuous internal dilution	
			including							
			6.00	@	109.82	81.7	76.00	82.00	1g/t Au cut-off, no top cut and max. 3m continuous internal dilution	
			including							
		UGA-17	45.00	@	2.65	10.4	52.00	97.00	0.26g/t Au cut-off, no top cut and max. 2m continuous internal dilution	
			including							
			35.00	@	3.31	12.3	60.00	95.00	1g/t Au cut-off, no top cut and max. 5m continuous internal dilution	
			including							
				19.00	@	5.08	12.9	67.00	86.00	2g/t Au cut-off, no top cut and max. 3m continuous internal dilution
		UGA-16	126.00	@	5.31	7.3	1.00	127.00	0.26g/t Au cut-off, no top cut and max. 7m continuous internal dilution	

Criteria	JORC Code Explanation	Details						
		including						
		70.00	@	9.23	7.8	40.00	110.00	0.5g/t Au cut-off, no top cut and max. 7m continuous internal dilution
		including						
		1.00	@	584.00	333.0	41.00	42.00	
		and						
		2.00	@	13.94	14.9	106.00	108.00	1g/t Au cut-off and no internal dilution
		UGA-15						
		124.00	@	1.47	11.6	3.00	127.00	0.26g/t Au cut-off and max. 6m continuous internal dilution
		including						
		14.00	@	2.70	27.5	17.00	31.00	1g/t Au cut-off and 4m internal dilution
		and						
		3.00	@	3.75	9.5	52.00	55.00	0.5g/t Au cut-off and no internal dilution
		and						
		7.00	@	7.97	25.3	64.00	71.00	1g/t Au cut-off and 1m internal dilution
		and						
		9.00	@	3.77	16.4	93.00	102.00	0.5g/t Au cut-off and 2m internal dilution
		UGA-14						
		108.00	@	2.22	7.6	26.00	134.00	0.2g/t Au cut-off and max. 7m continuous internal dilution
		including						
		63.00	@	3.53	9.6	71.00	134.00	0.26g/t Au cut-off and 9m internal dilution
		including						
42.00	@	4.98	11.9	91.00	133.00	1g/t Au cut-off and max. 5m continuous internal dilution		
including								
10.00	@	16.98	26.4	95.00	105.00	2g/t Au cut-off and 2m internal dilution		

Criteria	JORC Code Explanation	Details								
		UGA-13	2.00	@	1.74	3.5	78.00	80.00	0.26g/t Au cut-off and no internal dilution	
			including							
			4.00	@	0.61	3.3	99.00	103.00	0.26g/t Au cut-off and no internal dilution	
			including							
			3.00	@	0.82	8.5	132.00	135.00	0.26g/t Au cut-off and no internal dilution	
			including							
			19.00	@	4.25	3.7	152.00	171.00	0.26g/t Au cut-off and max. 5m continuous internal dilution	
			including							
			5.00	@	14.90	6.1	157.00	162.00	0.5g/t Au cut-off and 2m internal dilution	
		including								
		10.00	@	0.85	3.0	204.00	214.00	0.26g/t Au cut-off and 3m internal dilution		
		including								
		UGA-11	111.00	@	0.96	5.4	15.00	126.00	0.2g/t Au cut-off and max. 7m continuous internal dilution	
			including							
			19.00	@	4.23	17.2	107.00	126.00	1g/t Au cut-off and 5m internal dilution	
			including							
		6.00	@	8.39	21.0	117.00	123.00	3g/t Au cut-off and 3m internal dilution		
		UGA-08	137.00	@	0.60	1.2	0.00	137.00	0.2g/t Au cut-off and max. 3m continuous internal dilution	
			including							
			15.00	@	1.21	13.0	0.00	15.00	0.5g/t Au cut-off and max. 4m continuous internal dilution	
			and							
			5.00	@	1.22	15.3	32.0	37.00	0.5g/t Au cut-off and 1m internal dilution	
			and							
		5.00	@	4.48	5.2	87.00	92.00	0.3g/t Au cut-off and 3m internal dilution		

Criteria	JORC Code Explanation	Details							
			2.00	@	5.87	2.3	134.00	136.00	1g/t Au cut-off and no internal dilution
		UGA-09	5.00	@	0.64	5.6	16.00	21.00	0.26g/t Au cut-off and 3m internal dilution
			4.00	@	0.55	4.9	32.00	36.00	0.26g/t Au cut-off and 2m internal dilution
			2.00	@	2.38	3.0	46.00	48.00	0.26g/t Au cut-off and no internal dilution
			2.00	@	0.84	14.4	61.00	63.00	0.26g/t Au cut-off and no internal dilution
			21.00	@	0.96	3.6	86.00	107.00	0.26g/t Au cut-off and max. 2m continuous internal dilution
						including			
		7.00	@	2.24	6.0	100.00	107.00	0.5g/t Au cut-off and 2m internal dilution	
					including				
		4.00	@	3.31	9.0	103.00	107.00	1g/t Au cut-off and 1m internal dilution	
		UGA-07	112.00	@	0.87	7.7	16.00	128.00	0.26g/t Au cut-off and max. 5m continuous internal dilution
						including			
			24.00	@	2.28	11.5	17.00	41.00	0.5g/t Au cut-off and max. 7m continuous internal dilution
						including			
			4.00	@	10.86	36.2	34.00	38.00	1g/t Au cut-off and 2m internal dilution
			5.00	@	1.11	5.2	92.00	97.00	0.5g/t Au cut-off and 1m internal dilution
		3.00	@	1.57	5.0	112.00	115.00	0.5g/t Au cut-off and no internal dilution	

Criteria	JORC Code Explanation	Details							
		UGA-06	70.00	@	3.43	14.7	33.00	103.00	0.26g/t Au cut-off and max. 6m continuous internal dilution
			including						
			5.00	@	5.52	19.9	36.00	41.00	1g/t Au cut-off and no internal dilution
			and						
			8.00	@	8.55	22.5	56.00	64.00	2g/t Au cut-off and 1m internal dilution
			and						
			5.00	@	4.81	36.4	75.00	80.00	2g/t Au cut-off and 3m internal dilution
			and						
		4.00	@	22.81	37.4	98.00	102.00	2g/t Au cut-off and no internal dilution	
		UGA-05	32.00	@	4.62	17.5	70.00	102.00	0.26g/t Au cut-off and max. 3m continuous internal dilution
			including						
			9.00	@	14.53	48.2	90.00	99.00	2g/t Au cut-off and 3m internal dilution
		UGA-04	90.00	@	3.88	13.9	0.00	90.00	0.26g/t Au cut-off and max. 6m continuous internal dilution
			including						
			9.00	@	11.66	62.3	14.00	23.00	2g/t Au cut-off and 1m internal dilution
			and						
		UGA-03	73.00	@	2.14	8.8	211.00	284.00	0.26g/t Au cut-off and max. 3m continuous internal dilution, including a 1.39m historic mining void
			including						
			31.61	@	3.76	11.0	248.00	279.61	0.5g/t Au cut-off and max. 2m continuous internal dilution

Criteria	JORC Code Explanation	Details						
		including						
		24.00	@	4.74	13.4	252.00	276.00	1g/t Au cut-off and max. 3m continuous internal dilution
		including						
		15.00	@	6.70	15.3	252.00	267.00	2g/t Au cut-off and max. 3m continuous internal dilution
		including						
		7.00	@	11.65	24.7	260.00	267.00	5g/t Au cut-off and max. 1m continuous internal dilution
		UGA-02						
		7.90	@	0.58	9.2	0.10	7.80	0.26g/t Au cut-off and max. 3m continuous internal dilution
		and						
		9.00	@	0.94	6.5	17.00	26.00	0.26g/t Au cut-off and max. 2m continuous internal dilution
		including						
		4.00	@	1.52	10.2	17.00	21.00	0.5g/t Au cut-off and max. 1m continuous internal dilution
		including						
		5.00	@	0.91	13.7	46.00	51.00	0.5g/t Au cut-off and max. 2m continuous internal dilution
		including						
		8.00	@	0.92	5.0	92.00	97.00	0.5g/t Au cut-off and max. 2m internal dilution
		including						
		26.00	@	1.20	5.8	111.00	137.00	0.5g/t Au cut-off and max. 2m internal dilution
		including						
7.00	@	1.60	4.3	111.00	118.00	1g/t Au cut-off and max. 2m continuous internal dilution		
and								
6.00	@	1.50	10.8	124.00	130.00	1g/t Au cut-off and max. 1m continuous internal dilution		
including								
3.00	@	0.82	4.1	152.00	155.00	0.3g/t Au cut-off and no internal dilution		

Criteria	JORC Code Explanation	Details								
			15.00	@	1.16	3.5	168.00	183.00	0.5g/t Au cut-off and max. 1m continuous internal dilution	
		including								
			5.00	@	1.92	4.6	171.00	176.00	1g/t Au cut-off and max. 2m continuous internal dilution	
		UGA-01		2.00	@	2.43	76.7	1.00	3.00	0.5g/t Au cut-off and no internal dilution
				27.00	@	0.64	13.9	1.00	28.00	0.26g/t Au cut-off and max. 4m continuous internal dilution
			including							
				4.00	@	1.19	20.8	17.00	21.00	0.5g/t Au cut-off and max. 1m continuous internal dilution
				10.00	@	0.54	3.4	48.00	58.00	0.26g/t Au cut-off and max. 2m continuous internal dilution
				10.00	@	0.76	6.4	135.00	145.00	0.26g/t Au cut-off and max. 2m continuous internal dilution
			including							
				3.00	@	1.15	9.1	135.00	138.00	0.5g/t Au cut-off and no internal dilution
			and							
				3.00	@	1.04	6.4	142.00	145.00	0.5g/t Au cut-off and no internal dilution
			including							
				12.00	@	0.76	5.3	183.00	195.00	0.26g/t Au cut-off and max. 2m continuous internal dilution
			including							
			2.00	@	2.00	6.2	192.00	194.00	0.5g/t Au cut-off and no internal dilution	
	16.00	@	0.76	4.1	206.00	222.00	0.26g/t Au cut-off and max. 3m continuous internal dilution			
including										
	6.00	@	1.32	6.3	216.00	222.00	0.5g/t Au cut-off and max. 1m continuous internal dilution			

Criteria	JORC Code Explanation	Details																																																																																																			
		<table border="1"> <tr> <td>10.00</td> <td>@</td> <td>1.47</td> <td>9.7</td> <td>234.00</td> <td>244.00</td> <td>0.5g/t Au cut-off and max. 2m continuous internal dilution</td> </tr> </table>	10.00	@	1.47	9.7	234.00	244.00	0.5g/t Au cut-off and max. 2m continuous internal dilution																																																																																												
10.00	@	1.47	9.7	234.00	244.00	0.5g/t Au cut-off and max. 2m continuous internal dilution																																																																																															
Data aggregation methods	<ul style="list-style-type: none"> In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated. Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail. The assumptions used for any reporting of metal equivalent values should be clearly stated. 	<ul style="list-style-type: none"> All cut-off grades are reported. No top cut has been applied. The lower gold grade, larger intervals have been selected using a gold cut-off grade similar to the cut-off grade utilised for the Sturec Gold Project JORC 2012 Mineral Resource. While the higher gold grade, shorter intervals have been selected utilising incrementally increasing gold cut-off grades in order to visualise the mineralisation at a range of gold cut-off grades, which may be utilised in the future if the mineralisation needs to be high graded in order to support feasibility studies into the smaller, higher grade open pit mining or the possibility of being subjected to underground mining. Weighted means for each interval are calculated by: First multiply each of the widths of the individual sample intervals within the significant intersection by the assay result (Au g/t or Ag g/t) of each individual sample. Then sum all these values and divide by the overall width (m) of the significant intersection. Internal dilution was allowed as long as the aggregate weighted mean grade from the footwall or hangingwall side of the mineralised interval to the end of the dilution zone does not fall below the cut-off grade. Example of weighted mean calculation and treatment of internal dilution. <table border="1"> <thead> <tr> <th>Hole</th> <th>From (m)</th> <th>To (m)</th> <th>Interval (m)</th> <th>Sample Nr</th> <th>Au ppm (Au-AA26)</th> <th>Au g/t* interval</th> <th>Ag ppm (ME-ICP61)</th> <th>Ag g/t* interval</th> </tr> </thead> <tbody> <tr> <td>UGA-01</td> <td>234</td> <td>235</td> <td>1</td> <td>M294307</td> <td>4.23</td> <td>4.23</td> <td>44</td> <td>44</td> </tr> <tr> <td>UGA-01</td> <td>235</td> <td>236</td> <td>1</td> <td>M294308</td> <td>0.34</td> <td>0.34</td> <td>4.4</td> <td>4.4</td> </tr> <tr> <td>UGA-01</td> <td>236</td> <td>237</td> <td>1</td> <td>M294309</td> <td>0.5</td> <td>0.5</td> <td>5</td> <td>5</td> </tr> <tr> <td>UGA-01</td> <td>237</td> <td>238</td> <td>1</td> <td>M294310</td> <td>0.65</td> <td>0.65</td> <td>3.9</td> <td>3.9</td> </tr> <tr> <td>UGA-01</td> <td>238</td> <td>239</td> <td>1</td> <td>M294312</td> <td>0.27</td> <td>0.27</td> <td>4.2</td> <td>4.2</td> </tr> <tr> <td>UGA-01</td> <td>239</td> <td>240</td> <td>1</td> <td>M294313</td> <td>0.2</td> <td>0.2</td> <td>3.3</td> <td>3.3</td> </tr> <tr> <td>UGA-01</td> <td>240</td> <td>241</td> <td>1</td> <td>M294314</td> <td>0.8</td> <td>0.8</td> <td>7</td> <td>7</td> </tr> <tr> <td>UGA-01</td> <td>241</td> <td>242</td> <td>1</td> <td>M294315</td> <td>0.44</td> <td>0.44</td> <td>2.6</td> <td>2.6</td> </tr> <tr> <td>UGA-01</td> <td>242</td> <td>243</td> <td>1</td> <td>M294316</td> <td>0.5</td> <td>0.5</td> <td>1.9</td> <td>1.9</td> </tr> <tr> <td>UGA-01</td> <td>243</td> <td>244</td> <td>1</td> <td>M294317</td> <td>6.76</td> <td>6.76</td> <td>20.5</td> <td>20.5</td> </tr> </tbody> </table> <p>10 metres @ 1.47 g/t Au 9.68 g/t Ag from 234m using a 0.5g/t Au cut-off with 2m of continuous internal dilution</p>	Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm (Au-AA26)	Au g/t* interval	Ag ppm (ME-ICP61)	Ag g/t* interval	UGA-01	234	235	1	M294307	4.23	4.23	44	44	UGA-01	235	236	1	M294308	0.34	0.34	4.4	4.4	UGA-01	236	237	1	M294309	0.5	0.5	5	5	UGA-01	237	238	1	M294310	0.65	0.65	3.9	3.9	UGA-01	238	239	1	M294312	0.27	0.27	4.2	4.2	UGA-01	239	240	1	M294313	0.2	0.2	3.3	3.3	UGA-01	240	241	1	M294314	0.8	0.8	7	7	UGA-01	241	242	1	M294315	0.44	0.44	2.6	2.6	UGA-01	242	243	1	M294316	0.5	0.5	1.9	1.9	UGA-01	243	244	1	M294317	6.76	6.76	20.5	20.5
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm (Au-AA26)	Au g/t* interval	Ag ppm (ME-ICP61)	Ag g/t* interval																																																																																													
UGA-01	234	235	1	M294307	4.23	4.23	44	44																																																																																													
UGA-01	235	236	1	M294308	0.34	0.34	4.4	4.4																																																																																													
UGA-01	236	237	1	M294309	0.5	0.5	5	5																																																																																													
UGA-01	237	238	1	M294310	0.65	0.65	3.9	3.9																																																																																													
UGA-01	238	239	1	M294312	0.27	0.27	4.2	4.2																																																																																													
UGA-01	239	240	1	M294313	0.2	0.2	3.3	3.3																																																																																													
UGA-01	240	241	1	M294314	0.8	0.8	7	7																																																																																													
UGA-01	241	242	1	M294315	0.44	0.44	2.6	2.6																																																																																													
UGA-01	242	243	1	M294316	0.5	0.5	1.9	1.9																																																																																													
UGA-01	243	244	1	M294317	6.76	6.76	20.5	20.5																																																																																													

Criteria	JORC Code Explanation	Details																																																																																																																																																																																																																	
		<table border="1"> <tbody> <tr> <td>UGA-02</td> <td>16</td> <td>17</td> <td>1</td> <td>M294480</td> <td>0.24</td> <td>0.24</td> <td>2.2</td> <td>2.2</td> <td></td> <td></td> </tr> <tr> <td>UGA-02</td> <td>17</td> <td>18</td> <td>1</td> <td>M294481</td> <td>0.62</td> <td>0.62</td> <td>20.2</td> <td>20.2</td> <td>9 metres @</td> <td></td> </tr> <tr> <td>UGA-02</td> <td>18</td> <td>19</td> <td>1</td> <td>M294482</td> <td>4.3</td> <td>4.3</td> <td>13.1</td> <td>13.1</td> <td>0.94 g/t Au</td> <td></td> </tr> <tr> <td>UGA-02</td> <td>19</td> <td>20</td> <td>1</td> <td>M294483</td> <td>0.41</td> <td>0.41</td> <td>2.9</td> <td>2.9</td> <td>6.46 g/t Ag</td> <td></td> </tr> <tr> <td>UGA-02</td> <td>20</td> <td>21</td> <td>1</td> <td>M294484</td> <td>0.73</td> <td>0.73</td> <td>4.4</td> <td>4.4</td> <td>from</td> <td>17m</td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>using a 0.26g/t Au</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>cut-off with 2m of</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>continuous</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>internal dilution</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>including</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>4 metres @</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>1.52 g/t Au</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>10.15 g/t Ag</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>from</td> <td>17m</td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>using a 0.5g/t Au</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>cut-off with 1m</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>internal dilution</td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> </tbody> </table> <ul style="list-style-type: none"> No metal equivalents have been quoted. 	UGA-02	16	17	1	M294480	0.24	0.24	2.2	2.2			UGA-02	17	18	1	M294481	0.62	0.62	20.2	20.2	9 metres @		UGA-02	18	19	1	M294482	4.3	4.3	13.1	13.1	0.94 g/t Au		UGA-02	19	20	1	M294483	0.41	0.41	2.9	2.9	6.46 g/t Ag		UGA-02	20	21	1	M294484	0.73	0.73	4.4	4.4	from	17m										using a 0.26g/t Au											cut-off with 2m of											continuous											internal dilution											including											4 metres @											1.52 g/t Au											10.15 g/t Ag											from	17m										using a 0.5g/t Au											cut-off with 1m											internal dilution																							
UGA-02	16	17	1	M294480	0.24	0.24	2.2	2.2																																																																																																																																																																																																											
UGA-02	17	18	1	M294481	0.62	0.62	20.2	20.2	9 metres @																																																																																																																																																																																																										
UGA-02	18	19	1	M294482	4.3	4.3	13.1	13.1	0.94 g/t Au																																																																																																																																																																																																										
UGA-02	19	20	1	M294483	0.41	0.41	2.9	2.9	6.46 g/t Ag																																																																																																																																																																																																										
UGA-02	20	21	1	M294484	0.73	0.73	4.4	4.4	from	17m																																																																																																																																																																																																									
									using a 0.26g/t Au																																																																																																																																																																																																										
									cut-off with 2m of																																																																																																																																																																																																										
									continuous																																																																																																																																																																																																										
									internal dilution																																																																																																																																																																																																										
									including																																																																																																																																																																																																										
									4 metres @																																																																																																																																																																																																										
									1.52 g/t Au																																																																																																																																																																																																										
									10.15 g/t Ag																																																																																																																																																																																																										
									from	17m																																																																																																																																																																																																									
									using a 0.5g/t Au																																																																																																																																																																																																										
									cut-off with 1m																																																																																																																																																																																																										
									internal dilution																																																																																																																																																																																																										
Relationship between mineralisation widths and intercept length	<ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the downhole lengths are reported, there should be a clear statement to this effect (e.g. 'down hole length, true width not known'). 	<ul style="list-style-type: none"> Generally, the drilling from the Andrej Adit is at an angle to the strike of the mineralisation. As the mineralisation zone strikes approximately north-south similar to the Andrej Adit, the closer the hole azimuth is to north or south, the smaller the true thickness will be compared of the intersection thickness. Mineral Resource modelling suggests the Sturec ore body around UGA-30 is between 50-55m wide in true thickness. 3D modelling of UGA-27, UGA-26, UGA-25, UGA-24 and UGA-23 assay results obtained so far, suggest that in this southern extent of the Sturec ore body, the true thickness of mineralisation is between 20-50m wide. The mineralisation is funnel shaped with the thicker zone towards the top and getting thinner at depth. 																																																																																																																																																																																																																	
Diagrams	<ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole 	<ul style="list-style-type: none"> All relevant diagrams are reported in the body of this announcement. 																																																																																																																																																																																																																	

Criteria	JORC Code Explanation	Details
	<i>collar locations and appropriate sectional views.</i>	
Balanced reporting	<ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. 	<ul style="list-style-type: none"> All exploration results have been reported.
Other substantive exploration data	<ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. 	<ul style="list-style-type: none"> Several metallurgical test work programs have been completed at independent laboratories confirming that the Sturec ore is amenable to industry-standard cyanide leaching processing for gold and silver. However, the use of cyanide for ore processing was banned in Slovakia in 2014. In response to the cyanide ban, several metallurgical test work programs assessing alternative processing methodologies have been completed on the ore from Sturec. The three most promising are: <ul style="list-style-type: none"> Thiosulphate Leaching gold and silver extraction technology was investigated by the previous owners of the project (Arc Minerals Limited) between 2011-2014. The Thiosulphate Leaching test work results reported so far indicate that this alternate mineral processing methodology is generally applicable to the Sturec gold-silver ores. The most encouraging results came from the latest, Thiosulphate Leaching study completed in 2014 by CMC Chimie. In this study, Ammonium Thiosulphate leaching of the Sturec ore (10 batches of approximately 800kg each) produced a pregnant liquor that had a content of 3-8g/t Au and 10-25g/t Ag, which was then subjected to electrowinning and filtering/drying, producing a copper/gold/silver cement with an overall recovery of 90.5% for gold and 48.9% for silver. The resultant dry cement was approximately 1% gold-silver and about 50% copper. These results were used to justify the conclusion that Thiosulphate Leaching could be used as an alternative processing method to conventional cyanidation and that it was also more economically viable. These results are interpreted to indicate that a further, more detailed metallurgical test work investigation is warranted into this alternative processing method in order to underpin further economic analysis (scoping Study or PFS) of the Sturec Gold Project in light of Slovakia's ban on cyanidation mineral processing. In 2016-2017, Arc Minerals also investigated the Cycladex Process as another alternative to cyanidation. In this process a bromide-based solubilizing agent (lixiviant) leaches the ore creating potassium gold bromide (tetrabromoaurate: KAuBr_4). Then cyclodextrin, a commercially available corn-starch derivative, is added to the resultant pregnant liquor, which results in the spontaneous precipitation of crystals containing the gold. The gold is then released from the crystalline precipitate at high temperature using a furnace to yield solid gold metal. The Cycladex Process test work results reported indicate that this alternate mineral processing methodology is also generally applicable to the Sturec gold-silver ores and potentially cheaper than conventional cyanidation. These results are interpreted to indicate that further investigation is warranted into this alternative processing method and that a PFS-level metallurgical test work-study needs to be completed to underpin a revaluation of the 2013 PFS completed by SRK in light of Slovakia's ban on cyanidation mineral processing. As an alternative to onsite leaching, producing a gravity/flotation concentrate on site that could then be then further processed elsewhere (Austria/Belgium) has also been investigated. Gravity concentrate and flotation test work completed on 11 composite samples of Sturec ore found that gold recovery ranged from 64.1 to 93.9% and silver recovery ranged from 45.1 to 83.9%. This processing methodology is currently being used at Slovakia's only operating gold mine, which is of a very similar mineralisation style to Sturec; and so, there is a reasonable possibility it could also be used at Sturec. The main deterrents to this option are the cost of transporting this concentrate (obviously depending on the distance of the further processing facility) and the lower recovery of gold and silver (especially in fine ores). Further work needs to be done to better constrain the

Criteria	JORC Code Explanation	Details
		<p>metallurgical recovery of this processing methodology across the entire orebody, as well as understand the economic factors involved before an assessment of its suitability can be fully determined.</p> <ul style="list-style-type: none"> • Groundwater and geotechnical investigations were completed in 2013. The groundwater monitoring results and geotechnical data were found to be adequate to interpret reasonable open pit slope angles for the various host rock types for the purposes of an open pit optimisation that was used as justification for a 'reasonable prospects of economic extraction' interpretation. • Concerning the groundwater, it has been interpreted that the most likely current situation is that the water table around the open pit area was drawn down due the dewatering through the 'Heritage Adits'; with the Main Heritage Adit being situated some 300m below and transporting the groundwater 15km away to where it eventually reaches the surface. It was interpreted that the dewatering had occurred to the level with or below the maximum depth of the proposed pit (~300m). However, the possibility that the dewatering was not as efficient as interpreted has also considered and it has been recommended that up to 6 permanent monitoring wells be installed on the western and eastern sides of the pit to the full depth of the proposed pit. The primary purpose of these wells is to determine if there is any spatial and temporal variation in groundwater levels around the pit. • Geotechnical investigations found that the stability of the open pit was significantly controlled by the degree of argillic alteration of the predominantly andesite rock mass found at Sturec (host rock of the quartz veining). The modelling suggested that the pit slope needed to be as low as 43° in the highly argillic altered/clay rock type but that a 50° pit slope was adequate in the other rock types. • The groundwater and geotechnical investigation results have been used to model a recommended open pit design that achieved an adequate Factor of Safety (FoS) of greater than 2.0.
Further work	<ul style="list-style-type: none"> • <i>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> • <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i> 	<ul style="list-style-type: none"> • There is good potential for the delineation of further gold mineralisation within the Sturec Gold Project area through exploration. • Prospects such as Wolf, Vratislav, Katerina, Volle Henne and South Ridge are interpreted to be areas where further Mineral Resources could be defined at Sturec. Significant gold-silver bearing quartz vein mineralisation has been identified and variably explored/mined at each of these prospects.

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	K %	La ppm	Mg %	Mn ppm
UGA-30	0.00	1.00	1.00	M299481	0.52		10.6	4.19	90	560	0.6	4	0.05	<0.5	7	50	17	2.99	10	3.97	20	0.02	75
UGA-30	1.00	2.00	1.00	M299482	1.25		21.2	2.42	107	210	0.7	4	0.07	<0.5	6	55	28	1.92	<10	2.23	10	0.02	74
UGA-30	2.00	3.00	1.00	M299483	0.91		34.7	4.5	459	390	0.7	2	0.11	<0.5	22	47	29	3.66	10	3.76	20	0.03	60
UGA-30	3.00	4.00	1.00	M299484	0.34		6.9	2.96	153	290	0.7	2	0.06	<0.5	16	66	19	2.18	<10	3.06	10	0.03	67
UGA-30	4.00	5.00	1.00	M299485	3.21		20.3	1	690	80	0.6	<2	0.06	<0.5	22	64	23	1.96	<10	0.75	<10	0.02	93
UGA-30	5.00	6.00	1.00	M299486	0.16		6.4	2.4	426	80	0.7	<2	0.08	<0.5	9	78	13	2.73	<10	1.04	10	0.03	104
UGA-30	6.00	7.00	1.00	M299488	0.06		3.8	2.26	312	180	0.6	2	0.07	<0.5	14	51	12	1.96	<10	1.95	10	0.03	81
UGA-30	7.00	8.00	1.00	M299489	0.49		26.5	4.61	80	500	0.7	4	0.12	<0.5	11	84	24	3.01	10	5.15	20	0.02	67
UGA-30	8.00	9.00	1.00	M299490	0.29		4.9	6.16	273	570	0.9	<2	0.09	<0.5	21	74	24	3.62	10	5.16	20	0.06	45
UGA-30	9.00	10.00	1.00	M299491	2.08		25.7	5.05	529	460	0.8	3	0.07	<0.5	27	63	44	3.3	10	4.31	20	0.09	54
UGA-30	10.00	11.00	1.00	M299492	0.77		5.5	5.32	242	650	1	<2	0.03	<0.5	19	49	20	3.39	10	3.99	30	0.17	65
UGA-30	11.00	12.00	1.00	M299494	1.03		9.8	3.45	559	460	0.8	<2	0.08	<0.5	24	53	16	2.85	10	2.79	20	0.08	65
UGA-30	12.00	13.00	1.00	M299495	0.64		8.2	5.05	157	520	0.9	3	0.11	<0.5	13	41	21	3.31	10	4.34	20	0.1	61
UGA-30	13.00	14.00	1.00	M299496	4.25		12	4.18	803	370	0.8	4	0.11	<0.5	29	47	20	3.58	10	3.96	20	0.11	85
UGA-30	14.00	15.00	1.00	M299497	0.63		2.8	7.06	529	580	1.2	<2	0.2	<0.5	20	40	23	3.99	10	4.4	30	0.12	50
UGA-30	15.00	16.00	1.00	M299498	0.69		8.1	7	276	740	1.1	3	0.22	<0.5	14	39	32	3.1	10	4.91	30	0.12	64
UGA-30	16.00	17.00	1.00	M299499	0.07		3.5	7.12	1275	620	1	3	0.27	<0.5	41	37	19	4.38	10	4.72	30	0.13	51
UGA-30	17.00	18.00	1.00	M299501	0.25		13.4	7.11	988	600	1.2	4	0.26	<0.5	36	40	30	4.14	10	4.39	30	0.15	62
UGA-30	18.00	19.00	1.00	M299502	0.46		17.8	6.95	250	580	1.1	3	0.21	<0.5	16	40	40	2.62	10	4.23	30	0.27	80
UGA-30	19.00	20.00	1.00	M299503	0.98		8	7.61	465	580	1.6	3	0.23	<0.5	19	36	31	4.02	20	4	30	0.74	200
UGA-30	20.00	21.00	1.00	M299504	0.29		2.7	7.21	219	620	1.8	2	0.37	0.5	19	34	27	3.97	20	4.34	30	1.02	423
UGA-30	21.00	22.00	1.00	M299505	0.16		3.9	8.04	257	680	1.5	5	0.26	<0.5	18	36	36	3.46	20	5.11	40	0.28	86
UGA-30	22.00	23.00	1.00	M299506	0.28		2.3	7.68	187	670	1.2	5	0.25	<0.5	20	38	44	3.75	20	4.56	30	0.28	153
UGA-30	23.00	24.00	1.00	M299507	0.17		5.9	6.95	126	680	1.3	3	0.24	<0.5	19	36	35	3.78	10	4.86	30	0.41	196
UGA-30	24.00	25.00	1.00	M299508	0.08		3.1	6.25	904	140	1.3	4	0.57	<0.5	24	35	26	4.47	10	1.75	30	0.09	41
UGA-30	25.00	26.00	1.00	M299509	0.09		2.7	7.31	133	500	1.2	3	0.25	<0.5	19	37	37	3.8	20	5.72	30	0.28	54
UGA-30	26.00	27.00	1.00	M299510	0.25		3.8	6.7	166	510	1.1	2	0.23	<0.5	17	36	35	3.38	20	5.47	30	0.17	53
UGA-30	27.00	28.00	1.00	M299511	0.2		4.4	6.49	530	440	1.1	5	0.31	<0.5	18	35	32	3.65	10	5.01	30	0.12	55
UGA-30	28.00	29.00	1.00	M299512	0.14		3.6	5.99	1735	320	1.1	7	0.45	<0.5	32	32	30	4.84	10	4.21	30	0.09	42
UGA-30	29.00	30.00	1.00	M299513	0.53		10.2	5.26	4610	110	1.1	4	0.43	<0.5	30	35	23	7.11	10	1.11	30	0.04	48
UGA-30	30.00	31.00	1.00	M299514	0.14		9.3	4.86	451	470	0.8	<2	0.19	<0.5	13	50	18	2.78	10	5.33	20	0.03	63
UGA-30	31.00	32.00	1.00	M299515	0.58		6.9	5.4	768	570	0.9	3	0.2	<0.5	17	40	22	3.01	10	5.51	30	0.06	57
UGA-30	32.00	33.00	1.00	M299516	1.12		14.8	6.21	747	600	1.1	5	0.2	<0.5	15	43	28	3.39	10	4.74	30	0.14	80
UGA-30	33.00	34.00	1.00	M299517	0.46		3.6	6.49	162	590	1.4	5	0.26	<0.5	16	33	22	3.85	10	4.94	30	1.53	505
UGA-30	34.00	35.00	1.00	M299518	0.53		3.4	7	240	690	1.3	2	1.13	<0.5	15	32	38	4.14	10	5.34	30	1.74	907
UGA-30	35.00	36.00	1.00	M299519	0.12		2.2	7.16	2150	310	1.3	<2	0.41	<0.5	24	37	27	4.54	20	4.24	30	0.18	165
UGA-30	36.00	37.00	1.00	M299520	0.7		12.4	6.64	431	550	1	3	0.26	<0.5	21	41	31	2.8	10	5.69	30	0.15	146
UGA-30	37.00	38.00	1.00	M299521	0.24		4	6.78	220	600	1.2	2	0.42	<0.5	21	42	31	4.74	10	4.91	20	1.34	687
UGA-30	38.00	39.00	1.00	M299522	0.2		2.3	6.95	209	580	1	5	1.29	<0.5	19	39	26	4.17	10	5.36	30	1.35	557
UGA-30	39.00	40.00	1.00	M299523	0.32		2.6	6.43	219	550	1.2	<2	0.61	<0.5	20	40	28	4.5	10	4.9	20	1.08	844
UGA-30	40.00	41.00	1.00	M299524	0.21		2.7	6.75	951	370	1.1	5	0.32	<0.5	27	41	25	3.77	10	5.31	30	0.26	536
UGA-30	41.00	42.00	1.00	M299525	0.32		3.3	4.8	1355	190	0.9	3	0.19	<0.5	14	50	17	3.86	10	2.85	20	0.08	69
UGA-30	42.00	43.00	1.00	M299526	0.26		5.8	0.29	1040	10	0.5	3	0.19	<0.5	3	88	14	1.87	<10	0.04	<10	0.05	89
UGA-30	43.00	44.00	1.00	M299528	0.38		7.1	4.85	2010	370	0.9	2	0.38	<0.5	27	50	41	5.12	10	3.8	20	0.07	98
UGA-30	44.00	45.00	1.00	M299529	0.87		7.3	5.67	250	590	0.9	2	0.73	<0.5	15	39	27	3.9	10	4.37	20	1.06	481
UGA-30	45.00	46.00	1.00	M299531	0.87		10.4	6.76	180	630	1.2	2	0.73	<0.5	20	44	34	4.04	20	5.1	30	2.06	616
UGA-30	46.00	47.00	1.00	M299532	0.2		4.1	6.4	210	520	1	5	0.84	<0.5	18	50	34	4.4	10	4.81	20	1.98	714
UGA-30	47.00	48.00	1.00	M299533	0.19		2	6.75	230	590	1.1	<2	0.3	<0.5	17	56	37	3.18	10	5.83	30	0.21	130
UGA-30	48.00	49.00	1.00	M299534	0.43		2.8	5.77	275	590	1	5	0.85	<0.5	20	51	29	4.29	10	4.59	20	1.07	776
UGA-30	49.00	50.00	1.00	M299536	0.23		3.1	6.48	278	670	1.2	5	0.77	<0.5	20	44	33	4.4	10	4.56	30	1.01	540

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
UGA-30	0.00	1.00	1.00	3	0.1	6	130	3	2.82	76	8	101	<20	0.22	10	<10	57	<10	14			
UGA-30	1.00	2.00	1.00	3	0.04	5	210	2	1.37	131	5	54	<20	0.11	10	<10	30	<10	19			
UGA-30	2.00	3.00	1.00	6	0.1	12	410	5	3.74	83	10	79	<20	0.23	20	<10	78	<10	19			
UGA-30	3.00	4.00	1.00	5	0.06	7	220	<2	1.93	72	7	86	<20	0.15	10	<10	50	<10	19			
UGA-30	4.00	5.00	1.00	6	0.02	12	90	<2	1.48	187	2	36	<20	0.04	20	<10	12	<10	18			
UGA-30	5.00	6.00	1.00	7	0.02	9	240	<2	2.32	131	5	44	<20	0.1	20	<10	32	<10	21			
UGA-30	6.00	7.00	1.00	4	0.03	13	180	<2	1.73	96	3	57	<20	0.08	20	<10	28	<10	20			
UGA-30	7.00	8.00	1.00	7	0.07	10	500	5	2.93	76	11	83	<20	0.22	10	<10	63	<10	42			
UGA-30	8.00	9.00	1.00	4	0.08	17	460	6	3.82	66	17	103	<20	0.32	10	<10	114	<10	54			
UGA-30	9.00	10.00	1.00	5	0.05	20	370	11	3.39	132	12	128	<20	0.24	30	<10	79	<10	52			
UGA-30	10.00	11.00	1.00	4	0.05	13	260	7	3.44	92	11	165	<20	0.24	20	<10	83	<10	39			
UGA-30	11.00	12.00	1.00	5	0.03	15	230	<2	2.88	166	7	81	<20	0.15	40	<10	47	<10	34			
UGA-30	12.00	13.00	1.00	3	0.06	11	500	10	3.51	78	11	121	<20	0.23	10	<10	73	<10	49			
UGA-30	13.00	14.00	1.00	5	0.04	19	470	7	3.47	212	9	131	<20	0.19	70	<10	61	<10	40			
UGA-30	14.00	15.00	1.00	4	0.07	13	1150	9	4.16	85	15	228	<20	0.33	20	<10	113	<10	64			
UGA-30	15.00	16.00	1.00	4	0.08	9	1100	9	3.19	49	15	199	<20	0.32	10	<10	112	<10	65			
UGA-30	16.00	17.00	1.00	3	0.09	28	1120	11	4.74	144	15	157	<20	0.32	70	<10	106	<10	69			
UGA-30	17.00	18.00	1.00	3	0.09	27	1190	12	4.22	168	16	172	<20	0.34	60	<10	114	<10	64			
UGA-30	18.00	19.00	1.00	3	0.09	9	920	7	2.61	46	14	166	<20	0.32	10	<10	119	<10	58			
UGA-30	19.00	20.00	1.00	3	0.12	12	1080	8	3.17	61	16	181	<20	0.34	10	<10	127	<10	69			
UGA-30	20.00	21.00	1.00	2	0.1	14	1020	10	3.49	25	16	154	<20	0.35	10	<10	126	<10	87			
UGA-30	21.00	22.00	1.00	3	0.11	11	1150	10	3.52	40	17	211	<20	0.38	20	<10	133	<10	80			
UGA-30	22.00	23.00	1.00	2	0.1	13	1040	9	3.93	33	17	214	<20	0.36	10	<10	128	10	66			
UGA-30	23.00	24.00	1.00	4	0.08	11	970	10	3.8	39	16	183	<20	0.33	10	<10	117	<10	70			
UGA-30	24.00	25.00	1.00	4	0.02	13	2020	7	5	179	15	50	<20	0.31	50	<10	92	<10	41			
UGA-30	25.00	26.00	1.00	3	0.06	10	1260	7	4.12	37	17	139	<20	0.36	30	<10	127	<10	74			
UGA-30	26.00	27.00	1.00	2	0.06	9	1110	7	3.48	44	15	138	<20	0.32	20	<10	109	<10	67			
UGA-30	27.00	28.00	1.00	4	0.05	11	1580	5	3.61	120	14	116	<20	0.3	30	<10	98	10	53			
UGA-30	28.00	29.00	1.00	3	0.04	17	2360	10	5.29	256	11	88	<20	0.27	90	<10	80	<10	37			
UGA-30	29.00	30.00	1.00	5	0.02	17	2270	9	7.75	494	10	36	<20	0.24	160	<10	68	<10	38			
UGA-30	30.00	31.00	1.00	4	0.05	10	1210	6	2.72	124	9	94	<20	0.22	50	<10	59	<10	37			
UGA-30	31.00	32.00	1.00	4	0.05	12	1330	8	3.08	120	10	108	<20	0.25	50	<10	77	10	46			
UGA-30	32.00	33.00	1.00	5	0.07	11	1370	12	3.27	112	12	152	<20	0.28	40	<10	91	<10	52			
UGA-30	33.00	34.00	1.00	3	0.08	10	950	6	2.12	34	14	156	<20	0.3	10	<10	114	<10	63			
UGA-30	34.00	35.00	1.00	3	0.08	7	920	5	1.8	30	15	200	<20	0.3	20	<10	111	<10	75			
UGA-30	35.00	36.00	1.00	3	0.04	15	2100	5	4.56	185	16	118	<20	0.36	60	<10	124	<10	57			
UGA-30	36.00	37.00	1.00	3	0.07	15	800	7	2.8	93	15	170	<20	0.33	40	<10	106	<10	51			
UGA-30	37.00	38.00	1.00	5	0.09	12	1290	10	2.59	36	19	166	<20	0.36	10	<10	151	10	81			
UGA-30	38.00	39.00	1.00	3	0.09	8	1020	6	2.3	25	19	206	<20	0.36	10	<10	139	<10	65			
UGA-30	39.00	40.00	1.00	3	0.08	8	1150	7	2.31	32	19	142	<20	0.35	10	<10	140	10	63			
UGA-30	40.00	41.00	1.00	4	0.06	20	1530	3	2.96	136	18	114	<20	0.37	50	<10	138	10	66			
UGA-30	41.00	42.00	1.00	4	0.03	11	1360	5	3.92	178	12	57	<20	0.24	40	<10	98	<10	43			
UGA-30	42.00	43.00	1.00	7	0.01	7	460	<2	1.5	217	<1	18	<20	<0.01	40	<10	5	<10	5			
UGA-30	43.00	44.00	1.00	4	0.05	20	2160	<2	5.3	307	13	78	<20	0.25	100	<10	91	<10	36			
UGA-30	44.00	45.00	1.00	3	0.07	8	850	5	3.29	38	15	137	<20	0.29	10	<10	106	<10	52			
UGA-30	45.00	46.00	1.00	2	0.07	11	1030	4	2.42	31	18	173	<20	0.35	10	<10	147	10	61			
UGA-30	46.00	47.00	1.00	3	0.06	11	970	5	2.82	36	19	168	<20	0.33	10	<10	137	10	65			
UGA-30	47.00	48.00	1.00	3	0.1	13	1430	7	3.11	51	18	150	<20	0.35	10	<10	145	<10	76			
UGA-30	48.00	49.00	1.00	3	0.07	10	920	7	2.88	56	17	165	<20	0.3	10	<10	132	<10	82			
UGA-30	49.00	50.00	1.00	3	0.1	12	1050	5	3.38	35	17	160	<20	0.33	10	<10	132	<10	67			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-30	0.00	1.00	1.00							
UGA-30	1.00	2.00	1.00							
UGA-30	2.00	3.00	1.00							
UGA-30	3.00	4.00	1.00							
UGA-30	4.00	5.00	1.00							
UGA-30	5.00	6.00	1.00							
UGA-30	6.00	7.00	1.00							
UGA-30	7.00	8.00	1.00							
UGA-30	8.00	9.00	1.00							
UGA-30	9.00	10.00	1.00							
UGA-30	10.00	11.00	1.00							
UGA-30	11.00	12.00	1.00							
UGA-30	12.00	13.00	1.00							
UGA-30	13.00	14.00	1.00							
UGA-30	14.00	15.00	1.00							
UGA-30	15.00	16.00	1.00							
UGA-30	16.00	17.00	1.00							
UGA-30	17.00	18.00	1.00							
UGA-30	18.00	19.00	1.00							
UGA-30	19.00	20.00	1.00							
UGA-30	20.00	21.00	1.00							
UGA-30	21.00	22.00	1.00							
UGA-30	22.00	23.00	1.00							
UGA-30	23.00	24.00	1.00							
UGA-30	24.00	25.00	1.00							
UGA-30	25.00	26.00	1.00							
UGA-30	26.00	27.00	1.00							
UGA-30	27.00	28.00	1.00							
UGA-30	28.00	29.00	1.00							
UGA-30	29.00	30.00	1.00							
UGA-30	30.00	31.00	1.00							
UGA-30	31.00	32.00	1.00							
UGA-30	32.00	33.00	1.00							
UGA-30	33.00	34.00	1.00							
UGA-30	34.00	35.00	1.00							
UGA-30	35.00	36.00	1.00							
UGA-30	36.00	37.00	1.00							
UGA-30	37.00	38.00	1.00							
UGA-30	38.00	39.00	1.00							
UGA-30	39.00	40.00	1.00							
UGA-30	40.00	41.00	1.00							
UGA-30	41.00	42.00	1.00							
UGA-30	42.00	43.00	1.00							
UGA-30	43.00	44.00	1.00							
UGA-30	44.00	45.00	1.00							
UGA-30	45.00	46.00	1.00							
UGA-30	46.00	47.00	1.00							
UGA-30	47.00	48.00	1.00							
UGA-30	48.00	49.00	1.00							
UGA-30	49.00	50.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
					ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-30	50.00	51.00	1.00	M299537	0.11		2.6	7.07	221	550	1	<2	0.49	0.5	22	46	29	4.31	10	5.01	30	0.29	196
UGA-30	51.00	52.00	1.00	M299538	0.36		3.9	6.33	337	560	1	2	0.53	<0.5	18	44	29	4.03	10	4.67	30	0.31	260
UGA-30	52.00	53.00	1.00	M299539	0.54		7.7	5.55	1075	490	0.9	4	0.36	<0.5	29	45	33	4.85	10	4.86	20	0.04	51
UGA-30	53.00	54.00	1.00	M299540	0.27		4.2	6.25	191	600	0.8	3	0.23	<0.5	16	45	26	3.5	10	4.57	30	0.07	48
UGA-30	54.00	55.00	1.00	M299541	0.23		2.9	6.14	181	530	1.1	2	0.23	<0.5	19	44	27	4.63	10	4.71	30	0.11	69
UGA-30	55.00	56.00	1.00	M299542	0.08		2.7	5.9	118	730	0.7	4	0.45	<0.5	16	37	24	3.88	10	4.62	20	0.27	138
UGA-30	56.00	57.00	1.00	M299543	0.21		2.6	6.42	209	720	1.2	3	0.58	<0.5	18	38	28	4.1	10	4.24	20	1.13	522
UGA-30	57.00	58.00	1.00	M299544	8.06		26	6.78	358	620	1.6	2	0.47	<0.5	19	41	47	4.71	10	4.66	30	0.87	502
UGA-30	58.00	59.00	1.00	M299545	1.68		5.9	6.97	341	600	1.5	2	0.33	<0.5	20	43	32	4.48	10	5.72	30	0.33	315
UGA-30	59.00	60.00	1.00	M299546	3.45		19.2	7.57	394	700	1.9	2	0.36	<0.5	19	43	74	4.31	10	5.51	30	0.5	751
UGA-30	60.00	61.00	1.00	M299547	1.81		4.8	8	481	630	1.8	<2	0.41	<0.5	20	43	40	3.62	20	5.62	30	0.29	488
UGA-30	61.00	62.00	1.00	M299548	0.79		6.7	8.6	1275	860	1.9	<2	0.34	0.5	20	41	65	5.77	20	5.34	30	0.26	591
UGA-30	62.00	63.00	1.00	M299549	1.07		6.2	7.98	288	720	1.6	<2	0.38	0.5	18	44	41	3.35	20	6.37	30	0.26	522
UGA-30	63.00	64.00	1.00	M299551	0.32		6.1	7.83	164	720	1.5	2	0.32	<0.5	21	41	36	3.93	20	6.12	30	1.22	416
UGA-30	64.00	65.00	1.00	M299552	0.28		2	7.88	261	660	1.8	2	0.44	0.5	19	42	43	5.35	20	5.04	30	1	1545
UGA-30	65.00	66.00	1.00	M299553	1.01		6.9	7.65	715	720	1.6	<2	0.43	<0.5	19	40	52	4.39	10	4.53	30	0.23	509
UGA-30	66.00	67.00	1.00	M299554	1.7		4.5	7.18	774	590	1.7	3	0.36	0.5	21	47	31	4.65	10	4.96	30	0.31	775
UGA-30	67.00	68.00	1.00	M299555	0.88		2	8.89	359	560	1.6	<2	0.41	<0.5	17	46	57	1.69	20	6.79	30	0.22	169
UGA-30	68.00	69.00	1.00	M299556			14.2	5.76	490	470	1.4	<2	0.33	<0.5	16	34	58	3.67	10	4.44	20	0.23	254
UGA-30	69.00	70.00	1.00	M299557	0.36		3.9	6.84	214	590	1.2	<2	0.33	<0.5	15	49	28	3.1	10	5.48	30	0.25	233
UGA-30	70.00	71.00	1.00	M299558	0.74		43.1	6.79	423	390	1.4	<2	0.56	<0.5	15	52	34	2.68	20	5.03	30	0.22	146
UGA-30	71.00	72.00	1.00	M299559	1.08		5.5	8.25	627	560	1.6	<2	0.37	<0.5	20	51	41	3.28	20	6.14	30	0.32	474
UGA-30	72.00	73.00	1.00	M299560	1.17		4	8.2	575	540	1.7	<2	0.64	<0.5	20	50	46	3.07	20	5.97	30	0.32	408
UGA-30	73.00	74.00	1.00	M299561	1.37		9.8	8.11	247	650	2	<2	0.4	<0.5	20	57	43	4.89	20	6.27	30	0.55	961
UGA-30	74.00	75.00	1.00	M299562	1.81		15.6	6.36	1110	460	1.4	2	0.3	<0.5	19	49	42	5.32	10	4.4	20	0.26	252
UGA-30	75.00	76.00	1.00	M299565	0.56		2.8	7.66	800	650	1.6	<2	0.38	<0.5	20	49	35	3.75	20	5.37	30	0.27	304
UGA-30	76.00	77.00	1.00	M299566	0.14		2	8.17	131	820	1.6	<2	0.39	<0.5	19	50	33	4.45	20	6.51	30	0.57	884
UGA-30	77.00	78.00	1.00	M299567	0.56		12.2	7.68	226	710	1.4	<2	0.33	<0.5	17	56	38	2.22	20	6.22	30	0.21	206
UGA-30	78.00	79.00	1.00	M299568	0.34		4.4	7.89	123	630	1.4	<2	0.32	0.5	18	50	42	4.13	20	6.28	30	1.85	800
UGA-30	79.00	80.00	1.00	M299569	0.06		0.8	8.46	162	710	1.7	<2	0.69	0.5	21	50	34	5.46	20	6.51	30	1.04	1150
UGA-30	80.00	81.00	1.00	M299570	0.32		1.5	8.72	278	670	2	<2	0.44	0.5	23	51	38	4.59	20	5.71	30	0.67	917
UGA-30	81.00	82.00	1.00	M299571	4.35		21.6	6.27	960	380	1.4	<2	0.27	<0.5	17	52	77	3.03	10	4.06	20	0.12	96
UGA-30	82.00	83.00	1.00	M299572	0.34		2.3	9.23	854	460	2.6	<2	0.38	<0.5	24	56	46	3	20	4.88	30	0.15	162
UGA-30	83.00	84.00	1.00	M299573	0.25		3.5	7.25	429	540	1.2	<2	0.35	<0.5	19	45	30	4.38	10	5.31	30	0.35	652
UGA-30	84.00	85.00	1.00	M299574	4.23		15.8	7.38	305	180	1.5	2	0.36	<0.5	19	44	49	3.95	10	2.49	30	0.29	855
UGA-30	85.00	86.00	1.00	M299575	6.58		25.9	6.69	150	610	1.2	<2	0.31	<0.5	13	48	51	3.56	10	4.8	20	0.26	714
UGA-30	86.00	87.00	1.00	M299576	5.03		14	7.15	277	600	3	<2	0.23	<0.5	14	49	48	5.22	10	5.25	30	0.18	167
UGA-30	87.00	88.00	1.00	M299577	18.65		15.6	7.67	168	630	1.4	<2	0.33	<0.5	17	51	44	3.65	10	6.04	30	0.27	668
UGA-30	88.00	89.00	1.00	M299578	9.63		7.9	7.97	230	160	1.6	<2	0.38	<0.5	20	48	43	4.46	20	2.87	30	0.37	1635
UGA-30	89.00	90.00	1.00	M299580	0.74		2.5	8.48	188	640	1.3	<2	0.41	<0.5	18	53	37	4.4	20	6.89	30	0.43	1095
UGA-30	90.00	91.00	1.00	M299581	0.51		2.4	8.4	133	790	1.3	<2	0.63	<0.5	16	51	42	2.69	20	6.38	30	0.24	260
UGA-30	91.00	92.00	1.00	M299582	11.9		6.4	7.26	150	700	1.2	<2	0.35	<0.5	17	42	29	4.65	10	5.15	30	0.41	779
UGA-30	92.00	93.00	1.00	M299583	0.31		3.1	7.81	430	200	1.4	<2	0.39	0.5	20	45	43	4.82	20	2.89	30	0.39	1260
UGA-30	93.00	94.00	1.00	M299584	1.42		4.9	7.34	112	540	1.2	<2	0.34	<0.5	16	46	29	5.01	20	5.79	30	0.55	1190
UGA-30	94.00	95.00	1.00	M299585	0.21		2.4	7.5	127	540	1.3	<2	0.34	<0.5	16	46	29	4.47	10	5.42	30	0.43	682
UGA-30	95.00	97.00	2.00	M299586	1.6		65.5	7.58	153	510	1.2	<2	0.41	<0.5	15	48	52	2.6	10	5.07	30	0.2	60
UGA-30	97.00	98.00	1.00	M299587	1.21		14.6	6.61	265	470	1.2	<2	0.36	<0.5	16	43	36	2.92	10	4.52	30	0.17	60
UGA-30	98.00	99.00	1.00	M299588	0.25		3.7	7.34	332	250	1.2	<2	0.47	<0.5	20	42	26	3.58	20	3.81	30	0.29	50
UGA-30	99.00	100.00	1.00	M299589	0.43		8.5	6.15	583	260	1.1	<2	0.47	<0.5	15	41	32	3.66	10	3.08	20	0.16	45
UGA-30	100.00	101.00	1.00	M299591	0.12		3	7.19	158	520	0.9	<2	0.3	<0.5	17	50	38	2.21	10	5.11	30	0.17	47

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
UGA-30	50.00	51.00	1.00	2	0.11	12	1380	4	4.29	42	18	167	<20	0.37	20	<10	139	10	58			
UGA-30	51.00	52.00	1.00	8	0.08	12	1560	5	3.81	60	16	146	<20	0.33	20	<10	130	10	66			
UGA-30	52.00	53.00	1.00	2	0.06	20	2000	5	5.03	173	14	128	<20	0.28	60	<10	88	<10	42			
UGA-30	53.00	54.00	1.00	3	0.07	9	1260	5	3.68	41	16	159	<20	0.33	20	<10	122	<10	53			
UGA-30	54.00	55.00	1.00	3	0.06	11	1290	8	4.91	43	16	122	<20	0.32	20	<10	117	<10	52			
UGA-30	55.00	56.00	1.00	2	0.06	11	1010	5	4.01	32	16	119	<20	0.3	20	<10	103	<10	56			
UGA-30	56.00	57.00	1.00	2	0.06	12	960	11	3.36	24	17	152	<20	0.34	10	<10	122	<10	64			
UGA-30	57.00	58.00	1.00	4	0.06	12	1380	7	3.56	57	18	167	<20	0.35	20	<10	140	<10	73			
UGA-30	58.00	59.00	1.00	5	0.06	14	1200	11	3.42	62	18	159	<20	0.36	10	<10	142	10	76			
UGA-30	59.00	60.00	1.00	3	0.08	13	1130	14	2.24	41	19	112	<20	0.38	10	<10	157	<10	88			
UGA-30	60.00	61.00	1.00	2	0.08	12	1720	15	2.53	58	19	120	<20	0.4	20	<10	160	<10	71			
UGA-30	61.00	62.00	1.00	2	0.1	15	1290	15	3.92	45	22	180	<20	0.42	20	<10	156	<10	74			
UGA-30	62.00	63.00	1.00	2	0.1	12	1270	16	2.4	33	20	115	<20	0.4	10	<10	158	<10	77			
UGA-30	63.00	64.00	1.00	3	0.15	15	1190	15	2.61	24	19	117	<20	0.39	10	<10	159	<10	77			
UGA-30	64.00	65.00	1.00	2	0.2	11	1160	9	1.38	24	20	112	<20	0.39	20	<10	159	<10	89			
UGA-30	65.00	66.00	1.00	3	0.15	11	1600	14	3.66	55	18	112	<20	0.39	20	<10	136	<10	66			
UGA-30	66.00	67.00	1.00	5	0.07	14	1310	16	3.55	72	18	81	<20	0.36	20	<10	135	10	62			
UGA-30	67.00	68.00	1.00	2	0.06	9	1690	11	1.38	48	18	109	<20	0.44	20	<10	165	<10	78			
UGA-30	68.00	69.00	1.00	9	0.04	12	1290	12	3.53	72	15	88	<20	0.3	10	<10	122	<10	72		3.85	
UGA-30	69.00	70.00	1.00	4	0.06	9	1330	12	2.79	37	18	144	<20	0.34	10	<10	131	<10	64			
UGA-30	70.00	71.00	1.00	6	0.04	11	2330	16	2.52	74	17	127	<20	0.34	20	<10	136	<10	73			
UGA-30	71.00	72.00	1.00	3	0.05	12	1390	13	2.19	46	21	144	<20	0.41	20	<10	165	<10	72			
UGA-30	72.00	73.00	1.00	2	0.05	10	2630	15	2.07	56	19	114	<20	0.4	20	<10	148	<10	64			
UGA-30	73.00	74.00	1.00	3	0.08	13	1240	15	2.35	43	21	127	<20	0.4	10	<10	157	<10	80			
UGA-30	74.00	75.00	1.00	6	0.06	15	1170	12	5.11	101	17	74	<20	0.31	30	<10	126	<10	52			
UGA-30	75.00	76.00	1.00	2	0.09	13	1660	11	3.04	91	20	120	<20	0.38	30	<10	152	<10	78			
UGA-30	76.00	77.00	1.00	<1	0.17	14	1160	11	1.29	22	22	140	<20	0.4	10	<10	162	<10	79			
UGA-30	77.00	78.00	1.00	4	0.11	13	1270	9	1.61	53	19	141	<20	0.38	10	<10	145	<10	78			
UGA-30	78.00	79.00	1.00	2	0.12	13	1160	12	1.02	24	20	151	<20	0.39	10	<10	156	<10	80			
UGA-30	79.00	80.00	1.00	1	0.15	15	1190	14	1.31	20	22	157	<20	0.42	10	<10	170	<10	82			
UGA-30	80.00	81.00	1.00	2	0.24	18	1240	12	1.86	26	23	126	<20	0.43	10	<10	169	<10	104			
UGA-30	81.00	82.00	1.00	12	0.08	12	1060	16	2.82	130	14	65	<20	0.3	30	<10	114	<10	66			
UGA-30	82.00	83.00	1.00	2	0.07	17	1690	14	1.96	127	22	96	<20	0.47	30	<10	179	10	56			
UGA-30	83.00	84.00	1.00	2	0.05	12	1390	9	3.52	65	18	148	<20	0.37	20	<10	138	<10	68			
UGA-30	84.00	85.00	1.00	5	0.02	11	1380	14	2.89	68	18	63	<20	0.37	10	<10	143	<10	77			
UGA-30	85.00	86.00	1.00	2	0.06	11	1120	11	2.36	53	17	138	<20	0.33	10	<10	126	<10	81			
UGA-30	86.00	87.00	1.00	3	0.05	11	1440	11	1.87	183	17	124	<20	0.35	10	<10	129	<10	135			
UGA-30	87.00	88.00	1.00	2	0.06	10	1260	15	1.67	64	18	143	<20	0.38	20	<10	149	<10	77			
UGA-30	88.00	89.00	1.00	8	0.02	14	1370	12	1.69	77	22	62	<20	0.41	10	<10	165	<10	87			
UGA-30	89.00	90.00	1.00	2	0.1	14	1380	11	1.46	36	23	170	<20	0.42	10	<10	164	<10	86			
UGA-30	90.00	91.00	1.00	2	0.12	12	2570	14	2.02	26	21	172	<20	0.43	20	<10	154	10	80			
UGA-30	91.00	92.00	1.00	2	0.09	11	1270	13	3.09	26	19	139	<20	0.37	10	<10	143	<10	75			
UGA-30	92.00	93.00	1.00	8	0.03	14	1450	15	3.1	72	20	60	<20	0.39	10	<10	160	10	142			
UGA-30	93.00	94.00	1.00	3	0.06	10	1140	9	2.09	28	20	169	<20	0.37	10	<10	151	10	68			
UGA-30	94.00	95.00	1.00	3	0.07	10	1310	13	2.61	32	20	182	<20	0.38	10	<10	147	10	68			
UGA-30	95.00	97.00	2.00	4	0.07	10	1730	18	2.3	71	17	170	<20	0.38	10	<10	138	10	97			
UGA-30	97.00	98.00	1.00	3	0.06	11	1520	22	2.6	61	14	124	<20	0.33	10	<10	119	<10	78			
UGA-30	98.00	99.00	1.00	6	0.04	12	1920	13	3.77	65	18	103	<20	0.38	20	<10	147	<10	64			
UGA-30	99.00	100.00	1.00	5	0.03	11	2030	13	3.7	86	15	91	<20	0.31	20	<10	119	<10	56			
UGA-30	100.00	101.00	1.00	4	0.05	11	1220	10	2.22	37	19	154	<20	0.36	10	<10	137	10	81			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-30	50.00	51.00	1.00							
UGA-30	51.00	52.00	1.00							
UGA-30	52.00	53.00	1.00							
UGA-30	53.00	54.00	1.00							
UGA-30	54.00	55.00	1.00							
UGA-30	55.00	56.00	1.00							
UGA-30	56.00	57.00	1.00							
UGA-30	57.00	58.00	1.00							
UGA-30	58.00	59.00	1.00							
UGA-30	59.00	60.00	1.00							
UGA-30	60.00	61.00	1.00							
UGA-30	61.00	62.00	1.00							
UGA-30	62.00	63.00	1.00							
UGA-30	63.00	64.00	1.00							
UGA-30	64.00	65.00	1.00							
UGA-30	65.00	66.00	1.00							
UGA-30	66.00	67.00	1.00							
UGA-30	67.00	68.00	1.00							
UGA-30	68.00	69.00	1.00	16.8	3.65	0.297	17.7	1144	3.1	4.2
UGA-30	69.00	70.00	1.00							
UGA-30	70.00	71.00	1.00							
UGA-30	71.00	72.00	1.00							
UGA-30	72.00	73.00	1.00							
UGA-30	73.00	74.00	1.00							
UGA-30	74.00	75.00	1.00							
UGA-30	75.00	76.00	1.00							
UGA-30	76.00	77.00	1.00							
UGA-30	77.00	78.00	1.00							
UGA-30	78.00	79.00	1.00							
UGA-30	79.00	80.00	1.00							
UGA-30	80.00	81.00	1.00							
UGA-30	81.00	82.00	1.00							
UGA-30	82.00	83.00	1.00							
UGA-30	83.00	84.00	1.00							
UGA-30	84.00	85.00	1.00							
UGA-30	85.00	86.00	1.00							
UGA-30	86.00	87.00	1.00							
UGA-30	87.00	88.00	1.00							
UGA-30	88.00	89.00	1.00							
UGA-30	89.00	90.00	1.00							
UGA-30	90.00	91.00	1.00							
UGA-30	91.00	92.00	1.00							
UGA-30	92.00	93.00	1.00							
UGA-30	93.00	94.00	1.00							
UGA-30	94.00	95.00	1.00							
UGA-30	95.00	97.00	2.00							
UGA-30	97.00	98.00	1.00							
UGA-30	98.00	99.00	1.00							
UGA-30	99.00	100.00	1.00							
UGA-30	100.00	101.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
					ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-30	101.00	102.00	1.00	M299593	0.74		3.3	8.1	269	250	1.2	2	0.39	<0.5	23	55	48	2.93	20	4.54	30	0.17	45
UGA-30	102.00	103.00	1.00	M299594	0.24		3.8	6.3	198	150	1	<2	0.27	<0.5	16	42	39	2.5	10	2.88	30	0.19	54
UGA-30	103.00	104.00	1.00	M299595	0.39		3.4	7.37	112	330	0.8	<2	0.29	<0.5	17	44	32	3.85	10	5.24	30	0.26	569
UGA-30	104.00	105.00	1.00	M299596	0.18		2.3	7.32	150	220	0.9	<2	0.29	<0.5	18	50	31	2.52	10	3.5	30	0.21	188
UGA-30	105.00	106.00	1.00	M299597	0.74		2.6	7.52	134	320	1	<2	0.31	<0.5	18	45	29	3.95	10	4.2	30	0.36	872
UGA-30	106.00	107.00	1.00	M299598	2.54		12.8	6.8	325	490	1.2	<2	0.32	<0.5	13	36	36	4.6	10	4.84	30	0.3	587
UGA-30	107.00	108.00	1.00	M299599	0.21		3.4	7.21	182	570	1.2	<2	0.29	<0.5	16	33	26	4.03	10	5.25	30	0.37	652
UGA-30	108.00	109.00	1.00	M299601	0.28		14.2	7.06	295	510	1.2	<2	0.27	<0.5	14	34	29	3.62	20	5.14	30	0.29	209
UGA-30	109.00	110.00	1.00	M299602	0.25		4	7.74	275	220	1.4	<2	0.3	<0.5	17	33	33	3.7	20	3.62	30	0.33	430
UGA-30	110.00	111.00	1.00	M299603	0.26		4.1	8.17	376	190	1.3	2	0.32	<0.5	19	35	36	3.38	20	3.05	30	0.28	49
UGA-30	111.00	112.00	1.00	M299604	1.52		10.6	6.19	529	30	1.4	<2	0.27	<0.5	13	32	31	3.76	10	0.96	30	0.21	58
UGA-30	112.00	113.00	1.00	M299605	9.77		34.2	6.9	390	530	0.9	<2	0.28	<0.5	15	32	38	3.19	10	4.23	30	0.19	54
UGA-30	113.00	114.00	1.00	M299606	0.51		4.3	7.08	241	430	0.8	<2	0.25	<0.5	15	33	29	2.9	10	4.91	30	0.19	51
UGA-30	114.00	115.00	1.00	M299607	3.71		10.1	7.93	451	110	1	<2	0.3	<0.5	17	36	42	3.42	10	1.93	30	0.18	48
UGA-30	115.00	116.00	1.00	M299608	0.67		7.3	7.74	452	350	0.9	<2	0.27	0.5	19	35	38	3.23	10	3.62	30	0.18	49
UGA-30	116.00	117.00	1.00	M299609	0.92		6.5	7.56	311	320	0.9	<2	0.25	<0.5	16	36	33	2.68	10	3.97	30	0.13	40
UGA-30	117.00	118.00	1.00	M299610	0.56		8.1	7.64	776	200	1.1	<2	0.21	<0.5	19	38	40	4.04	20	3.15	30	0.15	52
UGA-30	118.00	119.00	1.00	M299611	2.39		7.3	7.94	658	20	1.2	<2	0.25	0.7	21	43	45	4.53	20	0.88	30	0.18	46
UGA-30	119.00	120.00	1.00	M299612	43.9		51.4	5.71	445	20	1	<2	0.09	<0.5	16	37	77	3.52	10	0.62	20	0.14	97
UGA-30	120.00	121.00	1.00	M299613	41.1		55.1	6.15	386	90	1.2	<2	0.21	<0.5	15	35	60	3.34	10	1.38	30	0.14	84
UGA-30	121.00	122.00	1.00	M299614	0.38		3.7	7.94	558	800	1.3	2	0.28	<0.5	18	42	64	3.68	20	5.63	30	0.18	67
UGA-30	122.00	123.00	1.00	M299615	1.25		5.4	7.17	529	770	1	<2	0.25	<0.5	17	37	43	3.23	10	5.13	30	0.12	54
UGA-30	123.00	124.00	1.00	M299616	0.42		4.8	7.37	440	600	1.3	<2	0.27	<0.5	21	41	34	3.74	10	5.85	30	0.13	85
UGA-30	124.00	125.00	1.00	M299617	0.2		2.8	7.09	262	600	1	<2	0.25	<0.5	21	39	32	2.42	20	4.34	30	0.1	50
UGA-30	125.00	126.00	1.00	M299618	6.49		28.3	6.87	1620	550	0.8	2	0.1	<0.5	21	37	53	4.06	10	4.58	30	0.1	62
UGA-30	126.00	127.00	1.00	M299620	0.7		7.7	6.94	995	260	1.3	<2	0.17	<0.5	20	39	34	4.01	20	2.77	30	0.14	57
UGA-30	127.00	128.00	1.00	M299621			94.5	3.75	1290	230	0.9	4	0.11	0.5	15	31	95	4	10	2	20	0.1	83
UGA-30	128.00	129.00	1.00	M299623	3.03		12.1	6.68	241	810	1.1	<2	0.25	<0.5	17	37	41	2.61	10	4.03	30	0.15	208
UGA-30	129.00	130.00	1.00	M299624	0.51		5	7.4	143	790	1.1	<2	0.29	<0.5	17	38	26	3.12	20	4.11	30	0.32	370
UGA-30	130.00	131.00	1.00	M299625	0.43		6.5	6.86	244	720	1.2	2	0.22	<0.5	18	37	29	3.2	20	4.04	30	0.19	69
UGA-30	131.00	132.00	1.00	M299626	0.3		4.5	6.83	130	710	1.1	<2	0.23	<0.5	18	37	28	2.81	20	4.47	30	0.19	56
UGA-30	132.00	133.00	1.00	M299627	12.4		95.3	6.27	246	610	0.9	<2	0.13	<0.5	18	34	37	3.17	10	4.4	20	0.21	63
UGA-30	133.00	134.00	1.00	M299628	0.19		3.6	7	216	460	1.3	2	0.24	<0.5	19	36	30	3.12	20	4.24	30	0.16	78
UGA-30	134.00	135.00	1.00	M299629	9.73		15	6.65	148	650	0.9	<2	0.2	<0.5	18	33	31	3.23	10	4.43	20	0.12	137
UGA-30	135.00	136.00	1.00	M299630	1.99		16.2	6.92	161	670	1	<2	0.24	<0.5	18	36	33	3.62	10	4.14	30	0.22	315
UGA-30	136.00	137.00	1.00	M299631	19.7		20.9	6.28	126	580	0.9	<2	0.21	<0.5	16	42	32	3.18	10	4.74	30	0.19	275
UGA-30	137.00	138.00	1.00	M299632	5.1		21.9	5.44	302	660	1.1	<2	0.21	<0.5	14	40	32	3.5	10	4.55	20	0.19	220
UGA-30	138.00	139.00	1.00	M299634	0.31		2.6	5.54	363	840	1.1	<2	0.19	<0.5	14	51	24	3.64	10	3.85	20	0.34	239
UGA-30	139.00	140.00	1.00	M299635	0.47		5.7	5.76	246	670	1	<2	0.2	<0.5	17	45	28	3.51	10	3.79	20	0.23	88
UGA-30	140.00	141.00	1.00	M299636	1.94		6.8	7.27	214	930	1.1	<2	0.16	<0.5	19	48	32	3.18	20	4.55	20	0.14	46
UGA-30	141.00	142.00	1.00	M299637	0.27		6.6	6.83	385	840	1.1	<2	0.09	0.5	17	38	30	3.75	10	4.82	20	0.11	56
UGA-30	142.00	143.00	1.00	M299638	0.17		5.4	6.46	571	820	1.4	<2	0.08	<0.5	16	37	29	4.45	10	4.2	20	0.14	55
UGA-30	143.00	144.00	1.00	M299639	0.19		3.7	7.66	302	830	1	2	0.05	<0.5	18	40	29	3.58	20	4.82	20	0.18	41
UGA-30	144.00	145.00	1.00	M299641	1.84		9	6.81	384	730	1.1	<2	0.1	<0.5	19	37	45	3.77	20	4.2	20	0.27	52
UGA-30	145.00	146.00	1.00	M299642	0.61		3.9	6.54	275	800	1.2	<2	0.09	<0.5	18	39	30	3.96	10	4.06	20	0.37	59
UGA-30	146.00	147.00	1.00	M299643	0.35		5.7	7.41	392	670	1.1	<2	0.15	<0.5	25	42	37	5.18	20	4.56	30	0.5	58
UGA-30	147.00	148.00	1.00	M299644	0.36		7.1	7.57	242	930	1.3	<2	0.17	<0.5	22	49	41	3.3	20	4.21	30	0.37	51
UGA-30	148.00	149.00	1.00	M299645	0.3		6	7.69	278	940	1.2	<2	0.22	<0.5	17	50	46	3.18	20	4.64	30	0.38	78
UGA-30	149.00	150.00	1.00	M299646	4.91		15	6.07	389	800	1	2	0.22	<0.5	16	40	45	3.83	10	4.12	20	0.91	134
UGA-30	150.00	151.00	1.00	M299647	1.39		30.2	6.98	417	770	1	<2	0.26	0.5	21	43	86	3.84	20	4.49	20	1.74	283

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-30	101.00	102.00	1.00	4	0.05	13	1660	10	3.17	63	20	123	<20	0.46	10	<10	169	10	81			
UGA-30	102.00	103.00	1.00	3	0.03	13	1080	14	2.55	62	15	78	<20	0.32	10	<10	122	10	71			
UGA-30	103.00	104.00	1.00	3	0.05	13	1150	13	3.09	46	19	137	<20	0.37	10	<10	143	<10	67			
UGA-30	104.00	105.00	1.00	3	0.03	12	1160	12	2.38	1060	18	92	<20	0.37	10	<10	140	10	67			
UGA-30	105.00	106.00	1.00	5	0.04	12	1150	13	2.98	4830	19	104	<20	0.38	10	<10	147	<10	79			
UGA-30	106.00	107.00	1.00	11	0.05	10	1360	20	3.31	94	17	123	<20	0.34	10	<10	128	<10	59			
UGA-30	107.00	108.00	1.00	4	0.06	11	1120	14	2.97	32	18	150	<20	0.35	20	<10	131	<10	59			
UGA-30	108.00	109.00	1.00	5	0.05	10	1110	14	3.56	50	16	145	<20	0.34	10	<10	127	<10	68			
UGA-30	109.00	110.00	1.00	2	0.03	11	1280	12	3.34	58	18	91	<20	0.39	10	<10	148	<10	71			
UGA-30	110.00	111.00	1.00	2	0.03	11	1350	9	3.58	69	19	76	<20	0.4	10	<10	148	10	83			
UGA-30	111.00	112.00	1.00	5	0.01	9	1200	17	3.71	147	14	23	<20	0.3	10	<10	103	<10	71			
UGA-30	112.00	113.00	1.00	7	0.04	10	1200	12	3.31	79	16	88	<20	0.34	10	<10	119	<10	67			
UGA-30	113.00	114.00	1.00	5	0.05	8	1110	13	3	51	16	136	<20	0.35	10	<10	135	<10	64			
UGA-30	114.00	115.00	1.00	11	0.02	11	1420	12	3.59	96	18	56	<20	0.4	10	<10	154	10	104			
UGA-30	115.00	116.00	1.00	9	0.04	15	1190	23	3.37	560	17	107	<20	0.37	10	<10	139	10	102			
UGA-30	116.00	117.00	1.00	16	0.04	11	1210	12	2.59	1395	16	109	<20	0.37	20	<10	133	10	52			
UGA-30	117.00	118.00	1.00	10	0.03	13	1210	16	3.82	200	19	74	<20	0.4	10	<10	146	10	58			
UGA-30	118.00	119.00	1.00	36	0.01	17	1430	27	4.85	249	19	20	<20	0.41	30	<10	157	<10	1520			
UGA-30	119.00	120.00	1.00	11	0.01	14	380	12	3.4	891	14	24	<20	0.3	10	<10	97	10	251			
UGA-30	120.00	121.00	1.00	5	0.02	13	970	16	3.18	153	15	37	<20	0.31	10	<10	111	<10	186			
UGA-30	121.00	122.00	1.00	3	0.07	12	1270	14	3.7	45	20	127	<20	0.41	20	<10	159	<10	84			
UGA-30	122.00	123.00	1.00	8	0.07	11	1200	10	3.24	55	15	119	<20	0.38	10	<10	130	10	59			
UGA-30	123.00	124.00	1.00	26	0.09	9	1250	8	3.73	64	18	147	<20	0.42	10	<10	149	<10	55			
UGA-30	124.00	125.00	1.00	29	0.08	11	1340	12	2.49	58	17	126	<20	0.42	10	<10	146	<10	54			
UGA-30	125.00	126.00	1.00	32	0.06	14	560	15	4.06	155	16	126	<20	0.38	50	<10	115	<10	45			
UGA-30	126.00	127.00	1.00	18	0.03	14	1060	11	4.02	131	18	51	<20	0.39	20	<10	141	10	47			
UGA-30	127.00	128.00	1.00	48	0.03	12	470	15	3.99	216	9	42	<20	0.19	40	<10	73	<10	167		67.9	
UGA-30	128.00	129.00	1.00	3	0.09	9	1060	10	2.13	46	17	133	<20	0.35	10	<10	130	<10	72			
UGA-30	129.00	130.00	1.00	3	0.1	10	1210	9	2.12	28	19	156	<20	0.4	20	<10	149	<10	71			
UGA-30	130.00	131.00	1.00	6	0.1	12	1100	11	3.06	59	18	151	<20	0.38	10	<10	144	<10	62			
UGA-30	131.00	132.00	1.00	4	0.12	12	1110	8	2.89	35	17	160	<20	0.37	10	<10	138	<10	68			
UGA-30	132.00	133.00	1.00	10	0.09	8	670	8	3.19	49	16	146	<20	0.34	20	<10	135	10	64			
UGA-30	133.00	134.00	1.00	5	0.07	11	1270	9	2.79	103	18	137	<20	0.39	10	<10	142	<10	91			
UGA-30	134.00	135.00	1.00	4	0.09	8	990	15	3.23	50	16	212	<20	0.37	10	<10	129	<10	76			
UGA-30	135.00	136.00	1.00	5	0.08	11	1080	10	3.43	60	19	164	<20	0.37	10	<10	141	<10	67			
UGA-30	136.00	137.00	1.00	3	0.06	9	920	12	2.77	85	17	106	<20	0.33	10	<10	128	<10	64			
UGA-30	137.00	138.00	1.00	4	0.06	11	990	11	2.63	81	15	102	<20	0.29	10	<10	112	<10	53			
UGA-30	138.00	139.00	1.00	4	0.07	10	850	8	3.16	60	16	129	<20	0.3	10	<10	109	<10	51			
UGA-30	139.00	140.00	1.00	5	0.08	12	890	11	3.61	42	16	150	<20	0.31	10	<10	126	<10	56			
UGA-30	140.00	141.00	1.00	3	0.09	11	950	8	3.23	40	18	178	<20	0.39	10	<10	132	<10	52			
UGA-30	141.00	142.00	1.00	3	0.07	12	760	8	3.66	43	18	169	<20	0.37	20	<10	119	<10	54			
UGA-30	142.00	143.00	1.00	6	0.07	10	870	11	3.75	73	16	157	<20	0.34	10	<10	108	<10	64			
UGA-30	143.00	144.00	1.00	4	0.08	11	580	14	3.72	33	17	203	<20	0.41	10	<10	138	<10	52			
UGA-30	144.00	145.00	1.00	6	0.06	13	800	17	3.87	54	16	143	<20	0.36	10	<10	134	<10	49			
UGA-30	145.00	146.00	1.00	4	0.05	11	760	12	4	40	17	93	<20	0.34	10	<10	128	<10	40			
UGA-30	146.00	147.00	1.00	6	0.05	16	840	16	5.63	38	19	109	<20	0.37	10	<10	147	<10	50			
UGA-30	147.00	148.00	1.00	4	0.07	12	1110	14	3.33	38	20	150	<20	0.4	10	<10	155	<10	63			
UGA-30	148.00	149.00	1.00	6	0.09	12	1390	13	3.05	34	19	142	<20	0.4	10	<10	147	10	62			
UGA-30	149.00	150.00	1.00	11	0.08	12	970	12	3.5	44	15	121	<20	0.31	10	<10	121	<10	70			
UGA-30	150.00	151.00	1.00	9	0.1	15	1180	12	2.25	41	17	138	<20	0.36	10	<10	148	<10	85			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-30	101.00	102.00	1.00							
UGA-30	102.00	103.00	1.00							
UGA-30	103.00	104.00	1.00							
UGA-30	104.00	105.00	1.00							
UGA-30	105.00	106.00	1.00							
UGA-30	106.00	107.00	1.00							
UGA-30	107.00	108.00	1.00							
UGA-30	108.00	109.00	1.00							
UGA-30	109.00	110.00	1.00							
UGA-30	110.00	111.00	1.00							
UGA-30	111.00	112.00	1.00							
UGA-30	112.00	113.00	1.00							
UGA-30	113.00	114.00	1.00							
UGA-30	114.00	115.00	1.00							
UGA-30	115.00	116.00	1.00							
UGA-30	116.00	117.00	1.00							
UGA-30	117.00	118.00	1.00							
UGA-30	118.00	119.00	1.00							
UGA-30	119.00	120.00	1.00							
UGA-30	120.00	121.00	1.00							
UGA-30	121.00	122.00	1.00							
UGA-30	122.00	123.00	1.00							
UGA-30	123.00	124.00	1.00							
UGA-30	124.00	125.00	1.00							
UGA-30	125.00	126.00	1.00							
UGA-30	126.00	127.00	1.00							
UGA-30	127.00	128.00	1.00	150.5	66	4.334	28.8	1193.5	64.8	67.1
UGA-30	128.00	129.00	1.00							
UGA-30	129.00	130.00	1.00							
UGA-30	130.00	131.00	1.00							
UGA-30	131.00	132.00	1.00							
UGA-30	132.00	133.00	1.00							
UGA-30	133.00	134.00	1.00							
UGA-30	134.00	135.00	1.00							
UGA-30	135.00	136.00	1.00							
UGA-30	136.00	137.00	1.00							
UGA-30	137.00	138.00	1.00							
UGA-30	138.00	139.00	1.00							
UGA-30	139.00	140.00	1.00							
UGA-30	140.00	141.00	1.00							
UGA-30	141.00	142.00	1.00							
UGA-30	142.00	143.00	1.00							
UGA-30	143.00	144.00	1.00							
UGA-30	144.00	145.00	1.00							
UGA-30	145.00	146.00	1.00							
UGA-30	146.00	147.00	1.00							
UGA-30	147.00	148.00	1.00							
UGA-30	148.00	149.00	1.00							
UGA-30	149.00	150.00	1.00							
UGA-30	150.00	151.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-30	151.00	152.00	1.00	M299648	0.85		4.8	7.65	180	700	1.1	3	0.22	<0.5	21	47	39	2.27	20	4.41	30	0.68	158
UGA-30	152.00	153.00	1.00	M299649	0.19		1.4	7.81	138	750	1.3	3	0.29	<0.5	19	45	61	3.53	20	5.38	20	2.11	326
UGA-30	153.00	154.00	1.00	M299650	8.14		14.2	7.07	777	850	1.1	2	0.26	<0.5	19	42	58	3.94	20	4.82	30	1.49	203
UGA-30	154.00	155.00	1.00	M299651	>100	139	87.3	6.74	915	480	1.1	<2	0.25	0.5	20	39	42	5	20	4.1	30	1.49	204
UGA-30	155.00	156.00	1.00	M299653	1.78		25.4	6.94	563	1010	1	2	0.25	0.5	19	41	62	4.29	10	4.64	30	1.94	249
UGA-30	156.00	157.00	1.00	M299654	0.53		5.7	6.43	673	670	1	2	0.24	<0.5	20	41	35	4.12	10	3.97	20	1.19	145
UGA-30	157.00	158.00	1.00	M299656	1.16		10.6	7.02	531	1030	1.1	5	0.37	<0.5	22	51	40	3.9	20	4.49	30	2.24	274
UGA-30	158.00	159.00	1.00	M299657	1.33		11.8	5.25	552	740	1	<2	0.25	<0.5	15	43	33	2.96	10	4.22	20	0.23	71
UGA-30	159.00	160.00	1.00	M299658	11.15		12.8	6.54	530	1040	1	<2	0.17	<0.5	16	50	47	2.65	10	4.36	20	0.2	42
UGA-30	160.00	161.00	1.00	M299659	0.43		15.5	7.25	257	940	1.2	<2	0.23	<0.5	19	54	47	2.71	20	5.41	30	0.86	139
UGA-30	161.00	162.00	1.00	M299661	0.34		6	6.6	219	900	0.8	<2	0.17	<0.5	15	49	37	1.8	10	4.37	20	0.46	91
UGA-30	162.00	163.00	1.00	M299662	1.23		29.7	3.38	620	440	0.8	2	0.07	<0.5	6	33	25	2.84	10	2.18	10	0.13	56
UGA-30	163.00	164.00	1.00	M299663	1.55		13.7	2.25	445	290	0.7	<2	0.16	<0.5	5	30	20	2.12	10	1.47	10	0.12	90
UGA-30	164.00	165.00	1.00	M299664	0.15		4.7	2.6	197	180	0.7	<2	0.07	<0.5	4	35	11	1.4	10	1.19	10	0.09	93
UGA-30	165.00	166.00	1.00	M299665	0.35		13.4	3.72	417	230	1	<2	0.09	<0.5	7	30	11	3.01	10	1.49	10	0.13	79
UGA-30	166.00	167.00	1.00	M299666	0.21		6.9	3.24	484	160	1	<2	0.06	<0.5	2	29	10	2.6	10	0.99	10	0.1	55
UGA-30	167.00	168.00	1.00	M299667	0.83		13.5	4.23	547	190	1.7	3	0.12	<0.5	10	29	23	3.95	10	1.61	20	0.17	89
UGA-30	168.00	170.00	2.00	M299668	1.15		27.4	3.09	270	170	0.7	<2	0.38	<0.5	5	28	28	2.17	10	1.24	10	0.12	99
UGA-30	170.00	173.20	3.20	M299670	1.81		22.2	5.27	238	600	1.2	5	1.08	<0.5	22	38	47	3.63	10	2.49	20	0.63	550
UGA-27	9.00	10.00	1.00	M299053	0.1		2.2	6.64	198	250	1	<2	0.87	<0.5	18	62	46	4.39	10	4.14	20	1.52	385
UGA-27	10.00	11.00	1.00	M299054	0.78		18	4.92	477	140	0.9	<2	6.74	<0.5	13	42	36	4.36	10	2.33	20	3.69	2120
UGA-27	11.00	12.00	1.00	M299056	0.15		3.1	6.33	188	390	1	<2	0.72	<0.5	18	60	51	4.06	10	4.29	20	1.07	307
UGA-27	12.00	13.00	1.00	M299057	0.1		2.9	6.44	191	400	1	<2	1.12	<0.5	18	60	41	4.2	10	4.49	30	1.33	377
UGA-27	13.00	14.00	1.00	M299058	0.09		1.6	6.79	202	440	1	<2	0.89	<0.5	19	66	42	4.76	10	4.85	20	1.32	365
UGA-27	14.00	15.00	1.00	M299059	0.34		2.3	6.7	296	650	1.1	<2	0.49	<0.5	20	68	36	4.18	10	4.52	20	0.97	365
UGA-27	15.00	16.00	1.00	M299060	0.1		2.7	6.61	145	550	1.1	<2	0.91	<0.5	19	64	30	4.08	10	4.5	20	1.37	462
UGA-27	16.00	17.00	1.00	M299061	0.08		1.4	6.98	102	440	1.3	<2	0.74	<0.5	21	68	30	4.36	10	4.83	30	1.26	568
UGA-27	17.00	18.00	1.00	M299062	0.41		5	7.05	107	450	1	<2	1.21	<0.5	19	69	28	4.46	10	4.84	20	1.27	466
UGA-27	18.00	19.00	1.00	M299063	0.18		2	7.36	69	480	1	<2	0.64	<0.5	23	73	33	4.93	10	4.8	30	1.09	358
UGA-27	19.00	20.00	1.00	M299064	0.08		1.2	7.31	96	600	1	<2	1.5	<0.5	20	71	33	4.58	10	5.08	30	1.45	775
UGA-27	20.00	21.00	1.00	M299065	0.09		0.9	6.75	126	410	0.9	<2	0.75	<0.5	20	68	30	4.17	10	5.29	20	1.52	449
UGA-27	21.00	22.00	1.00	M299066	0.07		0.7	7.23	148	320	1	<2	0.5	<0.5	20	73	31	4.33	10	5.36	20	1.74	426
UGA-27	22.00	23.00	1.00	M299067	0.07		1	7.15	136	300	1	<2	0.53	<0.5	20	77	36	4.32	10	5.22	20	2.14	492
UGA-27	23.00	24.00	1.00	M299068	0.07		0.6	6.92	127	720	0.9	<2	0.42	<0.5	20	68	28	4.56	10	5.19	20	2.11	482
UGA-27	24.00	25.00	1.00	M299069	0.62		3.3	6.49	259	660	0.8	<2	0.45	<0.5	18	65	27	4.84	10	4.42	20	1.62	426
UGA-27	25.00	26.00	1.00	M299071	0.11		1.2	6.81	115	590	0.8	<2	0.49	<0.5	19	69	29	4.47	10	4.42	20	1.96	520
UGA-27	26.00	27.00	1.00	M299072	0.15		2	6.91	229	610	0.9	<2	0.43	<0.5	21	64	33	4.48	10	5.19	30	1.76	433
UGA-27	27.00	28.00	1.00	M299073	0.13		1.6	7.05	241	670	0.9	<2	0.36	<0.5	22	69	33	4.68	10	5.19	20	1.8	448
UGA-27	28.00	29.00	1.00	M299074	0.22		2.6	6.86	313	460	0.9	<2	0.59	<0.5	21	64	35	5.17	10	5.35	20	2.25	648
UGA-27	29.00	30.00	1.00	M299075	0.18		1.5	6.79	223	660	0.8	<2	0.4	<0.5	20	62	36	4.51	10	5.27	20	1.88	421
UGA-27	30.00	31.00	1.00	M299076	0.06		1.5	7.3	91	630	1	<2	0.45	<0.5	20	67	36	4.67	10	5.11	20	2.16	454
UGA-27	31.00	32.00	1.00	M299077	0.21		1.5	7.57	197	710	1	<2	0.53	<0.5	23	70	52	4.53	10	5.01	30	2.21	432
UGA-27	32.00	33.00	1.00	M299079	0.15		1.3	7.13	157	570	0.9	<2	0.46	<0.5	20	71	40	4.56	10	4.78	20	1.87	422
UGA-27	33.00	34.00	1.00	M299081	0.1		1.4	6.43	236	490	0.9	3	0.57	<0.5	21	67	41	4.45	10	4.78	20	1.82	430
UGA-27	34.00	35.00	1.00	M299082	0.1		1.4	7.05	147	540	0.9	<2	0.41	<0.5	20	69	36	4.23	10	5.28	20	2.06	445
UGA-27	35.00	36.00	1.00	M299083	1.33		9.5	6.14	142	460	0.9	<2	0.56	<0.5	17	63	35	4.38	10	4.49	20	2	481
UGA-27	36.00	37.00	1.00	M299084	0.11		1.5	6.35	116	470	1	<2	0.54	<0.5	18	63	29	4.11	10	4.67	20	1.92	379
UGA-27	37.00	38.00	1.00	M299085	0.3		2.3	6.73	65	480	1	<2	1.12	<0.5	19	67	37	4.59	10	4.87	30	2.69	718
UGA-27	38.00	39.00	1.00	M299086	0.05		1.4	6.99	109	270	1	<2	1.03	<0.5	20	67	35	4.59	10	4.82	30	1.98	447
UGA-27	39.00	40.00	1.00	M299087	0.15		2	5.59	135	350	0.9	<2	1.44	<0.5	18	66	26	3.85	10	3.82	20	1.58	380

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-30	151.00	152.00	1.00	7	0.1	11	1090	14	1.21	34	18	140	<20	0.4	10	<10	160	<10	51		
UGA-30	152.00	153.00	1.00	4	0.15	13	1340	9	0.86	31	19	113	<20	0.4	<10	<10	170	<10	97		
UGA-30	153.00	154.00	1.00	13	0.1	12	1140	12	3.03	39	17	109	<20	0.35	10	<10	139	<10	69		
UGA-30	154.00	155.00	1.00	9	0.07	13	1040	14	4.23	40	17	125	<20	0.35	10	<10	140	<10	61		
UGA-30	155.00	156.00	1.00	6	0.08	15	1060	11	3.02	60	17	136	<20	0.34	10	<10	136	<10	85		
UGA-30	156.00	157.00	1.00	3	0.06	14	1010	10	3.7	33	16	104	<20	0.34	10	<10	126	<10	64		
UGA-30	157.00	158.00	1.00	3	0.06	14	1460	8	2.35	44	19	110	<20	0.36	10	<10	147	<10	100		
UGA-30	158.00	159.00	1.00	7	0.04	10	1190	8	2.64	61	14	78	<20	0.27	10	<10	115	<10	27		
UGA-30	159.00	160.00	1.00	17	0.06	13	810	14	2.67	56	16	120	<20	0.35	10	<10	128	<10	21		
UGA-30	160.00	161.00	1.00	3	0.06	15	1180	13	1.7	44	19	127	<20	0.38	10	<10	162	<10	57		
UGA-30	161.00	162.00	1.00	3	0.05	9	870	9	1.27	42	16	112	<20	0.34	10	<10	134	<10	39		
UGA-30	162.00	163.00	1.00	6	0.03	5	560	6	1.74	94	7	43	<20	0.15	<10	<10	75	<10	35		
UGA-30	163.00	164.00	1.00	6	0.02	6	590	5	1.43	142	5	35	<20	0.1	<10	<10	46	<10	22		
UGA-30	164.00	165.00	1.00	4	0.02	4	420	4	0.49	131	5	47	<20	0.1	10	<10	57	<10	11		
UGA-30	165.00	166.00	1.00	7	0.02	5	1120	4	0.69	109	8	37	<20	0.17	10	<10	80	<10	23		
UGA-30	166.00	167.00	1.00	8	0.02	4	1020	6	0.28	141	5	30	<20	0.13	<10	<10	74	<10	18		
UGA-30	167.00	168.00	1.00	31	0.02	8	820	9	2.18	179	9	46	<20	0.2	10	<10	78	<10	49		
UGA-30	168.00	170.00	2.00	14	0.02	3	1840	8	1.38	110	7	41	<20	0.13	10	<10	54	<10	21		
UGA-30	170.00	173.20	3.20	7	0.03	12	750	14	2.05	58	13	60	<20	0.27	10	<10	94	30	73		
UGA-27	9.00	10.00	1.00	3	0.03	17	830	12	2.67	15	20	68	<20	0.35	<10	<10	137	<10	62		
UGA-27	10.00	11.00	1.00	44	0.01	12	630	17	3.48	55	14	83	<20	0.26	<10	<10	106	<10	40		
UGA-27	11.00	12.00	1.00	3	0.03	13	890	11	2.93	23	19	71	<20	0.34	<10	<10	134	<10	54		
UGA-27	12.00	13.00	1.00	2	0.03	14	1840	11	2.83	17	20	77	<20	0.34	<10	<10	141	<10	55		
UGA-27	13.00	14.00	1.00	2	0.04	15	1710	8	3.07	24	21	80	<20	0.36	<10	<10	155	10	64		
UGA-27	14.00	15.00	1.00	1	0.07	15	1010	12	2.79	35	20	133	<20	0.37	<10	<10	149	10	61		
UGA-27	15.00	16.00	1.00	2	0.05	15	1120	11	2.62	16	20	108	<20	0.36	<10	<10	140	10	62		
UGA-27	16.00	17.00	1.00	1	0.06	13	1010	11	2.72	12	22	112	<20	0.38	<10	<10	155	<10	57		
UGA-27	17.00	18.00	1.00	3	0.05	15	970	12	3.32	14	22	122	<20	0.37	<10	<10	151	<10	64		
UGA-27	18.00	19.00	1.00	3	0.06	16	990	9	4.48	12	22	103	<20	0.4	<10	<10	153	10	63		
UGA-27	19.00	20.00	1.00	1	0.06	17	1020	11	3.84	16	22	155	<20	0.39	<10	<10	143	<10	75		
UGA-27	20.00	21.00	1.00	1	0.06	14	970	8	2.81	13	20	130	<20	0.37	<10	<10	138	<10	59		
UGA-27	21.00	22.00	1.00	1	0.05	16	1010	13	2.83	14	21	89	<20	0.4	<10	<10	148	10	60		
UGA-27	22.00	23.00	1.00	3	0.05	18	1170	8	1.89	22	21	81	<20	0.4	<10	<10	153	10	73		
UGA-27	23.00	24.00	1.00	1	0.05	16	1070	11	1.98	18	21	93	<20	0.36	<10	<10	139	10	66		
UGA-27	24.00	25.00	1.00	4	0.05	14	1170	12	2.99	27	20	129	<20	0.34	10	<10	140	10	56		
UGA-27	25.00	26.00	1.00	<1	0.05	15	810	11	1.97	12	21	127	<20	0.37	<10	<10	144	<10	63		
UGA-27	26.00	27.00	1.00	1	0.04	17	1120	14	2.53	18	21	105	<20	0.37	<10	<10	139	<10	61		
UGA-27	27.00	28.00	1.00	1	0.05	15	1210	12	2.38	28	21	106	<20	0.38	<10	<10	147	10	67		
UGA-27	28.00	29.00	1.00	2	0.05	16	1210	12	2.38	26	21	96	<20	0.36	10	<10	139	10	68		
UGA-27	29.00	30.00	1.00	1	0.05	16	1380	9	2.28	23	20	96	<20	0.35	<10	<10	131	10	60		
UGA-27	30.00	31.00	1.00	1	0.04	17	1360	11	2.43	11	22	90	<20	0.39	<10	<10	147	<10	67		
UGA-27	31.00	32.00	1.00	2	0.05	18	1530	14	2.22	15	23	96	<20	0.39	<10	<10	146	<10	68		
UGA-27	32.00	33.00	1.00	1	0.04	16	1380	9	2.49	20	21	91	<20	0.37	<10	<10	154	10	65		
UGA-27	33.00	34.00	1.00	2	0.04	17	1370	12	2.46	24	19	81	<20	0.34	<10	<10	136	10	60		
UGA-27	34.00	35.00	1.00	2	0.05	15	1220	12	2	19	21	124	<20	0.37	<10	<10	134	10	65		
UGA-27	35.00	36.00	1.00	2	0.04	16	1020	12	2.29	21	19	96	<20	0.33	<10	<10	125	10	57		
UGA-27	36.00	37.00	1.00	2	0.04	15	1130	10	2.33	13	19	93	<20	0.34	<10	<10	131	<10	58		
UGA-27	37.00	38.00	1.00	1	0.04	20	1030	10	1.7	5	21	109	<20	0.35	<10	<10	139	<10	69		
UGA-27	38.00	39.00	1.00	1	0.03	17	1100	11	2.45	13	21	90	<20	0.36	<10	<10	143	<10	67		
UGA-27	39.00	40.00	1.00	3	0.03	14	1060	10	2.29	25	17	115	<20	0.29	<10	<10	118	10	39		

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-30	151.00	152.00	1.00							
UGA-30	152.00	153.00	1.00							
UGA-30	153.00	154.00	1.00							
UGA-30	154.00	155.00	1.00							
UGA-30	155.00	156.00	1.00							
UGA-30	156.00	157.00	1.00							
UGA-30	157.00	158.00	1.00							
UGA-30	158.00	159.00	1.00							
UGA-30	159.00	160.00	1.00							
UGA-30	160.00	161.00	1.00							
UGA-30	161.00	162.00	1.00							
UGA-30	162.00	163.00	1.00							
UGA-30	163.00	164.00	1.00							
UGA-30	164.00	165.00	1.00							
UGA-30	165.00	166.00	1.00							
UGA-30	166.00	167.00	1.00							
UGA-30	167.00	168.00	1.00							
UGA-30	168.00	170.00	2.00							
UGA-30	170.00	173.20	3.20							
UGA-27	9.00	10.00	1.00							
UGA-27	10.00	11.00	1.00							
UGA-27	11.00	12.00	1.00							
UGA-27	12.00	13.00	1.00							
UGA-27	13.00	14.00	1.00							
UGA-27	14.00	15.00	1.00							
UGA-27	15.00	16.00	1.00							
UGA-27	16.00	17.00	1.00							
UGA-27	17.00	18.00	1.00							
UGA-27	18.00	19.00	1.00							
UGA-27	19.00	20.00	1.00							
UGA-27	20.00	21.00	1.00							
UGA-27	21.00	22.00	1.00							
UGA-27	22.00	23.00	1.00							
UGA-27	23.00	24.00	1.00							
UGA-27	24.00	25.00	1.00							
UGA-27	25.00	26.00	1.00							
UGA-27	26.00	27.00	1.00							
UGA-27	27.00	28.00	1.00							
UGA-27	28.00	29.00	1.00							
UGA-27	29.00	30.00	1.00							
UGA-27	30.00	31.00	1.00							
UGA-27	31.00	32.00	1.00							
UGA-27	32.00	33.00	1.00							
UGA-27	33.00	34.00	1.00							
UGA-27	34.00	35.00	1.00							
UGA-27	35.00	36.00	1.00							
UGA-27	36.00	37.00	1.00							
UGA-27	37.00	38.00	1.00							
UGA-27	38.00	39.00	1.00							
UGA-27	39.00	40.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-27	40.00	41.00	1.00	M299088	0.09		1.6	6.23	117	450	0.9	<2	0.46	<0.5	19	63	33	4.37	10	4.23	20	2.16	484
UGA-27	41.00	42.00	1.00	M299089	1.5		4.7	6.54	223	300	1	<2	0.8	<0.5	18	64	30	4.54	10	4.03	20	1.92	534
UGA-27	42.00	43.00	1.00	M299090	0.29		2.2	5.97	178	230	1	<2	0.53	<0.5	17	61	27	4.58	10	3.85	20	2.02	454
UGA-27	43.00	44.00	1.00	M299091	0.25		1.5	5.99	132	290	0.9	<2	0.47	<0.5	19	64	27	4.27	10	3.89	20	1.73	332
UGA-27	44.00	45.00	1.00	M299092	0.84		4.4	6.38	173	550	0.9	<2	0.38	<0.5	18	65	33	4.13	10	4.5	20	1.76	347
UGA-27	45.00	46.00	1.00	M299093	1.34		1.7	6.6	211	580	1	<2	0.48	<0.5	18	65	30	4.48	10	4.57	30	2.42	498
UGA-27	46.00	47.00	1.00	M299094	0.09		1.1	6.68	89	440	1	<2	0.47	<0.5	21	65	32	4.51	10	4.56	30	2.42	491
UGA-27	47.00	48.00	1.00	M299095	0.07		1.4	7.56	100	430	1	<2	0.37	<0.5	20	73	32	4.78	10	5.25	30	2.64	476
UGA-27	48.00	49.00	1.00	M299096	0.12		1.4	6.69	104	640	0.9	<2	0.37	<0.5	19	65	29	4.7	10	4.61	20	2.32	479
UGA-27	49.00	50.00	1.00	M299097	0.13		1.7	5.91	154	520	0.8	<2	0.46	<0.5	17	67	27	4.38	10	4.28	20	1.96	452
UGA-27	50.00	51.00	1.00	M299099	0.41		2.5	6.63	195	620	0.9	<2	0.45	<0.5	19	66	31	4.92	10	4.32	20	2.34	497
UGA-27	51.00	52.00	1.00	M299101	0.09		1.7	6.9	151	650	1	2	0.42	<0.5	20	67	31	4.9	10	4.52	20	1.93	379
UGA-27	52.00	53.00	1.00	M299102	0.05		0.8	7.79	169	330	1.1	<2	0.42	<0.5	19	82	37	5.46	10	4.78	30	2.91	597
UGA-27	53.00	54.00	1.00	M299103	0.11		1.9	7	228	550	1	<2	0.49	<0.5	20	71	32	4.83	10	5.1	20	1.97	424
UGA-27	54.00	55.00	1.00	M299104	0.06		1	7.46	108	340	1.1	<2	0.55	<0.5	19	75	35	5.79	10	4.4	20	3.44	646
UGA-27	55.00	56.00	1.00	M299105	0.08		0.9	6.44	82	410	1.1	<2	0.48	<0.5	17	70	39	4.68	10	3.55	20	2.89	543
UGA-27	56.00	57.00	1.00	M299106	0.07		1.4	6.89	198	680	1.4	<2	0.39	<0.5	22	69	40	5.69	10	4.41	20	2.44	820
UGA-27	57.00	58.00	1.00	M299107	0.91		4.6	5.58	282	630	1.2	<2	0.28	0.6	17	77	22	4.57	10	4.64	20	0.66	555
UGA-27	58.00	59.00	1.00	M299109	0.4		2.5	6.57	209	550	1.4	<2	0.49	<0.5	21	81	24	4.98	10	4.64	20	0.64	1045
UGA-27	59.00	60.00	1.00	M299110	0.08		1.6	7.26	138	520	1.4	<2	0.39	<0.5	21	89	30	5.14	20	4.99	20	1.6	694
UGA-27	60.00	61.00	1.00	M299111	0.34		2.2	6.42	150	600	1.1	<2	0.91	<0.5	18	68	25	4.86	10	4.53	20	2.58	604
UGA-27	61.00	62.00	1.00	M299112	0.29		2.7	6.61	374	690	1.1	<2	0.96	<0.5	18	40	27	4.9	10	4.81	30	1.86	443
UGA-27	62.00	63.00	1.00	M299113	0.1		1.5	6.93	148	640	1.1	<2	1.28	<0.5	15	33	18	4.31	10	4.83	30	1.76	505
UGA-27	63.00	64.00	1.00	M299114	0.08		1.7	7.16	114	640	1.2	<2	1.04	<0.5	16	30	19	3.85	20	5.2	30	1.55	483
UGA-27	64.00	65.00	1.00	M299115	0.18		2.4	6.67	146	740	1.2	<2	1	<0.5	12	29	21	3.64	10	4.22	30	1.24	455
UGA-27	65.00	66.00	1.00	M299116	0.19		1.8	6.34	82	320	1.3	<2	1.57	<0.5	13	29	19	3.95	10	2.85	30	1.37	749
UGA-27	66.00	67.00	1.00	M299117	0.11		1.4	6.47	86	670	1.2	<2	1.04	<0.5	11	30	17	3.5	10	4.56	30	1.15	425
UGA-27	67.00	68.00	1.00	M299118	0.1		1.6	6.08	81	650	1.1	<2	1.3	<0.5	12	30	17	4.11	10	4.32	30	1.44	473
UGA-27	68.00	69.00	1.00	M299119	0.23		2.2	6.63	75	640	1.1	<2	0.97	<0.5	11	31	22	3.93	10	4.52	30	1.51	441
UGA-27	69.00	70.00	1.00	M299120	0.14		2.1	6.88	139	510	1.1	<2	0.98	<0.5	14	30	22	4.26	10	4.7	30	1.5	449
UGA-27	70.00	71.00	1.00	M299121	0.1		1.5	5.8	76	760	1.1	<2	2.12	<0.5	12	29	25	4.22	10	4.08	20	1.82	815
UGA-27	71.00	72.00	1.00	M299122	0.19		1.8	6.88	92	600	1.3	<2	0.37	<0.5	14	31	27	4.01	10	5.03	30	1.26	479
UGA-27	72.00	73.00	1.00	M299123	0.13		1.6	6.67	159	610	1.1	<2	0.37	<0.5	12	30	24	3.87	10	3.4	30	1.68	353
UGA-27	73.00	74.00	1.00	M299124	0.13		1.2	7.2	164	720	1.2	<2	0.32	<0.5	13	31	28	4.04	10	3.52	30	2.15	393
UGA-27	74.00	75.00	1.00	M299125	0.1		1.3	6.96	105	680	1	<2	0.41	<0.5	13	28	25	4.24	10	3.53	30	2.3	470
UGA-27	75.00	76.00	1.00	M299126	0.16		1.8	6.72	224	710	1.2	<2	0.41	<0.5	13	31	25	3.88	10	3.57	30	1.86	332
UGA-27	76.00	77.00	1.00	M299127	0.17		1.9	6.55	238	650	1.3	<2	0.49	<0.5	12	30	23	3.55	10	3.48	30	2.12	363
UGA-27	77.00	78.00	1.00	M299129	0.1		2.2	6.87	235	520	1.1	<2	0.43	<0.5	17	34	35	5.26	10	3.69	30	2.43	510
UGA-27	78.00	79.00	1.00	M299130	2.08		9.2	7.14	140	650	1.1	<2	0.57	<0.5	17	43	39	4.4	20	3.82	30	2.34	488
UGA-27	79.00	80.00	1.00	M299131	0.93		2.2	7.51	117	500	1.1	<2	0.97	<0.5	18	43	40	4.35	10	3.52	30	2.18	435
UGA-27	80.00	81.00	1.00	M299132	0.12		1.2	7.48	168	630	1.1	<2	0.55	<0.5	18	40	30	5.01	10	3.88	30	2.58	568
UGA-27	81.00	82.00	1.00	M299133	0.27		3.7	7.32	217	590	1.1	<2	0.39	<0.5	17	43	29	4.9	10	3.59	30	2.38	428
UGA-27	82.00	83.00	1.00	M299134	0.05		1.3	7.37	71	360	1	<2	0.44	<0.5	20	41	27	5.08	10	3.92	30	2.19	420
UGA-27	83.00	84.00	1.00	M299135	0.24		4.1	7.2	149	390	1	<2	0.48	<0.5	18	42	31	5.04	10	3.73	30	1.8	330
UGA-27	84.00	85.00	1.00	M299136	0.18		2.5	6.96	172	480	1.2	<2	0.66	<0.5	18	41	25	4.66	10	3.94	30	1.25	254
UGA-27	85.00	86.00	1.00	M299137	0.19		2.7	7.35	154	590	1.5	2	0.42	<0.5	18	40	27	4.85	10	3.85	30	1.46	489
UGA-27	86.00	87.00	1.00	M299138	0.11		1.5	7.66	127	530	1.5	<2	0.62	<0.5	19	43	29	5.09	20	3.84	20	2.24	720
UGA-27	87.00	88.00	1.00	M299139	0.16		1.4	7.37	184	540	1.6	<2	0.3	<0.5	18	41	28	4.3	20	3.63	30	0.81	600
UGA-27	88.00	89.00	1.00	M299141	0.24		2.3	6.2	275	500	1.6	4	0.26	<0.5	16	37	29	4.53	10	4.3	30	0.74	698
UGA-27	89.00	90.00	1.00	M299142	0.56		2.6	6.47	175	500	1.3	<2	0.69	<0.5	14	40	42	4.36	10	3.69	30	2.19	454

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
UGA-27	40.00	41.00	1.00	2	0.04	16	1090	10	2.1	22	18	107	<20	0.34	10	<10	134	10	59			
UGA-27	41.00	42.00	1.00	3	0.03	16	1090	11	2.87	23	19	97	<20	0.35	10	<10	132	10	65			
UGA-27	42.00	43.00	1.00	5	0.03	15	1040	11	2.51	24	18	83	<20	0.31	<10	<10	129	10	57			
UGA-27	43.00	44.00	1.00	3	0.03	13	960	9	2.43	20	18	86	<20	0.31	10	<10	128	10	50			
UGA-27	44.00	45.00	1.00	2	0.04	15	960	8	2.39	16	19	166	<20	0.34	<10	<10	133	<10	57			
UGA-27	45.00	46.00	1.00	2	0.04	13	1030	9	2.49	13	19	171	<20	0.34	10	<10	138	10	60			
UGA-27	46.00	47.00	1.00	2	0.03	15	950	8	2.56	13	20	85	<20	0.35	10	<10	141	<10	62			
UGA-27	47.00	48.00	1.00	2	0.04	16	1120	7	2.16	14	22	111	<20	0.39	10	<10	154	10	72			
UGA-27	48.00	49.00	1.00	3	0.04	15	1160	9	2.58	21	20	119	<20	0.35	10	<10	136	10	63			
UGA-27	49.00	50.00	1.00	4	0.03	13	1150	12	2.48	35	18	114	<20	0.31	10	<10	123	10	53			
UGA-27	50.00	51.00	1.00	3	0.04	14	1410	12	2.74	19	20	99	<20	0.35	<10	<10	139	10	64			
UGA-27	51.00	52.00	1.00	4	0.04	16	1180	11	2.98	28	20	94	<20	0.36	10	<10	143	20	61			
UGA-27	52.00	53.00	1.00	2	0.04	17	1250	8	1.82	27	23	81	<20	0.4	<10	<10	157	<10	72			
UGA-27	53.00	54.00	1.00	3	0.04	15	1330	11	2.97	28	21	96	<20	0.38	10	<10	146	<10	61			
UGA-27	54.00	55.00	1.00	2	0.03	18	1160	9	1.6	19	23	66	<20	0.39	10	<10	156	10	73			
UGA-27	55.00	56.00	1.00	3	0.03	15	1010	9	1.42	24	19	80	<20	0.33	10	<10	128	10	61			
UGA-27	56.00	57.00	1.00	3	0.04	20	1050	10	3.33	25	22	123	<20	0.37	10	<10	138	10	78			
UGA-27	57.00	58.00	1.00	4	0.04	18	1060	10	3.44	40	19	88	<20	0.33	20	<10	145	10	89			
UGA-27	58.00	59.00	1.00	3	0.05	19	1850	11	3.12	35	21	101	<20	0.37	10	<10	163	<10	70			
UGA-27	59.00	60.00	1.00	2	0.06	19	1090	10	2.85	22	23	95	<20	0.39	10	<10	163	10	72			
UGA-27	60.00	61.00	1.00	2	0.04	15	940	8	2.22	23	20	114	<20	0.33	10	<10	137	10	70			
UGA-27	61.00	62.00	1.00	3	0.06	14	1040	11	3.31	24	19	134	<20	0.36	10	<10	135	10	74			
UGA-27	62.00	63.00	1.00	4	0.05	9	1120	10	2.27	18	17	130	<20	0.34	10	<10	123	10	63			
UGA-27	63.00	64.00	1.00	4	0.04	10	1110	13	2.13	21	15	124	<20	0.34	10	<10	115	<10	57			
UGA-27	64.00	65.00	1.00	4	0.03	7	980	9	1.99	22	14	115	<20	0.3	10	<10	104	<10	56			
UGA-27	65.00	66.00	1.00	4	0.02	7	960	11	2.19	32	14	74	<20	0.3	10	<10	100	10	63			
UGA-27	66.00	67.00	1.00	4	0.04	6	970	10	1.99	18	14	131	<20	0.3	10	<10	101	10	49			
UGA-27	67.00	68.00	1.00	4	0.03	7	1010	11	2.28	19	13	112	<20	0.28	10	<10	95	<10	54			
UGA-27	68.00	69.00	1.00	2	0.03	7	1160	9	2	15	15	106	<20	0.31	10	<10	105	<10	60			
UGA-27	69.00	70.00	1.00	3	0.04	6	1130	11	2.24	27	15	92	<20	0.32	10	<10	108	<10	63			
UGA-27	70.00	71.00	1.00	5	0.02	8	1050	12	2.22	30	13	121	<20	0.27	10	<10	89	<10	65			
UGA-27	71.00	72.00	1.00	5	0.04	9	990	11	2.12	21	15	81	<20	0.32	<10	<10	109	10	65			
UGA-27	72.00	73.00	1.00	6	0.05	10	1090	11	2.05	30	14	95	<20	0.29	10	<10	98	<10	57			
UGA-27	73.00	74.00	1.00	4	0.05	10	990	10	1.91	21	16	118	<20	0.32	<10	<10	110	<10	62			
UGA-27	74.00	75.00	1.00	3	0.05	10	960	8	1.67	17	15	103	<20	0.31	<10	<10	102	<10	59			
UGA-27	75.00	76.00	1.00	3	0.05	7	1060	9	2.3	18	15	98	<20	0.3	<10	<10	103	<10	57			
UGA-27	76.00	77.00	1.00	4	0.05	8	910	9	1.72	30	14	105	<20	0.29	<10	<10	97	<10	54			
UGA-27	77.00	78.00	1.00	3	0.05	10	1100	10	2.76	20	18	97	<20	0.34	<10	<10	128	<10	63			
UGA-27	78.00	79.00	1.00	4	0.07	11	1170	8	1.96	20	20	106	<20	0.37	<10	<10	142	<10	78			
UGA-27	79.00	80.00	1.00	3	0.09	10	1100	7	2.6	11	21	143	<20	0.39	<10	<10	149	<10	64			
UGA-27	80.00	81.00	1.00	2	0.07	11	1110	6	2.68	11	21	127	<20	0.39	10	<10	148	<10	73			
UGA-27	81.00	82.00	1.00	3	0.07	10	1060	8	2.9	13	20	118	<20	0.37	<10	<10	144	<10	69			
UGA-27	82.00	83.00	1.00	2	0.07	12	1190	8	3.35	7	21	95	<20	0.39	<10	<10	150	<10	65			
UGA-27	83.00	84.00	1.00	3	0.06	11	1070	11	3.75	23	21	86	<20	0.38	10	<10	148	<10	71			
UGA-27	84.00	85.00	1.00	7	0.08	11	1080	8	3.9	24	20	102	<20	0.36	<10	<10	139	<10	60			
UGA-27	85.00	86.00	1.00	6	0.06	11	1130	7	2.58	25	21	87	<20	0.38	10	<10	147	<10	67			
UGA-27	86.00	87.00	1.00	2	0.06	11	1080	5	1.99	17	21	90	<20	0.4	<10	<10	154	<10	78			
UGA-27	87.00	88.00	1.00	3	0.06	10	1050	9	2.52	22	20	96	<20	0.37	10	<10	143	<10	70			
UGA-27	88.00	89.00	1.00	5	0.03	10	960	11	3.01	33	18	122	<20	0.33	10	<10	128	<10	53			
UGA-27	89.00	90.00	1.00	3	0.04	8	930	7	2.2	24	17	90	<20	0.32	<10	<10	122	<10	59			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-27	40.00	41.00	1.00							
UGA-27	41.00	42.00	1.00							
UGA-27	42.00	43.00	1.00							
UGA-27	43.00	44.00	1.00							
UGA-27	44.00	45.00	1.00							
UGA-27	45.00	46.00	1.00							
UGA-27	46.00	47.00	1.00							
UGA-27	47.00	48.00	1.00							
UGA-27	48.00	49.00	1.00							
UGA-27	49.00	50.00	1.00							
UGA-27	50.00	51.00	1.00							
UGA-27	51.00	52.00	1.00							
UGA-27	52.00	53.00	1.00							
UGA-27	53.00	54.00	1.00							
UGA-27	54.00	55.00	1.00							
UGA-27	55.00	56.00	1.00							
UGA-27	56.00	57.00	1.00							
UGA-27	57.00	58.00	1.00							
UGA-27	58.00	59.00	1.00							
UGA-27	59.00	60.00	1.00							
UGA-27	60.00	61.00	1.00							
UGA-27	61.00	62.00	1.00							
UGA-27	62.00	63.00	1.00							
UGA-27	63.00	64.00	1.00							
UGA-27	64.00	65.00	1.00							
UGA-27	65.00	66.00	1.00							
UGA-27	66.00	67.00	1.00							
UGA-27	67.00	68.00	1.00							
UGA-27	68.00	69.00	1.00							
UGA-27	69.00	70.00	1.00							
UGA-27	70.00	71.00	1.00							
UGA-27	71.00	72.00	1.00							
UGA-27	72.00	73.00	1.00							
UGA-27	73.00	74.00	1.00							
UGA-27	74.00	75.00	1.00							
UGA-27	75.00	76.00	1.00							
UGA-27	76.00	77.00	1.00							
UGA-27	77.00	78.00	1.00							
UGA-27	78.00	79.00	1.00							
UGA-27	79.00	80.00	1.00							
UGA-27	80.00	81.00	1.00							
UGA-27	81.00	82.00	1.00							
UGA-27	82.00	83.00	1.00							
UGA-27	83.00	84.00	1.00							
UGA-27	84.00	85.00	1.00							
UGA-27	85.00	86.00	1.00							
UGA-27	86.00	87.00	1.00							
UGA-27	87.00	88.00	1.00							
UGA-27	88.00	89.00	1.00							
UGA-27	89.00	90.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-27	90.00	91.00	1.00	M299144	0.14		0.7	8.07	59	500	1.3	<2	0.41	<0.5	19	40	37	4.91	20	3.84	30	2.79	480
UGA-27	91.00	92.00	1.00	M299145	0.27		3.6	7.64	174	550	1.3	<2	0.44	<0.5	16	39	36	4.5	20	3.99	30	2.37	379
UGA-27	92.00	93.00	1.00	M299146	1.26		1.6	7.73	84	510	1.2	<2	0.64	<0.5	16	38	30	4.68	20	3.87	30	2.36	458
UGA-27	93.00	94.00	1.00	M299147	0.07		1.1	7.77	78	430	1.1	<2	0.43	<0.5	18	38	32	4.85	20	3.48	30	2.58	463
UGA-27	94.00	95.00	1.00	M299148	0.14		1.3	7.31	89	510	1.1	<2	0.47	<0.5	17	36	31	4.73	20	3.68	30	2.32	431
UGA-27	95.00	96.00	1.00	M299149	0.08		0.8	8.11	86	610	1.4	2	0.5	<0.5	18	40	34	4.94	20	3.52	30	2.82	537
UGA-27	96.00	97.00	1.00	M299151	0.12		0.8	7.68	214	670	1.4	5	0.93	<0.5	17	40	34	4.83	20	5.39	30	3.05	670
UGA-27	97.00	98.00	1.00	M299152	0.07		0.9	7.94	122	760	1.3	<2	0.85	<0.5	18	38	35	4.71	20	3.65	30	2.88	588
UGA-27	98.00	99.00	1.00	M299153	0.07		0.7	7.9	107	810	1.3	<2	0.65	<0.5	18	41	40	5.13	20	3.59	30	2.83	491
UGA-27	99.00	100.00	1.00	M299154	0.08		1	7.78	127	560	1.2	<2	0.71	<0.5	18	37	33	5.16	20	3.86	30	2.65	499
UGA-27	100.00	101.00	1.00	M299155	0.32		1.2	7.58	121	660	1.1	<2	1.02	<0.5	18	35	39	4.86	20	3.73	30	2.46	608
UGA-27	101.00	102.00	1.00	M299156	0.1		1.3	7.41	73	690	1.2	<2	0.97	<0.5	17	35	32	4.47	10	3.8	30	2.57	587
UGA-27	102.00	103.00	1.00	M299157	0.28		2.2	6.53	188	690	1.2	2	1.66	<0.5	14	33	29	4.48	10	3.63	20	2.08	559
UGA-27	103.00	104.00	1.00	M299158	0.15		1.9	6.23	158	660	1.1	<2	0.73	<0.5	12	34	30	4.23	10	3.25	20	1.83	488
UGA-27	104.00	105.00	1.00	M299159	0.48		3.4	5.93	228	430	1.2	<2	0.6	<0.5	13	35	30	5.42	10	3.25	20	1.34	1520
UGA-27	105.00	106.00	1.00	M299160	0.53		2.4	6.93	136	480	1.4	2	0.34	<0.5	15	36	25	5.73	10	3.26	20	0.71	2210
UGA-27	106.00	107.00	1.00	M299161	0.16		1.6	7.02	124	620	1.5	<2	0.51	<0.5	18	39	35	4.8	20	3.44	20	1.86	968
UGA-27	107.00	108.00	1.00	M299162	0.14		1.3	6.48	145	580	1.2	<2	0.66	<0.5	14	37	36	4.44	10	3.35	20	2.2	449
UGA-27	108.00	109.00	1.00	M299163	4.99		4	6.81	126	620	1.3	<2	0.97	<0.5	14	39	29	4.73	10	3.49	20	2.19	505
UGA-27	109.00	110.00	1.00	M299164	0.16		1.7	6.88	103	530	1.2	2	1.15	<0.5	14	42	31	4.25	10	3.47	20	1.69	357
UGA-27	110.00	111.00	1.00	M299165	0.13		1.6	7.05	127	730	1.3	<2	1.38	<0.5	15	43	33	4.17	10	3.24	20	1.78	385
UGA-27	111.00	112.00	1.00	M299166	0.03		0.5	7.62	61	500	1.4	<2	1.64	<0.5	17	45	32	4.8	20	3.56	20	2.74	789
UGA-27	112.00	113.00	1.00	M299167	0.04		0.6	8.29	112	570	2.3	<2	0.68	<0.5	19	49	36	4.07	20	3.71	20	1.41	948
UGA-27	113.00	114.00	1.00	M299168	1.77		3.4	6.74	479	210	1.8	<2	0.33	<0.5	17	44	42	4.53	10	2.16	20	0.46	1055
UGA-27	114.00	115.00	1.00	M299170	0.56		2	7.96	453	840	2.1	<2	0.45	<0.5	19	51	42	5.13	20	3.46	20	0.57	1230
UGA-27	115.00	116.00	1.00	M299172	0.33		0.7	8.19	150	610	2.4	<2	0.57	<0.5	20	50	51	4.76	20	3.14	20	0.87	1295
UGA-27	116.00	117.00	1.00	M299173	0.04		0.7	7.51	44	680	1.5	<2	1.93	<0.5	17	47	35	4.89	20	3.76	20	2.41	804
UGA-27	117.00	118.00	1.00	M299174	0.18		0.6	7.39	75	700	1.3	<2	2.6	<0.5	18	46	38	4.79	20	3.16	20	2.54	814
UGA-27	118.00	119.00	1.00	M299175	0.08		0.6	7.3	69	680	1.3	<2	1.71	<0.5	18	50	33	5.05	20	3.27	20	2.71	626
UGA-27	119.00	120.00	1.00	M299176	0.4		1.5	6.62	177	580	1.3	<2	1	<0.5	14	42	30	4.47	10	3.51	20	2	374
UGA-27	120.00	121.00	1.00	M299177	0.38		1.7	6.28	139	600	1.4	<2	0.69	<0.5	14	43	32	4.14	10	3.16	20	1.4	453
UGA-27	121.00	122.00	1.00	M299178	0.39		1.6	6.55	138	660	1.4	<2	0.97	<0.5	14	41	31	4.19	10	3.22	20	1.97	345
UGA-27	122.00	123.00	1.00	M299179	0.58		1.4	6.61	118	630	1.3	<2	0.94	<0.5	16	41	36	4.55	10	3.29	20	2.54	442
UGA-27	123.00	124.00	1.00	M299180	0.13		<0.5	8.01	37	590	1.6	2	1.36	<0.5	18	47	34	5.04	20	3.1	20	3.76	796
UGA-27	124.00	125.00	1.00	M299182	0.07		0.9	7.17	57	600	1.8	<2	1.12	<0.5	18	47	25	4.47	20	3.28	20	1.94	745
UGA-27	125.00	126.00	1.00	M299183	0.28		1.3	6.76	72	480	1.6	<2	0.61	<0.5	17	45	27	4.56	20	3.11	20	1.1	653
UGA-27	126.00	127.00	1.00	M299184	0.09		1	6.84	67	590	1.3	<2	1.18	<0.5	17	45	27	4.62	10	3.49	20	1.55	555
UGA-27	127.00	128.00	1.00	M299185	0.24		1.3	7.06	75	820	1.2	<2	0.87	<0.5	16	43	27	4.5	20	3.43	20	2.14	400
UGA-27	128.00	129.00	1.00	M299186	0.27		1.2	7.51	180	730	1.2	<2	0.77	<0.5	18	45	33	4.88	20	3.61	20	2.44	472
UGA-27	129.00	130.00	1.00	M299187	0.13		0.5	7.54	39	490	1.3	<2	1.82	<0.5	16	42	35	4.94	20	3.89	20	3.56	1035
UGA-27	130.00	131.00	1.00	M299188	0.29		1.1	7.04	67	560	1.1	<2	0.64	<0.5	16	45	30	4.58	20	3.38	20	2.24	438
UGA-27	131.00	132.00	1.00	M299190	0.15		4.9	6.89	48	700	1.1	<2	1.06	<0.5	16	43	27	4.14	10	3.59	20	1.98	506
UGA-27	132.00	133.00	1.00	M299191	0.09		0.9	6.69	59	640	1.2	<2	2.19	<0.5	15	42	26	4.67	20	3.26	20	2.82	871
UGA-27	133.00	134.00	1.00	M299192	0.19		1.2	6.69	109	740	1.2	<2	0.83	<0.5	15	44	27	4.39	20	3.26	20	2.12	473
UGA-27	134.00	135.00	1.00	M299193	0.42		0.9	6.88	118	710	1.2	7	1.21	<0.5	19	42	31	4.13	20	4.63	30	1.82	454
UGA-27	135.00	136.00	1.00	M299194	0.05		0.6	7	67	740	1.2	2	2.74	<0.5	19	36	23	4.87	20	4.86	30	2.35	852
UGA-27	136.00	137.00	1.00	M299195	0.27		1.3	7.31	185	760	1.3	4	1.73	0.5	18	36	33	4.76	20	4.68	30	2.11	554
UGA-27	137.00	138.00	1.00	M299196	0.06		<0.5	7.31	82	830	1.3	6	3.31	<0.5	20	35	23	4.99	20	4.72	30	2.54	968
UGA-27	138.00	139.00	1.00	M299197	0.06		<0.5	7.43	62	790	1.4	4	2.64	<0.5	20	36	19	4.88	10	4.8	30	2.27	706
UGA-27	139.00	140.00	1.00	M299198	0.7		<0.5	6.99	56	710	1.7	<2	2.11	<0.5	19	36	23	5.09	20	4.41	30	1.92	948

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-27	90.00	91.00	1.00	3	0.05	12	1130	6	1.89	12	22	96	<20	0.39	<10	<10	155	<10	69			
UGA-27	91.00	92.00	1.00	4	0.05	10	1090	9	2.31	21	20	82	<20	0.38	<10	<10	145	<10	66			
UGA-27	92.00	93.00	1.00	3	0.05	10	1090	8	2.55	12	21	77	<20	0.38	10	<10	146	<10	66			
UGA-27	93.00	94.00	1.00	3	0.05	10	1090	7	2.37	10	21	71	<20	0.38	10	<10	145	<10	65			
UGA-27	94.00	95.00	1.00	3	0.05	11	1020	8	2.64	9	20	95	<20	0.36	<10	<10	137	<10	61			
UGA-27	95.00	96.00	1.00	1	0.07	10	1140	9	1.31	11	22	116	<20	0.4	<10	<10	156	<10	68			
UGA-27	96.00	97.00	1.00	2	0.05	10	1150	11	1.4	10	21	110	<20	0.41	10	<10	156	<10	67			
UGA-27	97.00	98.00	1.00	2	0.06	11	1090	8	2.34	6	21	93	<20	0.39	<10	<10	148	<10	67			
UGA-27	98.00	99.00	1.00	2	0.08	11	1090	9	1.94	14	21	99	<20	0.39	<10	<10	149	<10	69			
UGA-27	99.00	100.00	1.00	1	0.07	12	1070	9	2.69	7	21	100	<20	0.39	<10	<10	149	<10	69			
UGA-27	100.00	101.00	1.00	2	0.06	12	1030	8	2.51	10	21	85	<20	0.38	<10	<10	141	<10	64			
UGA-27	101.00	102.00	1.00	2	0.05	10	1010	7	1.83	9	20	80	<20	0.37	<10	<10	131	<10	70			
UGA-27	102.00	103.00	1.00	2	0.04	9	960	7	2.04	16	18	81	<20	0.32	<10	<10	113	<10	65			
UGA-27	103.00	104.00	1.00	4	0.05	8	960	7	2.06	26	17	71	<20	0.33	10	<10	109	<10	60			
UGA-27	104.00	105.00	1.00	3	0.04	9	1240	9	2.44	32	17	55	<20	0.31	<10	<10	108	<10	72			
UGA-27	105.00	106.00	1.00	4	0.05	7	1180	9	2.24	31	20	51	<20	0.37	10	<10	139	<10	81			
UGA-27	106.00	107.00	1.00	1	0.06	9	1110	9	2.14	19	20	74	<20	0.37	<10	<10	140	<10	76			
UGA-27	107.00	108.00	1.00	1	0.06	8	950	9	2.36	19	18	77	<20	0.35	<10	<10	133	<10	62			
UGA-27	108.00	109.00	1.00	2	0.05	8	1020	8	2.19	21	19	70	<20	0.36	<10	<10	140	<10	68			
UGA-27	109.00	110.00	1.00	2	0.06	9	1040	8	2.54	18	20	78	<20	0.37	<10	<10	138	<10	59			
UGA-27	110.00	111.00	1.00	2	0.05	8	1040	9	1.89	19	20	87	<20	0.38	<10	<10	141	<10	63			
UGA-27	111.00	112.00	1.00	1	0.05	9	1110	7	0.52	15	21	88	<20	0.39	<10	<10	153	<10	74			
UGA-27	112.00	113.00	1.00	2	0.06	11	1220	9	0.48	26	22	69	<20	0.42	<10	<10	165	<10	75			
UGA-27	113.00	114.00	1.00	6	0.03	11	1070	10	2.68	56	19	25	<20	0.35	<10	<10	135	<10	79			
UGA-27	114.00	115.00	1.00	2	0.08	10	1220	10	1.65	279	23	76	<20	0.42	10	<10	159	<10	77			
UGA-27	115.00	116.00	1.00	2	0.07	13	1240	11	0.75	36	23	81	<20	0.44	10	<10	167	<10	78			
UGA-27	116.00	117.00	1.00	1	0.09	9	1100	8	1.48	13	21	118	<20	0.39	10	<10	160	<10	70			
UGA-27	117.00	118.00	1.00	2	0.31	10	1080	9	1.7	10	21	159	<20	0.39	<10	<10	152	<10	75			
UGA-27	118.00	119.00	1.00	2	0.24	10	1060	11	2.02	12	20	130	<20	0.38	<10	<10	146	<10	67			
UGA-27	119.00	120.00	1.00	3	0.06	8	1010	9	2.4	23	18	79	<20	0.35	<10	<10	119	<10	62			
UGA-27	120.00	121.00	1.00	3	0.05	9	920	9	2.33	22	18	68	<20	0.33	<10	<10	120	<10	61			
UGA-27	121.00	122.00	1.00	4	0.05	9	1100	9	2.37	22	19	82	<20	0.35	<10	<10	132	<10	64			
UGA-27	122.00	123.00	1.00	3	0.05	9	1090	8	2.09	26	19	68	<20	0.35	<10	<10	134	<10	66			
UGA-27	123.00	124.00	1.00	1	0.06	10	1190	8	0.52	19	22	90	<20	0.42	10	<10	161	<10	80			
UGA-27	124.00	125.00	1.00	2	0.07	9	1070	6	1.58	22	20	84	<20	0.39	10	<10	145	<10	71			
UGA-27	125.00	126.00	1.00	3	0.06	8	1010	8	2.14	21	19	63	<20	0.36	<10	<10	134	<10	62			
UGA-27	126.00	127.00	1.00	4	0.07	9	1040	8	2.34	15	19	78	<20	0.37	10	<10	138	<10	69			
UGA-27	127.00	128.00	1.00	6	0.06	8	1150	8	1.85	23	20	60	<20	0.37	<10	<10	146	<10	66			
UGA-27	128.00	129.00	1.00	4	0.09	9	1170	10	1.7	24	21	62	<20	0.4	<10	<10	151	<10	70			
UGA-27	129.00	130.00	1.00	1	0.05	9	1140	5	0.23	21	21	73	<20	0.4	<10	<10	154	<10	77			
UGA-27	130.00	131.00	1.00	3	0.06	8	1060	6	1.72	10	20	63	<20	0.37	<10	<10	144	<10	67			
UGA-27	131.00	132.00	1.00	2	0.07	8	1010	6	1.91	8	20	81	<20	0.36	<10	<10	138	<10	64			
UGA-27	132.00	133.00	1.00	2	0.06	9	990	6	1.79	6	19	92	<20	0.36	<10	<10	134	<10	61			
UGA-27	133.00	134.00	1.00	2	0.07	6	1000	6	1.93	7	19	78	<20	0.36	<10	<10	133	<10	59			
UGA-27	134.00	135.00	1.00	3	0.05	7	1060	12	2.16	16	19	92	<20	0.37	10	<10	136	<10	62			
UGA-27	135.00	136.00	1.00	3	0.06	7	1100	8	2.94	10	20	119	<20	0.38	10	<10	140	<10	67			
UGA-27	136.00	137.00	1.00	4	0.04	8	1190	11	2.74	18	20	100	<20	0.4	<10	<10	149	<10	73			
UGA-27	137.00	138.00	1.00	2	0.05	8	1190	13	3.05	9	21	119	<20	0.41	10	<10	153	<10	74			
UGA-27	138.00	139.00	1.00	2	0.04	6	1240	9	2.78	13	21	106	<20	0.41	<10	<10	153	<10	72			
UGA-27	139.00	140.00	1.00	3	0.04	9	1160	11	2.29	19	20	90	<20	0.38	<10	<10	152	<10	81			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-27	90.00	91.00	1.00							
UGA-27	91.00	92.00	1.00							
UGA-27	92.00	93.00	1.00							
UGA-27	93.00	94.00	1.00							
UGA-27	94.00	95.00	1.00							
UGA-27	95.00	96.00	1.00							
UGA-27	96.00	97.00	1.00							
UGA-27	97.00	98.00	1.00							
UGA-27	98.00	99.00	1.00							
UGA-27	99.00	100.00	1.00							
UGA-27	100.00	101.00	1.00							
UGA-27	101.00	102.00	1.00							
UGA-27	102.00	103.00	1.00							
UGA-27	103.00	104.00	1.00							
UGA-27	104.00	105.00	1.00							
UGA-27	105.00	106.00	1.00							
UGA-27	106.00	107.00	1.00							
UGA-27	107.00	108.00	1.00							
UGA-27	108.00	109.00	1.00							
UGA-27	109.00	110.00	1.00							
UGA-27	110.00	111.00	1.00							
UGA-27	111.00	112.00	1.00							
UGA-27	112.00	113.00	1.00							
UGA-27	113.00	114.00	1.00							
UGA-27	114.00	115.00	1.00							
UGA-27	115.00	116.00	1.00							
UGA-27	116.00	117.00	1.00							
UGA-27	117.00	118.00	1.00							
UGA-27	118.00	119.00	1.00							
UGA-27	119.00	120.00	1.00							
UGA-27	120.00	121.00	1.00							
UGA-27	121.00	122.00	1.00							
UGA-27	122.00	123.00	1.00							
UGA-27	123.00	124.00	1.00							
UGA-27	124.00	125.00	1.00							
UGA-27	125.00	126.00	1.00							
UGA-27	126.00	127.00	1.00							
UGA-27	127.00	128.00	1.00							
UGA-27	128.00	129.00	1.00							
UGA-27	129.00	130.00	1.00							
UGA-27	130.00	131.00	1.00							
UGA-27	131.00	132.00	1.00							
UGA-27	132.00	133.00	1.00							
UGA-27	133.00	134.00	1.00							
UGA-27	134.00	135.00	1.00							
UGA-27	135.00	136.00	1.00							
UGA-27	136.00	137.00	1.00							
UGA-27	137.00	138.00	1.00							
UGA-27	138.00	139.00	1.00							
UGA-27	139.00	140.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	K %	La ppm	Mg %	Mn ppm
UGA-27	140.00	141.00	1.00	M299199	0.19		0.5	6.64	119	500	1.9	<2	0.33	<0.5	17	33	20	4.5	10	4.48	30	0.72	684
UGA-27	141.00	142.00	1.00	M299201	0.32		1	6.68	172	240	2.2	3	0.36	<0.5	15	39	24	4.92	20	3.1	30	0.84	1255
UGA-27	142.00	143.00	1.00	M299202	0.14		1.6	6.68	105	550	1.8	2	0.33	<0.5	16	37	35	3.88	10	4.43	30	0.61	685
UGA-27	143.00	144.00	1.00	M299203	8.15		6.1	6.29	295	410	1.8	2	0.34	<0.5	16	44	41	3.54	10	3.99	30	0.39	198
UGA-27	144.00	145.00	1.00	M299204	2.13		3.1	6.33	305	270	1.9	<2	0.31	<0.5	17	43	63	3.73	20	2.66	30	0.4	304
UGA-27	145.00	146.00	1.00	M299205	0.38		1.5	6.57	258	310	2	<2	0.34	<0.5	15	39	29	4.17	10	3.02	30	0.53	662
UGA-27	146.00	147.00	1.00	M299206	0.72		2.1	6.78	222	470	2.1	3	0.35	<0.5	16	39	27	4.24	10	4.49	30	0.61	727
UGA-27	147.00	148.00	1.00	M299208	0.39		3.7	6.66	156	430	2.1	2	0.33	<0.5	17	40	31	3.85	20	4.49	30	0.61	610
UGA-27	148.00	149.00	1.00	M299209	0.74		1.7	6.83	295	190	2.5	3	0.32	<0.5	18	44	31	4.14	10	3.12	30	0.47	276
UGA-27	149.00	150.00	1.00	M299210	0.45		1.8	6.83	167	380	2.1	<2	0.34	<0.5	17	34	39	4.6	10	4.31	30	0.65	952
UGA-27	150.00	151.00	1.00	M299211	0.31		0.9	7.05	229	480	2.1	3	0.35	<0.5	17	37	26	4.32	20	4.84	30	0.65	755
UGA-27	151.00	152.00	1.00	M299212	0.04		0.7	7.79	89	100	2.4	4	0.44	<0.5	17	37	27	5.59	20	3.27	30	0.95	1750
UGA-27	152.00	153.00	1.00	M299213	0.05		0.6	7.49	113	30	2.2	3	0.4	<0.5	19	34	24	5.12	20	2.64	30	0.83	1200
UGA-27	153.00	154.00	1.00	M299214	0.03		<0.5	7.82	129	50	2.3	2	0.4	<0.5	21	32	28	5.5	20	3.03	30	0.93	1320
UGA-27	154.00	155.00	1.00	M299215	0.25		0.5	7.57	111	130	2.3	2	0.4	<0.5	16	34	32	5.49	20	3.31	30	0.98	1195
UGA-27	155.00	156.00	1.00	M299216	0.35		0.8	7.07	108	440	2	5	1.12	<0.5	17	34	49	5.26	10	4.09	30	1.19	1055
UGA-27	156.00	157.00	1.00	M299217	0.18		1.5	7.3	382	380	1.8	6	0.77	<0.5	19	37	51	6.33	10	4.33	30	0.72	1070
UGA-27	157.00	158.00	1.00	M299218	0.05		0.8	7.31	161	60	2.4	7	0.41	<0.5	18	37	44	5.17	20	2.61	30	0.82	1485
UGA-27	158.00	159.00	1.00	M299219	0.16		0.8	6.96	207	30	2.4	4	0.39	<0.5	19	35	30	5.33	20	2.43	30	0.74	971
UGA-27	159.00	160.00	1.00	M299220	0.14		0.9	6.53	188	30	2.5	3	0.4	<0.5	17	34	33	6.5	10	2.27	20	0.82	2220
UGA-27	160.00	161.00	1.00	M299221	0.43		2.4	6.41	244	110	2.4	2	0.47	<0.5	16	45	29	4.76	10	2.85	20	0.73	1195
UGA-27	161.00	162.00	1.00	M299223	0.12		0.5	6.94	174	320	2.5	<2	0.36	<0.5	18	44	26	4.54	10	4.02	30	0.65	953
UGA-27	162.00	163.00	1.00	M299224	0.82		1.1	6.48	183	100	2.7	3	0.41	<0.5	16	45	26	4.46	10	2.73	20	0.65	1150
UGA-27	163.00	164.00	1.00	M299225	0.2		0.9	6.3	220	50	2.7	5	0.36	<0.5	17	42	46	4.73	20	2.43	20	0.67	1100
UGA-27	164.00	165.00	1.00	M299226	0.15		1.1	6.84	199	340	2.7	5	0.37	<0.5	17	46	43	4.4	10	4.02	30	0.66	1125
UGA-27	165.00	166.00	1.00	M299227	0.23		1.5	5.91	280	80	2.9	3	0.32	<0.5	17	47	31	4.92	10	2.55	20	0.67	952
UGA-27	166.00	167.00	1.00	M299228	0.26		1.4	6.7	244	40	3	<2	0.36	<0.5	19	56	36	5.03	10	2.9	30	0.83	839
UGA-27	167.00	168.00	1.00	M299229	0.06		1.1	6.11	258	40	2.6	<2	0.34	<0.5	18	62	28	5.47	10	2.63	20	0.74	1170
UGA-27	168.00	169.00	1.00	M299231	0.14		1.6	7.06	297	30	2.6	<2	0.36	<0.5	19	55	52	4.34	10	2.79	30	0.7	890
UGA-27	169.00	170.00	1.00	M299232	0.05		1.4	7.2	109	40	2.8	<2	0.35	<0.5	22	60	30	4.39	20	3.16	30	0.75	722
UGA-27	170.00	171.00	1.00	M299233	0.04		1.3	7.29	106	40	2.8	<2	0.36	<0.5	19	59	38	4.17	20	3.21	30	0.77	839
UGA-27	171.00	172.00	1.00	M299234	0.44		1.6	6.09	325	30	2.9	<2	0.34	<0.5	18	52	20	4.89	10	2.72	20	0.69	1255
UGA-27	172.00	173.00	1.00	M299235	1.05		3	4.98	574	20	2.3	<2	0.28	<0.5	15	48	23	3.5	10	2.17	20	0.51	338
UGA-27	173.00	174.00	1.00	M299236	0.3		1.5	5.1	198	30	2.1	<2	0.27	<0.5	16	46	16	3.03	10	2.36	20	0.61	331
UGA-27	174.00	175.00	1.00	M299237	0.13		1	4.88	203	30	2.1	<2	0.3	0.9	14	39	16	4.67	10	2.26	20	0.59	1190
UGA-27	175.00	176.00	1.00	M299238	0.1		1.1	3.78	167	40	1.9	<2	0.21	<0.5	12	42	12	2.9	10	1.7	10	0.42	389
UGA-27	176.00	177.00	1.00	M299239	0.05		0.8	3.01	105	30	1.5	<2	0.16	<0.5	10	38	13	2.78	10	1.34	10	0.33	151
UGA-27	177.00	178.00	1.00	M299240	0.11		1.1	3.63	150	40	1.8	<2	0.19	<0.5	10	31	12	3.37	10	1.64	10	0.4	563
UGA-27	178.00	179.00	1.00	M299241	0.07		0.9	3.58	144	50	1.6	<2	0.2	<0.5	11	35	10	2.78	10	1.59	20	0.37	297
UGA-27	179.00	180.00	1.00	M299242	0.08		1.2	3.39	426	50	1.3	<2	0.22	<0.5	11	32	8	3.13	10	1.46	10	0.32	706
UGA-27	180.00	181.00	1.00	M299243	0.08		1.1	3.54	487	60	1.5	<2	0.23	<0.5	11	38	8	3.46	10	1.52	10	0.32	1125
UGA-27	181.00	182.00	1.00	M299244	0.06		1.2	3.96	283	60	1.7	<2	0.26	<0.5	11	41	9	3.44	10	1.74	10	0.37	819
UGA-27	182.00	183.00	1.00	M299245	0.04		1.6	4.98	176	90	2	<2	0.35	<0.5	13	40	16	3.62	10	2.17	20	0.43	1940
UGA-27	183.00	184.00	1.00	M299246	0.08		1.4	3.11	206	80	1.7	<2	0.23	<0.5	10	59	14	3.2	10	1.34	10	0.3	999
UGA-27	184.00	185.00	1.00	M299247	0.05		1.9	4.33	242	90	1.8	<2	0.24	<0.5	14	67	15	3.44	10	1.91	20	0.38	119
UGA-27	185.00	186.00	1.00	M299248	0.03		1.4	3.75	176	80	1.7	<2	0.21	<0.5	14	85	14	2.64	10	1.63	10	0.32	53
UGA-27	186.00	187.00	1.00	M299251	0.07		1.1	3.72	137	110	1.7	<2	0.21	<0.5	11	45	9	2.57	10	1.6	10	0.31	44
UGA-27	187.00	188.00	1.00	M299252	0.09		1.2	3.55	157	110	1.5	<2	0.19	<0.5	10	48	9	2.98	10	1.51	10	0.29	54
UGA-27	188.00	189.00	1.00	M299253	0.07		1.3	3.28	161	70	1.7	2	0.23	<0.5	10	52	13	3.51	10	1.42	10	0.31	1285
UGA-27	189.00	190.00	1.00	M299254	0.1		1.5	3.48	232	70	1.8	2	0.76	<0.5	12	73	15	3.99	10	1.51	10	0.5	1790

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-27	140.00	141.00	1.00	4	0.03	9	1120	13	2.49	29	19	56	<20	0.36	10	<10	140	<10	79			
UGA-27	141.00	142.00	1.00	6	0.02	10	1150	9	2.06	39	21	35	<20	0.37	10	<10	146	<10	61			
UGA-27	142.00	143.00	1.00	3	0.04	8	1110	7	2.07	32	19	59	<20	0.37	10	<10	136	<10	51			
UGA-27	143.00	144.00	1.00	7	0.03	9	1050	11	3.34	47	15	46	<20	0.35	10	<10	125	<10	361			
UGA-27	144.00	145.00	1.00	8	0.02	6	1070	11	3.26	62	17	30	<20	0.35	10	<10	127	<10	53			
UGA-27	145.00	146.00	1.00	5	0.03	10	1100	13	2.93	43	18	44	<20	0.36	<10	<10	134	<10	73			
UGA-27	146.00	147.00	1.00	5	0.04	9	1150	12	2.77	39	18	59	<20	0.37	<10	<10	139	<10	42			
UGA-27	147.00	148.00	1.00	5	0.04	8	1100	9	2.43	30	18	61	<20	0.36	10	<10	135	<10	109			
UGA-27	148.00	149.00	1.00	4	0.02	13	1100	8	4.07	47	19	39	<20	0.38	10	<10	142	<10	46			
UGA-27	149.00	150.00	1.00	2	0.04	9	1160	9	2.53	25	18	56	<20	0.37	<10	<10	137	<10	62			
UGA-27	150.00	151.00	1.00	4	0.04	10	1200	15	2.68	23	18	55	<20	0.38	10	<10	145	<10	52			
UGA-27	151.00	152.00	1.00	3	0.02	10	1380	8	2.1	27	21	32	<20	0.41	10	<10	158	<10	73			
UGA-27	152.00	153.00	1.00	3	0.01	10	1280	10	2.53	26	19	27	<20	0.41	<10	<10	145	<10	56			
UGA-27	153.00	154.00	1.00	3	0.01	11	1270	14	2.64	29	18	30	<20	0.42	<10	<10	143	<10	62			
UGA-27	154.00	155.00	1.00	4	0.02	10	1300	10	2.4	22	19	33	<20	0.39	<10	<10	151	<10	66			
UGA-27	155.00	156.00	1.00	3	0.03	8	1340	8	2.57	25	19	53	<20	0.38	10	<10	140	<10	58			
UGA-27	156.00	157.00	1.00	5	0.04	9	3050	14	4.2	27	20	57	<20	0.39	10	<10	152	<10	62			
UGA-27	157.00	158.00	1.00	3	0.01	12	1280	8	2.46	35	19	37	<20	0.39	10	<10	142	<10	227			
UGA-27	158.00	159.00	1.00	3	0.01	11	1300	13	3.31	31	18	29	<20	0.38	<10	<10	139	<10	144			
UGA-27	159.00	160.00	1.00	3	0.02	12	1160	9	3.21	29	19	40	<20	0.36	<10	<10	144	<10	62			
UGA-27	160.00	161.00	1.00	4	0.02	8	1670	9	2.59	36	18	36	<20	0.35	<10	<10	138	<10	60			
UGA-27	161.00	162.00	1.00	2	0.03	8	1140	11	2.73	20	19	53	<20	0.39	<10	<10	144	<10	52			
UGA-27	162.00	163.00	1.00	3	0.01	9	1340	5	2.37	35	17	24	<20	0.35	10	<10	134	<10	55			
UGA-27	163.00	164.00	1.00	4	0.01	12	1080	12	2.69	43	18	23	<20	0.34	10	<10	136	<10	60			
UGA-27	164.00	165.00	1.00	4	0.03	10	1110	11	2.5	30	19	37	<20	0.37	<10	<10	143	<10	47			
UGA-27	165.00	166.00	1.00	4	0.01	13	970	11	3.31	28	18	22	<20	0.33	<10	<10	127	<10	61			
UGA-27	166.00	167.00	1.00	3	0.02	14	1140	9	3.35	23	21	21	<20	0.37	<10	<10	145	10	57			
UGA-27	167.00	168.00	1.00	3	0.02	14	1030	7	3.67	27	19	20	<20	0.33	<10	<10	134	10	47			
UGA-27	168.00	169.00	1.00	4	0.02	15	1140	14	2.96	35	19	19	<20	0.37	10	<10	145	10	53			
UGA-27	169.00	170.00	1.00	2	0.02	16	1180	8	3.22	23	20	21	<20	0.39	<10	<10	150	10	60			
UGA-27	170.00	171.00	1.00	3	0.02	15	1200	6	2.75	18	21	20	<20	0.39	<10	<10	154	10	88			
UGA-27	171.00	172.00	1.00	4	0.01	15	1030	9	3.55	29	20	24	<20	0.34	<10	<10	136	10	59			
UGA-27	172.00	173.00	1.00	6	0.01	13	940	8	3.31	48	15	24	<20	0.27	<10	<10	107	10	36			
UGA-27	173.00	174.00	1.00	6	0.01	10	900	8	2.87	38	15	18	<20	0.28	10	<10	110	<10	40			
UGA-27	174.00	175.00	1.00	5	0.01	11	890	6	3.59	32	15	13	<20	0.26	<10	<10	102	<10	150			
UGA-27	175.00	176.00	1.00	3	0.01	11	660	6	2.71	42	12	10	<20	0.2	<10	<10	86	<10	85			
UGA-27	176.00	177.00	1.00	4	0.01	9	490	5	2.78	36	9	11	<20	0.15	<10	<10	68	<10	59			
UGA-27	177.00	178.00	1.00	4	0.01	9	530	6	3.03	48	11	12	<20	0.17	<10	<10	79	<10	39			
UGA-27	178.00	179.00	1.00	4	0.02	10	620	5	2.59	44	11	12	<20	0.18	<10	<10	78	<10	40			
UGA-27	179.00	180.00	1.00	3	0.01	10	710	4	2.81	46	10	11	<20	0.18	<10	<10	69	<10	47			
UGA-27	180.00	181.00	1.00	4	0.01	12	700	6	3	46	11	11	<20	0.2	<10	<10	73	10	37			
UGA-27	181.00	182.00	1.00	4	0.02	12	780	3	3.12	46	13	12	<20	0.22	<10	<10	84	<10	37			
UGA-27	182.00	183.00	1.00	3	0.02	10	990	7	2.64	41	15	13	<20	0.27	<10	<10	104	<10	52			
UGA-27	183.00	184.00	1.00	6	0.01	14	640	9	2.7	52	11	10	<20	0.17	<10	<10	67	10	33			
UGA-27	184.00	185.00	1.00	5	0.02	18	770	10	3.72	52	13	11	<20	0.24	<10	<10	97	<10	41			
UGA-27	185.00	186.00	1.00	5	0.02	18	690	11	2.79	55	11	11	<20	0.22	<10	<10	82	<10	45			
UGA-27	186.00	187.00	1.00	7	0.02	11	680	16	2.75	51	10	12	<20	0.21	<10	<10	95	<10	83			
UGA-27	187.00	188.00	1.00	25	0.02	11	660	65	3.14	72	9	10	<20	0.19	<10	<10	63	10	96			
UGA-27	188.00	189.00	1.00	8	0.01	14	650	12	2.72	50	11	10	<20	0.18	<10	<10	69	10	44			
UGA-27	189.00	190.00	1.00	11	0.02	16	750	13	3.07	49	12	15	<20	0.19	<10	<10	80	10	65			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-27	140.00	141.00	1.00							
UGA-27	141.00	142.00	1.00							
UGA-27	142.00	143.00	1.00							
UGA-27	143.00	144.00	1.00							
UGA-27	144.00	145.00	1.00							
UGA-27	145.00	146.00	1.00							
UGA-27	146.00	147.00	1.00							
UGA-27	147.00	148.00	1.00							
UGA-27	148.00	149.00	1.00							
UGA-27	149.00	150.00	1.00							
UGA-27	150.00	151.00	1.00							
UGA-27	151.00	152.00	1.00							
UGA-27	152.00	153.00	1.00							
UGA-27	153.00	154.00	1.00							
UGA-27	154.00	155.00	1.00							
UGA-27	155.00	156.00	1.00							
UGA-27	156.00	157.00	1.00							
UGA-27	157.00	158.00	1.00							
UGA-27	158.00	159.00	1.00							
UGA-27	159.00	160.00	1.00							
UGA-27	160.00	161.00	1.00							
UGA-27	161.00	162.00	1.00							
UGA-27	162.00	163.00	1.00							
UGA-27	163.00	164.00	1.00							
UGA-27	164.00	165.00	1.00							
UGA-27	165.00	166.00	1.00							
UGA-27	166.00	167.00	1.00							
UGA-27	167.00	168.00	1.00							
UGA-27	168.00	169.00	1.00							
UGA-27	169.00	170.00	1.00							
UGA-27	170.00	171.00	1.00							
UGA-27	171.00	172.00	1.00							
UGA-27	172.00	173.00	1.00							
UGA-27	173.00	174.00	1.00							
UGA-27	174.00	175.00	1.00							
UGA-27	175.00	176.00	1.00							
UGA-27	176.00	177.00	1.00							
UGA-27	177.00	178.00	1.00							
UGA-27	178.00	179.00	1.00							
UGA-27	179.00	180.00	1.00							
UGA-27	180.00	181.00	1.00							
UGA-27	181.00	182.00	1.00							
UGA-27	182.00	183.00	1.00							
UGA-27	183.00	184.00	1.00							
UGA-27	184.00	185.00	1.00							
UGA-27	185.00	186.00	1.00							
UGA-27	186.00	187.00	1.00							
UGA-27	187.00	188.00	1.00							
UGA-27	188.00	189.00	1.00							
UGA-27	189.00	190.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	K %	La ppm	Mg %	Mn ppm	
UGA-27	190.00	191.00	1.00	M299255	0.15		1.4	3.52	152	100	1.7	<2	1.09	<0.5	10	45	10	2.42	10	1.47	10	0.59	672	
UGA-27	191.00	192.00	1.00	M299256	0.11		0.9	3.48	92	130	1.8	2	1.9	1.2	6	23	8	2.77	10	1.4	10	0.84	2050	
UGA-27	192.00	193.00	1.00	M299258	0.11		<0.5	4.07	111	170	1.9	<2	3.24	<0.5	6	5	5	4.38	10	1.7	10	1.3	4410	
UGA-27	193.00	194.00	1.00	M299259	0.19		2.8	4.24	241	310	1.6	<2	0.97	<0.5	13	45	14	3.8	10	1.72	20	0.52	1580	
UGA-27	194.00	195.00	1.00	M299260	0.16		1.9	3.93	169	160	1.5	<2	1.57	<0.5	15	48	13	2.91	10	1.54	20	0.73	1020	
UGA-27	195.00	196.00	1.00	M299261	0.07		0.5	3.02	107	470	1.6	2	1.02	<0.5	9	33	4	1.91	10	1.22	20	0.52	623	
UGA-27	196.00	197.00	1.00	M299262	0.23		1.2	2.49	267	200	1.7	<2	2.27	<0.5	7	21	5	3.32	10	0.99	10	1.04	1290	
UGA-27	197.00	198.00	1.00	M299263	0.1		<0.5	0.35	256	470	0.9	<2	9.92	0.8	4	10	2	4.76	<10	0.11	10	4.93	4310	
UGA-27	198.00	200.00	2.00	M299264	0.07		<0.5	1.14	59	1330	1.3	<2	3.81	<0.5	22	12	2	2.21	<10	0.45	10	1.78	3080	
UGA-27	200.00	202.00	2.00	M299266	0.06		0.8	6.83	218	300	1.6	<2	1.24	<0.5	15	4	44	4.27	20	2.86	10	0.66	2810	
UGA-27	202.00	203.00	1.00	M299267	0.15		0.7	3.84	198	170	1.3	<2	0.44	<0.5	12	9	7	3.22	10	1.64	10	0.31	1585	
UGA-26	10.00	11.00	1.00	M298956	0.12		1.9	6.71	349	440	1	<2	0.51	<0.5	19	62	78	4.8	10	4.42	20	1.52	429	
UGA-26	11.00	12.00	1.00	M298957	0.1		1.2	6.27	274	440	0.9	<2	1.19	<0.5	16	60	33	4.47	10	4.11	20	1.88	429	
UGA-26	12.00	13.00	1.00	M298958	0.11		0.8	6.46	148	310	0.9	3	0.83	<0.5	18	61	40	5.03	10	4.5	30	1.9	537	
UGA-26	13.00	14.00	1.00	M298959	0.13		0.9	7.07	159	450	1.1	4	1.35	<0.5	19	67	43	4.96	10	4.78	30	2.23	566	
UGA-26	14.00	15.00	1.00	M298960	0.71		3	5.17	258	350	0.8	<2	1.18	<0.5	14	69	27	4.23	10	3.97	20	1.31	373	
UGA-26	15.00	16.00	1.00	M298963	0.1		0.8	7.06	128	330	1.2	<2	1.29	<0.5	17	71	31	4.44	20	4.31	30	1.52	464	
UGA-26	16.00	17.00	1.00	M298964	0.06		0.5	6.68	102	440	1.2	2	1.6	<0.5	19	65	36	4.96	20	4.24	30	1.64	483	
UGA-26	17.00	18.00	1.00	M298965	0.08		1.3	7.7	188	400	1.1	3	0.51	<0.5	20	81	37	4.06	20	4.39	20	0.51	144	
UGA-26	18.00	19.00	1.00	M298966	0.1		2.2	7.21	132	260	1.2	<2	0.45	<0.5	20	78	32	4.39	20	3.92	20	0.48	194	
UGA-26	19.00	20.00	1.00	M298967	0.18		2	6.51	125	410	1.3	<2	0.79	<0.5	19	68	40	5.24	10	4.38	20	1.14	1175	
UGA-26	20.00	21.00	1.00	M298968	0.1		1.5	6.63	99	210	1.5	5	0.59	<0.5	20	73	31	4.58	10	4.19	30	0.73	1165	
UGA-26	21.00	22.00	1.00	M298969	0.11		1.1	6.39	114	270	1.3	<2	0.34	<0.5	18	71	30	3.97	20	4.19	20	0.46	889	
UGA-26	22.00	23.00	1.00	M298971	0.45		3.8	6.55	270	120	1.7	<2	0.6	<0.5	19	70	34	3.52	20	2.8	20	0.42	636	
UGA-26	23.00	24.00	1.00	M298972	4.09		22.1	5.73	659	390	1.3	<2	0.4	<0.5	19	64	47	4.08	10	4.36	20	0.32	81	
UGA-26	24.00	25.00	1.00	M298973	0.16		1.9	6.51	340	560	1.3	<2	0.31	<0.5	21	71	30	3.37	10	4.27	30	0.6	329	
UGA-26	25.00	26.00	1.00	M298974	0.1		2.8	7.04	139	520	1.3	<2	0.33	<0.5	20	74	35	4.06	10	4.06	30	1.43	415	
UGA-26	26.00	27.00	1.00	M298975	0.13		1.4	6.57	175	460	1.1	2	0.53	<0.5	21	67	33	4.4	10	4.08	20	1.07	672	
UGA-26	27.00	28.00	1.00	M298976	0.07		1.1	6.82	228	390	1.2	<2	0.44	<0.5	24	69	37	6.58	10	4.1	20	1.48	1185	
UGA-26	28.00	29.00	1.00	M298977	0.06		1	6.89	156	600	1.1	2	0.41	<0.5	22	68	39	4.98	20	4.36	30	1.69	668	
UGA-26	29.00	30.00	1.00	M298978	0.09		1.3	6.62	222	380	0.9	<2	0.64	<0.5	20	68	35	4.2	10	4.2	20	1.45	459	
UGA-26	30.00	31.00	1.00	M298979	0.22		2.7	6.77	602	540	0.9	<2	0.52	<0.5	21	66	35	4.64	20	4.14	30	1.5	348	
UGA-26	31.00	32.00	1.00	M298980	0.39		2	6.71	277	560	1	2	0.54	<0.5	19	68	35	4.45	10	4.07	20	1.82	389	
UGA-26	32.00	33.00	1.00	M298981	0.16		1.2	6.29	199	430	0.9	3	0.5	<0.5	19	66	34	4.63	10	4.05	20	1.58	390	
UGA-26	33.00	34.00	1.00	M298982	0.15		1.5	6.55	202	460	1	2	0.51	<0.5	21	67	35	5.35	20	4.13	30	1.7	408	
UGA-26	34.00	35.00	1.00	M298983	0.74		4.1	6.71	406	460	1	2	0.41	<0.5	18	69	37	4.68	10	4.09	30	1.6	350	
UGA-26	35.00	36.00	1.00	M298984	0.17		1.7	6.71	259	430	1	<2	0.39	<0.5	21	65	33	5.06	20	4.04	30	1.78	465	
UGA-26	36.00	37.00	1.00	M298985	0.51		1.3	6.89	205	530	1	<2	0.41	<0.5	18	67	34	4.59	20	3.55	20	1.79	387	
UGA-26	37.00	38.00	1.00	M298986	1.06		0.9	7.19	141	510	1.1	<2	0.7	<0.5	18	69	37	4.99	20	3.31	30	2.31	528	
UGA-26	38.00	39.00	1.00	M298987	0.28		0.5	6.94	117	530	1	<2	0.42	<0.5	19	69	37	4.44	20	3.71	20	2.02	342	
UGA-26	39.00	40.00	1.00	M298988	0.07		0.6	7.43	89	570	1	<2	0.32	<0.5	24	73	38	4.53	20	3.5	30	2.43	375	
UGA-26	40.00	41.00	1.00	M298989	0.04		0.9	7.41	64	550	1.1	<2	0.42	<0.5	22	71	36	4.87	20	3.29	30	2.72	454	
UGA-26	41.00	42.00	1.00	M298990	0.34		1.5	7.33	137	640	1	<2	0.35	<0.5	21	73	34	4.52	10	3.51	20	2.43	430	
UGA-26	42.00	43.00	1.00	M298991	0.06		1.3	6.8	122	690	1.2	<2	0.67	<0.5	19	69	32	3.51	10	3.31	20	1.68	272	
UGA-26	43.00	44.00	1.00	M298992	0.34		7.9	3.08	118	330	0.6	<2	1.68	<0.5	10	55	16	3.66	10	2.16	10	1.44	315	
UGA-26	44.00	45.00	1.00	M298994	0.05		2.2	5.67	122	270	0.9	<2	0.95	<0.5	18	74	27	3.86	10	3.05	20	0.89	166	
UGA-26	45.00	46.00	1.00	M298995	0.06		2.7	5.89	145	560	1	<2	1.04	<0.5	19	73	29	3.83	10	3.32	20	0.95	149	
UGA-26	46.00	47.00	1.00	M298996	0.03		2.2	6.37	103	480	1.2	<2	2.1	<0.5	18	52	22	4.34	20	3.08	20	1.69	360	
UGA-26	47.00	48.00	1.00	M298997	0.04		1.8	5.77	110	380	1	<2	1.88	<0.5	15	37	17	4.11	10	3.12	20	1.34	321	
UGA-26	48.00	49.00	1.00	M298999	0.06		1.9	6.16	150	420	0.7	<2	3.68	<0.5	14	31	18	5.01	10	3.07	20	1.97	792	

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-27	190.00	191.00	1.00	10	0.02	10	570	21	2.1	65	10	18	<20	0.19	<10	<10	66	10	92			
UGA-27	191.00	192.00	1.00	12	0.04	3	410	31	1.33	60	8	25	<20	0.17	<10	<10	49	10	208			
UGA-27	192.00	193.00	1.00	9	0.04	4	490	17	1.6	52	10	28	<20	0.21	<10	<10	64	<10	79			
UGA-27	193.00	194.00	1.00	49	0.07	13	770	16	2.83	68	13	26	<20	0.22	10	<10	83	<10	46			
UGA-27	194.00	195.00	1.00	31	0.07	18	700	27	2.27	72	12	31	<20	0.21	<10	<10	74	<10	66			
UGA-27	195.00	196.00	1.00	15	0.03	8	430	22	1.51	71	7	23	<20	0.15	<10	<10	48	10	92			
UGA-27	196.00	197.00	1.00	26	0.03	7	310	34	2.8	92	7	31	<20	0.12	<10	<10	46	10	110			
UGA-27	197.00	198.00	1.00	8	0.01	7	50	19	2.84	116	1	85	<20	0.01	<10	<10	7	<10	86			
UGA-27	198.00	200.00	2.00	15	<0.01	15	220	15	0.4	133	2	37	<20	0.05	<10	<10	17	<10	46			
UGA-27	200.00	202.00	2.00	2	0.08	4	700	13	2.22	29	11	32	<20	0.33	10	<10	89	<10	54			
UGA-27	202.00	203.00	1.00	20	0.03	5	540	16	2.22	66	8	17	<20	0.2	10	<10	63	<10	47			
UGA-26	10.00	11.00	1.00	3	<0.01	16	1150	9	2.64	53	21	80	<20	0.37	10	<10	137	<10	76			
UGA-26	11.00	12.00	1.00	3	<0.01	13	1160	11	2.44	40	19	91	<20	0.35	10	<10	129	<10	62			
UGA-26	12.00	13.00	1.00	2	0.02	15	1100	9	2.65	25	20	106	<20	0.35	<10	<10	144	<10	71			
UGA-26	13.00	14.00	1.00	2	<0.01	14	980	8	2.5	23	23	132	<20	0.39	<10	<10	170	<10	75			
UGA-26	14.00	15.00	1.00	6	0.01	12	850	10	2.86	55	16	108	<20	0.28	10	<10	120	<10	53			
UGA-26	15.00	16.00	1.00	2	0.01	14	880	11	2.93	25	21	88	<20	0.39	<10	<10	149	<10	69			
UGA-26	16.00	17.00	1.00	2	<0.01	14	810	12	3.5	20	21	92	<20	0.37	10	<10	142	<10	60			
UGA-26	17.00	18.00	1.00	2	0.02	17	1120	7	4.1	32	23	112	<20	0.43	10	<10	143	<10	75			
UGA-26	18.00	19.00	1.00	2	0.03	18	1140	10	4.48	27	22	93	<20	0.41	10	<10	158	<10	77			
UGA-26	19.00	20.00	1.00	3	0.01	16	900	8	2.93	27	21	100	<20	0.36	10	<10	134	<10	72			
UGA-26	20.00	21.00	1.00	3	0.03	15	1190	8	1.93	27	20	81	<20	0.36	10	<10	133	<10	65			
UGA-26	21.00	22.00	1.00	2	0.01	15	1090	10	1.71	32	20	64	<20	0.36	10	<10	135	<10	55			
UGA-26	22.00	23.00	1.00	33	0.01	13	2440	13	2.43	73	20	35	<20	0.35	10	<10	148	<10	89			
UGA-26	23.00	24.00	1.00	58	<0.01	16	1690	19	4.34	82	18	42	<20	0.32	10	<10	149	<10	70			
UGA-26	24.00	25.00	1.00	6	<0.01	16	1230	12	2.72	30	20	99	<20	0.37	10	<10	138	<10	78			
UGA-26	25.00	26.00	1.00	4	0.01	17	1350	9	2.54	23	21	107	<20	0.39	10	<10	148	<10	78			
UGA-26	26.00	27.00	1.00	3	<0.01	17	1230	11	2.62	20	20	74	<20	0.37	10	<10	146	<10	59			
UGA-26	27.00	28.00	1.00	2	<0.01	19	990	12	3.36	25	22	67	<20	0.38	10	<10	160	<10	83			
UGA-26	28.00	29.00	1.00	6	<0.01	19	1450	13	2.06	33	21	75	<20	0.38	10	<10	142	<10	74			
UGA-26	29.00	30.00	1.00	4	0.01	14	1330	11	2.11	35	20	80	<20	0.36	10	<10	136	<10	67			
UGA-26	30.00	31.00	1.00	13	<0.01	18	1440	11	3.14	52	21	93	<20	0.38	10	<10	143	<10	61			
UGA-26	31.00	32.00	1.00	4	<0.01	16	1320	11	2.32	36	21	80	<20	0.37	10	<10	145	<10	69			
UGA-26	32.00	33.00	1.00	4	<0.01	15	1070	9	2.73	32	20	86	<20	0.35	<10	<10	139	<10	60			
UGA-26	33.00	34.00	1.00	4	<0.01	20	1090	11	3.51	34	20	88	<20	0.36	10	<10	147	<10	64			
UGA-26	34.00	35.00	1.00	4	<0.01	15	1220	12	3.32	34	21	102	<20	0.38	10	<10	149	<10	67			
UGA-26	35.00	36.00	1.00	3	<0.01	18	1040	10	3.37	27	20	75	<20	0.37	<10	<10	142	<10	60			
UGA-26	36.00	37.00	1.00	2	0.04	14	1100	7	2.63	16	21	123	<20	0.37	10	<10	139	<10	68			
UGA-26	37.00	38.00	1.00	2	0.03	15	1150	9	2.56	13	22	123	<20	0.37	10	<10	143	10	78			
UGA-26	38.00	39.00	1.00	3	0.03	14	1130	7	2.35	15	21	102	<20	0.38	10	<10	144	10	64			
UGA-26	39.00	40.00	1.00	2	0.04	16	1180	6	2.03	13	22	96	<20	0.39	10	<10	149	10	70			
UGA-26	40.00	41.00	1.00	2	0.04	16	1110	8	2.07	15	22	113	<20	0.39	10	<10	149	10	68			
UGA-26	41.00	42.00	1.00	2	0.05	18	1090	8	2.32	22	22	154	<20	0.39	10	<10	155	10	66			
UGA-26	42.00	43.00	1.00	3	0.04	15	1090	8	2.85	22	20	147	<20	0.37	10	<10	142	10	64			
UGA-26	43.00	44.00	1.00	4	0.02	8	560	7	3.27	56	9	81	<20	0.16	<10	<10	55	10	28			
UGA-26	44.00	45.00	1.00	2	0.04	15	910	8	4.03	24	18	99	<20	0.31	10	<10	112	10	55			
UGA-26	45.00	46.00	1.00	1	0.04	16	860	7	4.15	29	20	103	<20	0.34	10	<10	128	<10	63			
UGA-26	46.00	47.00	1.00	2	0.04	13	890	10	4.4	21	19	136	<20	0.35	10	<10	135	10	63			
UGA-26	47.00	48.00	1.00	2	0.04	8	880	5	4.27	22	16	138	<20	0.32	<10	<10	120	10	63			
UGA-26	48.00	49.00	1.00	2	0.07	9	1040	9	5.1	18	15	200	<20	0.31	<10	<10	102	10	49			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-27	190.00	191.00	1.00							
UGA-27	191.00	192.00	1.00							
UGA-27	192.00	193.00	1.00							
UGA-27	193.00	194.00	1.00							
UGA-27	194.00	195.00	1.00							
UGA-27	195.00	196.00	1.00							
UGA-27	196.00	197.00	1.00							
UGA-27	197.00	198.00	1.00							
UGA-27	198.00	200.00	2.00							
UGA-27	200.00	202.00	2.00							
UGA-27	202.00	203.00	1.00							
UGA-26	10.00	11.00	1.00							
UGA-26	11.00	12.00	1.00							
UGA-26	12.00	13.00	1.00							
UGA-26	13.00	14.00	1.00							
UGA-26	14.00	15.00	1.00							
UGA-26	15.00	16.00	1.00							
UGA-26	16.00	17.00	1.00							
UGA-26	17.00	18.00	1.00							
UGA-26	18.00	19.00	1.00							
UGA-26	19.00	20.00	1.00							
UGA-26	20.00	21.00	1.00							
UGA-26	21.00	22.00	1.00							
UGA-26	22.00	23.00	1.00							
UGA-26	23.00	24.00	1.00							
UGA-26	24.00	25.00	1.00							
UGA-26	25.00	26.00	1.00							
UGA-26	26.00	27.00	1.00							
UGA-26	27.00	28.00	1.00							
UGA-26	28.00	29.00	1.00							
UGA-26	29.00	30.00	1.00							
UGA-26	30.00	31.00	1.00							
UGA-26	31.00	32.00	1.00							
UGA-26	32.00	33.00	1.00							
UGA-26	33.00	34.00	1.00							
UGA-26	34.00	35.00	1.00							
UGA-26	35.00	36.00	1.00							
UGA-26	36.00	37.00	1.00							
UGA-26	37.00	38.00	1.00							
UGA-26	38.00	39.00	1.00							
UGA-26	39.00	40.00	1.00							
UGA-26	40.00	41.00	1.00							
UGA-26	41.00	42.00	1.00							
UGA-26	42.00	43.00	1.00							
UGA-26	43.00	44.00	1.00							
UGA-26	44.00	45.00	1.00							
UGA-26	45.00	46.00	1.00							
UGA-26	46.00	47.00	1.00							
UGA-26	47.00	48.00	1.00							
UGA-26	48.00	49.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
					ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-26	49.00	50.00	1.00	M299001	0.05		1.6	5.78	108	450	1.3	2	4.54	0.5	13	32	18	3.97	20	3.46	30	2.69	962
UGA-26	50.00	51.00	1.00	M299002	0.14		3.9	5.91	177	530	1	<2	2.17	<0.5	13	34	18	4.11	10	3.53	30	1.05	478
UGA-26	51.00	52.00	1.00	M299003	0.14		2.6	6	211	340	1.4	2	0.49	<0.5	15	39	23	4.04	10	3.74	30	0.44	53
UGA-26	52.00	53.00	1.00	M299004	0.08		3.5	6.11	135	480	1.2	<2	0.54	<0.5	17	45	31	4.31	10	4.02	20	0.47	223
UGA-26	53.00	54.00	1.00	M299005	0.05		2.7	6.59	197	400	1.3	<2	0.76	<0.5	18	46	31	4.45	10	3.34	20	0.7	211
UGA-26	54.00	55.00	1.00	M299006	0.04		1.8	7.04	184	630	1.4	<2	1.34	<0.5	19	44	32	4.32	20	3.34	30	1.14	359
UGA-26	55.00	56.00	1.00	M299007	0.13		3	4.45	150	440	0.8	<2	2.23	<0.5	11	40	19	3.99	10	2.99	20	1.88	333
UGA-26	56.00	57.00	1.00	M299008	1.07		>100	2.58	157	180	0.7	<2	1.78	1.6	7	36	79	3.15	10	0.95	10	1.84	353
UGA-26	57.00	58.00	1.00	M299009	0.35		3.4	5.97	197	830	1	<2	0.78	<0.5	14	40	21	3.6	10	3.66	30	2.15	309
UGA-26	58.00	59.00	1.00	M299010	3.12		53.4	5.97	224	590	1.1	<2	0.75	0.8	14	35	75	3.99	10	3.23	20	2.29	332
UGA-26	59.00	60.00	1.00	M299011	0.26		13.2	6.1	281	830	1.1	<2	0.44	0.8	14	37	103	3.89	10	3.59	20	1.86	232
UGA-26	60.00	61.00	1.00	M299012	0.24		3.2	6.17	249	930	1.1	<2	0.42	<0.5	16	45	21	4.01	10	3.68	20	2.72	234
UGA-26	61.00	62.00	1.00	M299013	0.17		2.2	5.54	194	750	0.9	<2	0.39	<0.5	16	48	17	3.59	10	3.3	20	2.93	269
UGA-26	62.00	63.00	1.00	M299014	2.03		10.2	5.07	276	640	0.8	2	0.45	<0.5	13	59	24	3.67	10	3.24	20	2.06	224
UGA-26	63.00	64.00	1.00	M299015	0.53		4.1	3.52	281	420	0.8	<2	0.55	<0.5	10	50	15	3.3	10	2.92	10	1.92	317
UGA-26	64.00	65.00	1.00	M299016	0.38		6.9	5.25	171	510	0.8	<2	0.22	<0.5	15	52	22	3.69	10	3.17	20	0.25	53
UGA-26	65.00	66.00	1.00	M299017	0.11		3.8	5.43	81	520	1	<2	0.32	<0.5	15	52	21	4.1	10	3.6	20	0.54	141
UGA-26	66.00	67.00	1.00	M299018	0.4		10.6	5.18	44	540	1.2	<2	1.19	<0.5	14	44	29	4.16	10	3.04	20	1.76	462
UGA-26	67.00	68.00	1.00	M299019	0.23		5.8	5.48	66	630	1.2	<2	1.24	<0.5	13	48	18	4.03	10	3.33	20	1.65	290
UGA-26	68.00	69.00	1.00	M299020	0.51		7.6	4.57	224	530	1.2	<2	0.82	<0.5	12	50	22	4.25	10	3.27	20	1.62	246
UGA-26	69.00	70.00	1.00	M299022	0.74		21.9	4.8	414	530	1.4	<2	0.82	<0.5	13	59	34	4.07	10	3.37	20	1.04	469
UGA-26	70.00	71.00	1.00	M299023	2.95		10.1	4.97	469	180	1.4	<2	0.36	0.5	14	56	32	3.1	10	1.98	20	0.29	233
UGA-26	71.00	72.00	1.00	M299024	0.8		16.3	4.72	118	550	1	<2	1.14	<0.5	13	60	19	3.99	10	3.62	20	0.71	433
UGA-26	72.00	73.00	1.00	M299025	0.89		8.9	5.47	422	570	1	<2	1.44	<0.5	14	58	39	4.04	10	3.9	20	1.58	256
UGA-26	73.00	74.00	1.00	M299026	0.82		10	5.73	578	650	1	<2	1.63	<0.5	15	55	43	3.76	10	4.25	20	1.84	283
UGA-26	74.00	75.00	1.00	M299027	0.76		4.6	5.19	488	580	1.1	<2	0.97	<0.5	15	59	37	4.13	10	3.8	20	1.14	520
UGA-26	75.00	76.00	1.00	M299028	0.71		8.8	4.61	523	400	1.1	<2	0.25	<0.5	13	62	65	4.39	10	2.93	20	0.27	484
UGA-26	76.00	77.00	1.00	M299029	0.71		8	4.88	252	570	1.2	<2	0.64	<0.5	13	54	18	4.52	10	3.6	20	0.63	1010
UGA-26	77.00	78.00	1.00	M299031	0.63		3.8	4.53	350	160	1.7	<2	0.62	<0.5	12	57	22	4.12	10	1.32	20	0.19	380
UGA-26	78.00	79.00	1.00	M299032	5.95		>100	2.29	481	20	1	<2	0.38	0.8	6	78	51	3.51	10	0.34	10	0.16	258
UGA-26	79.00	80.00	1.00	M299034	0.22		2.3	5.18	151	50	1.3	<2	0.29	<0.5	14	45	17	4.52	10	1.79	20	0.6	943
UGA-26	80.00	81.00	1.00	M299035	0.21		2.7	5.05	196	60	1.5	<2	0.31	<0.5	13	41	24	4.85	10	1.82	20	0.56	952
UGA-26	81.00	82.00	1.00	M299036	0.13		4	5.85	195	80	1.8	<2	0.28	<0.5	16	39	20	4.54	10	2.25	20	0.55	544
UGA-26	82.00	83.00	1.00	M299037	0.15		5.1	5.1	103	70	1.6	<2	0.28	<0.5	13	33	17	3.49	10	1.94	20	0.47	229
UGA-26	83.00	84.00	1.00	M299038	0.16		4.2	5.04	103	60	1.4	<2	0.47	<0.5	13	39	18	3.43	10	1.84	20	0.58	398
UGA-26	84.00	85.00	1.00	M299039	1.42		4.8	2.74	133	30	0.9	<2	0.2	<0.5	7	46	10	2.19	10	1	10	0.23	127
UGA-26	85.00	86.00	1.00	M299040	0.79		6.7	3.17	152	40	0.9	<2	0.23	<0.5	8	47	13	2.5	10	1.19	10	0.29	121
UGA-26	86.00	87.00	1.00	M299041	0.8		3	3.6	132	50	1	<2	0.74	<0.5	9	42	12	2.83	10	1.4	10	0.52	220
UGA-26	87.00	88.00	1.00	M299042	0.83		2.7	3.19	109	90	1.3	<2	0.51	<0.5	8	25	9	2.33	10	1.2	10	0.34	123
UGA-26	88.00	89.00	1.00	M299044	0.15		0.5	7.04	90	200	1.4	<2	1.98	<0.5	19	25	27	4.45	10	2.45	20	1.66	756
UGA-26	89.00	90.00	1.00	M299045	0.01		<0.5	8.28	40	220	1.5	<2	3.03	<0.5	21	38	29	4.91	20	2.62	20	2.25	1050
UGA-26	90.00	91.00	1.00	M299046	0.02		<0.5	9.37	61	290	2.1	<2	2.11	<0.5	21	24	29	4.98	20	3.59	20	1.68	682
UGA-26	91.00	92.00	1.00	M299047	0.4		<0.5	7.67	49	250	1.4	<2	2.89	<0.5	15	17	23	4.56	20	2.41	20	2.41	1190
UGA-26	92.00	93.00	1.00	M299048	0.01		<0.5	7.51	29	300	1.5	<2	2.8	<0.5	15	13	18	4.31	20	2.37	20	2.26	1035
UGA-26	93.00	94.00	1.00	M299049	0.01		<0.5	7.28	20	280	1.4	<2	3.66	<0.5	14	15	21	4.13	20	2.2	20	2.35	1110
UGA-26	94.00	95.00	1.00	M299051	0.02		0.7	7.75	55	290	1.5	<2	3.19	<0.5	18	17	35	4.53	20	2.55	20	2.19	994
UGA-26	95.00	96.00	1.00	M299052	0.03		<0.5	8.91	71	310	1.9	<2	2.48	<0.5	24	25	57	5.18	20	3.33	20	1.78	811
UGA-25	32.00	33.00	1.00	M298810	0.06		0.8	6.49	1610	290	1.9	2	2.2	<0.5	21	64	38	4.64	10	3.61	20	0.38	294
UGA-25	33.00	34.00	1.00	M298811	0.1		1	6.83	103	410	1.4	2	0.31	<0.5	20	70	32	4.45	10	4.02	20	0.84	859
UGA-25	34.00	35.00	1.00	M298812	0.46		4.9	6.75	115	440	1.3	<2	0.31	<0.5	16	75	35	3.64	10	4.35	20	0.49	598

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-26	49.00	50.00	1.00	3	0.03	4	870	9	3.42	24	14	182	<20	0.27	10	<10	106	10	73			
UGA-26	50.00	51.00	1.00	6	0.04	9	1070	6	4.05	40	13	135	<20	0.27	10	<10	90	10	53			
UGA-26	51.00	52.00	1.00	8	0.04	12	1990	11	4.5	49	15	69	<20	0.31	10	<10	114	<10	48			
UGA-26	52.00	53.00	1.00	2	0.06	9	1040	8	4.61	32	17	106	<20	0.33	10	<10	113	<10	52			
UGA-26	53.00	54.00	1.00	2	0.04	12	1080	6	4.88	28	19	105	<20	0.35	10	<10	127	<10	73			
UGA-26	54.00	55.00	1.00	3	0.04	11	1120	8	4.5	26	20	171	<20	0.38	10	<10	145	10	73			
UGA-26	55.00	56.00	1.00	4	0.04	8	770	7	3.91	41	12	115	<20	0.24	10	<10	88	10	46			
UGA-26	56.00	57.00	1.00	4	0.02	4	550	48	2.96	127	7	67	<20	0.14	10	<10	57	10	145	136		
UGA-26	57.00	58.00	1.00	2	0.09	9	1040	7	3.22	23	16	169	<20	0.33	10	<10	122	<10	44			
UGA-26	58.00	59.00	1.00	21	0.09	7	900	77	3.35	71	15	120	<20	0.32	<10	<10	132	<10	151			
UGA-26	59.00	60.00	1.00	4	0.1	7	970	44	3.44	57	15	108	<20	0.32	10	<10	116	10	125			
UGA-26	60.00	61.00	1.00	2	0.09	9	1020	8	3.13	28	17	110	<20	0.33	10	<10	122	<10	48			
UGA-26	61.00	62.00	1.00	2	0.04	13	860	5	2.48	28	16	93	<20	0.3	10	<10	105	<10	49			
UGA-26	62.00	63.00	1.00	4	0.04	11	990	5	2.88	46	14	105	<20	0.26	10	<10	78	<10	44			
UGA-26	63.00	64.00	1.00	4	0.03	9	800	5	2.5	78	9	77	<20	0.17	10	<10	50	10	31			
UGA-26	64.00	65.00	1.00	4	0.04	13	980	9	4	34	14	102	<20	0.27	10	<10	94	10	55			
UGA-26	65.00	66.00	1.00	4	0.03	14	830	12	4.14	26	15	78	<20	0.29	10	<10	110	10	72			
UGA-26	66.00	67.00	1.00	2	0.03	9	780	10	3.73	30	15	102	<20	0.27	10	<10	97	<10	79			
UGA-26	67.00	68.00	1.00	3	0.03	10	860	8	3.84	19	15	112	<20	0.29	10	<10	103	10	57			
UGA-26	68.00	69.00	1.00	6	0.03	9	980	11	3.44	57	12	71	<20	0.22	10	10	87	<10	47			
UGA-26	69.00	70.00	1.00	7	0.04	12	1480	5	2.91	64	12	69	<20	0.23	<10	<10	93	<10	57			
UGA-26	70.00	71.00	1.00	29	0.02	13	1460	18	2.79	69	12	37	<20	0.25	<10	<10	119	<10	78			
UGA-26	71.00	72.00	1.00	4	0.06	10	850	8	3.54	46	13	90	<20	0.24	<10	<10	89	<10	40			
UGA-26	72.00	73.00	1.00	5	0.1	8	1100	10	3.26	41	16	107	<20	0.28	<10	<10	115	<10	51			
UGA-26	73.00	74.00	1.00	2	0.1	11	880	8	2.95	36	16	127	<20	0.3	10	10	118	<10	52			
UGA-26	74.00	75.00	1.00	3	0.09	10	910	10	3.21	46	15	102	<20	0.28	<10	<10	108	<10	62			
UGA-26	75.00	76.00	1.00	4	0.03	10	890	10	3.79	56	13	46	<20	0.25	<10	<10	88	<10	56			
UGA-26	76.00	77.00	1.00	3	0.03	12	950	6	2.95	39	14	61	<20	0.25	<10	10	100	<10	56			
UGA-26	77.00	78.00	1.00	5	0.02	12	2540	7	3.28	96	11	35	<20	0.23	<10	10	87	<10	58			
UGA-26	78.00	79.00	1.00	19	0.01	8	1330	55	2.63	171	6	23	<20	0.1	<10	<10	43	<10	115	133		
UGA-26	79.00	80.00	1.00	3	0.01	9	950	8	3.52	32	14	12	<20	0.27	<10	<10	103	<10	62			
UGA-26	80.00	81.00	1.00	3	0.01	11	980	7	3.84	35	13	12	<20	0.26	<10	<10	99	<10	56			
UGA-26	81.00	82.00	1.00	3	0.01	10	900	8	3.98	29	15	13	<20	0.3	<10	<10	112	<10	65			
UGA-26	82.00	83.00	1.00	2	0.01	8	960	7	3.41	44	13	11	<20	0.26	<10	<10	103	<10	57			
UGA-26	83.00	84.00	1.00	3	0.01	9	840	5	3.08	43	13	15	<20	0.26	<10	10	99	<10	50			
UGA-26	84.00	85.00	1.00	13	0.01	6	720	3	1.8	72	7	15	<20	0.13	<10	10	55	<10	22			
UGA-26	85.00	86.00	1.00	6	0.01	7	650	5	2.25	60	8	13	<20	0.15	<10	<10	62	<10	31			
UGA-26	86.00	87.00	1.00	19	0.01	7	1200	3	2.53	66	10	21	<20	0.18	<10	<10	77	<10	34			
UGA-26	87.00	88.00	1.00	23	0.02	4	1290	8	2.22	102	9	18	<20	0.17	<10	<10	66	<10	58			
UGA-26	88.00	89.00	1.00	3	0.02	9	820	7	2.39	20	21	45	<20	0.39	<10	10	147	<10	93			
UGA-26	89.00	90.00	1.00	<1	0.02	10	880	5	2.16	13	24	51	<20	0.46	<10	<10	146	<10	64			
UGA-26	90.00	91.00	1.00	<1	0.03	10	810	11	3.64	15	22	52	<20	0.48	<10	<10	145	<10	79			
UGA-26	91.00	92.00	1.00	<1	0.03	6	770	6	0.66	10	20	65	<20	0.42	<10	<10	139	<10	72			
UGA-26	92.00	93.00	1.00	<1	0.05	4	790	6	0.29	8	19	70	<20	0.42	<10	10	130	<10	75			
UGA-26	93.00	94.00	1.00	1	0.07	2	770	5	0.22	10	18	87	<20	0.41	<10	<10	133	<10	79			
UGA-26	94.00	95.00	1.00	<1	0.04	4	900	11	1.46	11	21	100	<20	0.46	<10	<10	163	<10	74			
UGA-26	95.00	96.00	1.00	<1	0.03	8	700	18	3.09	15	26	63	<20	0.46	<10	10	163	<10	95			
UGA-25	32.00	33.00	1.00	2	0.04	17	9030	11	4	72	18	91	<20	0.34	20	<10	123	<10	62			
UGA-25	33.00	34.00	1.00	4	0.03	18	1100	9	1.84	21	20	84	<20	0.35	<10	<10	138	10	83			
UGA-25	34.00	35.00	1.00	10	0.04	13	1110	9	1.91	30	19	79	<20	0.35	10	<10	131	10	64			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-26	49.00	50.00	1.00							
UGA-26	50.00	51.00	1.00							
UGA-26	51.00	52.00	1.00							
UGA-26	52.00	53.00	1.00							
UGA-26	53.00	54.00	1.00							
UGA-26	54.00	55.00	1.00							
UGA-26	55.00	56.00	1.00							
UGA-26	56.00	57.00	1.00							
UGA-26	57.00	58.00	1.00							
UGA-26	58.00	59.00	1.00							
UGA-26	59.00	60.00	1.00							
UGA-26	60.00	61.00	1.00							
UGA-26	61.00	62.00	1.00							
UGA-26	62.00	63.00	1.00							
UGA-26	63.00	64.00	1.00							
UGA-26	64.00	65.00	1.00							
UGA-26	65.00	66.00	1.00							
UGA-26	66.00	67.00	1.00							
UGA-26	67.00	68.00	1.00							
UGA-26	68.00	69.00	1.00							
UGA-26	69.00	70.00	1.00							
UGA-26	70.00	71.00	1.00							
UGA-26	71.00	72.00	1.00							
UGA-26	72.00	73.00	1.00							
UGA-26	73.00	74.00	1.00							
UGA-26	74.00	75.00	1.00							
UGA-26	75.00	76.00	1.00							
UGA-26	76.00	77.00	1.00							
UGA-26	77.00	78.00	1.00							
UGA-26	78.00	79.00	1.00							
UGA-26	79.00	80.00	1.00							
UGA-26	80.00	81.00	1.00							
UGA-26	81.00	82.00	1.00							
UGA-26	82.00	83.00	1.00							
UGA-26	83.00	84.00	1.00							
UGA-26	84.00	85.00	1.00							
UGA-26	85.00	86.00	1.00							
UGA-26	86.00	87.00	1.00							
UGA-26	87.00	88.00	1.00							
UGA-26	88.00	89.00	1.00							
UGA-26	89.00	90.00	1.00							
UGA-26	90.00	91.00	1.00							
UGA-26	91.00	92.00	1.00							
UGA-26	92.00	93.00	1.00							
UGA-26	93.00	94.00	1.00							
UGA-26	94.00	95.00	1.00							
UGA-26	95.00	96.00	1.00							
UGA-25	32.00	33.00	1.00							
UGA-25	33.00	34.00	1.00							
UGA-25	34.00	35.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-25	35.00	36.00	1.00	M298813	0.17		1.3	6.2	280	530	1.4	<2	0.35	<0.5	17	67	32	4.63	10	4.11	20	0.49	513
UGA-25	36.00	37.00	1.00	M298814	0.08		0.9	6.44	181	520	1.4	<2	0.57	<0.5	16	65	35	5.03	10	3.64	20	0.57	1005
UGA-25	37.00	38.00	1.00	M298815	0.11		1.2	6.77	130	480	1.4	<2	0.43	<0.5	18	79	28	3.16	10	4.38	20	0.34	377
UGA-25	38.00	39.00	1.00	M298816	0.32		1.4	6.45	183	400	1.2	<2	0.37	<0.5	18	76	33	3.35	10	4.45	20	0.27	328
UGA-25	39.00	40.00	1.00	M298818	0.2		3.4	6.43	457	390	1.5	<2	1	<0.5	16	67	42	3.42	10	3.97	20	0.28	84
UGA-25	40.00	41.00	1.00	M298819	0.17		1.6	6.51	183	470	1.4	<2	0.39	<0.5	18	66	29	4.52	10	4.23	30	0.67	878
UGA-25	41.00	42.00	1.00	M298821	0.13		1.2	6.54	149	460	1.4	<2	0.43	<0.5	22	72	31	6.64	10	4.08	20	0.8	2210
UGA-25	42.00	43.00	1.00	M298822	1.32		5.2	6.41	124	690	1.3	2	0.37	<0.5	21	68	30	5.35	10	4.19	20	0.62	1535
UGA-25	43.00	44.00	1.00	M298823	0.24		1.6	6.02	167	670	1.1	<2	0.5	<0.5	19	63	27	4.92	10	3.32	20	0.84	924
UGA-25	44.00	45.00	1.00	M298824	0.1		1.1	6.83	150	610	1.2	2	0.95	<0.5	18	66	34	5.56	10	4.31	20	1.42	940
UGA-25	45.00	46.00	1.00	M298825	0.15		1.5	6.19	154	720	1	3	0.54	<0.5	19	61	29	5.08	10	3.6	20	1.17	732
UGA-25	46.00	47.00	1.00	M298826	1.96		29.6	6	157	690	0.9	<2	0.68	<0.5	18	60	37	4.6	10	3.79	20	1.09	583
UGA-25	47.00	48.00	1.00	M298827	0.28		1.7	6.16	145	620	1	<2	1.65	<0.5	18	59	27	4.56	10	3.73	20	1.42	580
UGA-25	48.00	49.00	1.00	M298828	0.08		1	6.37	95	470	1.3	<2	2.45	<0.5	20	58	33	5.33	10	3.89	20	1.95	813
UGA-25	49.00	50.00	1.00	M298829	0.06		0.6	6.58	67	350	1.4	<2	0.42	<0.5	20	65	29	4.95	10	4.2	20	0.9	1225
UGA-25	50.00	51.00	1.00	M298830	0.09		0.8	7.1	128	490	1.6	<2	0.46	<0.5	20	70	39	2.82	10	4.24	20	0.39	193
UGA-25	51.00	52.00	1.00	M298831	0.09		0.8	7.58	84	380	1.4	<2	0.37	<0.5	19	76	37	2.99	10	3.61	20	0.64	389
UGA-25	52.00	53.00	1.00	M298832	0.07		0.6	6.7	110	340	1.5	<2	0.36	<0.5	22	71	34	5.76	20	3.62	20	0.88	1640
UGA-25	53.00	54.00	1.00	M298833	0.04		<0.5	6.95	86	290	1.7	<2	0.98	<0.5	24	66	35	6.95	10	3.9	30	1.17	1360
UGA-25	54.00	55.00	1.00	M298834	0.06		1.5	6.8	158	270	1.7	<2	1.26	<0.5	27	65	37	7.68	10	3.94	20	1.37	1710
UGA-25	55.00	56.00	1.00	M298835	0.12		1.3	7.22	120	520	1.6	2	0.35	<0.5	22	73	35	5.71	10	3.85	20	0.66	1270
UGA-25	56.00	57.00	1.00	M298836	0.17		2.1	6.73	212	410	1.2	<2	0.34	<0.5	19	75	31	4.21	10	3.68	20	0.36	71
UGA-25	57.00	58.00	1.00	M298837	0.19		6.9	6.6	456	310	1.3	2	0.51	<0.5	20	71	29	4.32	10	3.69	20	0.31	99
UGA-25	58.00	59.00	1.00	M298838	0.08		1.9	6.15	89	350	1.4	<2	0.28	<0.5	17	64	25	4.51	10	3.54	20	0.66	801
UGA-25	59.00	60.00	1.00	M298839	0.06		1	6.79	91	370	1.2	<2	0.49	<0.5	21	77	29	4.67	10	3.47	20	1.14	712
UGA-25	60.00	61.00	1.00	M298841	0.04		1.1	7.28	46	560	1.2	<2	0.9	<0.5	23	71	37	4.84	10	3.9	20	1.38	738
UGA-25	61.00	62.00	1.00	M298842	0.07		1.5	6.83	76	470	1.2	<2	1.19	<0.5	21	72	28	5.12	10	3.61	20	1.21	436
UGA-25	62.00	63.00	1.00	M298843	0.14		1.9	7.1	183	450	1.3	<2	1.19	<0.5	20	69	31	4.85	10	4.27	30	1.3	403
UGA-25	63.00	64.00	1.00	M298844	0.03		0.8	7.65	48	490	1.6	<2	1.17	<0.5	19	80	39	4.95	20	4	20	1.86	756
UGA-25	64.00	65.00	1.00	M298845	0.04		0.7	6.47	57	300	1.1	4	1.44	<0.5	19	76	34	4.02	10	4.12	30	2.08	542
UGA-25	65.00	66.00	1.00	M298846	0.04		1.5	6.6	43	650	1.1	2	1.1	<0.5	20	69	37	4.05	10	3.88	30	1.31	397
UGA-25	66.00	67.00	1.00	M298847	0.06		1.5	6.49	66	610	1.2	<2	1.66	<0.5	19	71	32	5.31	10	3.72	20	2.29	773
UGA-25	67.00	68.00	1.00	M298848	0.05		1.3	6.65	66	570	1.2	3	1.04	<0.5	20	74	31	5.3	10	3.78	20	2.15	826
UGA-25	68.00	69.00	1.00	M298849	0.04		1.5	6.85	85	540	1.4	3	0.9	<0.5	18	74	31	4.58	10	3.93	30	1.69	640
UGA-25	69.00	70.00	1.00	M298851	0.12		1.1	6.07	127	740	1.5	3	0.77	<0.5	18	68	27	5.02	10	3.51	20	1.47	859
UGA-25	70.00	71.00	1.00	M298852	0.23		1.4	6.25	114	600	1.7	<2	0.38	<0.5	20	69	30	5.97	10	3.59	20	1.26	1360
UGA-25	71.00	72.00	1.00	M298853	0.06		1.3	6.5	87	130	1.7	5	0.36	<0.5	19	74	33	4.52	10	3.91	30	1.08	971
UGA-25	72.00	73.00	1.00	M298854	0.07		1.5	6.21	103	320	1.8	2	0.35	<0.5	21	74	27	5.47	10	3.79	20	0.72	1635
UGA-25	73.00	74.00	1.00	M298856	0.1		1.7	6.27	126	510	1.7	<2	0.37	<0.5	21	70	27	6.02	10	3.7	20	0.83	1525
UGA-25	74.00	75.00	1.00	M298857	0.1		1.8	5.89	109	470	1.6	<2	0.36	<0.5	17	71	25	3.86	10	4	20	0.63	578
UGA-25	75.00	76.00	1.00	M298858	0.16		1.8	6.31	163	510	1.9	<2	0.41	<0.5	18	71	29	5.5	10	4	20	0.79	1860
UGA-25	76.00	77.00	1.00	M298859	0.45		2.5	6.09	232	430	1.7	3	0.44	<0.5	17	75	24	3.44	10	3.82	20	0.47	523
UGA-25	77.00	78.00	1.00	M298860	0.32		3	5.77	148	310	1.7	<2	0.42	<0.5	18	75	30	4.04	10	3.58	20	0.59	673
UGA-25	78.00	79.00	1.00	M298862	0.1		1.5	6.83	53	280	1.6	<2	0.56	<0.5	21	81	38	4.3	10	4.19	20	1.52	704
UGA-25	79.00	80.00	1.00	M298863	0.08		1.6	6.72	101	370	1.7	<2	0.41	<0.5	21	71	34	4.79	10	3.9	20	1.24	660
UGA-25	80.00	81.00	1.00	M298864	0.08		1.4	6.01	113	250	1.5	<2	0.37	<0.5	18	76	30	4.51	10	3.48	20	1.3	640
UGA-25	81.00	82.00	1.00	M298865	0.05		1.2	6.95	85	290	1.5	<2	0.38	<0.5	19	76	43	5.53	20	4.07	30	1.54	942
UGA-25	82.00	83.00	1.00	M298866	0.07		1.4	6.54	93	280	1.3	2	0.33	<0.5	19	73	34	4.7	10	3.77	20	1.69	713
UGA-25	83.00	84.00	1.00	M298867	0.33		1.7	6.74	205	360	1.2	<2	0.41	<0.5	20	69	43	5.13	20	4.15	30	2.1	722
UGA-25	84.00	85.00	1.00	M298868	0.09		1.6	6.52	202	490	1.1	4	0.41	<0.5	20	66	32	5.27	10	3.75	20	1.58	662

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-25	35.00	36.00	1.00	5	0.03	11	1220	11	3.09	31	19	67	<20	0.31	10	<10	<10	135	<10	59		
UGA-25	36.00	37.00	1.00	2	0.03	13	2090	6	2.9	28	19	76	<20	0.34	<10	<10	<10	141	<10	68		
UGA-25	37.00	38.00	1.00	3	0.04	11	1660	10	2.14	26	19	82	<20	0.36	<10	<10	<10	133	<10	47		
UGA-25	38.00	39.00	1.00	5	0.04	12	1420	8	2.71	33	18	77	<20	0.34	10	<10	<10	134	<10	48		
UGA-25	39.00	40.00	1.00	15	0.04	13	4040	11	3.31	57	19	102	<20	0.33	10	<10	<10	144	<10	74		
UGA-25	40.00	41.00	1.00	4	0.04	17	1280	10	2.52	27	20	107	<20	0.34	10	<10	<10	137	<10	82		
UGA-25	41.00	42.00	1.00	3	0.05	14	1180	11	2.54	25	20	113	<20	0.35	10	<10	<10	136	<10	90		
UGA-25	42.00	43.00	1.00	2	0.04	16	1060	11	2.44	27	20	117	<20	0.34	<10	<10	<10	130	<10	76		
UGA-25	43.00	44.00	1.00	4	0.04	14	950	11	2.62	20	18	106	<20	0.32	<10	<10	<10	126	<10	71		
UGA-25	44.00	45.00	1.00	1	0.04	17	1010	9	2.51	18	21	127	<20	0.35	10	<10	<10	141	<10	75		
UGA-25	45.00	46.00	1.00	1	0.04	14	910	10	2.31	18	19	123	<20	0.33	10	<10	<10	129	<10	71		
UGA-25	46.00	47.00	1.00	6	0.03	14	990	9	2.34	30	19	123	<20	0.31	<10	<10	<10	123	<10	66		
UGA-25	47.00	48.00	1.00	2	0.03	14	910	12	2.58	16	19	135	<20	0.32	<10	<10	<10	124	<10	49		
UGA-25	48.00	49.00	1.00	1	0.03	15	940	10	2.56	16	19	104	<20	0.33	<10	<10	<10	133	<10	64		
UGA-25	49.00	50.00	1.00	1	0.03	13	1050	7	2.1	23	20	59	<20	0.34	<10	<10	<10	153	10	73		
UGA-25	50.00	51.00	1.00	4	0.04	11	1790	9	2.44	21	20	68	<20	0.37	10	<10	<10	146	10	67		
UGA-25	51.00	52.00	1.00	3	0.04	15	1450	5	1.91	22	22	67	<20	0.41	<10	<10	<10	158	10	101		
UGA-25	52.00	53.00	1.00	3	0.04	18	1180	9	2.7	23	20	61	<20	0.37	<10	<10	<10	145	<10	106		
UGA-25	53.00	54.00	1.00	1	0.03	19	950	8	4.12	15	22	58	<20	0.35	<10	<10	<10	155	10	81		
UGA-25	54.00	55.00	1.00	1	0.03	21	1070	14	4.1	24	22	62	<20	0.36	<10	<10	<10	150	20	78		
UGA-25	55.00	56.00	1.00	2	0.05	15	1110	13	3.77	18	22	88	<20	0.38	<10	<10	<10	146	<10	104		
UGA-25	56.00	57.00	1.00	3	0.04	14	1320	13	4.4	31	21	91	<20	0.35	10	<10	<10	153	<10	68		
UGA-25	57.00	58.00	1.00	4	0.06	15	2020	10	4.47	50	19	105	<20	0.35	10	<10	<10	123	<10	55		
UGA-25	58.00	59.00	1.00	2	0.04	13	900	10	3.15	16	19	60	<20	0.32	10	<10	<10	119	10	90		
UGA-25	59.00	60.00	1.00	1	0.04	16	970	11	2.94	16	21	62	<20	0.37	10	<10	<10	139	<10	79		
UGA-25	60.00	61.00	1.00	1	0.04	15	1040	9	2.88	16	21	78	<20	0.37	10	<10	<10	137	10	66		
UGA-25	61.00	62.00	1.00	2	0.05	16	1040	12	3.95	18	21	87	<20	0.35	<10	<10	<10	135	10	51		
UGA-25	62.00	63.00	1.00	7	0.03	16	1760	17	3.58	28	22	69	<20	0.37	<10	<10	<10	152	10	59		
UGA-25	63.00	64.00	1.00	1	0.06	16	1090	12	1.53	15	24	74	<20	0.41	<10	<10	<10	162	10	77		
UGA-25	64.00	65.00	1.00	2	0.01	14	970	9	1.83	22	20	98	<20	0.36	10	<10	<10	133	<10	64		
UGA-25	65.00	66.00	1.00	3	<0.01	13	1110	14	2.62	20	21	86	<20	0.38	<10	<10	<10	135	<10	50		
UGA-25	66.00	67.00	1.00	5	<0.01	15	1140	12	1.85	19	21	94	<20	0.36	<10	<10	<10	144	<10	73		
UGA-25	67.00	68.00	1.00	2	<0.01	17	1040	9	1.7	16	21	87	<20	0.37	10	<10	<10	145	<10	74		
UGA-25	68.00	69.00	1.00	2	<0.01	15	1110	7	1.92	16	20	82	<20	0.38	<10	<10	<10	140	<10	75		
UGA-25	69.00	70.00	1.00	2	<0.01	14	990	10	2.05	21	19	93	<20	0.34	<10	<10	<10	130	<10	53		
UGA-25	70.00	71.00	1.00	2	<0.01	15	1010	12	2.11	22	19	90	<20	0.35	<10	<10	<10	134	<10	63		
UGA-25	71.00	72.00	1.00	2	0.02	14	1050	7	1.63	28	20	40	<20	0.36	<10	<10	<10	137	<10	81		
UGA-25	72.00	73.00	1.00	3	<0.01	16	1000	10	2.04	27	19	55	<20	0.35	10	<10	<10	134	<10	62		
UGA-25	73.00	74.00	1.00	2	<0.01	18	1040	10	2.46	25	20	63	<20	0.35	<10	<10	<10	132	<10	61		
UGA-25	74.00	75.00	1.00	4	<0.01	12	1180	10	2.23	27	18	65	<20	0.33	<10	<10	<10	134	<10	67		
UGA-25	75.00	76.00	1.00	3	<0.01	14	1270	10	2.11	30	21	87	<20	0.35	10	<10	<10	139	<10	61		
UGA-25	76.00	77.00	1.00	16	<0.01	15	1680	11	2.43	39	18	76	<20	0.34	10	<10	<10	136	<10	64		
UGA-25	77.00	78.00	1.00	7	<0.01	14	1370	13	2.5	38	18	56	<20	0.32	10	<10	<10	133	<10	54		
UGA-25	78.00	79.00	1.00	4	0.01	20	1420	7	1.7	30	21	52	<20	0.38	<10	<10	<10	140	<10	75		
UGA-25	79.00	80.00	1.00	2	<0.01	16	1400	13	2.55	28	20	50	<20	0.38	10	<10	<10	150	<10	64		
UGA-25	80.00	81.00	1.00	3	0.01	14	1270	8	2.07	28	19	38	<20	0.33	<10	<10	<10	131	<10	60		
UGA-25	81.00	82.00	1.00	2	<0.01	17	1190	10	2.26	22	21	43	<20	0.38	<10	<10	<10	147	<10	68		
UGA-25	82.00	83.00	1.00	3	0.01	16	1120	11	1.8	26	20	47	<20	0.37	<10	<10	<10	139	<10	63		
UGA-25	83.00	84.00	1.00	4	0.01	18	1560	12	1.85	29	21	68	<20	0.37	10	<10	<10	140	<10	70		
UGA-25	84.00	85.00	1.00	2	<0.01	16	1040	9	2.83	24	20	69	<20	0.36	10	<10	<10	140	<10	57		

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-25	35.00	36.00	1.00							
UGA-25	36.00	37.00	1.00							
UGA-25	37.00	38.00	1.00							
UGA-25	38.00	39.00	1.00							
UGA-25	39.00	40.00	1.00							
UGA-25	40.00	41.00	1.00							
UGA-25	41.00	42.00	1.00							
UGA-25	42.00	43.00	1.00							
UGA-25	43.00	44.00	1.00							
UGA-25	44.00	45.00	1.00							
UGA-25	45.00	46.00	1.00							
UGA-25	46.00	47.00	1.00							
UGA-25	47.00	48.00	1.00							
UGA-25	48.00	49.00	1.00							
UGA-25	49.00	50.00	1.00							
UGA-25	50.00	51.00	1.00							
UGA-25	51.00	52.00	1.00							
UGA-25	52.00	53.00	1.00							
UGA-25	53.00	54.00	1.00							
UGA-25	54.00	55.00	1.00							
UGA-25	55.00	56.00	1.00							
UGA-25	56.00	57.00	1.00							
UGA-25	57.00	58.00	1.00							
UGA-25	58.00	59.00	1.00							
UGA-25	59.00	60.00	1.00							
UGA-25	60.00	61.00	1.00							
UGA-25	61.00	62.00	1.00							
UGA-25	62.00	63.00	1.00							
UGA-25	63.00	64.00	1.00							
UGA-25	64.00	65.00	1.00							
UGA-25	65.00	66.00	1.00							
UGA-25	66.00	67.00	1.00							
UGA-25	67.00	68.00	1.00							
UGA-25	68.00	69.00	1.00							
UGA-25	69.00	70.00	1.00							
UGA-25	70.00	71.00	1.00							
UGA-25	71.00	72.00	1.00							
UGA-25	72.00	73.00	1.00							
UGA-25	73.00	74.00	1.00							
UGA-25	74.00	75.00	1.00							
UGA-25	75.00	76.00	1.00							
UGA-25	76.00	77.00	1.00							
UGA-25	77.00	78.00	1.00							
UGA-25	78.00	79.00	1.00							
UGA-25	79.00	80.00	1.00							
UGA-25	80.00	81.00	1.00							
UGA-25	81.00	82.00	1.00							
UGA-25	82.00	83.00	1.00							
UGA-25	83.00	84.00	1.00							
UGA-25	84.00	85.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
					ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-25	85.00	86.00	1.00	M298869	0.04		1.3	6.26	56	270	1	<2	0.48	<0.5	17	67	32	4.44	10	3.74	20	1.58	608
UGA-25	86.00	87.00	1.00	M298870	0.08		1.7	6.5	81	350	1.1	<2	0.37	<0.5	19	68	32	4.76	10	4.09	20	1.61	559
UGA-25	87.00	88.00	1.00	M298871	0.16		1.9	5.85	138	340	1.1	2	0.49	<0.5	17	66	34	4.22	10	3.49	20	1.48	492
UGA-25	88.00	89.00	1.00	M298872	0.05		1.4	5.92	99	200	1.2	<2	0.62	<0.5	18	69	31	4.81	10	3.11	20	1.56	569
UGA-25	89.00	90.00	1.00	M298873	0.06		1.3	6.7	115	260	1.3	<2	0.73	<0.5	24	68	37	5.99	10	3.87	20	1.55	965
UGA-25	90.00	91.00	1.00	M298874	0.08		1.5	6.34	129	270	1.5	<2	0.61	<0.5	23	71	30	6.29	10	3.81	20	1.25	1210
UGA-25	91.00	92.00	1.00	M298875	0.1		1.8	6.63	60	340	1.5	2	0.3	<0.5	18	76	39	2.78	10	3.93	20	0.6	311
UGA-25	92.00	93.00	1.00	M298876	0.09		1.9	6.25	183	340	1.6	2	0.3	<0.5	18	68	34	3.85	10	3.68	20	0.58	516
UGA-25	93.00	94.00	1.00	M298877	0.05		1.8	6.64	71	430	1.9	3	0.36	<0.5	19	71	36	5.27	10	3.82	20	0.96	1180
UGA-25	94.00	95.00	1.00	M298878	0.1		2.4	6.21	198	400	2	2	0.35	<0.5	19	67	29	4.44	10	3.84	20	0.69	873
UGA-25	95.00	96.00	1.00	M298879	0.62		18.8	3.81	502	100	1.5	<2	0.36	<0.5	13	70	29	4.63	10	1.91	20	0.41	156
UGA-25	96.00	97.00	1.00	M298881	0.37		5.9	4.13	394	230	1.2	<2	0.46	<0.5	13	62	24	4.21	10	2.59	10	0.37	68
UGA-25	97.00	98.00	1.00	M298882	0.37		3.7	4.54	899	410	1.7	<2	1.82	<0.5	13	52	16	5.22	10	4.81	20	0.1	81
UGA-25	98.00	99.00	1.00	M298883	0.25		3.2	4.69	176	440	0.8	<2	0.6	<0.5	12	52	17	3.84	10	4.24	10	0.1	205
UGA-25	99.00	100.00	1.00	M298885	0.47		5	4.78	284	470	0.9	<2	0.61	<0.5	13	57	23	4.45	10	3.99	20	0.11	491
UGA-25	100.00	101.00	1.00	M298886	0.32		3.6	4.77	240	430	0.8	<2	0.43	<0.5	13	70	20	3.79	10	4.06	20	0.08	159
UGA-25	101.00	102.00	1.00	M298887	0.19		2.3	4.02	539	540	0.7	2	0.28	<0.5	10	64	16	3.84	<10	4.4	10	0.09	141
UGA-25	102.00	103.00	1.00	M298888	0.5		4.2	3.67	806	350	0.6	<2	0.46	<0.5	10	68	14	4.49	<10	4.05	10	0.06	110
UGA-25	103.00	104.00	1.00	M298889	0.36		2.8	5.37	554	320	0.9	<2	0.6	<0.5	17	52	24	4.69	10	4.56	20	0.15	267
UGA-25	104.00	105.00	1.00	M298891	0.58		7.9	6.26	981	350	1.7	<2	0.4	<0.5	21	52	33	5.19	10	3.61	20	0.26	475
UGA-25	105.00	106.00	1.00	M298892	1.44		16.6	6.36	1290	270	1.7	2	0.41	<0.5	18	57	41	5.58	10	4.61	20	0.21	61
UGA-25	106.00	107.00	1.00	M298893	2.46		27.1	5.57	2010	290	1.6	<2	0.44	<0.5	16	58	55	6.47	10	3.75	20	0.16	70
UGA-25	107.00	108.00	1.00	M298894	0.88		15	5.54	1085	350	1.8	2	0.44	<0.5	17	64	32	5.78	10	4.06	20	0.19	81
UGA-25	108.00	109.00	1.00	M298895	0.18		2.4	7.28	385	440	1.7	<2	0.38	<0.5	20	61	35	3.54	10	4.18	30	0.25	50
UGA-25	109.00	110.00	1.00	M298896	0.19		3.4	6.91	322	350	2	2	0.39	<0.5	21	63	33	5.63	10	4.77	20	0.41	446
UGA-25	110.00	111.00	1.00	M298897	0.92		16.8	5.6	1810	250	1.9	<2	0.51	<0.5	16	58	35	7.43	10	4.33	20	0.24	557
UGA-25	111.00	112.00	1.00	M298898	0.57		8.7	6.85	1105	390	1.6	<2	0.89	<0.5	18	52	33	7.72	10	5.51	20	0.54	1600
UGA-25	112.00	113.00	1.00	M298899	0.53		6.3	8.17	1030	650	1.8	<2	0.45	<0.5	22	57	38	4.74	20	5.19	30	0.32	524
UGA-25	113.00	114.00	1.00	M298901	1.32		19.6	7.04	1995	350	1.9	<2	0.84	<0.5	18	59	50	6.23	10	5.08	20	0.27	110
UGA-25	114.00	115.00	1.00	M298902	1.4		16.8	6.62	1810	300	2	<2	0.7	<0.5	17	55	45	6.28	10	5.03	20	0.2	65
UGA-25	115.00	116.00	1.00	M298903	0.94		10.2	7.19	1210	300	1.9	<2	0.53	<0.5	19	65	40	4.83	10	4.46	30	0.24	73
UGA-25	116.00	117.00	1.00	M298904	0.62		7.9	7.32	959	350	1.8	<2	0.51	<0.5	19	57	34	5.27	10	4.58	30	0.31	711
UGA-25	117.00	118.00	1.00	M298905	0.56		7.8	6.57	1035	260	1.4	<2	0.49	<0.5	17	56	29	4.78	10	4.13	20	0.28	58
UGA-25	118.00	119.00	1.00	M298906	0.91		8.1	4.04	3280	200	1.4	<2	1.07	<0.5	15	68	28	8.93	10	2.85	20	0.14	84
UGA-25	119.00	120.00	1.00	M298907	0.83		9	6.23	3370	140	1.8	<2	1.19	<0.5	20	59	35	8.39	10	4.9	20	0.27	61
UGA-25	120.00	121.00	1.00	M298908	1.22		14.6	6.26	2370	560	1.1	<2	0.78	<0.5	17	57	32	6.65	10	5.28	20	0.18	58
UGA-25	121.00	122.00	1.00	M298909	3.97		35.6	3.86	4770	250	0.9	<2	0.66	<0.5	11	65	47	10.6	10	3.82	10	0.1	87
UGA-25	122.00	123.00	1.00	M298911	6.82		51.1	4.26	3200	260	1.4	<2	0.52	<0.5	11	53	84	11.05	10	3.7	10	0.12	236
UGA-25	123.00	124.00	1.00	M298912	2.06		18	6.31	1520	200	1.8	<2	0.44	<0.5	16	57	49	6.18	10	4.09	20	0.25	239
UGA-25	124.00	125.00	1.00	M298913	2.6		19.7	3.51	1505	210	1	<2	1.1	<0.5	9	69	36	5.95	10	3.07	20	0.16	386
UGA-25	125.00	126.00	1.00	M298914	1.55		15.3	5.58	1600	270	1.7	<2	0.68	<0.5	16	65	36	7.24	10	4.71	20	0.25	553
UGA-25	126.00	127.00	1.00	M298915	1		8.7	6.68	1065	380	1.9	<2	0.51	<0.5	18	60	37	5.22	10	3.87	20	0.22	143
UGA-25	127.00	128.00	1.00	M298917	0.17		2.5	7.67	376	630	2.1	<2	0.35	<0.5	19	61	38	3.9	20	3.32	30	0.32	151
UGA-25	128.00	129.00	1.00	M298918	0.18		2.7	7.51	360	560	1.8	<2	0.42	<0.5	22	56	44	5.85	20	3.22	30	1.19	946
UGA-25	129.00	130.00	1.00	M298919	0.03		<0.5	7.8	52	770	1.5	<2	1.84	<0.5	20	47	47	5.11	20	3.21	30	2.4	933
UGA-25	130.00	131.00	1.00	M298920	0.46		15.9	6.7	288	410	1.4	<2	0.42	<0.5	18	60	28	5.26	10	3.15	20	0.98	553
UGA-25	131.00	132.00	1.00	M298921	0.38		5.4	2.36	955	290	1	<2	0.84	<0.5	7	80	17	4.49	10	1.72	10	0.1	153
UGA-25	132.00	133.00	1.00	M298922	0.35		5.8	2.66	696	220	0.8	<2	0.4	<0.5	7	88	17	4.38	10	1.23	10	0.16	159
UGA-25	133.00	134.00	1.00	M298923	0.18		4.4	6.65	414	750	1.4	<2	0.71	<0.5	19	59	30	4.49	10	3.62	20	1.38	518
UGA-25	134.00	135.00	1.00	M298924	0.41		8.8	6.43	511	230	1.2	<2	1.06	<0.5	17	58	31	5.04	10	3.1	20	1.81	301

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
UGA-25	85.00	86.00	1.00	2	0.01	15	1020	8	1.83	21	19	47	<20	0.34	10	<10	126	<10	57			
UGA-25	86.00	87.00	1.00	3	<0.01	15	960	9	2.21	23	20	50	<20	0.36	10	<10	140	<10	59			
UGA-25	87.00	88.00	1.00	5	<0.01	15	1200	11	2.05	31	18	50	<20	0.33	<10	<10	132	<10	60			
UGA-25	88.00	89.00	1.00	2	0.01	16	1210	11	2.29	29	18	41	<20	0.32	<10	<10	125	<10	55			
UGA-25	89.00	90.00	1.00	3	0.01	20	1030	11	2.43	23	21	46	<20	0.36	<10	<10	144	<10	76			
UGA-25	90.00	91.00	1.00	4	0.01	16	1090	10	2.52	29	20	42	<20	0.34	<10	<10	136	<10	77			
UGA-25	91.00	92.00	1.00	4	0.01	16	1190	7	1.87	36	20	56	<20	0.36	<10	<10	148	<10	84			
UGA-25	92.00	93.00	1.00	6	<0.01	16	1080	11	2.82	39	18	50	<20	0.35	10	<10	136	<10	57			
UGA-25	93.00	94.00	1.00	3	<0.01	15	1190	6	2.68	35	21	67	<20	0.37	10	<10	146	<10	74			
UGA-25	94.00	95.00	1.00	5	<0.01	15	1270	8	3.32	43	19	49	<20	0.35	<10	<10	136	<10	81			
UGA-25	95.00	96.00	1.00	18	<0.01	11	1460	12	4.9	90	12	24	<20	0.21	10	<10	81	<10	43			
UGA-25	96.00	97.00	1.00	13	0.02	11	1760	14	4.37	68	12	45	<20	0.21	10	<10	84	<10	53			
UGA-25	97.00	98.00	1.00	17	0.06	8	7630	11	4.43	114	12	149	<20	0.22	20	<10	65	<10	52			
UGA-25	98.00	99.00	1.00	5	0.07	10	2460	8	3.53	42	12	130	<20	0.24	10	<10	64	<10	43			
UGA-25	99.00	100.00	1.00	6	0.07	8	2510	11	3.81	44	14	103	<20	0.24	10	<10	75	<10	45			
UGA-25	100.00	101.00	1.00	5	0.06	11	1780	9	3.69	40	13	103	<20	0.24	<10	<10	67	<10	47			
UGA-25	101.00	102.00	1.00	5	0.05	7	1130	9	3.42	59	7	73	<20	0.18	10	<10	37	<10	37			
UGA-25	102.00	103.00	1.00	7	0.05	8	1890	10	4.23	76	9	88	<20	0.19	10	<10	34	<10	40			
UGA-25	103.00	104.00	1.00	6	0.09	12	2440	10	4.42	49	14	112	<20	0.29	10	<10	66	<10	49			
UGA-25	104.00	105.00	1.00	2	0.09	12	1500	8	4.61	162	18	88	<20	0.34	10	<10	133	<10	44			
UGA-25	105.00	106.00	1.00	5	0.06	14	1670	13	5.66	149	16	82	<20	0.32	20	<10	115	<10	49			
UGA-25	106.00	107.00	1.00	6	0.04	15	1840	12	6	338	15	62	<20	0.27	20	<10	125	<10	41			
UGA-25	107.00	108.00	1.00	7	0.04	12	1840	13	5.36	150	15	58	<20	0.27	20	<10	114	<10	47			
UGA-25	108.00	109.00	1.00	3	0.06	16	1580	14	3.68	37	19	91	<20	0.37	10	<10	152	<10	78			
UGA-25	109.00	110.00	1.00	2	0.07	15	1490	11	4.85	40	19	81	<20	0.35	10	<10	138	<10	60			
UGA-25	110.00	111.00	1.00	4	0.06	13	2000	15	6.81	197	15	78	<20	0.27	10	<10	100	<10	42			
UGA-25	111.00	112.00	1.00	6	0.07	13	3410	12	5.49	114	20	104	<20	0.33	20	<10	137	<10	77			
UGA-25	112.00	113.00	1.00	4	0.09	15	1660	14	4	84	21	105	<20	0.41	10	<10	162	<10	71			
UGA-25	113.00	114.00	1.00	5	0.09	15	3440	14	6.28	213	18	98	<20	0.35	20	<10	136	<10	53			
UGA-25	114.00	115.00	1.00	6	0.07	15	3000	14	6.05	173	17	88	<20	0.32	20	<10	128	<10	55			
UGA-25	115.00	116.00	1.00	4	0.07	16	2200	12	4.6	105	19	76	<20	0.36	10	<10	149	<10	62			
UGA-25	116.00	117.00	1.00	2	0.08	12	1960	13	4.51	69	20	90	<20	0.36	10	<10	145	<10	72			
UGA-25	117.00	118.00	1.00	7	0.08	14	1970	13	5.02	61	17	86	<20	0.34	20	<10	128	<10	51			
UGA-25	118.00	119.00	1.00	11	0.03	11	4370	11	9.54	174	10	59	<20	0.21	30	<10	68	<10	40			
UGA-25	119.00	120.00	1.00	5	0.11	13	4940	15	8.99	170	14	91	<20	0.31	40	<10	107	<10	25			
UGA-25	120.00	121.00	1.00	8	0.14	12	3160	13	7.15	130	14	114	<20	0.31	20	<10	96	<10	37			
UGA-25	121.00	122.00	1.00	14	0.05	9	2740	22	>10.0	278	9	65	<20	0.19	40	<10	60	<10	23			
UGA-25	122.00	123.00	1.00	18	0.06	12	2110	25	>10.0	225	11	58	<20	0.19	20	<10	79	<10	35			
UGA-25	123.00	124.00	1.00	5	0.11	15	1730	17	6.25	115	15	77	<20	0.31	<10	<10	116	<10	58			
UGA-25	124.00	125.00	1.00	11	0.06	8	4560	15	5.75	172	9	66	<20	0.15	10	<10	65	<10	63			
UGA-25	125.00	126.00	1.00	5	0.11	15	2770	17	6.33	124	13	89	<20	0.26	10	<10	102	<10	53			
UGA-25	126.00	127.00	1.00	4	0.16	14	2130	13	5.14	83	16	88	<20	0.34	10	<10	129	10	54			
UGA-25	127.00	128.00	1.00	1	0.18	16	1410	12	3.5	34	20	86	<20	0.41	20	<10	153	10	51			
UGA-25	128.00	129.00	1.00	2	0.18	15	1260	12	3.86	28	20	89	<20	0.39	<10	<10	149	<10	97			
UGA-25	129.00	130.00	1.00	1	0.52	10	1110	7	2.28	10	21	183	<20	0.4	10	<10	141	<10	62			
UGA-25	130.00	131.00	1.00	28	0.17	12	1100	11	4.15	30	18	76	<20	0.34	10	<10	123	<10	63			
UGA-25	131.00	132.00	1.00	306	0.05	7	3500	5	4.45	96	6	62	<20	0.11	30	<10	37	<10	32			
UGA-25	132.00	133.00	1.00	171	0.04	7	1670	5	4.26	67	5	52	<20	0.1	10	<10	48	<10	38			
UGA-25	133.00	134.00	1.00	15	0.16	13	1250	9	3.65	32	18	84	<20	0.35	<10	<10	136	<10	80			
UGA-25	134.00	135.00	1.00	7	0.16	12	1310	5	4.36	41	18	95	<20	0.34	10	<10	126	<10	66			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-25	85.00	86.00	1.00							
UGA-25	86.00	87.00	1.00							
UGA-25	87.00	88.00	1.00							
UGA-25	88.00	89.00	1.00							
UGA-25	89.00	90.00	1.00							
UGA-25	90.00	91.00	1.00							
UGA-25	91.00	92.00	1.00							
UGA-25	92.00	93.00	1.00							
UGA-25	93.00	94.00	1.00							
UGA-25	94.00	95.00	1.00							
UGA-25	95.00	96.00	1.00							
UGA-25	96.00	97.00	1.00							
UGA-25	97.00	98.00	1.00							
UGA-25	98.00	99.00	1.00							
UGA-25	99.00	100.00	1.00							
UGA-25	100.00	101.00	1.00							
UGA-25	101.00	102.00	1.00							
UGA-25	102.00	103.00	1.00							
UGA-25	103.00	104.00	1.00							
UGA-25	104.00	105.00	1.00							
UGA-25	105.00	106.00	1.00							
UGA-25	106.00	107.00	1.00							
UGA-25	107.00	108.00	1.00							
UGA-25	108.00	109.00	1.00							
UGA-25	109.00	110.00	1.00							
UGA-25	110.00	111.00	1.00							
UGA-25	111.00	112.00	1.00							
UGA-25	112.00	113.00	1.00							
UGA-25	113.00	114.00	1.00							
UGA-25	114.00	115.00	1.00							
UGA-25	115.00	116.00	1.00							
UGA-25	116.00	117.00	1.00							
UGA-25	117.00	118.00	1.00							
UGA-25	118.00	119.00	1.00							
UGA-25	119.00	120.00	1.00							
UGA-25	120.00	121.00	1.00							
UGA-25	121.00	122.00	1.00							
UGA-25	122.00	123.00	1.00							
UGA-25	123.00	124.00	1.00							
UGA-25	124.00	125.00	1.00							
UGA-25	125.00	126.00	1.00							
UGA-25	126.00	127.00	1.00							
UGA-25	127.00	128.00	1.00							
UGA-25	128.00	129.00	1.00							
UGA-25	129.00	130.00	1.00							
UGA-25	130.00	131.00	1.00							
UGA-25	131.00	132.00	1.00							
UGA-25	132.00	133.00	1.00							
UGA-25	133.00	134.00	1.00							
UGA-25	134.00	135.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn	
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm	ppm
UGA-25	135.00	136.00	1.00	M298925	0.16		3.1	7.65	304	760	1.4	<2	0.75	<0.5	19	64	83	5.07	20	3.07	30	2.52	403	
UGA-25	136.00	137.00	1.00	M298926	0.21		4	7.39	404	800	1.6	<2	0.77	<0.5	21	62	38	4.74	20	3.21	30	2.54	394	
UGA-25	137.00	138.00	1.00	M298927	0.34		7.6	6.12	537	570	1.2	<2	0.48	<0.5	17	67	33	4.35	10	3.36	20	1.48	339	
UGA-25	138.00	139.00	1.00	M298929	0.66		11	7.3	1290	220	1.8	<2	0.33	<0.5	21	62	62	6.02	10	2.92	20	1.23	195	
UGA-25	139.00	140.00	1.00	M298930	0.34		7	6.2	589	550	1.4	<2	0.45	<0.5	19	57	28	5.06	20	3.31	20	1.9	583	
UGA-25	140.00	141.00	1.00	M298931	0.52		11	5.74	838	540	1.2	<2	0.86	<0.5	16	57	42	4.97	10	3.04	20	1.49	355	
UGA-25	141.00	142.00	1.00	M298932	0.71		10.7	6.46	1390	270	1.2	<2	1.14	<0.5	18	57	57	5.68	10	3.11	20	2.07	311	
UGA-25	142.00	143.00	1.00	M298933	0.33		3	7.23	742	780	1.5	<2	1.18	<0.5	19	61	48	4.61	20	3.16	20	2.34	371	
UGA-25	143.00	144.00	1.00	M298934	0.5		6.3	6.03	679	700	1.3	2	1.66	<0.5	15	59	62	4.78	10	3.25	20	2.31	408	
UGA-25	144.00	145.00	1.00	M298936	0.73		9.5	6.69	1085	650	1.5	<2	0.78	0.5	19	60	58	5.14	10	3.08	20	2.25	606	
UGA-25	145.00	146.00	1.00	M298937	0.71		5.6	5.4	546	690	1.2	<2	1.37	<0.5	14	60	29	3.97	10	3.16	20	1.92	462	
UGA-25	146.00	147.00	1.00	M298938	0.68		5.3	6.25	899	620	1.2	<2	1.2	<0.5	15	61	28	3.96	10	3.3	20	1.37	306	
UGA-25	147.00	148.00	1.00	M298939	0.39		4.7	6.09	474	460	1.2	<2	0.95	<0.5	16	47	31	4.32	10	2.86	20	1.21	484	
UGA-25	148.00	149.00	1.00	M298940	0.05		1.4	6.64	89	100	1.7	<2	0.93	<0.5	18	37	27	4.19	10	2.47	20	1.19	593	
UGA-25	149.00	150.00	1.00	M298941	0.03		<0.5	7.4	78	210	1.6	<2	2.66	<0.5	16	21	29	3.95	20	2.89	20	1.65	863	
UGA-25	150.00	151.00	1.00	M298942	0.01		<0.5	7.83	83	280	1.8	<2	1.88	<0.5	16	23	31	3.93	20	2.89	20	1.39	848	
UGA-25	158.00	159.00	1.00	M298943	0.28		0.7	6.91	181	160	1.7	<2	0.27	<0.5	11	25	27	3.68	20	2.28	20	1.03	523	
UGA-25	159.00	160.00	1.00	M298944	0.19		0.8	7.11	96	170	1.7	<2	0.27	<0.5	14	24	27	3.89	20	2.43	20	0.9	493	
UGA-25	160.00	161.00	1.00	M298945	0.09		0.6	7.76	67	190	1.8	<2	0.3	<0.5	14	24	34	4.06	20	2.68	20	0.97	554	
UGA-25	161.00	162.00	1.00	M298946	0.06		0.9	6.94	116	170	1.6	<2	0.76	<0.5	14	22	25	4.48	20	2.95	20	0.81	388	
UGA-25	173.00	174.00	1.00	M298947	0.05		0.9	7.55	115	120	1.4	<2	0.52	<0.5	17	24	27	4.86	20	2.88	10	1.39	617	
UGA-25	174.00	175.00	1.00	M298948	0.05		1.4	7.93	167	170	1.5	<2	0.7	<0.5	18	24	29	4.28	20	3.45	20	0.85	332	
UGA-25	175.00	176.00	1.00	M298949	0.15		1.3	7.3	181	140	1.5	<2	0.42	<0.5	13	27	33	3.94	20	3.13	20	0.63	155	
UGA-25	176.00	177.00	1.00	M298951	0.11		1.2	7.06	119	110	1.2	<2	1.6	<0.5	15	24	35	4.28	20	3.03	20	1.16	577	
UGA-25	177.00	178.00	1.00	M298952	0.03		1.3	7.28	108	140	1.3	<2	0.46	<0.5	15	23	31	3.58	20	3.02	20	0.7	225	
UGA-25	178.00	179.00	1.00	M298953	0.04		1.4	7.32	143	150	1.4	<2	0.6	<0.5	17	23	26	4.41	20	2.75	20	1.32	499	
UGA-25	179.00	180.00	1.00	M298954	0.03		1.3	7.84	78	180	1.9	<2	0.51	<0.5	14	24	32	4.04	20	2.74	20	1.61	671	
UGA-25	180.00	180.80	0.80	M298955	0.07		1.6	7.13	98	140	1.5	<2	0.38	<0.5	16	22	30	4.49	20	2.65	20	1.42	494	
UGA-24	24.00	25.00	1.00	M298656	0.21		1.6	6.3	179	590	0.9	3	0.75	<0.5	16	64	29	4.09	10	4.67	20	1.06	408	
UGA-24	25.00	26.00	1.00	M298657	0.27		2.4	6.26	304	630	0.9	<2	0.82	<0.5	16	61	32	4.83	10	4.79	20	1.09	469	
UGA-24	26.00	27.00	1.00	M298658	0.12		1.2	6.86	142	650	1.1	<2	2.74	<0.5	18	64	36	4.75	10	5.34	20	1.92	707	
UGA-24	27.00	28.00	1.00	M298659	0.34		1.8	6.43	236	730	1.2	<2	0.64	<0.5	18	62	28	4.58	10	4.34	20	0.93	497	
UGA-24	28.00	29.00	1.00	M298661	0.2		1.7	6.36	252	240	1	<2	0.86	<0.5	17	58	28	3.88	10	3.76	20	0.72	300	
UGA-24	29.00	30.00	1.00	M298662	0.27		3	6.35	230	670	1.1	<2	0.81	<0.5	18	61	31	4.04	10	4.7	20	0.88	433	
UGA-24	30.00	31.00	1.00	M298663	1.84		6.4	6.13	290	750	1.2	<2	0.62	<0.5	17	63	29	4.01	10	4.23	20	0.94	378	
UGA-24	31.00	32.00	1.00	M298664	0.88		8.7	6.32	384	810	1.1	3	0.32	<0.5	17	65	35	3.63	10	4.68	20	0.85	235	
UGA-24	32.00	33.00	1.00	M298665	1.45		28.1	5.75	284	700	1.2	<2	0.54	<0.5	16	58	31	3.98	10	4.5	20	0.93	309	
UGA-24	33.00	34.00	1.00	M298667	0.28		2	6.3	303	710	1.3	2	1.06	<0.5	19	59	27	4.45	10	4.47	20	0.92	436	
UGA-24	34.00	35.00	1.00	M298668	0.21		2.2	6.05	280	750	1.1	3	1.45	<0.5	19	58	26	4.41	10	4.38	20	1.28	644	
UGA-24	35.00	36.00	1.00	M298669	2.43		17	6.13	394	870	1.1	<2	0.6	<0.5	17	61	40	4.29	10	4.47	20	1.02	623	
UGA-24	36.00	37.00	1.00	M298670	8.63		18	5.79	313	710	1.1	4	1.05	<0.5	18	61	42	4.13	10	4.82	20	0.9	603	
UGA-24	37.00	38.00	1.00	M298672	0.31		2.1	6.01	292	750	1.2	<2	0.93	<0.5	18	59	24	4.25	10	4.32	20	0.88	714	
UGA-24	38.00	39.00	1.00	M298673	0.13		1.5	6.76	231	670	1.2	2	0.5	<0.5	21	64	29	4.51	10	4.29	20	0.71	793	
UGA-24	39.00	40.00	1.00	M298674	0.89		2.6	5.52	278	610	1	<2	0.96	<0.5	16	56	39	3.71	10	4.26	20	0.73	508	
UGA-24	40.00	41.00	1.00	M298675	1.33		4.6	4.7	249	500	0.9	<2	0.45	<0.5	15	60	72	3.45	10	3.92	20	0.3	628	
UGA-24	41.00	42.00	1.00	M298676	0.27		2.5	6.13	251	720	1.2	<2	0.35	<0.5	20	61	33	4.21	10	4.95	20	0.35	939	
UGA-24	42.00	43.00	1.00	M298677	0.13		1.2	6.61	145	590	1.2	<2	0.37	<0.5	18	65	31	4.31	10	4.68	20	0.46	1135	
UGA-24	43.00	44.00	1.00	M298678	0.26		1.3	6.38	121	560	1.3	<2	0.36	<0.5	21	64	30	5.45	10	4.4	20	0.57	1655	
UGA-24	44.00	45.00	1.00	M298679	0.13		1.1	6.72	178	630	1.5	<2	0.39	<0.5	23	64	30	5.77	10	4.29	20	0.67	1600	
UGA-24	45.00	46.00	1.00	M298680	0.16		1.7	6.15	192	580	1.5	<2	0.39	<0.5	22	58	32	5.61	10	3.86	20	0.61	1340	

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-25	135.00	136.00	1.00	3	0.19	15	1230	9	3.34	24	22	96	<20	0.41	10	<10	157	<10	74			
UGA-25	136.00	137.00	1.00	4	0.19	16	1180	8	3.06	28	21	88	<20	0.4	<10	<10	158	<10	73			
UGA-25	137.00	138.00	1.00	70	0.15	12	1160	8	3.36	51	17	91	<20	0.32	10	<10	119	<10	70			
UGA-25	138.00	139.00	1.00	2	0.18	16	1250	12	4.63	67	21	86	<20	0.39	10	<10	152	<10	72			
UGA-25	139.00	140.00	1.00	35	0.13	14	1150	10	3.81	47	17	74	<20	0.32	10	<10	127	<10	78			
UGA-25	140.00	141.00	1.00	57	0.11	14	1890	9	3.79	64	17	76	<20	0.29	10	<10	112	<10	58			
UGA-25	141.00	142.00	1.00	6	0.13	14	1820	12	4.62	75	19	88	<20	0.34	10	<10	132	<10	60			
UGA-25	142.00	143.00	1.00	2	0.14	16	1310	7	2.59	19	21	92	<20	0.4	<10	<10	156	10	73			
UGA-25	143.00	144.00	1.00	9	0.09	12	2310	11	2.72	44	18	91	<20	0.33	10	<10	132	<10	69			
UGA-25	144.00	145.00	1.00	4	0.09	16	1330	7	3.31	33	19	89	<20	0.35	10	<10	131	<10	83			
UGA-25	145.00	146.00	1.00	6	0.03	13	1210	10	2.59	38	16	87	<20	0.28	10	<10	116	<10	58			
UGA-25	146.00	147.00	1.00	3	0.04	14	1010	8	3.06	27	17	86	<20	0.32	<10	<10	120	<10	55			
UGA-25	147.00	148.00	1.00	3	0.03	13	1140	8	3.21	31	16	71	<20	0.3	<10	<10	116	<10	58			
UGA-25	148.00	149.00	1.00	2	0.01	8	930	9	2.96	19	17	30	<20	0.35	10	<10	124	<10	62			
UGA-25	149.00	150.00	1.00	<1	0.02	4	800	10	3.05	11	18	46	<20	0.41	<10	<10	123	<10	62			
UGA-25	150.00	151.00	1.00	1	0.02	5	860	12	2.36	8	19	45	<20	0.45	<10	<10	131	<10	77			
UGA-25	158.00	159.00	1.00	1	0.02	3	800	9	0.82	21	16	17	<20	0.38	10	<10	117	10	55			
UGA-25	159.00	160.00	1.00	3	0.02	5	820	6	1.42	19	17	18	<20	0.4	<10	<10	122	10	65			
UGA-25	160.00	161.00	1.00	1	0.02	3	910	10	1.62	11	19	19	<20	0.45	<10	<10	132	10	78			
UGA-25	161.00	162.00	1.00	3	0.02	2	670	13	3.99	12	17	22	<20	0.4	10	<10	136	10	27			
UGA-25	173.00	174.00	1.00	2	0.02	5	930	17	2.18	7	18	23	<20	0.46	10	<10	140	10	84			
UGA-25	174.00	175.00	1.00	3	0.02	5	900	11	3.88	7	19	28	<20	0.46	10	<10	130	10	91			
UGA-25	175.00	176.00	1.00	6	0.02	3	860	12	3.86	15	18	23	<20	0.43	<10	<10	127	10	77			
UGA-25	176.00	177.00	1.00	3	0.02	6	800	15	3.34	13	18	42	<20	0.4	<10	<10	117	10	66			
UGA-25	177.00	178.00	1.00	3	0.01	4	860	12	2.98	12	17	24	<20	0.43	<10	<10	124	<10	74			
UGA-25	178.00	179.00	1.00	1	0.01	7	850	19	2.43	13	18	30	<20	0.42	<10	<10	127	<10	68			
UGA-25	179.00	180.00	1.00	1	<0.01	6	910	13	1.09	16	19	27	<20	0.46	<10	<10	135	<10	63			
UGA-25	180.00	180.80	0.80	2	0.01	4	850	14	2.22	12	18	23	<20	0.4	<10	<10	126	<10	86			
UGA-24	24.00	25.00	1.00	2	<0.01	15	840	7	2.09	25	19	99	<20	0.34	10	<10	137	<10	63			
UGA-24	25.00	26.00	1.00	4	<0.01	15	920	10	2.71	40	19	112	<20	0.33	10	<10	134	<10	72			
UGA-24	26.00	27.00	1.00	2	<0.01	16	960	10	1.88	18	20	151	<20	0.37	10	10	144	<10	72			
UGA-24	27.00	28.00	1.00	2	<0.01	14	920	11	2.94	24	20	105	<20	0.35	<10	<10	139	<10	64			
UGA-24	28.00	29.00	1.00	2	0.04	13	860	7	3.44	15	18	115	<20	0.34	10	<10	119	<10	43			
UGA-24	29.00	30.00	1.00	2	<0.01	14	880	8	2.74	32	19	106	<20	0.34	10	<10	126	<10	58			
UGA-24	30.00	31.00	1.00	3	<0.01	15	890	7	2.82	35	17	98	<20	0.33	10	<10	125	<10	62			
UGA-24	31.00	32.00	1.00	4	<0.01	15	920	9	2.81	48	17	100	<20	0.34	10	<10	126	<10	58			
UGA-24	32.00	33.00	1.00	3	<0.01	14	850	11	2.95	44	17	91	<20	0.31	10	<10	116	<10	80			
UGA-24	33.00	34.00	1.00	2	<0.01	15	890	10	3.25	23	18	114	<20	0.33	10	10	128	<10	62			
UGA-24	34.00	35.00	1.00	2	<0.01	13	890	8	2.34	16	18	118	<20	0.32	10	<10	124	<10	70			
UGA-24	35.00	36.00	1.00	4	<0.01	14	950	10	2.7	48	18	112	<20	0.33	10	<10	121	<10	78			
UGA-24	36.00	37.00	1.00	5	<0.01	14	930	11	2.81	47	17	100	<20	0.3	10	<10	113	<10	57			
UGA-24	37.00	38.00	1.00	3	<0.01	13	980	7	2.6	28	18	93	<20	0.32	10	<10	120	<10	50			
UGA-24	38.00	39.00	1.00	3	<0.01	16	1070	9	2.55	23	20	89	<20	0.37	10	<10	133	<10	60			
UGA-24	39.00	40.00	1.00	3	<0.01	12	930	6	2.45	36	16	102	<20	0.29	10	<10	96	<10	42			
UGA-24	40.00	41.00	1.00	5	<0.01	11	1490	8	2.2	59	13	75	<20	0.24	<10	<10	82	<10	62			
UGA-24	41.00	42.00	1.00	7	<0.01	15	1270	9	2.83	34	17	96	<20	0.32	<10	<10	120	<10	66			
UGA-24	42.00	43.00	1.00	3	<0.01	14	1200	8	2.17	29	19	93	<20	0.36	10	<10	133	<10	59			
UGA-24	43.00	44.00	1.00	2	<0.01	15	960	8	2.01	28	19	91	<20	0.34	<10	<10	125	<10	74			
UGA-24	44.00	45.00	1.00	3	<0.01	18	1020	13	2.43	27	19	91	<20	0.36	<10	<10	135	<10	87			
UGA-24	45.00	46.00	1.00	4	<0.01	19	1130	10	2.93	28	19	80	<20	0.33	10	<10	130	<10	84			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-25	135.00	136.00	1.00							
UGA-25	136.00	137.00	1.00							
UGA-25	137.00	138.00	1.00							
UGA-25	138.00	139.00	1.00							
UGA-25	139.00	140.00	1.00							
UGA-25	140.00	141.00	1.00							
UGA-25	141.00	142.00	1.00							
UGA-25	142.00	143.00	1.00							
UGA-25	143.00	144.00	1.00							
UGA-25	144.00	145.00	1.00							
UGA-25	145.00	146.00	1.00							
UGA-25	146.00	147.00	1.00							
UGA-25	147.00	148.00	1.00							
UGA-25	148.00	149.00	1.00							
UGA-25	149.00	150.00	1.00							
UGA-25	150.00	151.00	1.00							
UGA-25	158.00	159.00	1.00							
UGA-25	159.00	160.00	1.00							
UGA-25	160.00	161.00	1.00							
UGA-25	161.00	162.00	1.00							
UGA-25	173.00	174.00	1.00							
UGA-25	174.00	175.00	1.00							
UGA-25	175.00	176.00	1.00							
UGA-25	176.00	177.00	1.00							
UGA-25	177.00	178.00	1.00							
UGA-25	178.00	179.00	1.00							
UGA-25	179.00	180.00	1.00							
UGA-25	180.00	180.80	0.80							
UGA-24	24.00	25.00	1.00							
UGA-24	25.00	26.00	1.00							
UGA-24	26.00	27.00	1.00							
UGA-24	27.00	28.00	1.00							
UGA-24	28.00	29.00	1.00							
UGA-24	29.00	30.00	1.00							
UGA-24	30.00	31.00	1.00							
UGA-24	31.00	32.00	1.00							
UGA-24	32.00	33.00	1.00							
UGA-24	33.00	34.00	1.00							
UGA-24	34.00	35.00	1.00							
UGA-24	35.00	36.00	1.00							
UGA-24	36.00	37.00	1.00							
UGA-24	37.00	38.00	1.00							
UGA-24	38.00	39.00	1.00							
UGA-24	39.00	40.00	1.00							
UGA-24	40.00	41.00	1.00							
UGA-24	41.00	42.00	1.00							
UGA-24	42.00	43.00	1.00							
UGA-24	43.00	44.00	1.00							
UGA-24	44.00	45.00	1.00							
UGA-24	45.00	46.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-24	46.00	47.00	1.00	M298681	0.3		2	6.08	193	630	1.3	<2	0.36	<0.5	19	59	37	4.63	10	4.25	20	0.51	1055
UGA-24	47.00	48.00	1.00	M298683	0.22		2	5.54	212	580	1.2	<2	0.38	<0.5	26	58	35	6.8	10	3.76	20	0.57	2580
UGA-24	48.00	49.00	1.00	M298684	0.15		1.2	6.37	152	470	1.4	<2	0.45	<0.5	28	61	51	7.67	10	3.79	20	0.77	2380
UGA-24	49.00	50.00	1.00	M298685	0.09		0.5	7.59	67	410	1.7	<2	0.41	<0.5	20	75	37	5.11	20	3.93	30	0.73	1325
UGA-24	50.00	51.00	1.00	M298686	0.04		<0.5	7.98	64	340	1.7	<2	0.44	<0.5	22	77	41	4.04	20	4.26	30	0.64	970
UGA-24	51.00	52.00	1.00	M298687	0.06		<0.5	7.91	103	240	2.2	<2	0.44	<0.5	23	70	54	5.22	20	3.53	30	0.77	1095
UGA-24	52.00	53.00	1.00	M298688	0.04		<0.5	7.89	41	280	1.8	<2	0.45	<0.5	22	76	51	5.16	20	3.91	30	0.83	1405
UGA-24	53.00	54.00	1.00	M298689	0.1		1.2	6.91	86	380	2	<2	0.45	<0.5	23	64	46	7.62	10	3.41	30	1.02	2350
UGA-24	54.00	55.00	1.00	M298690	0.07		0.7	6.21	81	400	1.6	<2	0.47	<0.5	30	58	29	9.42	10	2.65	20	0.95	3970
UGA-24	55.00	56.00	1.00	M298691	0.03		<0.5	6.29	64	410	1.5	<2	0.47	<0.5	30	59	30	9.5	10	2.75	20	0.96	3970
UGA-24	56.00	57.00	1.00	M298692	0.1		0.9	6.27	124	540	1.6	<2	0.43	<0.5	32	58	33	8.56	10	2.96	20	0.87	3420
UGA-24	57.00	58.00	1.00	M298693	0.42		3	6.35	226	660	1.5	<2	0.4	<0.5	19	59	37	4.71	10	4.02	20	0.77	959
UGA-24	58.00	59.00	1.00	M298694	0.2		2	5.94	201	590	1.3	<2	0.83	<0.5	26	56	30	6.8	10	3.55	20	1.2	1930
UGA-24	59.00	60.00	1.00	M298695	0.13		1.2	5.79	157	500	1.2	<2	1.32	<0.5	37	50	28	8.71	10	3.29	20	1.32	3520
UGA-24	60.00	61.00	1.00	M298697	0.08		1.7	6.28	94	520	1.3	<2	0.78	<0.5	33	59	30	8.38	10	3.3	20	1.12	3480
UGA-24	61.00	62.00	1.00	M298698	0.08		1	5.88	90	460	1.4	<2	1.86	<0.5	30	56	31	7.22	10	3.17	20	1.46	2590
UGA-24	62.00	63.00	1.00	M298699	0.1		1.2	6.61	107	510	1.5	<2	0.86	<0.5	24	61	31	5.61	10	3.62	20	1.02	1440
UGA-24	63.00	64.00	1.00	M298701	0.07		1.3	6.46	76	480	1.3	<2	1.63	<0.5	27	60	41	5.96	10	3.23	20	1.32	1620
UGA-24	64.00	65.00	1.00	M298702	0.08		0.9	6.19	79	470	1.2	3	2.38	<0.5	27	54	32	6.3	10	3.02	20	1.62	1600
UGA-24	65.00	66.00	1.00	M298703	0.13		1	7.39	50	380	1.5	<2	0.46	<0.5	25	68	38	5.48	10	3.43	20	0.85	1295
UGA-24	66.00	67.00	1.00	M298704	0.24		1.1	5.71	100	430	1.3	3	0.38	<0.5	36	53	22	8.05	10	3.13	20	0.79	2520
UGA-24	67.00	68.00	1.00	M298705	0.08		1	7.19	91	340	1.3	<2	0.4	<0.5	26	66	46	5.48	10	3.86	30	0.83	1110
UGA-24	68.00	69.00	1.00	M298706	0.11		0.8	6.93	64	330	1.5	<2	0.98	<0.5	21	65	35	4.89	10	3.76	20	0.97	819
UGA-24	69.00	70.00	1.00	M298707	0.12		1	8.4	82	240	2.2	<2	0.36	<0.5	22	79	39	2.08	20	3.97	30	0.48	161
UGA-24	70.00	71.00	1.00	M298708	0.12		1.8	6.5	103	270	1.5	4	0.56	<0.5	28	58	35	6.05	10	2.45	20	0.73	1495
UGA-24	71.00	72.00	1.00	M298710	0.08		0.6	7.66	89	380	1.5	3	0.47	<0.5	30	72	49	6.81	20	2.83	30	0.92	1705
UGA-24	72.00	73.00	1.00	M298711	0.1		1	6.97	107	300	1.4	<2	1.1	<0.5	24	61	45	6.76	10	3.25	30	1.14	1030
UGA-24	73.00	74.00	1.00	M298712	0.06		0.6	7.05	62	310	1.3	2	0.62	<0.5	20	69	43	4.63	20	3.2	30	0.79	453
UGA-24	74.00	75.00	1.00	M298713	0.04		0.8	8.12	34	170	1.6	2	1.16	<0.5	20	76	101	4.72	20	3.55	30	1.34	670
UGA-24	75.00	76.00	1.00	M298714	0.03		0.7	7.12	30	330	1.3	2	0.86	<0.5	19	66	57	4.41	10	3.38	30	0.96	397
UGA-24	76.00	77.00	1.00	M298715	0.07		0.5	7.37	76	460	1.4	<2	1.55	<0.5	21	69	52	5.17	20	3.65	30	1.22	498
UGA-24	77.00	78.00	1.00	M298716	0.09		<0.5	7.76	79	530	1.2	<2	1.29	<0.5	23	74	53	4.44	20	4.22	20	0.95	423
UGA-24	78.00	79.00	1.00	M298718	0.05		0.7	7.24	41	520	1.4	<2	2.21	<0.5	21	69	36	5.41	20	4	20	1.4	566
UGA-24	79.00	80.00	1.00	M298719	0.2		1	7.51	98	290	1.6	2	1.77	<0.5	20	71	46	4.86	20	3.45	20	1.18	779
UGA-24	80.00	81.00	1.00	M298721	0.21		1.7	7.26	201	60	1.9	3	0.65	<0.5	22	73	31	5.45	10	2.07	20	0.81	1485
UGA-24	81.00	82.00	1.00	M298722	0.13		1.2	6.9	272	40	2	<2	0.5	<0.5	31	65	36	6.12	10	1.56	20	0.74	2370
UGA-24	82.00	83.00	1.00	M298723	0.12		1.3	6	742	40	1.7	3	0.48	<0.5	32	58	39	4.46	10	1.44	20	0.4	669
UGA-24	83.00	84.00	1.00	M298724	0.03		0.9	6.21	177	40	2.5	3	0.61	<0.5	21	59	26	7.65	10	1.42	20	0.68	4250
UGA-24	84.00	85.00	1.00	M298725	0.27		1.2	6.85	213	30	1.8	3	0.44	<0.5	23	62	28	5.06	10	1.41	20	0.62	1445
UGA-24	85.00	86.00	1.00	M298726	0.06		1.2	7.24	84	30	1.8	2	0.38	<0.5	22	68	31	4.59	10	1.67	30	0.71	1090
UGA-24	86.00	87.00	1.00	M298727	0.04		1.2	7.26	87	30	1.9	4	0.38	<0.5	22	63	38	4.37	20	1.88	30	0.77	840
UGA-24	87.00	88.00	1.00	M298728	0.06		1.2	5.99	114	60	2.1	<2	0.4	<0.5	21	57	25	5.8	10	1.62	20	0.75	2150
UGA-24	88.00	89.00	1.00	M298729	0.02		0.8	6.15	73	70	2.6	3	0.46	<0.5	21	59	29	7.63	10	1.68	20	0.95	3670
UGA-24	89.00	90.00	1.00	M298730	0.07		0.8	6.41	143	30	2.3	<2	0.48	<0.5	24	57	33	6.58	10	1.39	20	0.93	3380
UGA-24	90.00	91.00	1.00	M298731	0.11		1.4	6.7	234	30	1.8	<2	0.42	<0.5	20	60	31	4.63	10	1.28	20	0.86	1485
UGA-24	91.00	92.00	1.00	M298732	0.16		1.4	6.68	381	110	1.7	<2	0.38	<0.5	21	62	28	4.43	10	1.96	20	0.63	1080
UGA-24	92.00	93.00	1.00	M298733	0.14		0.9	7.18	416	80	2.2	<2	0.42	<0.5	23	65	30	7.07	10	2.05	20	0.81	3090
UGA-24	93.00	94.00	1.00	M298734	0.22		1.6	7.23	628	140	1.8	<2	0.75	<0.5	25	65	30	3.11	10	2.32	20	0.37	58
UGA-24	94.00	95.00	1.00	M298735	0.16		1.7	7.95	367	130	2.2	<2	0.63	<0.5	28	73	36	4.01	20	2.59	30	0.48	992
UGA-24	95.00	96.00	1.00	M298736	0.24		2	6.52	603	130	1.5	2	0.43	<0.5	22	61	33	3.7	10	2.17	20	0.34	61

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-24	46.00	47.00	1.00	3	<0.01	17	1150	8	2.6	29	18	85	<20	0.33	10	<10	127	<10	92			
UGA-24	47.00	48.00	1.00	2	<0.01	22	1040	9	2.66	31	16	81	<20	0.3	<10	<10	113	<10	125			
UGA-24	48.00	49.00	1.00	4	<0.01	23	1260	8	2.97	27	19	73	<20	0.34	10	<10	141	<10	123			
UGA-24	49.00	50.00	1.00	1	<0.01	16	1330	8	1.68	21	22	66	<20	0.41	<10	<10	155	<10	96			
UGA-24	50.00	51.00	1.00	3	<0.01	19	1570	9	1.64	28	22	56	<20	0.43	10	<10	166	<10	89			
UGA-24	51.00	52.00	1.00	2	<0.01	22	1580	9	2.13	30	22	43	<20	0.41	<10	<10	164	<10	105			
UGA-24	52.00	53.00	1.00	2	<0.01	18	1480	7	1.26	24	23	48	<20	0.43	<10	<10	181	<10	113			
UGA-24	53.00	54.00	1.00	1	<0.01	22	1180	8	2.05	22	21	76	<20	0.36	<10	<10	141	<10	123			
UGA-24	54.00	55.00	1.00	1	<0.01	28	1040	11	1.75	23	18	67	<20	0.33	<10	<10	123	<10	160			
UGA-24	55.00	56.00	1.00	1	<0.01	25	1020	6	1.62	17	19	59	<20	0.33	<10	<10	124	<10	160			
UGA-24	56.00	57.00	1.00	1	<0.01	28	1050	9	1.9	15	18	82	<20	0.33	<10	<10	124	<10	188			
UGA-24	57.00	58.00	1.00	2	<0.01	15	1310	9	2.21	26	19	114	<20	0.34	10	<10	128	10	83			
UGA-24	58.00	59.00	1.00	1	<0.01	19	940	9	2.39	16	17	98	<20	0.31	10	10	120	<10	141			
UGA-24	59.00	60.00	1.00	1	<0.01	25	940	9	2.06	11	17	96	<20	0.31	<10	<10	116	<10	182			
UGA-24	60.00	61.00	1.00	1	<0.01	24	1040	8	1.76	14	18	120	<20	0.33	10	<10	126	<10	180			
UGA-24	61.00	62.00	1.00	1	<0.01	20	930	9	2.02	17	18	110	<20	0.31	10	<10	120	<10	165			
UGA-24	62.00	63.00	1.00	1	<0.01	18	1080	10	2.3	15	19	111	<20	0.35	10	<10	132	<10	105			
UGA-24	63.00	64.00	1.00	1	<0.01	18	1080	10	2.14	12	19	114	<20	0.35	10	<10	126	<10	109			
UGA-24	64.00	65.00	1.00	1	<0.01	18	1010	9	2.18	12	18	115	<20	0.33	<10	<10	125	<10	104			
UGA-24	65.00	66.00	1.00	1	<0.01	15	1170	6	2.18	20	19	85	<20	0.39	10	<10	147	10	90			
UGA-24	66.00	67.00	1.00	1	<0.01	21	860	10	3.3	21	17	102	<20	0.3	<10	<10	120	<10	161			
UGA-24	67.00	68.00	1.00	2	<0.01	17	1130	8	2.56	16	22	71	<20	0.39	10	<10	148	<10	84			
UGA-24	68.00	69.00	1.00	1	<0.01	15	1190	11	2.71	15	20	67	<20	0.37	10	<10	150	10	121			
UGA-24	69.00	70.00	1.00	3	0.01	26	1490	5	1.67	19	20	62	<20	0.46	10	<10	178	<10	72			
UGA-24	70.00	71.00	1.00	3	<0.01	19	1170	9	3.11	24	19	38	<20	0.35	<10	<10	137	<10	136			
UGA-24	71.00	72.00	1.00	1	<0.01	23	1180	9	2.83	19	23	45	<20	0.41	10	<10	156	10	108			
UGA-24	72.00	73.00	1.00	1	<0.01	19	1210	8	4.09	19	21	60	<20	0.37	10	<10	153	<10	66			
UGA-24	73.00	74.00	1.00	1	<0.01	15	1060	8	3.09	15	20	36	<20	0.39	<10	<10	152	<10	61			
UGA-24	74.00	75.00	1.00	1	0.01	17	1110	5	1.98	12	23	39	<20	0.44	10	<10	162	10	76			
UGA-24	75.00	76.00	1.00	1	<0.01	16	1010	8	2.74	13	20	44	<20	0.38	10	<10	147	<10	50			
UGA-24	76.00	77.00	1.00	1	<0.01	17	980	9	3.35	13	22	62	<20	0.39	<10	<10	150	10	56			
UGA-24	77.00	78.00	1.00	<1	<0.01	16	1160	7	3.13	11	22	78	<20	0.42	10	<10	143	10	41			
UGA-24	78.00	79.00	1.00	2	<0.01	16	1120	11	3.63	15	22	83	<20	0.4	10	<10	159	<10	87			
UGA-24	79.00	80.00	1.00	1	<0.01	17	1120	11	2.92	19	22	76	<20	0.41	<10	<10	161	10	73			
UGA-24	80.00	81.00	1.00	1	0.01	19	1110	9	2.94	29	22	25	<20	0.42	10	<10	160	10	88			
UGA-24	81.00	82.00	1.00	1	0.01	19	1580	9	2.72	56	21	20	<20	0.37	10	<10	144	<10	41			
UGA-24	82.00	83.00	1.00	4	0.01	20	1840	11	3.87	138	16	20	<20	0.34	20	<10	119	10	22			
UGA-24	83.00	84.00	1.00	2	0.01	14	1650	5	2.43	56	21	14	<20	0.32	10	<10	128	<10	63			
UGA-24	84.00	85.00	1.00	1	0.01	17	1480	8	3.05	64	21	15	<20	0.35	10	<10	134	<10	67			
UGA-24	85.00	86.00	1.00	1	0.01	17	1280	9	2.91	43	20	16	<20	0.38	<10	<10	143	<10	71			
UGA-24	86.00	87.00	1.00	2	0.01	15	1270	8	3	36	19	14	<20	0.38	<10	<10	136	<10	75			
UGA-24	87.00	88.00	1.00	1	0.01	15	1090	6	2.59	42	18	19	<20	0.31	<10	<10	114	<10	68			
UGA-24	88.00	89.00	1.00	1	0.01	15	1080	7	2.11	45	22	20	<20	0.31	<10	<10	128	<10	83			
UGA-24	89.00	90.00	1.00	1	0.01	15	1350	8	2.1	54	18	16	<20	0.32	10	<10	117	<10	85			
UGA-24	90.00	91.00	1.00	3	0.01	15	1410	5	2.16	58	18	16	<20	0.34	<10	<10	121	<10	66			
UGA-24	91.00	92.00	1.00	3	0.01	18	1350	8	2.9	45	18	31	<20	0.35	10	<10	125	<10	63			
UGA-24	92.00	93.00	1.00	2	0.01	18	1190	10	2.86	37	24	27	<20	0.37	10	<10	145	<10	91			
UGA-24	93.00	94.00	1.00	3	0.01	19	3210	9	3.37	68	22	39	<20	0.37	10	<10	153	<10	89			
UGA-24	94.00	95.00	1.00	3	0.01	19	2610	9	2.94	73	25	37	<20	0.42	10	<10	161	<10	78			
UGA-24	95.00	96.00	1.00	3	0.01	14	1750	7	4.01	70	19	35	<20	0.34	10	<10	127	<10	61			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-24	46.00	47.00	1.00							
UGA-24	47.00	48.00	1.00							
UGA-24	48.00	49.00	1.00							
UGA-24	49.00	50.00	1.00							
UGA-24	50.00	51.00	1.00							
UGA-24	51.00	52.00	1.00							
UGA-24	52.00	53.00	1.00							
UGA-24	53.00	54.00	1.00							
UGA-24	54.00	55.00	1.00							
UGA-24	55.00	56.00	1.00							
UGA-24	56.00	57.00	1.00							
UGA-24	57.00	58.00	1.00							
UGA-24	58.00	59.00	1.00							
UGA-24	59.00	60.00	1.00							
UGA-24	60.00	61.00	1.00							
UGA-24	61.00	62.00	1.00							
UGA-24	62.00	63.00	1.00							
UGA-24	63.00	64.00	1.00							
UGA-24	64.00	65.00	1.00							
UGA-24	65.00	66.00	1.00							
UGA-24	66.00	67.00	1.00							
UGA-24	67.00	68.00	1.00							
UGA-24	68.00	69.00	1.00							
UGA-24	69.00	70.00	1.00							
UGA-24	70.00	71.00	1.00							
UGA-24	71.00	72.00	1.00							
UGA-24	72.00	73.00	1.00							
UGA-24	73.00	74.00	1.00							
UGA-24	74.00	75.00	1.00							
UGA-24	75.00	76.00	1.00							
UGA-24	76.00	77.00	1.00							
UGA-24	77.00	78.00	1.00							
UGA-24	78.00	79.00	1.00							
UGA-24	79.00	80.00	1.00							
UGA-24	80.00	81.00	1.00							
UGA-24	81.00	82.00	1.00							
UGA-24	82.00	83.00	1.00							
UGA-24	83.00	84.00	1.00							
UGA-24	84.00	85.00	1.00							
UGA-24	85.00	86.00	1.00							
UGA-24	86.00	87.00	1.00							
UGA-24	87.00	88.00	1.00							
UGA-24	88.00	89.00	1.00							
UGA-24	89.00	90.00	1.00							
UGA-24	90.00	91.00	1.00							
UGA-24	91.00	92.00	1.00							
UGA-24	92.00	93.00	1.00							
UGA-24	93.00	94.00	1.00							
UGA-24	94.00	95.00	1.00							
UGA-24	95.00	96.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-24	96.00	97.00	1.00	M298737	0.08		2.4	7.26	474	110	1.8	<2	0.41	<0.5	26	70	33	4	20	2.64	30	0.5	62
UGA-24	97.00	98.00	1.00	M298738	0.76		7.8	5.4	901	20	2.1	3	1.28	<0.5	19	50	29	5.14	10	1.28	20	0.39	71
UGA-24	98.00	99.00	1.00	M298739	0.26		2.4	5.19	412	30	1.6	<2	1.79	<0.5	24	50	29	4.14	10	0.81	20	0.28	74
UGA-24	99.00	100.00	1.00	M298741	0.34		3	5.2	616	30	1.5	<2	1.1	<0.5	18	40	30	5.29	10	0.5	20	0.12	71
UGA-24	100.00	101.00	1.00	M298742	0.29		2.4	3.39	954	250	1	<2	0.89	<0.5	11	35	14	4.68	10	2.16	10	0.07	120
UGA-24	101.00	102.00	1.00	M298743	0.22		2.3	5.33	170	510	0.7	4	0.37	<0.5	15	39	20	3.04	10	4.63	20	0.05	67
UGA-24	102.00	103.00	1.00	M298744	0.09		1.8	4.14	141	530	0.7	4	0.26	<0.5	11	34	16	3.3	<10	3.98	10	0.1	226
UGA-24	103.00	104.00	1.00	M298745	0.11		2.3	5.26	133	800	0.7	3	0.36	<0.5	13	36	13	3.63	<10	4.44	20	0.12	477
UGA-24	104.00	105.00	1.00	M298746	0.35		3	3.46	156	490	0.9	<2	0.7	<0.5	9	32	14	2.9	<10	2.78	10	0.15	335
UGA-24	105.00	106.00	1.00	M298747	0.15		2.2	4.38	161	540	0.8	4	0.41	<0.5	13	38	19	3.19	10	3.72	20	0.09	80
UGA-24	106.00	107.00	1.00	M298748	0.25		2.9	3.77	237	520	0.7	2	0.32	<0.5	10	35	16	3.37	<10	3.65	10	0.07	75
UGA-24	107.00	108.00	1.00	M298749	0.96		5.9	3.74	418	490	0.7	<2	0.63	<0.5	9	34	18	3.94	<10	3.56	10	0.09	431
UGA-24	108.00	109.00	1.00	M298751	0.75		6.7	4.5	386	830	0.8	4	0.35	<0.5	13	43	22	3.47	10	3.97	20	0.1	102
UGA-24	109.00	110.00	1.00	M298753	3.44		14.7	2.93	1750	200	0.9	<2	0.99	<0.5	13	35	28	5.32	<10	1.94	10	0.06	87
UGA-24	110.00	111.00	1.00	M298754	4.67		25.9	3.36	1995	180	0.8	<2	1.01	<0.5	12	33	55	5.99	<10	2.58	10	0.06	69
UGA-24	111.00	112.00	1.00	M298755	1.29		10	3.67	831	280	0.7	2	0.44	<0.5	11	41	23	4.91	<10	3.22	10	0.06	78
UGA-24	112.00	113.00	1.00	M298756	0.32		3.6	5.76	328	710	1	<2	0.39	<0.5	16	37	21	3.49	10	4.05	20	0.16	56
UGA-24	113.00	114.00	1.00	M298757	0.2		4.5	6.15	288	550	0.9	5	0.35	<0.5	18	33	22	3.92	10	4.47	30	0.13	52
UGA-24	114.00	115.00	1.00	M298758	0.36		4.5	5.07	405	240	1	2	0.42	<0.5	15	32	21	4.55	10	3.37	20	0.12	204
UGA-24	115.00	116.00	1.00	M298759	1.5		16.6	3.62	1490	310	0.9	<2	0.73	<0.5	9	33	28	5.91	<10	3.29	10	0.06	82
UGA-24	116.00	117.00	1.00	M298760	0.88		13.9	3.73	1045	320	0.8	<2	0.48	<0.5	11	32	31	5.53	<10	3.6	10	0.11	153
UGA-24	117.00	118.00	1.00	M298761	0.64		10.2	3.44	1035	300	0.7	<2	0.56	<0.5	10	36	27	5.06	<10	3.3	10	0.09	81
UGA-24	118.00	119.00	1.00	M298762	0.51		7.7	4.76	892	380	0.8	<2	0.83	<0.5	13	31	22	4.93	<10	3.65	20	0.07	61
UGA-24	119.00	120.00	1.00	M298763	0.63		9.5	4.92	1235	450	1	<2	0.72	<0.5	15	33	25	6	10	3.66	20	0.13	77
UGA-24	120.00	121.00	1.00	M298765	0.73		12.8	5.48	1980	310	1.2	<2	1.06	<0.5	14	34	30	5.65	10	4.12	20	0.12	61
UGA-24	121.00	122.00	1.00	M298766	1.54		21.5	3.84	2530	160	1.2	2	1.69	<0.5	17	42	42	7.93	10	4.11	10	0.05	62
UGA-24	122.00	123.00	1.00	M298767	0.96		14.4	6.26	1220	200	1	<2	0.66	<0.5	18	44	40	6.37	10	4.05	20	0.13	62
UGA-24	123.00	124.00	1.00	M298768	0.8		16	4.88	917	210	0.9	4	0.37	<0.5	15	42	33	5.94	10	3.44	20	0.12	63
UGA-24	124.00	125.00	1.00	M298770	0.16		3.5	7.04	327	1000	1.2	<2	0.38	<0.5	19	63	28	4.21	10	4.71	20	0.16	72
UGA-24	125.00	126.00	1.00	M298771	0.14		3.4	6.37	298	950	1.3	<2	0.3	<0.5	18	57	27	4.45	10	4.46	20	0.19	62
UGA-24	126.00	127.00	1.00	M298772	0.29		6.6	5.74	628	320	1.2	2	0.47	<0.5	15	51	30	5.08	10	3.76	20	0.14	67
UGA-24	127.00	128.00	1.00	M298773	0.11		3.7	6.69	210	1250	1.1	2	0.42	<0.5	16	53	28	3.35	10	4.66	20	0.28	377
UGA-24	128.00	129.00	1.00	M298774	0.12		2.9	6.7	239	760	1.2	2	0.38	<0.5	18	55	24	3.52	10	4.75	30	0.4	52
UGA-24	129.00	130.00	1.00	M298775	0.29		4.4	6.87	403	840	1.1	<2	0.43	<0.5	18	54	30	3.48	10	4.13	30	0.38	48
UGA-24	130.00	131.00	1.00	M298776	0.27		4.7	6.9	550	460	0.9	2	0.32	<0.5	19	55	30	4.87	10	3.81	30	0.27	54
UGA-24	131.00	132.00	1.00	M298777	0.41		4.4	7.72	608	1050	1.5	2	0.37	<0.5	23	58	37	4.43	10	4.27	30	1.62	324
UGA-24	132.00	133.00	1.00	M298778	0.18		3.1	7.98	283	1130	1.4	2	0.38	<0.5	22	57	36	5.21	20	4.36	30	2.92	783
UGA-24	133.00	134.00	1.00	M298779	0.36		5.2	7.2	506	730	1.1	<2	1.17	<0.5	18	51	42	5.28	10	4.49	30	2.3	347
UGA-24	134.00	135.00	1.00	M298781	0.28		5.4	7.02	428	870	1.2	2	1.08	<0.5	17	48	34	4.39	10	4.93	30	1.86	274
UGA-24	135.00	136.00	1.00	M298782	0.37		4.9	5.86	426	610	0.9	<2	1.56	<0.5	15	40	26	5.92	10	4.22	20	2.47	436
UGA-24	136.00	137.00	1.00	M298783	0.14		3.2	6.51	224	460	1.1	3	0.95	<0.5	17	45	25	4.92	10	4	20	1.97	345
UGA-24	137.00	138.00	1.00	M298784	0.34		3.7	6.33	252	790	1	2	1.92	<0.5	13	37	23	4.72	10	4.7	20	2.62	512
UGA-24	138.00	139.00	1.00	M298785	2.01		13.6	6.32	760	700	1.3	<2	1.83	<0.5	16	44	42	5.17	10	4.16	30	2.62	434
UGA-24	139.00	140.00	1.00	M298786	0.41		5	7.17	708	840	1.7	2	0.76	<0.5	23	52	38	6.57	10	4.54	30	1.66	1080
UGA-24	140.00	141.00	1.00	M298787	0.57		5.4	7.05	854	730	1.4	<2	0.5	<0.5	19	51	34	5.02	10	4.08	30	0.66	355
UGA-24	141.00	142.00	1.00	M298788	0.59		6.6	6.41	736	500	1.4	2	0.69	<0.5	17	51	34	3.78	10	4.24	20	0.28	55
UGA-24	142.00	143.00	1.00	M298790	0.31		4.9	6.18	386	930	1.4	<2	0.4	<0.5	15	49	30	3.09	10	4.39	20	0.38	233
UGA-24	143.00	144.00	1.00	M298791	0.52		5.5	5.73	437	710	1.3	2	0.39	<0.5	14	42	29	4.24	10	4.61	20	0.43	580
UGA-24	144.00	145.00	1.00	M298792	0.88		6	5.85	1095	550	1.5	<2	0.59	<0.5	15	40	43	4.06	10	4.13	20	0.5	597
UGA-24	145.00	146.00	1.00	M298793	0.74		6.5	6.34	808	670	1.5	<2	0.41	<0.5	16	49	46	3.8	10	4.33	20	0.38	332

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-24	96.00	97.00	1.00	5	0.01	19	1710	8	4.42	70	21	30	<20	0.38	10	<10	150	<10	73			
UGA-24	97.00	98.00	1.00	7	0.01	14	5590	8	5.26	130	16	27	<20	0.25	10	<10	96	<10	43			
UGA-24	98.00	99.00	1.00	10	0.01	10	7810	8	4.32	76	18	38	<20	0.25	10	<10	104	<10	48			
UGA-24	99.00	100.00	1.00	9	0.01	11	4830	8	5.35	108	15	28	<20	0.27	10	<10	76	<10	32			
UGA-24	100.00	101.00	1.00	8	0.01	9	3840	4	4.31	118	9	65	<20	0.17	20	<10	46	<10	26			
UGA-24	101.00	102.00	1.00	3	<0.01	9	1570	4	3.09	41	11	79	<20	0.26	10	<10	65	<10	39			
UGA-24	102.00	103.00	1.00	3	0.01	6	1050	4	3.07	45	10	81	<20	0.2	10	<10	56	<10	40			
UGA-24	103.00	104.00	1.00	3	0.01	9	1480	4	3.28	40	13	109	<20	0.26	10	<10	61	<10	61			
UGA-24	104.00	105.00	1.00	4	<0.01	8	2740	2	2.4	55	8	65	<20	0.16	10	<10	44	<10	35			
UGA-24	105.00	106.00	1.00	4	<0.01	6	1720	3	3.24	43	10	67	<20	0.23	10	<10	61	<10	28			
UGA-24	106.00	107.00	1.00	4	<0.01	6	1350	3	3.51	56	8	72	<20	0.18	10	<10	42	<10	33			
UGA-24	107.00	108.00	1.00	8	0.01	6	2620	3	3.59	68	9	67	<20	0.18	10	<10	39	<10	37			
UGA-24	108.00	109.00	1.00	5	<0.01	8	1470	8	3.51	90	10	79	<20	0.21	10	<10	55	<10	42			
UGA-24	109.00	110.00	1.00	9	0.01	7	4330	6	5.29	233	7	54	<20	0.14	30	<10	36	<10	24			
UGA-24	110.00	111.00	1.00	7	0.03	7	4530	6	6.32	331	8	51	<20	0.16	30	<10	37	<10	22			
UGA-24	111.00	112.00	1.00	7	0.03	8	1900	3	5.27	134	7	62	<20	0.17	20	<10	31	<10	30			
UGA-24	112.00	113.00	1.00	3	0.07	9	1640	5	3.74	52	14	90	<20	0.29	10	<10	92	<10	43			
UGA-24	113.00	114.00	1.00	3	0.06	10	1490	5	4.23	50	16	125	<20	0.32	20	<10	89	<10	48			
UGA-24	114.00	115.00	1.00	3	0.06	9	1800	6	4.53	56	13	88	<20	0.26	10	<10	69	<10	42			
UGA-24	115.00	116.00	1.00	6	0.08	8	3090	6	5.68	154	7	60	<20	0.16	10	<10	40	<10	30			
UGA-24	116.00	117.00	1.00	5	0.09	8	1990	7	5.43	99	8	64	<20	0.19	10	<10	45	<10	34			
UGA-24	117.00	118.00	1.00	4	0.08	8	2320	10	5.07	67	8	73	<20	0.18	10	<10	51	<10	25			
UGA-24	118.00	119.00	1.00	4	0.12	8	3490	9	5.04	60	9	99	<20	0.23	10	<10	53	<10	30			
UGA-24	119.00	120.00	1.00	4	0.15	8	3000	11	6.06	69	11	87	<20	0.25	10	<10	78	<10	35			
UGA-24	120.00	121.00	1.00	5	0.11	9	4490	9	5.73	146	12	92	<20	0.27	20	<10	91	<10	25			
UGA-24	121.00	122.00	1.00	7	0.1	11	7200	12	7.94	203	9	96	<20	0.24	20	<10	73	<10	26			
UGA-24	122.00	123.00	1.00	3	0.13	10	2790	10	6.42	91	16	106	<20	0.33	10	<10	104	<10	42			
UGA-24	123.00	124.00	1.00	5	0.07	9	1650	10	5.89	71	13	89	<20	0.26	10	<10	77	<10	43			
UGA-24	124.00	125.00	1.00	4	0.25	15	1610	10	3.7	38	19	119	<20	0.36	10	<10	130	<10	59			
UGA-24	125.00	126.00	1.00	2	0.22	15	1260	9	3.78	44	17	106	<20	0.32	10	<10	117	<10	57			
UGA-24	126.00	127.00	1.00	4	0.1	12	2010	10	4.45	61	15	93	<20	0.28	10	<10	88	<10	39			
UGA-24	127.00	128.00	1.00	3	0.25	11	1710	10	3.06	29	18	114	<20	0.34	10	<10	105	<10	53			
UGA-24	128.00	129.00	1.00	3	0.16	12	1550	10	3.74	30	19	94	<20	0.34	10	<10	124	<10	73			
UGA-24	129.00	130.00	1.00	3	0.18	14	1760	10	3.72	35	18	105	<20	0.34	10	<10	129	<10	64			
UGA-24	130.00	131.00	1.00	3	0.13	16	1320	14	5.25	31	16	92	<20	0.35	10	<10	107	<10	57			
UGA-24	131.00	132.00	1.00	2	0.22	18	1420	11	3.7	29	19	103	<20	0.39	10	<10	154	<10	83			
UGA-24	132.00	133.00	1.00	2	0.24	16	1210	8	2.76	21	21	106	<20	0.39	10	<10	155	<10	81			
UGA-24	133.00	134.00	1.00	3	0.17	13	1460	10	4.1	34	19	101	<20	0.35	10	<10	138	<10	58			
UGA-24	134.00	135.00	1.00	5	0.19	10	1570	12	3.62	36	17	113	<20	0.35	10	<10	132	<10	59			
UGA-24	135.00	136.00	1.00	3	0.14	12	1930	12	4.91	26	15	100	<20	0.28	10	<10	107	<10	57			
UGA-24	136.00	137.00	1.00	3	0.12	13	1380	10	4.17	25	16	103	<20	0.32	10	<10	120	<10	55			
UGA-24	137.00	138.00	1.00	5	0.16	11	1570	8	3.82	23	16	105	<20	0.3	10	<10	122	<10	52			
UGA-24	138.00	139.00	1.00	3	0.16	13	3170	15	3.92	62	18	93	<20	0.31	10	<10	133	<10	59			
UGA-24	139.00	140.00	1.00	2	0.21	19	1520	15	4.9	29	19	83	<20	0.35	10	<10	141	<10	77			
UGA-24	140.00	141.00	1.00	2	0.2	14	1960	12	4.8	34	18	86	<20	0.35	10	<10	132	<10	58			
UGA-24	141.00	142.00	1.00	4	0.16	12	2790	11	3.95	42	15	82	<20	0.31	10	<10	112	<10	59			
UGA-24	142.00	143.00	1.00	2	0.25	14	1510	9	2.85	34	15	76	<20	0.3	10	<10	114	<10	50			
UGA-24	143.00	144.00	1.00	3	0.21	11	1420	10	3.64	42	14	81	<20	0.28	10	<10	92	<10	52			
UGA-24	144.00	145.00	1.00	3	0.19	12	2330	9	3.47	44	14	85	<20	0.27	10	<10	105	<10	50			
UGA-24	145.00	146.00	1.00	2	0.22	13	1580	11	3.54	36	15	87	<20	0.3	10	<10	110	<10	56			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-24	96.00	97.00	1.00							
UGA-24	97.00	98.00	1.00							
UGA-24	98.00	99.00	1.00							
UGA-24	99.00	100.00	1.00							
UGA-24	100.00	101.00	1.00							
UGA-24	101.00	102.00	1.00							
UGA-24	102.00	103.00	1.00							
UGA-24	103.00	104.00	1.00							
UGA-24	104.00	105.00	1.00							
UGA-24	105.00	106.00	1.00							
UGA-24	106.00	107.00	1.00							
UGA-24	107.00	108.00	1.00							
UGA-24	108.00	109.00	1.00							
UGA-24	109.00	110.00	1.00							
UGA-24	110.00	111.00	1.00							
UGA-24	111.00	112.00	1.00							
UGA-24	112.00	113.00	1.00							
UGA-24	113.00	114.00	1.00							
UGA-24	114.00	115.00	1.00							
UGA-24	115.00	116.00	1.00							
UGA-24	116.00	117.00	1.00							
UGA-24	117.00	118.00	1.00							
UGA-24	118.00	119.00	1.00							
UGA-24	119.00	120.00	1.00							
UGA-24	120.00	121.00	1.00							
UGA-24	121.00	122.00	1.00							
UGA-24	122.00	123.00	1.00							
UGA-24	123.00	124.00	1.00							
UGA-24	124.00	125.00	1.00							
UGA-24	125.00	126.00	1.00							
UGA-24	126.00	127.00	1.00							
UGA-24	127.00	128.00	1.00							
UGA-24	128.00	129.00	1.00							
UGA-24	129.00	130.00	1.00							
UGA-24	130.00	131.00	1.00							
UGA-24	131.00	132.00	1.00							
UGA-24	132.00	133.00	1.00							
UGA-24	133.00	134.00	1.00							
UGA-24	134.00	135.00	1.00							
UGA-24	135.00	136.00	1.00							
UGA-24	136.00	137.00	1.00							
UGA-24	137.00	138.00	1.00							
UGA-24	138.00	139.00	1.00							
UGA-24	139.00	140.00	1.00							
UGA-24	140.00	141.00	1.00							
UGA-24	141.00	142.00	1.00							
UGA-24	142.00	143.00	1.00							
UGA-24	143.00	144.00	1.00							
UGA-24	144.00	145.00	1.00							
UGA-24	145.00	146.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-24	146.00	147.00	1.00	M298794	0.6		9.3	5.03	450	590	1.2	<2	0.41	<0.5	15	50	31	4	10	3.91	20	0.53	573
UGA-24	147.00	148.00	1.00	M298796	0.61		5.6	5.31	585	560	1.1	<2	0.54	<0.5	15	42	36	3.91	10	3.42	20	0.83	645
UGA-24	148.00	149.00	1.00	M298797	0.32		7.9	5.37	237	130	1.2	<2	0.93	<0.5	15	47	26	3.61	10	2.15	20	0.98	413
UGA-24	149.00	150.00	1.00	M298798	0.06		0.5	7.54	110	150	1.5	5	2.27	<0.5	17	24	30	4.59	10	2.57	20	2.57	1170
UGA-24	150.00	151.00	1.00	M298799	0.07		0.7	7.92	109	200	1.8	<2	0.82	<0.5	16	21	35	4.09	20	3	20	1.68	556
UGA-24	151.00	152.00	1.00	M298801	0.11		0.5	7.01	94	230	1.3	2	0.64	<0.5	13	19	22	3.83	10	2.31	20	1.87	696
UGA-24	152.00	153.00	1.00	M298802	0.13		0.7	6.99	113	230	1.4	2	0.72	<0.5	13	20	19	3.53	20	2.32	20	1.72	644
UGA-24	153.00	154.00	1.00	M298803	0.15		1.3	5.66	105	830	1.2	2	0.74	<0.5	11	17	19	3.52	10	1.97	10	1.68	790
UGA-24	154.00	155.00	1.00	M298804	0.27		1.5	6.91	178	250	1.4	3	0.32	<0.5	14	20	25	4.23	20	2.42	20	1.68	568
UGA-24	155.00	156.00	1.00	M298805	0.14		1.2	6.9	162	300	1.4	2	0.31	<0.5	13	22	16	3.64	20	2.43	20	1.5	423
UGA-24	156.00	157.00	1.00	M298806	0.11		1.4	6.97	124	240	1.4	2	0.32	<0.5	14	22	20	4.29	20	2.42	10	1.85	553
UGA-24	157.00	158.00	1.00	M298807	0.08		0.8	7.56	98	210	1.4	<2	0.41	<0.5	12	21	24	3.87	20	2.63	20	1.72	498
UGA-24	158.00	159.00	1.00	M298808	0.12		0.7	7.58	139	160	1.4	2	0.63	<0.5	14	23	30	4.07	20	2.78	20	1.8	603
UGA-23	38.00	39.00	1.00	M298514	0.1		2.2	6.45	224	480	1.4	5	0.49	<0.5	15	57	70	3.8	10	3.34	20	0.43	548
UGA-23	39.00	40.00	1.00	M298515	0.38		3.8	6.37	201	500	1.6	2	0.78	<0.5	15	55	45	4.05	10	3.46	20	0.56	725
UGA-23	40.00	41.00	1.00	M298516	0.07		1.4	6.47	103	380	1.4	<2	0.34	<0.5	18	60	33	6	10	3.48	20	0.66	1645
UGA-23	41.00	42.00	1.00	M298517	0.08		0.8	6.48	138	250	1.8	<2	0.42	<0.5	18	57	36	8.81	10	3.51	20	1.02	3080
UGA-23	42.00	43.00	1.00	M298518	0.13		1.3	6.65	118	380	1.5	2	0.35	<0.5	21	62	32	6.85	10	3.72	20	0.72	2130
UGA-23	43.00	44.00	1.00	M298519	0.06		0.8	7	93	390	1.4	<2	0.31	<0.5	19	68	28	4.79	10	3.41	20	0.53	904
UGA-23	44.00	45.00	1.00	M298520	0.21		2.3	6.77	133	460	1.5	<2	0.34	<0.5	18	65	30	4.93	10	3.19	20	0.61	828
UGA-23	45.00	46.00	1.00	M298522	0.32		2.3	6.78	124	490	1.5	<2	0.3	<0.5	17	67	31	4.58	10	3.6	20	0.53	538
UGA-23	46.00	47.00	1.00	M298523	0.09		2.3	7.02	175	440	1.4	<2	0.37	<0.5	17	69	29	5.78	10	3.55	20	0.59	793
UGA-23	47.00	48.00	1.00	M298524	0.37		2.7	7.22	347	500	1.5	3	0.69	<0.5	20	69	32	4.78	10	3.56	20	0.44	707
UGA-23	48.00	49.00	1.00	M298525	0.27		2.6	6.76	312	370	1.6	2	0.67	<0.5	20	62	24	4.29	10	3.52	20	0.5	506
UGA-23	49.00	50.00	1.00	M298526	0.61		1.5	7.05	110	290	1.5	<2	0.4	<0.5	17	65	29	4.5	10	4.42	20	0.63	1295
UGA-23	50.00	51.00	1.00	M298527	0.5		1.9	6.47	129	360	1.3	2	0.32	<0.5	18	64	28	3.19	10	4.18	20	0.5	356
UGA-23	51.00	52.00	1.00	M298528	1.04		4.7	8.2	117	180	1.8	<2	0.48	<0.5	18	83	38	5.43	20	3.86	30	1.05	1560
UGA-23	52.00	53.00	1.00	M298531	0.15		1.5	7.14	85	550	1.4	<2	0.34	<0.5	18	69	40	4.18	10	3.57	30	0.83	763
UGA-23	53.00	54.00	1.00	M298532	0.12		1.5	7.09	66	660	1.1	<2	0.36	<0.5	20	67	34	4.27	10	3.63	20	1.22	567
UGA-23	54.00	55.00	1.00	M298533	0.12		1.3	6.94	80	460	0.9	<2	0.54	<0.5	19	65	31	4.32	10	4.07	20	1.52	515
UGA-23	55.00	56.00	1.00	M298534	0.04		1.1	7.27	56	280	1	5	0.97	<0.5	19	69	32	4.99	10	4.51	20	1.66	623
UGA-23	56.00	57.00	1.00	M298535	0.06		1.5	6.97	85	470	1	<2	0.57	<0.5	19	67	31	4.06	10	3.65	20	0.96	363
UGA-23	57.00	58.00	1.00	M298536	0.06		1.4	6.27	113	440	1.1	2	1.74	<0.5	21	55	24	5.42	10	3.94	20	1.62	580
UGA-23	58.00	59.00	1.00	M298537	0.06		1.1	6.95	77	560	1.2	3	0.51	<0.5	19	64	28	4.42	10	3.78	20	0.84	786
UGA-23	59.00	60.00	1.00	M298538	0.07		1.7	6.69	78	440	1.5	3	0.46	<0.5	18	65	24	5.65	10	3.81	20	0.81	1370
UGA-23	60.00	61.00	1.00	M298539	0.23		2	6.59	116	570	1.4	<2	0.38	<0.5	19	61	24	4.36	10	3.82	20	0.68	553
UGA-23	61.00	62.00	1.00	M298541	0.05		1.3	6.64	97	580	1.4	<2	0.43	<0.5	26	63	30	7	10	3.6	20	0.98	1830
UGA-23	62.00	63.00	1.00	M298542	0.17		1.3	7.09	65	480	1.2	<2	0.36	<0.5	20	67	28	4.8	10	4.39	20	1.18	899
UGA-23	63.00	64.00	1.00	M298543	0.06		1.8	6.8	103	510	1.4	3	0.36	<0.5	20	61	28	4.68	10	3.66	20	0.93	739
UGA-23	64.00	65.00	1.00	M298544	0.08		1.6	6.77	94	460	1.7	<2	0.38	<0.5	20	63	27	5.79	10	3.78	20	0.94	1450
UGA-23	65.00	66.00	1.00	M298545	1.72		2.2	6.9	115	500	1.6	2	0.5	<0.5	19	66	29	3.98	10	4.2	20	0.69	820
UGA-23	66.00	67.00	1.00	M298546	0.08		1.4	6.58	99	440	1.3	<2	0.33	<0.5	19	67	27	4.63	10	4.33	20	1.02	847
UGA-23	67.00	68.00	1.00	M298547	0.03		1.5	7.3	45	530	1	<2	0.34	<0.5	20	71	33	3.92	10	3.59	20	1.4	584
UGA-23	68.00	69.00	1.00	M298548	2.14		18.5	6.81	92	610	0.9	2	0.36	<0.5	19	64	45	4.1	10	3.38	20	1.45	416
UGA-23	69.00	70.00	1.00	M298549	0.11		1.7	6.39	83	520	1	<2	0.94	<0.5	20	67	31	4.67	10	4.5	20	1.51	713
UGA-23	70.00	71.00	1.00	M298550	0.08		1.2	6.4	111	500	1.2	<2	2	<0.5	22	65	32	5.92	10	4.34	20	2.23	1005
UGA-23	71.00	72.00	1.00	M298551	0.18		1.6	6.19	232	590	1	<2	1.29	<0.5	20	64	32	5.47	10	4.46	20	1.72	715
UGA-23	72.00	73.00	1.00	M298552	0.24		2.2	6.45	223	710	1	5	0.41	<0.5	19	65	33	4.03	10	4.37	20	1.46	409
UGA-23	73.00	74.00	1.00	M298553	0.21		2.5	6.4	267	750	1.2	<2	0.31	<0.5	17	64	34	4.75	10	4.47	20	1.42	718
UGA-23	74.00	75.00	1.00	M298554	0.92		5.7	6.28	502	720	1.4	<2	0.34	<0.5	19	65	33	5.35	10	4.76	20	0.91	569

Hole	From (m)	To (m)	Interval (m)	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
				ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-24	146.00	147.00	1.00	9	0.05	11	1030	7	3.24	52	14	78	<20	0.26	10	<10	91	<10	63			
UGA-24	147.00	148.00	1.00	5	0.01	12	940	2	2.94	44	14	68	<20	0.26	<10	<10	98	<10	62			
UGA-24	148.00	149.00	1.00	2	<0.01	14	880	6	3.09	34	14	41	<20	0.26	<10	<10	104	<10	69			
UGA-24	149.00	150.00	1.00	<1	0.01	6	840	9	1.45	16	19	52	<20	0.41	<10	<10	138	<10	73			
UGA-24	150.00	151.00	1.00	<1	0.01	6	860	13	2.23	16	18	25	<20	0.45	<10	<10	129	<10	76			
UGA-24	151.00	152.00	1.00	1	0.01	4	800	7	0.8	18	16	24	<20	0.38	<10	<10	112	<10	59			
UGA-24	152.00	153.00	1.00	1	0.01	4	820	9	0.85	20	16	25	<20	0.39	<10	<10	111	<10	53			
UGA-24	153.00	154.00	1.00	1	<0.01	2	660	10	0.8	30	13	28	<20	0.31	<10	<10	93	<10	44			
UGA-24	154.00	155.00	1.00	1	0.01	5	770	9	1.37	23	16	19	<20	0.38	<10	<10	115	<10	67			
UGA-24	155.00	156.00	1.00	1	<0.01	5	790	8	1.1	22	15	18	<20	0.37	<10	<10	113	<10	57			
UGA-24	156.00	157.00	1.00	1	<0.01	6	810	7	0.89	18	16	18	<20	0.39	<10	<10	121	<10	69			
UGA-24	157.00	158.00	1.00	2	<0.01	5	840	7	0.78	17	17	19	<20	0.39	<10	<10	119	<10	64			
UGA-24	158.00	159.00	1.00	<1	0.01	5	860	9	0.81	18	17	21	<20	0.43	<10	<10	127	<10	68			
UGA-23	38.00	39.00	1.00	3	<0.01	12	1840	6	3.04	44	19	88	<20	0.34	<10	<10	139	<10	63			
UGA-23	39.00	40.00	1.00	3	<0.01	13	3010	8	2.74	38	19	87	<20	0.33	<10	<10	128	<10	82			
UGA-23	40.00	41.00	1.00	2	0.01	13	970	7	3.04	25	19	81	<20	0.34	<10	<10	142	<10	89			
UGA-23	41.00	42.00	1.00	2	0.01	15	940	6	3.11	23	20	62	<20	0.34	<10	<10	162	<10	111			
UGA-23	42.00	43.00	1.00	2	0.01	17	950	7	3.19	26	20	79	<20	0.35	<10	<10	145	<10	104			
UGA-23	43.00	44.00	1.00	1	0.01	14	1100	8	3.44	24	19	74	<20	0.38	10	<10	139	<10	65			
UGA-23	44.00	45.00	1.00	1	0.01	14	1260	8	3.63	28	20	86	<20	0.37	10	<10	151	<10	76			
UGA-23	45.00	46.00	1.00	1	0.01	14	1090	6	3.7	26	19	93	<20	0.36	10	<10	125	<10	65			
UGA-23	46.00	47.00	1.00	2	0.01	13	1390	4	4.76	34	19	91	<20	0.37	10	<10	125	<10	90			
UGA-23	47.00	48.00	1.00	3	0.03	18	2770	7	4.23	50	21	101	<20	0.38	10	<10	137	<10	51			
UGA-23	48.00	49.00	1.00	4	<0.01	14	2740	10	3.92	51	21	74	<20	0.36	10	<10	139	<10	80			
UGA-23	49.00	50.00	1.00	2	0.01	12	1380	9	2.15	30	21	64	<20	0.36	<10	<10	134	<10	81			
UGA-23	50.00	51.00	1.00	3	<0.01	13	1160	7	2.15	36	19	58	<20	0.34	10	<10	120	<10	57			
UGA-23	51.00	52.00	1.00	9	0.02	17	1350	3	0.84	29	24	64	<20	0.42	<10	<10	167	<10	114			
UGA-23	52.00	53.00	1.00	3	0.03	15	1010	8	1.92	18	21	83	<20	0.37	10	<10	138	<10	92			
UGA-23	53.00	54.00	1.00	1	<0.01	18	1060	4	1.94	23	21	100	<20	0.37	<10	<10	134	<10	70			
UGA-23	54.00	55.00	1.00	7	<0.01	15	1090	5	1.92	34	20	80	<20	0.36	10	<10	132	<10	68			
UGA-23	55.00	56.00	1.00	2	0.01	18	1120	4	1.7	25	22	79	<20	0.37	10	<10	139	<10	78			
UGA-23	56.00	57.00	1.00	5	<0.01	16	1170	9	2.35	26	21	70	<20	0.37	10	<10	132	<10	63			
UGA-23	57.00	58.00	1.00	3	<0.01	18	1130	9	3.11	29	18	90	<20	0.32	<10	<10	115	<10	59			
UGA-23	58.00	59.00	1.00	4	<0.01	15	1330	6	2.18	34	20	98	<20	0.37	<10	<10	125	<10	64			
UGA-23	59.00	60.00	1.00	5	<0.01	17	1420	7	2.84	31	19	116	<20	0.35	<10	<10	127	<10	75			
UGA-23	60.00	61.00	1.00	6	<0.01	16	1310	8	2.96	30	19	129	<20	0.35	<10	<10	131	<10	79			
UGA-23	61.00	62.00	1.00	4	<0.01	22	1240	8	2.71	30	20	107	<20	0.34	10	<10	130	<10	96			
UGA-23	62.00	63.00	1.00	3	<0.01	16	1110	4	1.92	24	21	86	<20	0.37	<10	<10	139	<10	67			
UGA-23	63.00	64.00	1.00	4	<0.01	18	1130	8	2.51	25	20	79	<20	0.36	<10	<10	132	<10	75			
UGA-23	64.00	65.00	1.00	5	<0.01	16	1090	6	2.31	21	20	68	<20	0.35	<10	<10	131	<10	69			
UGA-23	65.00	66.00	1.00	4	<0.01	13	1730	3	2.11	29	19	104	<20	0.36	<10	<10	141	<10	69			
UGA-23	66.00	67.00	1.00	3	<0.01	17	920	4	2.34	21	19	118	<20	0.34	10	<10	132	<10	77			
UGA-23	67.00	68.00	1.00	2	<0.01	15	1040	4	1.74	16	21	143	<20	0.4	10	<10	146	<10	97			
UGA-23	68.00	69.00	1.00	3	<0.01	16	980	8	2.2	26	19	142	<20	0.36	10	<10	136	<10	77			
UGA-23	69.00	70.00	1.00	2	<0.01	17	940	8	1.77	15	19	138	<20	0.34	10	<10	131	<10	59			
UGA-23	70.00	71.00	1.00	<1	<0.01	17	910	7	1.57	17	19	158	<20	0.34	10	<10	130	10	61			
UGA-23	71.00	72.00	1.00	2	<0.01	17	1050	7	2.14	27	19	137	<20	0.33	10	<10	131	<10	61			
UGA-23	72.00	73.00	1.00	4	<0.01	17	1190	8	2.31	28	18	134	<20	0.35	10	<10	132	10	60			
UGA-23	73.00	74.00	1.00	1	<0.01	16	960	9	2.39	24	19	126	<20	0.34	10	<10	132	10	65			
UGA-23	74.00	75.00	1.00	2	<0.01	16	1160	11	3	45	19	117	<20	0.33	10	<10	135	<10	68			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-24	146.00	147.00	1.00							
UGA-24	147.00	148.00	1.00							
UGA-24	148.00	149.00	1.00							
UGA-24	149.00	150.00	1.00							
UGA-24	150.00	151.00	1.00							
UGA-24	151.00	152.00	1.00							
UGA-24	152.00	153.00	1.00							
UGA-24	153.00	154.00	1.00							
UGA-24	154.00	155.00	1.00							
UGA-24	155.00	156.00	1.00							
UGA-24	156.00	157.00	1.00							
UGA-24	157.00	158.00	1.00							
UGA-24	158.00	159.00	1.00							
UGA-23	38.00	39.00	1.00							
UGA-23	39.00	40.00	1.00							
UGA-23	40.00	41.00	1.00							
UGA-23	41.00	42.00	1.00							
UGA-23	42.00	43.00	1.00							
UGA-23	43.00	44.00	1.00							
UGA-23	44.00	45.00	1.00							
UGA-23	45.00	46.00	1.00							
UGA-23	46.00	47.00	1.00							
UGA-23	47.00	48.00	1.00							
UGA-23	48.00	49.00	1.00							
UGA-23	49.00	50.00	1.00							
UGA-23	50.00	51.00	1.00							
UGA-23	51.00	52.00	1.00							
UGA-23	52.00	53.00	1.00							
UGA-23	53.00	54.00	1.00							
UGA-23	54.00	55.00	1.00							
UGA-23	55.00	56.00	1.00							
UGA-23	56.00	57.00	1.00							
UGA-23	57.00	58.00	1.00							
UGA-23	58.00	59.00	1.00							
UGA-23	59.00	60.00	1.00							
UGA-23	60.00	61.00	1.00							
UGA-23	61.00	62.00	1.00							
UGA-23	62.00	63.00	1.00							
UGA-23	63.00	64.00	1.00							
UGA-23	64.00	65.00	1.00							
UGA-23	65.00	66.00	1.00							
UGA-23	66.00	67.00	1.00							
UGA-23	67.00	68.00	1.00							
UGA-23	68.00	69.00	1.00							
UGA-23	69.00	70.00	1.00							
UGA-23	70.00	71.00	1.00							
UGA-23	71.00	72.00	1.00							
UGA-23	72.00	73.00	1.00							
UGA-23	73.00	74.00	1.00							
UGA-23	74.00	75.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
Hole	From (m)	To (m)	Interval (m)	Sample Nr	Au ppm	Au ppm	Ag ppm	Al %	As ppm	Ba ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	Ga ppm	K %	La ppm	Mg %	Mn ppm
UGA-23	75.00	76.00	1.00	M298555	0.56		2.9	7.27	364	730	1.5	<2	0.38	<0.5	19	76	36	4.52	10	4.45	20	1.1	822
UGA-23	76.00	77.00	1.00	M298556	0.56		3.2	6.32	357	610	1.3	4	0.37	<0.5	17	71	38	4.17	10	4.69	20	0.74	568
UGA-23	77.00	78.00	1.00	M298558	0.55		3.7	6.78	386	440	2	<2	0.33	<0.5	22	75	34	6.01	10	4.3	20	0.44	308
UGA-23	78.00	79.00	1.00	M298559	0.58		6.5	6	823	210	1.6	<2	0.48	<0.5	20	67	29	6.48	10	5.04	20	0.3	83
UGA-23	79.00	80.00	1.00	M298561	1.66		34.2	5.28	277	580	1.1	<2	0.35	<0.5	16	64	27	3.55	10	4.49	20	0.28	163
UGA-23	80.00	81.00	1.00	M298562	3.76		21.8	2.92	215	290	0.6	4	0.38	<0.5	8	48	18	2.32	<10	2.96	10	0.05	84
UGA-23	81.00	82.00	1.00	M298564	0.46		12.3	3.22	227	460	0.7	<2	0.28	<0.5	8	40	13	2.68	<10	2.97	10	0.27	227
UGA-23	82.00	83.00	1.00	M298565	0.44		3.6	4.19	1760	230	1.2	2	0.42	<0.5	18	38	13	5.87	10	4.03	10	0.07	72
UGA-23	83.00	84.00	1.00	M298566	0.72		4.7	4.24	2300	50	1.3	<2	1.01	<0.5	18	41	16	5.99	<10	0.63	20	0.09	66
UGA-23	84.00	85.00	1.00	M298567	0.85		5.1	5.52	1595	120	1.9	4	1.18	<0.5	19	42	16	5.96	10	1.32	20	0.15	61
UGA-23	85.00	86.00	1.00	M298568	0.68		14.3	4.44	891	250	1.3	<2	0.36	<0.5	14	44	26	6.05	10	4.08	20	0.13	161
UGA-23	86.00	87.00	1.00	M298569	0.27		1.8	3.78	506	480	0.9	<2	0.55	<0.5	11	45	16	3.8	<10	3.77	20	0.11	141
UGA-23	87.00	88.00	1.00	M298570	0.24		2.3	4.96	333	580	0.8	<2	0.59	<0.5	13	36	14	3.53	10	4.63	20	0.09	57
UGA-23	88.00	89.00	1.00	M298571	1.05		2	2.52	2150	200	0.8	<2	1.65	<0.5	13	44	11	6.48	<10	2.35	10	0.04	94
UGA-23	89.00	90.00	1.00	M298572	0.64		1.8	3.33	472	450	0.7	2	1.54	<0.5	9	47	16	3.86	<10	3.47	10	0.04	83
UGA-23	90.00	91.00	1.00	M298573	1.88		5	3.6	544	280	0.6	<2	0.85	<0.5	11	57	18	4.23	<10	3.95	20	0.05	80
UGA-23	91.00	92.00	1.00	M298575	0.23		1.7	5.22	1725	350	1.3	<2	2.13	<0.5	17	52	16	5.39	10	4.74	20	0.13	57
UGA-23	92.00	93.00	1.00	M298576	0.18		2.1	5.42	312	660	0.7	3	0.54	<0.5	14	55	18	3.52	10	4.96	20	0.11	58
UGA-23	93.00	94.00	1.00	M298577	0.6		3.4	3.99	717	480	1.1	3	1.44	<0.5	12	46	16	3.51	<10	4.15	20	0.06	77
UGA-23	94.00	95.00	1.00	M298578	0.54		3.2	3.37	803	240	0.8	<2	1.16	<0.5	10	51	18	4.97	<10	3.47	10	0.06	73
UGA-23	95.00	96.00	1.00	M298579	2.14		5	3.72	1080	120	0.9	<2	1.25	<0.5	12	44	21	6.05	<10	3.63	20	0.09	65
UGA-23	96.00	97.00	1.00	M298581	2.24		6.6	4.02	2520	110	2.1	<2	2.85	<0.5	18	45	26	9.96	10	1.52	20	0.15	67
UGA-23	97.00	98.00	1.00	M298582	1.12		6.5	5.59	831	200	1.3	3	0.98	<0.5	17	56	32	4.2	10	4.42	20	0.17	55
UGA-23	98.00	99.00	1.00	M298583	0.7		7.3	6.19	761	310	1.8	<2	0.63	<0.5	18	47	30	5.12	10	5.14	20	0.2	754
UGA-23	99.00	100.00	1.00	M298584	2.54		6.8	6.33	806	770	1.5	2	0.62	<0.5	19	45	32	5.49	10	4.36	20	0.32	1710
UGA-23	100.00	101.00	1.00	M298585	0.62		7.3	6.36	1095	270	1.3	<2	0.56	<0.5	17	45	35	6.2	10	3.54	20	0.45	1790
UGA-23	101.00	102.00	1.00	M298586	0.53		4.4	6.58	857	740	1.2	<2	0.37	<0.5	18	49	35	4.43	10	3.82	20	0.43	1125
UGA-23	102.00	103.00	1.00	M298587	0.42		5.8	6.96	916	830	1.5	<2	0.43	<0.5	19	49	29	5.5	10	4.31	20	0.41	1540
UGA-23	103.00	104.00	1.00	M298588	0.41		4.5	6.29	992	520	1.5	2	0.72	<0.5	16	45	30	4.2	10	3.96	20	0.28	349
UGA-23	104.00	105.00	1.00	M298589	0.6		7.2	6.71	1305	340	1.6	<2	0.48	<0.5	17	49	37	5.28	10	4.13	20	0.28	405
UGA-23	105.00	106.00	1.00	M298590	0.38		4.3	6.64	911	520	1.6	3	0.42	<0.5	17	59	34	4.91	10	3.54	20	0.39	750
UGA-23	106.00	107.00	1.00	M298591	0.52		5.8	5.95	1285	520	1.7	3	1.68	<0.5	16	50	29	4.13	10	3.75	20	0.23	68
UGA-23	107.00	108.00	1.00	M298592	0.25		2.9	7.31	1105	690	2.3	<2	0.43	<0.5	21	55	39	6.82	10	4.06	30	0.65	1930
UGA-23	108.00	109.00	1.00	M298593	0.86		5.3	7.14	1385	280	1.6	<2	0.76	<0.5	21	61	54	4.9	10	3.63	20	0.26	61
UGA-23	109.00	110.00	1.00	M298594	0.35		4.1	6.54	1415	380	2	<2	1.11	<0.5	19	61	47	4.66	10	3.28	20	0.23	60
UGA-23	110.00	111.00	1.00	M298595	0.6		5.5	7.3	1585	310	1.7	<2	0.93	<0.5	20	60	44	4.8	10	4.19	30	0.3	55
UGA-23	111.00	112.00	1.00	M298596	0.48		5.4	7.63	1415	580	1.6	<2	0.35	<0.5	19	63	36	4.57	10	4.27	30	0.32	97
UGA-23	112.00	113.00	1.00	M298597	1.05		9.7	7.63	1485	370	1.7	3	0.36	<0.5	20	61	73	6.9	10	3.74	30	0.36	808
UGA-23	113.00	114.00	1.00	M298598	0.76		7.2	8.34	1440	490	1.9	6	0.38	<0.5	22	68	63	5.28	20	4.26	30	0.34	119
UGA-23	114.00	115.00	1.00	M298599	0.63		8.1	6.69	1235	250	1.3	<2	0.45	<0.5	18	61	37	4.71	10	3.77	20	0.24	81
UGA-23	115.00	116.00	1.00	M298601	0.42		5.3	6.31	1060	150	1.2	<2	0.29	<0.5	18	50	32	5.88	10	3.52	20	1.26	1005
UGA-23	116.00	117.00	1.00	M298603	0.57		5.8	7.79	1180	900	1.8	5	0.38	<0.5	20	62	69	6.53	20	3.68	30	0.62	839
UGA-23	117.00	118.00	1.00	M298604	0.44		6.7	7.93	962	570	1.8	5	0.45	<0.5	21	65	57	4.63	10	4.37	30	0.31	208
UGA-23	118.00	119.00	1.00	M298605	0.11		2.3	3.51	210	300	0.9	3	0.46	<0.5	9	46	17	2.45	10	2.63	10	0.19	75
UGA-23	119.00	120.00	1.00	M298606	0.04		0.9	3.51	92	330	0.9	<2	0.31	<0.5	9	53	14	2.78	<10	3.37	10	0.21	208
UGA-23	120.00	121.00	1.00	M298607	0.05		1.8	4.97	90	620	0.8	4	0.51	<0.5	12	52	17	3.05	<10	4.35	10	0.31	369
UGA-23	121.00	122.00	1.00	M298609	0.02		1.6	5.51	37	250	1.7	3	0.64	<0.5	18	65	28	4.79	10	3.6	20	0.7	617
UGA-23	122.00	123.00	1.00	M298610	0.02		1.6	5.2	55	210	1.7	5	0.48	<0.5	17	60	19	4.01	10	2.97	20	0.48	467
UGA-23	123.00	124.00	1.00	M298611	0.04		2.3	5.08	40	200	1.4	2	1.88	<0.5	16	57	19	4.31	10	2.71	20	1.26	391
UGA-23	124.00	125.00	1.00	M298612	0.07		1.9	4.45	50	100	1.1	2	1.22	<0.5	13	56	18	3.13	10	1.55	10	0.87	188

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-23	75.00	76.00	1.00	1	<0.01	17	1330	9	1.99	27	22	132	<20	0.4	10	<10	155	<10	85			
UGA-23	76.00	77.00	1.00	1	<0.01	14	1190	10	2.76	44	19	141	<20	0.34	10	<10	137	10	72			
UGA-23	77.00	78.00	1.00	3	0.01	19	1320	10	5.05	49	20	131	<20	0.37	10	<10	153	10	78			
UGA-23	78.00	79.00	1.00	6	0.03	17	2060	14	6.05	78	17	123	<20	0.32	10	<10	122	<10	59			
UGA-23	79.00	80.00	1.00	4	<0.01	13	1410	11	3.59	72	14	141	<20	0.27	10	<10	99	<10	75			
UGA-23	80.00	81.00	1.00	4	0.01	7	1570	6	2.09	74	6	96	<20	0.13	10	<10	27	<10	39			
UGA-23	81.00	82.00	1.00	3	0.02	7	1110	6	2.2	66	8	62	<20	0.15	10	<10	42	<10	31			
UGA-23	82.00	83.00	1.00	4	0.05	10	1830	8	5.5	160	9	82	<20	0.2	40	<10	48	<10	38			
UGA-23	83.00	84.00	1.00	4	0.01	13	4410	8	6.14	193	11	39	<20	0.22	40	<10	54	<10	21			
UGA-23	84.00	85.00	1.00	4	0.01	14	5150	11	5.76	141	13	43	<20	0.28	30	<10	72	<10	22			
UGA-23	85.00	86.00	1.00	7	0.04	9	1590	10	4.82	137	13	78	<20	0.23	20	10	65	<10	44			
UGA-23	86.00	87.00	1.00	7	<0.01	8	2300	8	3.7	71	9	79	<20	0.2	10	<10	63	<10	21			
UGA-23	87.00	88.00	1.00	5	0.01	9	2550	9	3.58	56	11	105	<20	0.25	10	<10	87	<10	25			
UGA-23	88.00	89.00	1.00	17	0.01	11	7000	7	6.46	182	6	68	<20	0.12	40	<10	30	<10	21			
UGA-23	89.00	90.00	1.00	6	<0.01	8	6810	6	3.79	68	9	74	<20	0.16	<10	<10	38	<10	22			
UGA-23	90.00	91.00	1.00	10	0.02	9	3610	13	4.31	71	9	89	<20	0.18	10	<10	50	<10	27			
UGA-23	91.00	92.00	1.00	10	0.03	14	9250	6	4.86	139	14	147	<20	0.28	30	10	77	<10	55			
UGA-23	92.00	93.00	1.00	18	<0.01	10	2350	11	3.62	49	13	109	<20	0.28	20	<10	74	<10	51			
UGA-23	93.00	94.00	1.00	29	0.01	11	6250	9	3.25	90	9	85	<20	0.2	20	<10	52	<10	30			
UGA-23	94.00	95.00	1.00	35	0.02	9	5060	9	5.03	79	8	67	<20	0.16	20	<10	50	<10	23			
UGA-23	95.00	96.00	1.00	40	0.03	11	5330	9	6.17	87	9	72	<20	0.19	20	<10	54	<10	27			
UGA-23	96.00	97.00	1.00	19	0.01	17	>10000	14	>10.0	134	10	66	<20	0.23	30	<10	78	<10	24			
UGA-23	97.00	98.00	1.00	10	0.04	13	4160	13	4.46	71	14	91	<20	0.29	10	<10	105	<10	60			
UGA-23	98.00	99.00	1.00	2	0.06	17	2580	14	4.42	57	15	91	<20	0.31	<10	<10	129	<10	75			
UGA-23	99.00	100.00	1.00	3	0.04	14	2300	9	3.93	64	17	87	<20	0.3	10	<10	117	<10	131			
UGA-23	100.00	101.00	1.00	2	0.11	15	1990	12	4.18	66	17	95	<20	0.31	20	<10	129	<10	85			
UGA-23	101.00	102.00	1.00	3	0.09	13	1250	8	3.37	33	17	109	<20	0.32	10	<10	118	<10	73			
UGA-23	102.00	103.00	1.00	2	0.09	16	1450	10	3.89	41	18	100	<20	0.33	10	<10	132	<10	88			
UGA-23	103.00	104.00	1.00	3	0.1	12	2970	8	4.14	51	16	90	<20	0.3	10	<10	121	<10	60			
UGA-23	104.00	105.00	1.00	3	0.14	12	1890	10	4.65	68	18	98	<20	0.33	10	<10	124	<10	61			
UGA-23	105.00	106.00	1.00	2	0.11	15	1570	10	4.03	46	18	98	<20	0.34	10	<10	133	<10	71			
UGA-23	106.00	107.00	1.00	3	0.09	10	7320	10	4.24	72	15	100	<20	0.29	10	<10	107	<10	44			
UGA-23	107.00	108.00	1.00	2	0.1	17	1430	11	4.59	39	20	93	<20	0.36	10	<10	139	<10	94			
UGA-23	108.00	109.00	1.00	3	0.16	13	3250	13	5.06	43	18	113	<20	0.36	10	<10	126	<10	62			
UGA-23	109.00	110.00	1.00	4	0.15	13	4810	12	4.46	58	17	108	<20	0.36	10	<10	135	<10	63			
UGA-23	110.00	111.00	1.00	2	0.14	15	3910	8	5.03	61	18	126	<20	0.37	20	<10	117	<10	54			
UGA-23	111.00	112.00	1.00	2	0.14	13	1370	6	4.47	56	21	138	<20	0.39	20	<10	143	<10	54			
UGA-23	112.00	113.00	1.00	3	0.15	17	1400	7	4.89	64	21	119	<20	0.38	10	<10	136	<10	92			
UGA-23	113.00	114.00	1.00	3	0.13	17	1510	14	4.91	57	22	112	<20	0.42	10	<10	151	<10	96			
UGA-23	114.00	115.00	1.00	2	0.1	15	1850	13	4.8	70	17	102	<20	0.34	10	<10	116	<10	76			
UGA-23	115.00	116.00	1.00	3	0.1	14	1030	15	4.36	43	17	83	<20	0.31	10	<10	138	<10	87			
UGA-23	116.00	117.00	1.00	3	0.03	17	1560	10	4.17	58	22	91	<20	0.39	10	<10	150	<10	91			
UGA-23	117.00	118.00	1.00	2	0.03	15	1860	11	4.09	61	21	92	<20	0.4	10	10	142	<10	74			
UGA-23	118.00	119.00	1.00	3	<0.01	7	1930	6	2.43	34	9	78	<20	0.15	10	<10	51	<10	52			
UGA-23	119.00	120.00	1.00	2	0.01	9	910	5	2.62	35	9	152	<20	0.17	10	<10	33	<10	84			
UGA-23	120.00	121.00	1.00	3	<0.01	11	710	5	2.82	23	10	143	<20	0.18	10	<10	39	<10	43			
UGA-23	121.00	122.00	1.00	4	0.01	16	910	8	4.68	23	18	158	<20	0.3	10	<10	108	<10	53			
UGA-23	122.00	123.00	1.00	3	0.01	14	1520	2	3.75	26	15	92	<20	0.27	10	<10	99	<10	55			
UGA-23	123.00	124.00	1.00	3	<0.01	15	770	8	4.32	30	16	112	<20	0.27	10	<10	93	<10	47			
UGA-23	124.00	125.00	1.00	2	<0.01	13	810	3	3.27	24	13	63	<20	0.22	<10	<10	77	<10	56			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-23	75.00	76.00	1.00							
UGA-23	76.00	77.00	1.00							
UGA-23	77.00	78.00	1.00							
UGA-23	78.00	79.00	1.00							
UGA-23	79.00	80.00	1.00							
UGA-23	80.00	81.00	1.00							
UGA-23	81.00	82.00	1.00							
UGA-23	82.00	83.00	1.00							
UGA-23	83.00	84.00	1.00							
UGA-23	84.00	85.00	1.00							
UGA-23	85.00	86.00	1.00							
UGA-23	86.00	87.00	1.00							
UGA-23	87.00	88.00	1.00							
UGA-23	88.00	89.00	1.00							
UGA-23	89.00	90.00	1.00							
UGA-23	90.00	91.00	1.00							
UGA-23	91.00	92.00	1.00							
UGA-23	92.00	93.00	1.00							
UGA-23	93.00	94.00	1.00							
UGA-23	94.00	95.00	1.00							
UGA-23	95.00	96.00	1.00							
UGA-23	96.00	97.00	1.00							
UGA-23	97.00	98.00	1.00							
UGA-23	98.00	99.00	1.00							
UGA-23	99.00	100.00	1.00							
UGA-23	100.00	101.00	1.00							
UGA-23	101.00	102.00	1.00							
UGA-23	102.00	103.00	1.00							
UGA-23	103.00	104.00	1.00							
UGA-23	104.00	105.00	1.00							
UGA-23	105.00	106.00	1.00							
UGA-23	106.00	107.00	1.00							
UGA-23	107.00	108.00	1.00							
UGA-23	108.00	109.00	1.00							
UGA-23	109.00	110.00	1.00							
UGA-23	110.00	111.00	1.00							
UGA-23	111.00	112.00	1.00							
UGA-23	112.00	113.00	1.00							
UGA-23	113.00	114.00	1.00							
UGA-23	114.00	115.00	1.00							
UGA-23	115.00	116.00	1.00							
UGA-23	116.00	117.00	1.00							
UGA-23	117.00	118.00	1.00							
UGA-23	118.00	119.00	1.00							
UGA-23	119.00	120.00	1.00							
UGA-23	120.00	121.00	1.00							
UGA-23	121.00	122.00	1.00							
UGA-23	122.00	123.00	1.00							
UGA-23	123.00	124.00	1.00							
UGA-23	124.00	125.00	1.00							

					Au-AA26	Au-GRA22	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61
					Au	Au	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Co	Cr	Cu	Fe	Ga	K	La	Mg	Mn
Hole	From (m)	To (m)	Interval (m)	Sample Nr	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	%	ppm	%	ppm
UGA-23	125.00	126.00	1.00	M298613	0.11		1.4	4.48	165	30	1.3	<2	2.91	<0.5	13	43	17	3.56	10	1.57	10	1.87	738
UGA-23	126.00	127.00	1.00	M298614	0.05		1.5	5.47	137	120	1.6	<2	0.82	<0.5	12	28	25	3.08	10	2.16	20	0.76	345
UGA-23	127.00	128.00	1.00	M298615	0.11		0.9	7.14	160	200	1.6	<2	0.28	<0.5	14	20	30	4.29	10	2.73	20	0.83	888
UGA-23	128.00	129.00	1.00	M298616	0.04		1.2	7.72	267	290	1.6	<2	0.3	<0.5	17	23	34	3.75	10	3.1	20	0.59	270
UGA-23	129.00	130.00	1.00	M298617	0.05		1.1	7.67	400	150	1.6	2	1.14	<0.5	15	22	30	4.05	20	3.3	20	1.05	377
UGA-23	130.00	131.00	1.00	M298618	0.03		1.1	7.26	229	130	1.4	<2	2.01	<0.5	15	24	28	4.17	20	2.63	20	1.66	1030
UGA-23	131.00	132.00	1.00	M298620	2.41		2	6.16	117	110	1.5	<2	0.25	<0.5	12	20	21	3.12	10	2.48	20	0.7	446
UGA-23	132.00	133.00	1.00	M298621	0.49		1.1	6.63	70	120	1.6	<2	0.27	<0.5	15	21	29	3.69	10	2.34	20	1.02	734
UGA-23	133.00	134.00	1.00	M298622	0.6		1.2	7.18	74	120	1.8	<2	0.3	<0.5	12	20	34	3.78	20	2.55	20	1.18	706
UGA-23	134.00	135.00	1.00	M298623	0.68		2	7.14	321	140	2.2	<2	0.3	<0.5	16	20	33	3.49	20	2.57	20	0.98	627
UGA-23	135.00	136.00	1.00	M298624	0.53		1.1	7.04	84	180	1.9	<2	0.31	<0.5	13	20	34	3.74	20	2.4	20	0.99	693
UGA-23	136.00	137.00	1.00	M298625	0.33		0.7	6.56	62	170	1.4	<2	0.28	<0.5	14	22	28	3	10	2.3	20	0.72	479
UGA-23	137.00	138.00	1.00	M298626	0.01		<0.5	7.61	35	270	1.8	<2	2.7	<0.5	16	19	20	4.8	20	2.71	20	2.05	1195
UGA-23	143.00	144.00	1.00	M298627	0.01		<0.5	7.89	25	260	1.8	<2	2.32	<0.5	9	3	36	3.28	20	3.23	10	1.32	961
UGA-23	144.00	145.00	1.00	M298628	0.27		0.6	8.72	51	290	2	<2	1.26	<0.5	12	4	44	3.67	20	3.47	20	1	877
UGA-23	145.00	146.00	1.00	M298629	0.22		0.9	8.54	57	340	2.1	<2	0.45	<0.5	14	3	40	4.65	20	3.25	20	0.87	1105
UGA-23	146.00	147.00	1.00	M298630	0.88		1.9	7.46	67	270	1.7	<2	0.49	0.7	10	4	85	2	10	3	20	0.5	327
UGA-23	147.00	148.00	1.00	M298632	0.41		1.3	7.41	52	230	1.6	<2	0.32	<0.5	9	6	66	2.33	10	2.64	20	0.44	407
UGA-23	148.00	149.00	1.00	M298633	0.08		0.9	8.18	70	330	1.9	<2	1.65	<0.5	16	3	35	4.06	20	3.31	10	1.06	1275
UGA-23	149.00	150.00	1.00	M298634	0.02		<0.5	8.69	72	440	2	<2	1.25	<0.5	10	3	37	3.38	20	3.88	20	1.08	724
UGA-23	164.00	165.00	1.00	M298635	<0.01		<0.5	7.9	11	360	1.3	2	4.64	<0.5	12	3	34	3.43	20	2.8	10	0.86	847
UGA-23	165.00	166.00	1.00	M298636	<0.01		<0.5	7.37	18	330	1.3	<2	4.69	<0.5	9	3	32	3.43	10	2.63	10	1	880
UGA-23	166.00	167.00	1.00	M298637	0.01		<0.5	7.39	34	380	1.3	2	4.14	<0.5	10	2	37	3.12	20	2.65	10	0.59	714
UGA-23	167.00	168.00	1.00	M298638	<0.01		<0.5	7.14	22	390	1.3	4	4.01	<0.5	9	3	36	2.94	20	2.52	10	0.61	677
UGA-23	168.00	169.00	1.00	M298639	<0.01		<0.5	7.42	23	380	1.4	<2	3.68	<0.5	11	3	39	3.01	20	2.64	10	0.59	640
UGA-23	169.00	170.00	1.00	M298641	0.01		<0.5	7.76	20	380	1.3	4	4.45	<0.5	10	3	35	3.24	20	2.58	10	0.77	747
UGA-23	170.00	171.00	1.00	M298642	<0.01		<0.5	7.96	19	390	1.4	<2	4.38	<0.5	9	2	37	3.28	20	2.72	10	0.69	756
UGA-23	171.00	172.00	1.00	M298643	<0.01		<0.5	7.5	26	390	1.3	<2	3.87	<0.5	10	2	38	3.22	20	2.85	10	0.65	700
UGA-23	172.00	173.00	1.00	M298644	0.01		<0.5	7.88	35	400	1.2	<2	4.87	<0.5	9	2	36	3.39	20	2.91	10	0.98	790

				ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	ME-ICP61	Ag-OG62	Au-SCR24
				Mo	Na	Ni	P	Pb	S	Sb	Sc	Sr	Th	Ti	Tl	U	V	W	Zn	Ag	Au Total (+)(-) Combined	
Hole	From (m)	To (m)	Interval (m)	ppm	%	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
UGA-23	125.00	126.00	1.00	2	0.01	11	680	7	3.58	22	13	73	<20	0.23	<10	<10	87	<10	49			
UGA-23	126.00	127.00	1.00	2	0.01	8	700	11	2.97	32	14	29	<20	0.29	10	<10	93	<10	56			
UGA-23	127.00	128.00	1.00	2	0.01	4	800	2	2.89	20	17	18	<20	0.39	10	<10	115	<10	70			
UGA-23	128.00	129.00	1.00	1	<0.01	8	860	4	3.52	18	17	18	<20	0.44	10	<10	125	<10	77			
UGA-23	129.00	130.00	1.00	3	0.01	6	890	12	3.99	19	18	29	<20	0.43	10	<10	130	<10	78			
UGA-23	130.00	131.00	1.00	2	0.01	4	770	10	2.74	17	17	53	<20	0.39	10	<10	120	<10	40			
UGA-23	131.00	132.00	1.00	2	0.01	3	730	9	1.96	24	14	18	<20	0.35	<10	<10	110	<10	33			
UGA-23	132.00	133.00	1.00	2	0.01	5	820	7	1	21	15	21	<20	0.37	<10	<10	115	<10	57			
UGA-23	133.00	134.00	1.00	1	0.01	4	860	6	0.61	20	16	19	<20	0.39	10	<10	122	<10	59			
UGA-23	134.00	135.00	1.00	1	0.01	7	810	14	0.71	30	16	17	<20	0.4	<10	<10	121	<10	53			
UGA-23	135.00	136.00	1.00	<1	0.01	4	820	11	0.5	18	16	21	<20	0.39	<10	<10	116	<10	70			
UGA-23	136.00	137.00	1.00	3	0.02	5	780	7	0.75	27	15	20	<20	0.36	<10	<10	106	<10	73			
UGA-23	137.00	138.00	1.00	1	0.01	7	650	17	0.54	14	18	48	<20	0.43	10	<10	121	<10	69			
UGA-23	143.00	144.00	1.00	1	0.06	1	830	12	0.62	14	12	49	<20	0.43	<10	<10	95	<10	62			
UGA-23	144.00	145.00	1.00	2	0.04	3	890	13	1.18	13	13	30	<20	0.45	10	<10	100	<10	73			
UGA-23	145.00	146.00	1.00	1	0.03	4	870	14	0.79	16	13	22	<20	0.43	10	<10	100	<10	71			
UGA-23	146.00	147.00	1.00	4	0.03	4	1770	16	0.67	28	11	23	<20	0.38	10	<10	87	<10	109			
UGA-23	147.00	148.00	1.00	1	0.06	3	910	10	0.98	21	10	28	<20	0.36	10	<10	85	<10	81			
UGA-23	148.00	149.00	1.00	1	0.05	2	790	11	1.04	11	12	29	<20	0.41	10	<10	91	<10	66			
UGA-23	149.00	150.00	1.00	<1	0.01	5	700	18	0.44	14	13	27	<20	0.45	<10	<10	85	<10	78			
UGA-23	164.00	165.00	1.00	<1	0.05	1	790	14	0.32	8	11	84	<20	0.41	<10	<10	88	<10	66			
UGA-23	165.00	166.00	1.00	1	0.06	2	780	13	0.22	11	11	101	<20	0.39	<10	<10	82	<10	90			
UGA-23	166.00	167.00	1.00	<1	0.06	<1	800	13	0.37	10	10	74	<20	0.42	<10	<10	89	<10	54			
UGA-23	167.00	168.00	1.00	<1	0.1	2	810	10	0.24	10	10	80	<20	0.42	<10	<10	87	<10	52			
UGA-23	168.00	169.00	1.00	<1	0.1	<1	820	14	0.29	11	10	79	<20	0.43	<10	<10	94	<10	79			
UGA-23	169.00	170.00	1.00	1	0.07	<1	840	11	0.31	12	11	82	<20	0.42	<10	<10	89	<10	61			
UGA-23	170.00	171.00	1.00	<1	0.08	<1	860	10	0.2	10	11	74	<20	0.44	<10	<10	92	<10	57			
UGA-23	171.00	172.00	1.00	<1	0.1	<1	830	11	0.27	10	11	78	<20	0.42	10	<10	98	<10	72			
UGA-23	172.00	173.00	1.00	<1	0.12	<1	830	12	0.51	9	11	107	<20	0.41	<10	<10	87	<10	60			

				Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-SCR24	Au-AA26	Au-AA26D
				Au (+) Fraction	Au (-) Fraction	Au (+) mg	WT. + Frac Entire	WT. - Frac Entire	Au	Au
Hole	From (m)	To (m)	Interval (m)	ppm	ppm	mg	g	g	ppm	ppm
UGA-23	125.00	126.00	1.00							
UGA-23	126.00	127.00	1.00							
UGA-23	127.00	128.00	1.00							
UGA-23	128.00	129.00	1.00							
UGA-23	129.00	130.00	1.00							
UGA-23	130.00	131.00	1.00							
UGA-23	131.00	132.00	1.00							
UGA-23	132.00	133.00	1.00							
UGA-23	133.00	134.00	1.00							
UGA-23	134.00	135.00	1.00							
UGA-23	135.00	136.00	1.00							
UGA-23	136.00	137.00	1.00							
UGA-23	137.00	138.00	1.00							
UGA-23	143.00	144.00	1.00							
UGA-23	144.00	145.00	1.00							
UGA-23	145.00	146.00	1.00							
UGA-23	146.00	147.00	1.00							
UGA-23	147.00	148.00	1.00							
UGA-23	148.00	149.00	1.00							
UGA-23	149.00	150.00	1.00							
UGA-23	164.00	165.00	1.00							
UGA-23	165.00	166.00	1.00							
UGA-23	166.00	167.00	1.00							
UGA-23	167.00	168.00	1.00							
UGA-23	168.00	169.00	1.00							
UGA-23	169.00	170.00	1.00							
UGA-23	170.00	171.00	1.00							
UGA-23	171.00	172.00	1.00							
UGA-23	172.00	173.00	1.00							