

16 October 2024

SXG Confirms Third High-Grade Gold-Antimony Mineralised Zone At Sunday Creek Project

140 m Down-dip Extension, Includes 3.3 m @ 34.1 g/t AuEq and 12.9 m @ 7.4 g/t AuEq

Melbourne, Australia — Southern Cross Gold Ltd (“SXG” or the “Company”) (ASX: SXG) announces a significant discovery expanding mineralisation 140 m below previous drilling at the historic Golden Dyke mine at the 100%-owned Sunday Creek Gold-Antimony Project in Victoria (Figure 5).

Results from two diamond drill holes (SDDSC132 and SDDSC138 – Figures 1 and 2) significantly improve the immediate prospectivity of Sunday Creek demonstrating that Golden Dyke has become the third high-grade gold-antimony prospect located 260 m and 600 m west respectively from the first two, Rising Sun and Apollo.

HIGHLIGHTS

- **High-Grade Results:** Drilling has yielded further exceptional results 140 m below previous drilling at Golden Dyke. These discoveries are located outside the January 23, 2024 exploration target estimation, and include:
 - **SDDSC138**, drilled up to 250 m below surface, confirmed **twelve vein sets** from Rising Sun to Golden Dyke. The hole demonstrated high-grade continuity in three vein sets and defined nine new vein sets. The hole included **15 intercepts of Au > 20 g/t (up to 183 g/t Au)** and **19 intercepts of Sb > 5% (up to 33.8% Sb)**. Selected highlights include:
 - **3.3 m @ 34.1 g/t AuEq** (24.6 g/t Au, 5.0% Sb) from 294.6 m, including:
 - **1.8 m @ 62.3 g/t AuEq** (44.8 g/t Au, 9.3% Sb) from 294.6 m
 - **12.9 m @ 7.4 g/t AuEq** (4.5 g/t Au, 1.6% Sb) from 311.0 m, including:
 - **3.1 m @ 20.2 g/t AuEq** (11.3 g/t Au, 4.7% Sb) from 316.9 m
 - **SDDSC132**, drilled up to 480 m below surface, is the **deepest reported hole drilled east-west at Golden Dyke**. The hole intercepted **six vein sets** across Rising Sun and Golden Dyke, **five of which are new**. Selected highlights include:
 - **2.2 m @ 16.7 g/t AuEq** (13.0 g/t Au, 2.0% Sb) from 146.2 m, including:
 - **0.3 m @ 110.1 g/t AuEq** (77.0 g/t Au, 17.6% Sb) from 146.4 m
 - **6.5 m @ 4.7 g/t AuEq** (3.0 g/t Au, 0.9% Sb) from 541.9 m, including:
 - **2.6 m @ 10.5 g/t AuEq** (6.9 g/t Au, 1.9% Sb) from 543.2 m
- **Ongoing Exploration:** The company has planned a significant number of further holes under Golden Dyke, with 60 km of diamond drilling planned at Sunday Creek over the next year. Twenty-two holes are currently being processed and analysed with an additional five holes in progress. Five rigs are operating with a sixth rig due at site during early November 2024.

SOUTHERN CROSS GOLD LTD

Level 21, 459 Collins Street, Melbourne Vic 3000 Australia
 Justin Mouchacca - Company Secretary
 p: +61 3 8630 3321 e: jm@southerncrossgold.com.au
 Nicholas Mead - Investor Relations
 p: +61 415 153 122 e: info@southerncrossgold.com.au

ABN: 70 652 166 795
 ASX Code: SXG
 Issued Capital: 198.4M fully paid shares

Michael Hudson, Managing Director of SXG states: *"The Sunday Creek project keeps on delivering, this time through more high-grade gold and antimony results from our deepest holes under the most prolific historic mine, Golden Dyke, which now joins Rising Sun and Apollo as the third high-grade mineralised prospect at Sunday Creek.*

"Sunday Creek continues to expand and be better understood through our systematic drill program. SDDSC138 has revealed twelve vein sets, including nine that were previously unmodelled. High-grade intercepts, such as 1.8 m @ 62.3 g/t AuEq from 294.6 m, confirm that the system continues below the historic Golden Dyke mine and west of the prior globally-leading drill results we have already delivered below the historic Rising Sun and Apollo mines.

"Importantly, SDDSC132, drilled up to 480 m below surface is our deepest east-west hole at Golden Dyke to date, intercepted six vein sets, indicating that the mineralisation extends at depth as it does at Rising Sun and Apollo immediately to its east. This hole was targeted to test up to 140 m below our previously reported SDDSC130 and demonstrates continuity of the system, that is crucial for our ongoing definition work.

"The Golden Dyke area is situated 260 m west of Rising Sun and 600 m west of Apollo and represents a significant expansion of the known mineralised footprint at the exciting Sunday Creek project. These results are particularly significant as they establish a third distinct high-grade mineralised zone within the Sunday Creek project. The identification of this new zone, alongside the previously known Rising Sun and Apollo areas, substantially increases the project's potential.

"With our planned 60 km diamond drilling program over the coming year, we expect to further delineate these zones and potentially uncover additional mineralised areas, that could significantly expand our mineral inventory at Sunday Creek.

"Strategically, these exciting discoveries compliment recent SXG releases that outline additional freehold land acquisitions, regional geophysical surveys and the Scheme of Arrangement with Mawson Gold Ltd that will lead to a consolidated ownership of Sunday Creek, as well as a dual listing in Australia and Canada on both the ASX and TSXV respectively."

Drill Hole Discussion

SDDSC138 was drilled east to west, parallel to and within the dyke/breccia host structure (the ladder "rails") and intercepted twelve mineralised vein sets (the ladder "rungs") across Rising Sun and Golden Dyke, while testing a prospective corridor of 292 m (cumulative downhole length of dyke and sericite/carbonate altered sediment). SDDSC138 included **15 intercepts of Au > 20 g/t (up to 183 g/t Au)** and **19 intercepts of Sb > 5% (up to 33.8% Sb)**. This hole drilled up to 250 m below surface and 55 m to 85 m above and parallel to SDDSC130 (reported [05 September, 2024](#)) which provided continuity of mineralised structures, some relatively close to surface:

Extended highlights from SDDSC138 include:

- **0.3 m @ 38.3 g/t AuEq** (24.7 g/t Au, 7.3% Sb) from 131.9 m, including:
 - o **0.1 m @ 122.2 g/t AuEq** (77.5 g/t Au, 23.8% Sb) from 131.9 m
- **1.9 m @ 2.0 g/t AuEq** (0.7 g/t Au, 0.7% Sb) from 143.2 m
- **1.2 m @ 8.4 g/t AuEq** (8.2 g/t Au, 0.1% Sb) from 285.9 m
- **3.3 m @ 34.1 g/t AuEq** (24.6 g/t Au, 5.0% Sb) from 294.6 m, including:
 - o **1.8 m @ 62.3 g/t AuEq** (44.8 g/t Au, 9.3% Sb) from 294.6 m
- **1.0 m @ 2.9 g/t AuEq** (0.7 g/t Au, 1.2% Sb) from 302.5 m
- **12.9 m @ 7.4 g/t AuEq** (4.5 g/t Au, 1.6% Sb) from 311.0 m, including:

- **0.4 m @ 20.3 g/t AuEq** (16.4 g/t Au, 2.1% Sb) from 311.0 m
- **1.6 m @ 11.9 g/t AuEq** (7.9 g/t Au, 2.1% Sb) from 313.0 m
- **3.1 m @ 20.2 g/t AuEq** (11.3 g/t Au, 4.7% Sb) from 316.9 m
- **3.0 m @ 3.1 g/t AuEq** (2.8 g/t Au, 0.2% Sb) from 336.2 m, including:
 - **1.0 m @ 5.5 g/t AuEq** (5.2 g/t Au, 0.1% Sb) from 337.7 m
- **6.9 m @ 3.2 g/t AuEq** (2.1 g/t Au, 0.6% Sb) from 351.6 m, including:
 - **2.0 m @ 5.3 g/t AuEq** (4.0 g/t Au, 0.7% Sb) from 354.0 m
- **4.7 m @ 1.1 g/t AuEq** (0.9 g/t Au, 0.1% Sb) from 367.5 m
- **0.7 m @ 3.7 g/t AuEq** (1.1 g/t Au, 1.4% Sb) from 380.9 m
- **2.4 m @ 1.7 g/t AuEq** (1.1 g/t Au, 0.3% Sb) from 386.1 m
- **1.4 m @ 3.7 g/t AuEq** (2.9 g/t Au, 0.4% Sb) from 398.3 m
- **0.6 m @ 3.6 g/t AuEq** (2.9 g/t Au, 0.4% Sb) from 402.3 m
- **4.5 m @ 3.9 g/t AuEq** (3.2 g/t Au, 0.4% Sb) from 405.2 m, including:
 - **1.1 m @ 10.8 g/t AuEq** (9.9 g/t Au, 0.5% Sb) from 408.2 m
- **10.5 m @ 6.2 g/t AuEq** (4.2 g/t Au, 1.1% Sb) from 414.0 m, including:
 - **1.8 m @ 9.7 g/t AuEq** (6.7 g/t Au, 1.6% Sb) from 414.0 m
 - **0.2 m @ 80.1 g/t AuEq** (78.2 g/t Au, 1.0% Sb) from 417.0 m
 - **2.7 m @ 7.5 g/t AuEq** (3.9 g/t Au, 1.9% Sb) from 421.8 m
- **1.1 m @ 17.4 g/t AuEq** (12.9 g/t Au, 2.4% Sb) from 427.6 m
- **0.8 m @ 3.0 g/t AuEq** (0.5 g/t Au, 1.3% Sb) from 434.4 m
- **3.5 m @ 1.3 g/t AuEq** (0.4 g/t Au, 0.5% Sb) from 439.3 m
- **1.7 m @ 41.7 g/t AuEq** (38.3 g/t Au, 1.8% Sb) from 445.0 m
- **8.5 m @ 4.8 g/t AuEq** (1.7 g/t Au, 1.7% Sb) from 453.4 m, including:
 - **0.5 m @ 22.2 g/t AuEq** (9.7 g/t Au, 6.6% Sb) from 456.7 m
 - **0.9 m @ 22.8 g/t AuEq** (3.2 g/t Au, 10.4% Sb) from 458.6 m

SDDSC132, drilled up to 480 m below surface, is the deepest reported east to west drill hole (parallel to the ladder “rails”) drilled at the Golden Dyke prospect, with two deeper holes being processed/in progress (SDDSC141 and SDDSC147). The hole intercepted six high-grade vein sets across Rising Sun and Golden Dyke (Figures 1 to 3), while testing a prospective corridor of 210 m (cumulative downhole length of dyke and sericite/carbonate altered sediment). SDDSC132 was drilled up to 140 m below and parallel to SDDSC130. The hole included **five intervals of > 20 g/t Au (up to 77.0 g/t Au)** and **five intervals > 5% Sb (up to 17.6% Sb)**.

Extended highlights from SDDSC132 include:

- **0.8 m @ 6.5 g/t AuEq** (6.5 g/t Au, 0.0% Sb) from 126.0 m
- **2.2 m @ 16.7 g/t AuEq** (13.0 g/t Au, 2.0% Sb) from 146.2 m, including:
 - **0.3 m @ 110.1 g/t AuEq** (77.0 g/t Au, 17.6% Sb) from 146.4 m
 - **0.4 m @ 21.0 g/t AuEq** (20.9 g/t Au, 0.0% Sb) from 148.0 m

- **3.3 m @ 1.2 g/t AuEq** (0.7 g/t Au, 0.3% Sb) from 151.2 m
- **1.8 m @ 2.3 g/t AuEq** (2.3 g/t Au, 0.0% Sb) from 162.1 m
- **1.6 m @ 3.6 g/t AuEq** (3.2 g/t Au, 0.2% Sb) from 170.8 m
- **3.5 m @ 4.0 g/t AuEq** (2.8 g/t Au, 0.7% Sb) from 186.6 m, including:
 - o **0.1 m @ 57.8 g/t AuEq** (28.5 g/t Au, 15.6% Sb) from 186.6 m
- **1.7 m @ 2.4 g/t AuEq** (1.9 g/t Au, 0.2% Sb) from 534.3 m
- **6.5 m @ 4.7 g/t AuEq** (3.0 g/t Au, 0.9% Sb) from 541.9 m, including:
 - o **2.6 m @ 10.5 g/t AuEq** (6.9 g/t Au, 1.9% Sb) from 543.2 m
- **3.6 m @ 3.9 g/t AuEq** (3.0 g/t Au, 0.5% Sb) from 550.8 m, including:
 - o **1.8 m @ 4.4 g/t AuEq** (2.8 g/t Au, 0.8% Sb) from 550.8 m
- **3.6 m @ 1.0 g/t AuEq** (0.7 g/t Au, 0.2% Sb) from 570.2 m
- **1.4 m @ 2.1 g/t AuEq** (0.3 g/t Au, 1.0% Sb) from 588.5 m
- **0.7 m @ 2.9 g/t AuEq** (1.7 g/t Au, 0.6% Sb) from 610.3 m

Pending Results and Update

Twenty-two holes (SDDSC129, 131, 133-137, 139-143, 146, 050W1, 050W2, 092W1, 092W2, 137W1, 137W2) are currently being processed and analysed, with five holes (SDDSC120W1, 144, 145, 146W1, 147) in progress (Figure 1 and 2).

Exploration Target

On January 23, 2024, SXG announced the maiden gold and antimony **Exploration Target** at its flagship 100%-owned Sunday Creek Project in Victoria, Australia. The Exploration Target ranges reported are shown in Table 1. Notably, the Exploration Target was constrained to the current drill footprint at Apollo and Rising Sun as they contain sufficient drilling to determine continuity and infer grade ranges. This represents approximately **one third to one half the strike of the main drill area and significant potential exists to increase the size of the exploration target** with high grade drill results drilled for up to 450 m beyond the Exploration Target area. Drilling since January has significantly expanded the footprint of mineralisation beyond the bounds of the exploration target area, especially including SDDSC130 announced in this press release (Figure 2).

Table 1. Sunday Creek Exploration Target for Apollo and Rising Sun at the Sunday Creek Project

Range	Tonnes (Mt)	AuEq g/t*	Au g/t	Sb %	Au Eq (Moz)	Au (Moz)	Sb (kt)
Lower Case	4.4	7.2	5.3	1.2	1.0	0.74	53.5
Upper Case	5.1	9.7	7.8	1.2	1.6	1.28	62.8

The potential quantity and grade of the Exploration Target is conceptual in nature and therefore is an approximation. There has been insufficient exploration to estimate a Mineral Resource and it is uncertain if further exploration will result in the estimation of a Mineral Resource. The Exploration Target has been prepared and reported in accordance with the 2012 edition of the JORC Code.

About Sunday Creek

The Sunday Creek epizonal-style gold project is located 60 km north of Melbourne within 19,365 hectares of granted exploration tenements. SXG is also the freehold landholder of 133.29 hectares that form the key portion in and around the main drilled area at the Sunday Creek Project.

Gold and antimony form in a relay of vein sets that cut across a steeply dipping zone of intensely altered rocks (the “host”). When observed from above, the host resembles the side rails of a ladder, where the sub-vertical mineralised vein sets are the rungs that extend from surface to depth. At Apollo and Rising Sun these individual ‘rungs’ have been defined over 600 m depth extent from surface to 1,100 m below surface, are 2.5 m to 3.5 m wide (median widths) (and up to 10 m), and 20 m to 100 m in strike.

Cumulatively, 136 drill holes for 61,969 m have been reported by SXG (and Mawson Gold Ltd) from Sunday Creek since late 2020. An additional 11 holes for 566 m from Sunday Creek were abandoned due to deviation or hole conditions. Fourteen drillholes for 2,383 m have been reported regionally outside of the main Sunday Creek drill area. A total of 64 historic drill holes for 5,599 m were completed from the late 1960s to 2008. The project now contains a total of **forty-six (46) >100 g/t AuEq x m and fifty-five (55) >50 to 100 g/t AuEq x m drill holes** by applying a 2 m @ 1 g/t lower cut.

Our systematic drill program is strategically targeting these significant vein formations, initially these have been defined over 1,350 m strike of the host from Christina to Apollo prospects, of which approximately 620 m has been more intensively drill tested (Rising Sun to Apollo). At least 62 ‘rungs’ have been defined to date, defined by high-grade intercepts (20 g/t to >7,330 g/t Au) along with lower grade edges. Ongoing step-out drilling is aiming to uncover the potential extent of this mineralised system.

Geologically, the project is located within the Melbourne Structural Zone in the Lachlan Fold Belt. The regional host to the Sunday Creek mineralisation is an interbedded turbidite sequence of siltstones and minor sandstones metamorphosed to sub-greenschist facies and folded into a set of open north-west trending folds.

Further Information

Further discussion and analysis of the Sunday Creek project is available through the interactive Vrify 3D animations, presentations and videos all available on the SXG website. These data, along with an interview on these results with Managing Director Michael Hudson can be viewed at www.southerncrossgold.com.au.

No upper gold grade cut is applied in the averaging and intervals are reported as drill thickness. However, during future Mineral Resource studies, the requirement for assay top cutting will be assessed.

Figures 1 to 5 show project location, plan and longitudinal views of drill results reported here and Tables 2 to 4 provide collar and assay data. The true thickness of the mineralised intervals reported individually as estimated true widths (“ETW”), otherwise they are interpreted to be approximately 40% to 70% of the sampled thickness for other reported holes. Lower grades were cut at 1.0 g/t AuEq lower cutoff over a maximum width of 2 m with higher grades cut at 5.0 g/t AuEq lower cutoff over a maximum of 1 m width unless specified.

Critical Metal Epizonal Gold-Antimony Deposits

Sunday Creek (Figure 1) is an epizonal gold-antimony deposit formed in the late Devonian (like Fosterville, Costerfield and Redcastle), 60 million years later than mesozonal gold systems formed in Victoria (for example Ballarat and Bendigo). Epizonal deposits are a form of orogenic gold deposit classified according to their depth of formation: epizonal (<6 km), mesozonal (6-12 km) and hypozonal (>12 km).

Epizonal deposits in Victoria often have associated high levels of the critical metal, antimony, and Sunday Creek is no exception. China claims a 56 per cent share of global mined supplies of antimony, according to a 2023 European Union study. Antimony features highly on the critical minerals lists of many countries including Australia, the United States of America, Canada, Japan and the European Union. Australia ranks seventh for antimony production despite all production coming from a single mine at Costerfield in Victoria, located nearby to all SXG projects. Antimony alloys with lead and tin which results in improved properties for solders, munitions, bearings and batteries. Antimony is a prominent additive for halogen-containing flame retardants. Adequate supplies of antimony are critical to the world's energy transition, and to the high-tech industry, especially the semi-conductor and defence sectors where it is a critical additive to primers in munitions.

In August 2024, the Chinese government announced it will place export limits from September 15, 2024 on

antimony and antimony products. This will put pressure on Western defence supply chains and negatively affect the supply of the metal and push up pricing given China's dominance of the supply of the metal in the global markets. This is positive for SXG as we are likely to have one of the very few large and high-quality projects of antimony in the western world that can feed western demand into the future.

Antimony represents approximately 20% in situ recoverable value of Sunday Creek at an AuEq of 1.88.

Gold Equivalent Calculation

SXG considers that both gold and antimony that are included in the gold equivalent calculation ("AuEq") have reasonable potential to be recovered at Sunday Creek, given current geochemical understanding, historic production statistics and geologically analogous mining operations. Historically, ore from Sunday Creek was treated onsite or shipped to the Costerfield mine, located 54 km to the northwest of the project, for processing during WW1. SXG considers that it is appropriate to adopt the same gold equivalent variables as Mandalay Resources Ltd in its Mandalay Technical Report, 2024 dated 28 March 2024. The gold equivalence formula used by Mandalay Resources was calculated using Costerfield's 2023 production costs, using a gold price of US\$1,900 per ounce, an antimony price of US\$12,000 per tonne and 2023 total year metal recoveries of 94% for gold and 89% for antimony, and is as follows:

$$AuEq = Au (g/t) + 1.88 \times Sb (\%)$$

Based on the latest Costerfield calculation and given the similar geological styles and historic toll treatment of Sunday Creek mineralisation at Costerfield, SXG considers that a $AuEq = Au (g/t) + 1.88 \times Sb (\%)$ is appropriate to use for the initial exploration targeting of gold-antimony mineralisation at Sunday Creek.

- Ends -

This announcement has been approved for release by the Board of Southern Cross Gold Ltd.

Competent Person Statement

Information in this announcement that relates to new exploration results contained in this report is based on information compiled by Mr Kenneth Bush and Mr Michael Hudson. Mr Bush is a Member of Australian Institute of Geoscientists and a Registered Professional Geologist in the field of Mining (#10315) and Mr Hudson is a Fellow of The Australasian Institute of Mining and Metallurgy. Mr Bush and Mr Hudson each have sufficient experience relevant to the style of mineralisation and type of deposit under consideration, and to the activities undertaken, to qualify as a Competent Person as defined in the 2012 Edition of the Joint Ore Reserves Committee (JORC) Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves. Mr Bush is Exploration Manager and Mr Hudson is Managing Director of Southern Cross Gold Limited and both consent to the inclusion in the report of the matters based on their information in the form and context in which it appears.

Information in this report that relates to the Exploration Target for the Sunday Creek Project is based on information compiled by Mr Kenneth Bush and Mr Michael Hudson. Mr Bush is a Member of Australian Institute of Geoscientists and Mr Hudson is a Fellow of The Australasian Institute of Mining and Metallurgy. Mr Bush and Mr Hudson each have sufficient experience relevant to the style of mineralisation and type of deposit under consideration, and to the activities undertaken, to qualify as a Competent Person as defined in the 2012 Edition of the Joint Ore Reserves Committee (JORC) Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves. Mr Bush is Exploration Manager and Mr Hudson is Managing Director of Southern Cross Gold Limited and both consent to the inclusion in the report of the matters based on their information in the form and context in which it appears.

Certain information in this announcement that relates to prior exploration results is extracted from the Independent Geologist's Report dated 16 March 2022 which was issued with the consent of the Competent Person, Mr Terry C. Lees. The report is included the Company's prospectus dated 17 March 2022 which was released as an announcement to ASX on 12 May 2022 and is available at www2.asx.com.au under code "SXG". The Company confirms that it is not aware of any new information or data that materially affects the information related to exploration results included in the original market announcement. The Company confirms that the form and context of the Competent Persons' findings in relation to the report have not been materially modified from the original

market announcement.

Certain information in this announcement also relates to prior drill hole exploration results, are extracted from the following announcements, which are available to view on www.southerncrossgold.com.au:

- [4 October, 2022](#) SDDSC046, [20 October, 2022](#) SDDSC049, [1 June, 2023](#) SDDSC066, [12 October, 2023](#) SDDL003 & 4, [23 October, 2023](#) SDDSC082, [9 November, 2023](#) SDDSC091, [13 June 2024](#) SDDSC118, [5 September, 2024](#) SDDSC130.

The Company confirms that it is not aware of any new information or data that materially affects the information included in the original document/announcement and the Company confirms that the form and context in which the Competent Person's findings are presented have not materially modified from the original market announcement.

For further information, please contact:

Justin Mouchacca, Company Secretary, jm@southerncrossgold.com.au, +61 3 8630 3321

Nicholas Mead, Corporate Development, nm@southerncrossgold.com.au, +61 415 153 122

Figure 2: Sunday Creek longitudinal section across A-B in the plane of the dyke breccia/alterated sediment host looking towards the north (striking 236 degrees) showing mineralised veins sets. Showing holes SDDSC132 and 138 reported here (blue highlighted box, black trace), with selected intersections and prior reported drill holes. The vertical extents of the vein sets are limited by proximity to drill hole pierce points. For location refer to Figure 1.




Figure 3: Sunday Creek regional plan view showing soil sampling, structural framework, regional historic epizonal gold mining areas and broad regional areas tested by 12 holes for 2,383 m drill program. The regional drill areas are at Tonstal, Consols and Leviathan located 4,000-7,500 m along strike from the main drill area at Golden Dyke- Apollo.




Figure 4: Location of the Sunday Creek project, along with the Redcastle JV.




Table 2: Drill collar summary table for recent drill holes in progress.

Hole_ID	Depth (m)	Prospect	East GDA94_Z55	North GDA94_Z55	Elevation	Azimuth	Plunge
SDDSC114W1	625.1	Rising Sun	330464	5867914	286.6	82	-58
SDDSC119W1	643	Apollo	331498	5867858	336.7	272.5	-45.2
SDDSC123	124.3	Apollo	331499	5867859	337	276	-52
SDDSC124	969.3	Apollo	331499	5867859	337	274	-52.2
SDDSC121W1	953.4	Rising Sun	330510	5867852	296.6	72	-63.8
SDDSC125	551.7	Golden Dyke	330462	5867920	285.6	212	-68
SDDSC126	941.4	Rising Sun	330815	5867599	295.7	321.6	-54
SDDSC122W1	1007.8	Rising Sun	330338	5867860	276.5	72	-61.4
SDDSC050W1	797.1	Rising Sun	330539	5867885	295.3	77	-63
SDDSC127	483.2	Apollo	331498	5867858	336.9	271.3	-43.3
SDDSC128	745.1	Apollo	331465	5867867	333.1	272.6	-43.3
SDDSC129	1269.8	Rising Sun	330388	5867860	276.5	77.3	-57.3
SDDSC092W1	767	Rising Sun	330537.2	5867882.6	295.5	82.2	-61.1
SDDSC130	614	Golden Dyke	330777	5867891	295.9	255	-42
SDDSC050W2	789.4	Rising Sun	330539	5867885	295.3	77	-63
SDDSC131	179.6	Christina	330081	5867609	273.1	284	-47
SDDSC132	746.3	Golden Dyke	330776.9	5867890.5	295.9	261.5	-50
SDDSC133	347.2	Apollo East	331380	5867740	335	8	-42
SDDSC134	230.9	Christina	330080.9	5867609.3	273.1	302.5	-61.5
SDDSC135	182.4	Christina	330080.9	5867609.3	273.1	342.5	-51
SDDSC136	349	Apollo East	331380	5867740	335	329	-41
SDDSC137	299.7	Christina	330080.9	5867609.3	273	40	-62
SDDSC138	530.1	Golden Dyke	330776.9	5867890.5	296	250	-36
SDDSC139	469.2	Apollo East	331465.4	5867865.1	333.2	267	-37.4
SDDSC140	349.9	Christina	330080.9	5867609.3	273.1	8.9	-70.2
SDDSC092W2	739.3	Rising Sun	330537.2	5867882.6	295.5	82.2	-61.1
SDDSC137W1	199.5	Christina	330074.9	5867612.4	273.6	41	-61.9
SDDSC137W2	223	Christina	330074.9	5867612.4	273.6	41	-61.9
SDDSC092W3	799.5	Rising Sun	330537.2	5867882.6	295.5	82.2	-61.1
SDDSC141	935.3	Golden Dyke	330809	5867842	301	271.5	-53
SDDSC142	500.7	Christina	330075	5867612	273.6	292	-70
SDDSC143	667.8	Apollo	331464.1	5867864.9	332.9	270.3	-39.1
SDDSC144	In progress plan 700 m	Rising Sun	330338.1	5867860	276.5	76	-55.5
SDDSC145	In progress plan 925 m	Apollo	331593.6	5867955	344.4	264.2	-40
SDDSC120W1	In progress plan 1050 m	Rising Sun	331107.9	5867977.2	319.2	266.5	-55
SDDSC146	245.7	Christina	330072.8	5867611.9	273.7	273	-42
SDDSC146W1	In progress plan 500 m	Christina	330072.8	5867611.9	273.7	273	-42
SDDSC147	In progress plan 1430 m	Golden Dyke	330809	5867842	277.5	277.5	-56.5

Table 3: Table of mineralised drill hole intersections reported from SDDSC132 and 138 using two cutoff criteria. Lower grades cut at 1.0 g/t AuEq lower cutoff over a maximum of 2 m with higher grades cut at 5.0 g/t AuEq cutoff over a maximum of 1 m.

Hole-ID	From (m)	To (m)	Length (m)	Au g/t	Sb%	AuEq g/t
SDDSC132	126.0	126.8	0.8	6.5	0.0	6.5
SDDSC132	146.2	148.4	2.2	13.0	2.0	16.7
including	146.4	146.7	0.3	77.0	17.6	110.1
including	148.0	148.4	0.4	20.9	0.0	21.0
SDDSC132	151.2	154.5	3.3	0.7	0.3	1.2
SDDSC132	162.1	163.9	1.8	2.3	0.0	2.3
SDDSC132	170.8	172.4	1.6	3.2	0.2	3.6
SDDSC132	186.6	190.1	3.5	2.8	0.7	4.0
including	186.6	186.7	0.1	28.5	15.6	57.8
SDDSC132	534.3	536.0	1.7	1.9	0.2	2.4
SDDSC132	541.9	548.4	6.5	3.0	0.9	4.7
including	543.2	545.8	2.6	6.9	1.9	10.5
SDDSC132	550.8	554.4	3.6	3.0	0.5	3.9
including	550.8	552.6	1.8	2.8	0.8	4.4
SDDSC132	570.2	573.8	3.6	0.7	0.2	1.0
SDDSC132	588.5	589.9	1.4	0.3	1.0	2.1
SDDSC132	610.3	611.0	0.7	1.7	0.6	2.9
SDDSC138	131.9	132.2	0.3	24.7	7.3	38.3
including	131.9	132.0	0.1	77.5	23.8	122.2
SDDSC138	143.2	145.1	1.9	0.7	0.7	2.0
SDDSC138	285.9	287.1	1.2	8.2	0.1	8.4
SDDSC138	294.6	297.9	3.3	24.6	5.0	34.1
including	294.6	296.4	1.8	44.8	9.3	62.3
SDDSC138	302.5	303.5	1.0	0.7	1.2	2.9
SDDSC138	311.0	323.9	12.9	4.5	1.6	7.4
including	311.0	311.4	0.4	16.4	2.1	20.3
including	313.0	314.6	1.6	7.9	2.1	11.9
including	316.9	320.0	3.1	11.3	4.7	20.2
SDDSC138	336.2	339.2	3.0	2.8	0.2	3.1
including	337.7	338.7	1.0	5.2	0.1	5.5
SDDSC138	351.6	358.5	6.9	2.1	0.6	3.2
including	354.0	356.0	2.0	4.0	0.7	5.3
SDDSC138	367.5	372.2	4.7	0.9	0.1	1.1
SDDSC138	380.9	381.6	0.7	1.1	1.4	3.7
SDDSC138	386.1	388.5	2.4	1.1	0.3	1.7
SDDSC138	398.3	399.7	1.4	2.9	0.4	3.7
SDDSC138	402.3	402.9	0.6	2.9	0.4	3.6

SDDSC138	405.2	409.7	4.5	3.2	0.4	3.9
including	408.2	409.3	1.1	9.9	0.5	10.8
SDDSC138	414.0	424.5	10.5	4.2	1.1	6.2
including	414.0	415.8	1.8	6.7	1.6	9.7
including	417.0	417.2	0.2	78.2	1.0	80.1
including	421.8	424.5	2.7	3.9	1.9	7.5
SDDSC138	427.6	428.7	1.1	12.9	2.4	17.4
SDDSC138	434.4	435.2	0.8	0.5	1.3	3.0
SDDSC138	439.3	442.8	3.5	0.4	0.5	1.3
SDDSC138	445.0	446.7	1.7	38.3	1.8	41.7
SDDSC138	453.4	461.9	8.5	1.7	1.7	4.8
including	456.7	457.2	0.5	9.7	6.6	22.2
including	458.6	459.5	0.9	3.2	10.4	22.8
Hole-ID	From (m)	To (m)	Length (m)	Au g/t	Sb%	AuEq g/t
SDDSC132	125.98	126.78	0.8	6.5	0.0	6.5
SDDSC132	146.22	148.42	2.2	13.0	2.0	16.7
including	146.42	146.72	0.3	77.0	17.6	110.1
including	148.04	148.44	0.4	20.9	0.0	21.0
SDDSC132	151.17	154.47	3.3	0.7	0.3	1.2
SDDSC132	162.06	163.86	1.8	2.3	0.0	2.3
SDDSC132	170.8	172.4	1.6	3.2	0.2	3.6
SDDSC132	186.61	190.11	3.5	2.8	0.7	4.0
including	186.61	186.71	0.1	28.5	15.6	57.8
SDDSC132	534.26	535.96	1.7	1.9	0.2	2.4
SDDSC132	541.89	548.39	6.5	3.0	0.9	4.7
including	543.18	545.78	2.6	6.9	1.9	10.5
SDDSC132	550.8	554.4	3.6	3.0	0.5	3.9
including	550.8	552.6	1.8	2.8	0.8	4.4
SDDSC132	570.18	573.78	3.6	0.7	0.2	1.0
SDDSC132	588.53	589.93	1.4	0.3	1.0	2.1
SDDSC132	610.29	610.99	0.7	1.7	0.6	2.9
SDDSC138	131.93	132.23	0.3	24.7	7.3	38.3
including	131.93	132.03	0.1	77.5	23.8	122.2
SDDSC138	143.18	145.08	1.9	0.7	0.7	2.0
SDDSC138	285.85	287.05	1.2	8.2	0.1	8.4
SDDSC138	294.61	297.91	3.3	24.6	5.0	34.1
including	294.61	296.41	1.8	44.8	9.3	62.3
SDDSC138	302.48	303.48	1	0.7	1.2	2.9
SDDSC138	311	323.9	12.9	4.5	1.6	7.4
including	311	311.4	0.4	16.4	2.1	20.3
including	312.95	314.55	1.6	7.9	2.1	11.9
including	316.94	320.04	3.1	11.3	4.7	20.2

SDDSC138	336.23	339.23	3	2.8	0.2	3.1
including	337.69	338.69	1	5.2	0.1	5.5
SDDSC138	351.59	358.49	6.9	2.1	0.6	3.2
including	354	356	2	4.0	0.7	5.3
SDDSC138	367.45	372.15	4.7	0.9	0.1	1.1
SDDSC138	380.89	381.59	0.7	1.1	1.4	3.7
SDDSC138	386.05	388.45	2.4	1.1	0.3	1.7
SDDSC138	398.33	399.73	1.4	2.9	0.4	3.7
SDDSC138	402.33	402.93	0.6	2.9	0.4	3.6
SDDSC138	405.21	409.71	4.5	3.2	0.4	3.9
including	408.23	409.33	1.1	9.9	0.5	10.8
SDDSC138	414	424.5	10.5	4.2	1.1	6.2
including	414	415.8	1.8	6.7	1.6	9.7
including	416.96	417.16	0.2	78.2	1.0	80.1
including	421.8	424.5	2.7	3.9	1.9	7.5
SDDSC138	427.55	428.65	1.1	12.9	2.4	17.4
SDDSC138	434.4	435.2	0.8	0.5	1.3	3.0
SDDSC138	439.32	442.82	3.5	0.4	0.5	1.3
SDDSC138	445	446.7	1.7	38.3	1.8	41.7
SDDSC138	453.4	461.9	8.5	1.7	1.7	4.8
including	456.73	457.23	0.5	9.7	6.6	22.2
including	458.55	459.45	0.9	3.2	10.4	22.8

Table 4: All individual assays reported from SDDSC132 and 138 reported here >0.1g/t AuEq.

Hole number	From (m)	To (m)	Length (m)	Au ppm	Sb%	AuEq (g/t)
SDDSC132	34.4	35.6	1.2	0.2	0.0	0.2
SDDSC132	124.0	124.6	0.7	0.2	0.0	0.2
SDDSC132	124.6	125.3	0.6	0.2	0.0	0.2
SDDSC132	125.3	126.0	0.7	0.2	0.0	0.2
SDDSC132	126.0	126.8	0.8	6.5	0.0	6.5
SDDSC132	126.8	127.3	0.5	0.2	0.0	0.2
SDDSC132	127.3	127.9	0.5	0.1	0.0	0.1
SDDSC132	127.9	128.4	0.5	0.7	0.0	0.7
SDDSC132	140.8	141.2	0.4	0.1	0.0	0.1
SDDSC132	145.8	146.2	0.4	0.9	0.0	0.9
SDDSC132	146.2	146.4	0.2	3.9	0.1	4.2
SDDSC132	146.4	146.7	0.3	77.0	17.6	110.1
SDDSC132	146.7	146.9	0.2	0.7	0.0	0.7
SDDSC132	146.9	147.4	0.5	0.3	0.0	0.3
SDDSC132	148.0	148.5	0.4	20.9	0.0	21.0
SDDSC132	148.5	148.6	0.1	0.1	0.0	0.1
SDDSC132	148.6	149.1	0.5	0.1	0.0	0.2
SDDSC132	149.1	149.5	0.4	0.3	0.0	0.4
SDDSC132	149.5	150.0	0.6	0.1	0.0	0.1
SDDSC132	151.2	151.6	0.5	1.0	0.0	1.1
SDDSC132	151.6	152.0	0.4	1.1	0.0	1.1
SDDSC132	152.0	152.8	0.8	0.2	0.0	0.2
SDDSC132	152.8	153.2	0.5	0.1	0.0	0.2
SDDSC132	153.2	153.4	0.2	1.9	0.6	3.0
SDDSC132	153.4	154.0	0.6	0.1	0.0	0.1
SDDSC132	154.0	154.4	0.4	1.4	0.4	2.1
SDDSC132	154.4	154.5	0.1	2.2	6.6	14.6
SDDSC132	154.5	155.0	0.5	0.8	0.1	1.0
SDDSC132	155.0	156.2	1.2	0.2	0.0	0.2
SDDSC132	156.2	156.4	0.2	0.5	0.0	0.5
SDDSC132	156.4	157.1	0.7	0.2	0.0	0.2
SDDSC132	157.1	157.5	0.4	0.9	0.0	1.0
SDDSC132	157.5	158.5	1.0	0.1	0.0	0.1
SDDSC132	158.5	159.5	1.0	0.2	0.0	0.2
SDDSC132	159.5	160.5	1.0	0.4	0.0	0.4
SDDSC132	160.5	161.3	0.8	0.4	0.0	0.4
SDDSC132	161.3	161.7	0.4	0.6	0.0	0.6
SDDSC132	161.7	162.1	0.4	0.8	0.0	0.8
SDDSC132	162.1	162.2	0.1	2.2	0.0	2.2

SDDSC132	162.2	162.6	0.4	0.5	0.0	0.5
SDDSC132	162.6	163.2	0.6	2.0	0.0	2.0
SDDSC132	163.2	163.3	0.2	4.4	0.0	4.4
SDDSC132	163.3	163.8	0.5	3.6	0.0	3.6
SDDSC132	166.0	166.6	0.6	0.3	0.0	0.3
SDDSC132	166.6	166.9	0.3	1.3	0.0	1.3
SDDSC132	166.9	167.2	0.3	2.4	0.0	2.4
SDDSC132	167.2	167.6	0.4	0.8	0.0	0.8
SDDSC132	167.6	168.4	0.8	0.2	0.0	0.2
SDDSC132	170.0	170.8	0.8	0.1	0.0	0.1
SDDSC132	170.8	171.0	0.2	1.0	0.5	1.9
SDDSC132	171.7	172.1	0.4	0.4	0.0	0.4
SDDSC132	172.1	172.4	0.3	15.3	0.6	16.5
SDDSC132	172.4	173.3	0.9	0.2	0.0	0.2
SDDSC132	176.5	176.6	0.1	0.7	0.1	0.9
SDDSC132	176.6	176.9	0.2	7.1	0.3	7.7
SDDSC132	177.7	178.4	0.7	0.1	0.0	0.1
SDDSC132	178.4	178.7	0.4	0.5	0.0	0.5
SDDSC132	178.7	179.3	0.6	0.3	0.0	0.4
SDDSC132	180.3	180.6	0.3	0.9	0.0	0.9
SDDSC132	184.5	185.0	0.5	0.2	0.0	0.2
SDDSC132	185.4	186.0	0.6	0.2	0.0	0.2
SDDSC132	186.6	186.8	0.1	28.5	15.6	57.8
SDDSC132	186.8	187.7	0.9	0.2	0.0	0.3
SDDSC132	187.7	188.2	0.5	0.3	0.0	0.3
SDDSC132	188.2	189.0	0.9	4.2	0.0	4.2
SDDSC132	189.0	190.1	1.1	1.7	0.1	1.8
SDDSC132	193.2	193.4	0.2	1.1	0.0	1.1
SDDSC132	193.4	193.9	0.6	0.4	0.0	0.4
SDDSC132	194.7	195.2	0.5	0.3	0.0	0.3
SDDSC132	195.2	195.7	0.6	0.1	0.0	0.1
SDDSC132	196.9	197.3	0.4	3.7	0.0	3.7
SDDSC132	460.2	460.8	0.6	0.6	0.0	0.6
SDDSC132	460.8	461.5	0.7	0.1	0.0	0.1
SDDSC132	461.5	461.9	0.3	0.1	0.0	0.2
SDDSC132	461.9	462.3	0.4	0.2	0.1	0.3
SDDSC132	475.0	475.2	0.2	0.1	0.0	0.1
SDDSC132	493.0	493.6	0.6	0.1	0.0	0.2
SDDSC132	515.9	516.6	0.7	0.2	0.0	0.2
SDDSC132	516.6	516.8	0.2	0.0	1.0	1.9
SDDSC132	532.7	533.3	0.7	0.3	0.0	0.3

SDDSC132	533.3	533.8	0.4	0.3	0.1	0.5
SDDSC132	533.8	534.3	0.5	0.1	0.3	0.6
SDDSC132	534.3	535.0	0.7	2.4	0.2	2.8
SDDSC132	535.0	535.2	0.2	4.5	1.1	6.5
SDDSC132	535.2	536.0	0.9	0.9	0.1	1.2
SDDSC132	536.0	537.1	1.1	0.2	0.0	0.3
SDDSC132	538.1	538.2	0.1	2.4	0.4	3.2
SDDSC132	538.2	538.6	0.4	0.1	0.0	0.2
SDDSC132	538.6	538.7	0.2	0.7	0.3	1.3
SDDSC132	539.8	540.3	0.4	0.2	0.1	0.4
SDDSC132	540.3	540.4	0.2	0.3	0.2	0.6
SDDSC132	540.4	541.3	0.8	0.4	0.0	0.4
SDDSC132	541.9	542.4	0.5	0.5	0.3	1.1
SDDSC132	542.4	543.2	0.8	0.2	0.0	0.2
SDDSC132	543.2	543.3	0.1	28.7	0.0	28.8
SDDSC132	543.3	543.8	0.5	0.2	0.0	0.2
SDDSC132	543.8	544.2	0.4	8.7	0.3	9.3
SDDSC132	544.2	544.4	0.2	2.5	0.2	2.8
SDDSC132	544.4	545.2	0.8	0.7	0.2	1.1
SDDSC132	545.2	545.4	0.2	61.2	0.2	61.6
SDDSC132	545.4	545.8	0.5	1.1	10.4	20.7
SDDSC132	545.8	546.6	0.8	0.3	0.1	0.4
SDDSC132	546.6	547.2	0.6	0.1	0.1	0.2
SDDSC132	547.2	547.5	0.3	0.6	0.4	1.4
SDDSC132	547.5	548.0	0.6	0.1	0.0	0.1
SDDSC132	548.0	548.4	0.4	0.9	1.2	3.1
SDDSC132	548.4	549.0	0.6	0.1	0.1	0.3
SDDSC132	549.0	549.9	0.9	0.2	0.4	1.0
SDDSC132	549.9	550.8	0.9	0.1	0.0	0.1
SDDSC132	550.8	550.9	0.1	3.1	1.4	5.7
SDDSC132	550.9	551.5	0.6	0.3	0.4	1.0
SDDSC132	551.5	551.9	0.4	2.4	1.7	5.5
SDDSC132	551.9	552.4	0.5	5.2	0.8	6.6
SDDSC132	552.4	552.6	0.2	7.1	0.7	8.4
SDDSC132	552.6	553.2	0.7	0.1	0.1	0.2
SDDSC132	553.2	554.0	0.8	0.2	0.1	0.4
SDDSC132	554.0	554.2	0.2	18.3	0.1	18.6
SDDSC132	554.2	554.4	0.2	13.3	0.2	13.7
SDDSC132	554.4	555.1	0.8	0.2	0.1	0.4
SDDSC132	555.1	556.3	1.2	0.0	0.1	0.1
SDDSC132	556.3	557.1	0.8	0.1	0.0	0.1

SDDSC132	565.1	565.8	0.7	0.3	0.0	0.3
SDDSC132	565.8	566.0	0.3	2.9	0.0	2.9
SDDSC132	566.0	567.2	1.2	0.3	0.0	0.3
SDDSC132	570.2	570.5	0.3	1.2	0.1	1.4
SDDSC132	570.5	571.3	0.8	0.1	0.0	0.1
SDDSC132	571.3	571.6	0.4	0.1	0.0	0.2
SDDSC132	571.6	572.0	0.4	1.2	1.0	3.1
SDDSC132	572.0	572.5	0.5	0.9	0.0	1.0
SDDSC132	572.5	572.7	0.2	1.4	0.1	1.5
SDDSC132	572.7	573.3	0.7	0.3	0.0	0.4
SDDSC132	573.3	573.8	0.5	1.0	0.4	1.8
SDDSC132	573.8	574.4	0.6	0.3	0.0	0.3
SDDSC132	574.4	574.6	0.1	0.7	0.0	0.8
SDDSC132	577.2	578.2	1.0	0.5	0.1	0.6
SDDSC132	579.2	580.2	1.0	0.2	0.0	0.2
SDDSC132	580.2	580.4	0.2	0.6	0.9	2.3
SDDSC132	584.3	584.4	0.1	1.0	0.5	1.9
SDDSC132	584.4	585.0	0.5	0.1	0.0	0.1
SDDSC132	585.0	585.9	1.0	0.3	0.2	0.7
SDDSC132	585.9	586.4	0.5	0.1	0.0	0.2
SDDSC132	586.4	587.1	0.7	0.5	0.1	0.6
SDDSC132	587.1	587.4	0.3	0.4	0.2	0.8
SDDSC132	587.4	587.7	0.3	0.5	0.1	0.6
SDDSC132	587.7	588.5	0.9	0.1	0.2	0.5
SDDSC132	588.5	588.7	0.2	1.0	6.5	13.2
SDDSC132	588.7	589.7	1.0	0.1	0.0	0.2
SDDSC132	589.7	589.9	0.2	0.7	0.8	2.3
SDDSC132	591.8	592.0	0.2	0.1	0.0	0.2
SDDSC132	592.0	592.6	0.5	0.5	0.1	0.6
SDDSC132	592.6	593.5	0.9	0.5	0.0	0.5
SDDSC132	606.8	607.1	0.3	0.2	0.4	0.9
SDDSC132	609.0	609.9	0.9	0.1	0.0	0.2
SDDSC132	609.9	610.3	0.4	0.6	0.2	0.8
SDDSC132	610.3	611.0	0.7	1.7	0.6	2.9
SDDSC132	611.0	611.3	0.3	0.5	0.1	0.6
SDDSC132	611.3	611.9	0.6	0.1	0.0	0.2
SDDSC132	611.9	612.7	0.8	0.0	0.2	0.4
SDDSC132	613.8	614.2	0.4	0.1	0.1	0.2
SDDSC132	616.4	617.0	0.6	1.5	0.0	1.6
SDDSC132	617.7	618.1	0.4	0.2	0.0	0.2
SDDSC132	618.1	618.5	0.5	0.1	0.1	0.4

SDDSC132	618.5	618.7	0.2	0.1	0.1	0.2
SDDSC132	618.7	619.8	1.1	0.2	0.0	0.3
SDDSC132	628.6	629.0	0.4	0.1	0.0	0.1
SDDSC132	629.0	630.0	1.0	0.0	0.0	0.1
SDDSC132	633.5	633.6	0.2	0.5	0.4	1.2
SDDSC132	634.9	635.0	0.1	1.8	0.2	2.0
SDDSC132	635.0	635.6	0.6	0.2	0.2	0.5
SDDSC132	636.4	637.1	0.7	0.1	0.0	0.2
SDDSC132	638.2	639.1	0.9	0.1	0.0	0.2
SDDSC132	650.2	650.3	0.2	1.3	0.0	1.3
SDDSC138	39.9	40.8	0.9	0.3	0.0	0.3
SDDSC138	40.8	41.8	1.0	0.2	0.0	0.3
SDDSC138	41.8	43.1	1.3	0.2	0.0	0.2
SDDSC138	54.1	55.1	1.0	0.2	0.0	0.2
SDDSC138	73.8	74.8	1.0	0.1	0.0	0.1
SDDSC138	74.8	75.5	0.7	0.2	0.0	0.2
SDDSC138	79.9	80.9	1.0	0.1	0.0	0.1
SDDSC138	131.8	131.9	0.2	0.2	0.2	0.5
SDDSC138	131.9	132.0	0.1	77.5	23.8	122.2
SDDSC138	132.0	132.3	0.2	1.8	0.1	1.9
SDDSC138	132.3	133.0	0.7	0.4	0.0	0.4
SDDSC138	133.0	133.9	0.9	0.8	0.0	0.9
SDDSC138	133.9	134.1	0.3	0.1	0.0	0.1
SDDSC138	134.5	135.3	0.8	0.4	0.0	0.4
SDDSC138	135.3	135.6	0.3	1.0	0.3	1.5
SDDSC138	135.6	135.9	0.3	2.6	0.0	2.6
SDDSC138	135.9	136.0	0.1	1.3	0.0	1.3
SDDSC138	136.0	136.5	0.5	0.3	0.0	0.3
SDDSC138	136.5	137.0	0.5	0.2	0.0	0.2
SDDSC138	138.0	138.9	0.9	0.1	0.0	0.2
SDDSC138	138.9	139.1	0.2	0.8	0.2	1.2
SDDSC138	139.1	139.5	0.5	0.2	0.0	0.2
SDDSC138	139.5	139.9	0.4	0.2	0.1	0.3
SDDSC138	143.0	143.2	0.2	0.1	0.0	0.1
SDDSC138	143.2	143.3	0.1	0.6	7.1	14.0
SDDSC138	143.3	143.6	0.3	0.4	0.0	0.4
SDDSC138	143.6	144.7	1.0	0.2	0.0	0.3
SDDSC138	144.7	145.1	0.4	2.0	1.1	4.0
SDDSC138	145.1	145.8	0.7	0.4	0.0	0.4
SDDSC138	148.6	148.8	0.2	0.3	0.0	0.4
SDDSC138	267.7	269.0	1.3	0.3	0.0	0.3

SDDSC138	271.6	272.8	1.2	0.3	0.0	0.3
SDDSC138	279.0	279.8	0.8	0.4	0.0	0.4
SDDSC138	279.8	281.0	1.3	0.2	0.0	0.2
SDDSC138	281.0	281.8	0.8	0.2	0.0	0.2
SDDSC138	284.7	285.0	0.3	0.4	0.1	0.6
SDDSC138	285.0	285.9	0.9	0.1	0.0	0.1
SDDSC138	285.9	286.4	0.5	5.3	0.0	5.4
SDDSC138	286.4	286.6	0.2	6.5	0.4	7.2
SDDSC138	286.6	287.1	0.5	11.7	0.0	11.8
SDDSC138	287.1	288.2	1.1	0.4	0.0	0.4
SDDSC138	288.2	288.8	0.6	0.2	0.0	0.2
SDDSC138	294.6	294.9	0.3	180.0	26.3	229.4
SDDSC138	294.9	295.5	0.5	2.8	1.1	4.8
SDDSC138	295.5	295.8	0.3	62.6	23.0	105.8
SDDSC138	295.8	296.3	0.5	0.7	0.3	1.3
SDDSC138	296.3	296.4	0.1	5.6	0.0	5.6
SDDSC138	296.4	297.1	0.7	0.7	0.0	0.7
SDDSC138	297.1	297.6	0.5	0.3	0.0	0.3
SDDSC138	297.6	298.0	0.3	3.0	0.0	3.0
SDDSC138	298.0	298.6	0.7	0.4	0.0	0.4
SDDSC138	298.6	299.5	0.8	0.1	0.0	0.1
SDDSC138	302.5	303.2	0.7	0.7	1.6	3.7
SDDSC138	303.2	303.5	0.3	0.7	0.2	1.0
SDDSC138	303.5	303.7	0.2	0.2	0.4	1.0
SDDSC138	306.7	306.8	0.1	0.5	0.0	0.6
SDDSC138	306.8	307.6	0.8	0.2	0.0	0.2
SDDSC138	308.5	309.8	1.3	0.2	0.0	0.2
SDDSC138	309.8	310.3	0.5	0.4	0.0	0.4
SDDSC138	310.3	311.0	0.7	0.1	0.0	0.1
SDDSC138	311.0	311.4	0.4	16.4	2.1	20.4
SDDSC138	311.4	312.1	0.7	0.4	0.1	0.5
SDDSC138	313.0	313.1	0.1	62.4	8.7	78.7
SDDSC138	313.1	314.0	0.9	0.3	0.0	0.4
SDDSC138	314.0	314.2	0.2	2.3	4.4	10.5
SDDSC138	314.2	314.4	0.2	4.4	1.5	7.1
SDDSC138	314.4	314.5	0.1	17.8	9.0	34.8
SDDSC138	314.5	315.0	0.5	2.7	0.4	3.4
SDDSC138	315.0	315.6	0.6	1.2	0.6	2.2
SDDSC138	315.6	315.8	0.2	1.9	0.9	3.5
SDDSC138	315.8	316.5	0.6	0.2	0.2	0.6
SDDSC138	316.5	316.9	0.5	0.2	0.4	1.1

SDDSC138	316.9	317.2	0.2	44.8	33.8	108.3
SDDSC138	317.2	317.6	0.4	3.5	3.6	10.3
SDDSC138	317.6	317.8	0.2	60.6	9.2	77.9
SDDSC138	317.8	318.4	0.6	0.6	0.2	1.0
SDDSC138	318.4	319.0	0.6	3.8	1.5	6.6
SDDSC138	319.0	319.1	0.1	51.1	10.6	71.0
SDDSC138	319.1	319.2	0.1	3.5	2.3	7.9
SDDSC138	319.2	319.6	0.4	0.2	0.1	0.4
SDDSC138	319.6	320.0	0.4	4.1	2.1	8.0
SDDSC138	320.0	320.3	0.3	0.7	0.3	1.4
SDDSC138	320.3	320.7	0.3	0.1	0.0	0.2
SDDSC138	320.7	321.8	1.1	0.2	0.0	0.2
SDDSC138	321.8	322.8	1.1	1.2	0.1	1.3
SDDSC138	322.8	322.9	0.1	0.9	3.3	7.0
SDDSC138	323.6	323.9	0.3	0.7	0.3	1.3
SDDSC138	324.8	325.1	0.2	0.1	0.0	0.1
SDDSC138	326.3	327.3	1.0	0.1	0.0	0.1
SDDSC138	328.1	328.5	0.5	1.8	0.5	2.7
SDDSC138	328.5	328.9	0.4	0.4	0.1	0.6
SDDSC138	329.5	330.0	0.5	0.3	0.0	0.3
SDDSC138	332.3	332.4	0.1	0.3	0.0	0.3
SDDSC138	335.0	335.3	0.3	0.3	0.0	0.4
SDDSC138	336.2	336.9	0.7	0.7	0.5	1.6
SDDSC138	336.9	337.7	0.8	0.2	0.1	0.5
SDDSC138	337.7	338.6	1.0	5.2	0.1	5.5
SDDSC138	338.6	339.2	0.6	4.7	0.0	4.7
SDDSC138	339.2	340.0	0.8	0.6	0.0	0.6
SDDSC138	340.0	341.0	1.0	0.2	0.1	0.3
SDDSC138	341.0	342.1	1.1	0.3	0.1	0.4
SDDSC138	342.1	342.3	0.2	0.4	0.6	1.4
SDDSC138	342.3	343.3	1.0	0.1	0.0	0.2
SDDSC138	345.6	345.9	0.4	0.9	0.1	1.2
SDDSC138	347.2	347.4	0.2	0.3	0.1	0.4
SDDSC138	348.5	348.7	0.2	2.3	0.0	2.3
SDDSC138	350.0	350.3	0.3	0.2	0.2	0.6
SDDSC138	350.3	351.3	1.0	0.2	0.0	0.2
SDDSC138	351.3	351.6	0.3	0.4	0.2	0.7
SDDSC138	351.6	352.6	1.0	1.1	0.5	2.1
SDDSC138	352.6	353.0	0.4	6.0	1.8	9.4
SDDSC138	353.0	353.6	0.7	1.9	0.4	2.7
SDDSC138	353.6	354.0	0.4	1.8	1.3	4.3

SDDSC138	354.0	354.7	0.7	3.7	1.4	6.2
SDDSC138	354.7	355.4	0.7	1.9	0.2	2.4
SDDSC138	355.4	355.7	0.3	2.8	0.8	4.3
SDDSC138	355.7	356.0	0.3	10.6	0.3	11.2
SDDSC138	356.0	356.6	0.6	0.5	0.3	1.1
SDDSC138	356.6	357.3	0.7	0.9	0.3	1.6
SDDSC138	357.3	358.3	1.0	0.1	0.0	0.1
SDDSC138	358.3	358.5	0.2	0.8	0.3	1.4
SDDSC138	358.5	359.4	0.9	0.3	0.1	0.4
SDDSC138	360.6	361.0	0.4	0.7	0.1	0.8
SDDSC138	361.0	361.5	0.5	0.6	0.0	0.7
SDDSC138	361.5	362.1	0.6	0.4	0.3	0.9
SDDSC138	362.1	362.7	0.6	0.9	0.2	1.2
SDDSC138	362.7	362.9	0.3	1.0	0.2	1.4
SDDSC138	362.9	364.1	1.1	0.3	0.4	1.0
SDDSC138	366.2	367.1	1.0	0.3	0.0	0.4
SDDSC138	367.1	367.5	0.3	0.4	0.2	0.7
SDDSC138	367.5	367.9	0.4	0.6	0.3	1.2
SDDSC138	367.9	368.0	0.1	13.9	0.8	15.5
SDDSC138	368.6	369.5	0.9	0.1	0.0	0.2
SDDSC138	369.5	370.2	0.7	2.9	0.3	3.4
SDDSC138	371.9	372.2	0.3	1.5	0.0	1.6
SDDSC138	372.2	373.2	1.0	0.1	0.0	0.1
SDDSC138	373.2	374.2	1.0	0.2	0.0	0.2
SDDSC138	375.8	376.5	0.7	0.3	0.0	0.3
SDDSC138	376.5	376.7	0.2	1.8	0.1	2.0
SDDSC138	376.7	377.0	0.3	2.0	0.1	2.2
SDDSC138	377.5	378.3	0.8	0.5	0.0	0.6
SDDSC138	378.3	379.2	1.0	0.3	0.1	0.4
SDDSC138	379.2	380.0	0.8	0.5	0.0	0.6
SDDSC138	380.0	380.6	0.6	0.3	0.4	1.0
SDDSC138	380.6	380.9	0.3	0.8	0.1	1.0
SDDSC138	380.9	381.6	0.7	1.1	1.4	3.7
SDDSC138	386.1	386.9	0.8	0.7	0.3	1.3
SDDSC138	386.9	387.6	0.8	0.3	0.0	0.4
SDDSC138	387.6	387.7	0.1	9.1	3.6	15.8
SDDSC138	387.7	388.5	0.8	1.1	0.2	1.5
SDDSC138	388.5	388.9	0.4	0.2	0.0	0.2
SDDSC138	392.0	393.0	1.0	0.2	0.0	0.3
SDDSC138	393.0	394.1	1.1	0.1	0.0	0.1
SDDSC138	395.2	396.3	1.1	0.3	0.0	0.3

SDDSC138	397.0	397.6	0.6	0.3	0.0	0.3
SDDSC138	397.6	398.3	0.7	0.6	0.0	0.6
SDDSC138	398.3	398.8	0.5	6.2	0.3	6.7
SDDSC138	398.8	399.2	0.4	1.0	0.2	1.3
SDDSC138	399.2	399.8	0.5	1.3	0.8	2.8
SDDSC138	400.0	400.1	0.1	0.4	0.0	0.4
SDDSC138	400.1	400.3	0.2	0.6	0.2	0.9
SDDSC138	400.3	401.3	1.0	0.3	0.1	0.4
SDDSC138	401.3	402.3	1.0	0.3	0.0	0.3
SDDSC138	402.3	402.9	0.5	3.2	0.4	3.9
SDDSC138	402.9	403.0	0.1	1.2	0.5	2.2
SDDSC138	403.0	403.4	0.4	0.3	0.0	0.4
SDDSC138	404.0	404.3	0.2	0.4	0.1	0.6
SDDSC138	404.3	405.2	0.9	0.1	0.0	0.2
SDDSC138	405.2	405.6	0.4	2.3	0.2	2.7
SDDSC138	405.6	406.0	0.4	1.1	1.4	3.8
SDDSC138	406.5	407.5	1.0	0.4	0.2	0.7
SDDSC138	407.5	408.2	0.8	0.8	0.2	1.2
SDDSC138	408.2	408.4	0.2	35.6	1.2	37.9
SDDSC138	408.4	408.7	0.3	0.8	0.4	1.6
SDDSC138	408.7	409.3	0.6	0.1	0.0	0.2
SDDSC138	409.3	409.4	0.1	49.5	1.8	52.8
SDDSC138	409.4	409.7	0.3	1.5	1.0	3.3
SDDSC138	409.7	410.2	0.5	0.1	0.0	0.1
SDDSC138	410.2	410.7	0.5	0.2	0.1	0.3
SDDSC138	410.7	411.6	0.9	0.6	0.0	0.7
SDDSC138	413.3	414.0	0.7	0.1	0.0	0.1
SDDSC138	414.0	414.4	0.4	17.4	1.4	20.1
SDDSC138	414.4	414.6	0.2	4.5	0.4	5.4
SDDSC138	414.6	415.1	0.5	2.7	0.9	4.5
SDDSC138	415.1	415.4	0.3	7.2	5.2	16.9
SDDSC138	415.4	415.7	0.3	1.8	0.1	2.0
SDDSC138	415.7	415.8	0.1	2.6	1.9	6.2
SDDSC138	415.8	416.3	0.5	1.0	0.6	2.0
SDDSC138	416.3	416.6	0.3	2.5	0.3	3.1
SDDSC138	416.6	417.0	0.3	0.8	0.1	1.0
SDDSC138	417.0	417.1	0.1	141.0	1.6	144.1
SDDSC138	417.1	417.2	0.1	15.4	0.4	16.1
SDDSC138	417.2	418.0	0.8	0.2	0.0	0.3
SDDSC138	418.0	418.2	0.2	0.4	0.1	0.6
SDDSC138	418.2	418.4	0.1	1.7	0.9	3.3

SDDSC138	418.4	419.3	0.9	0.6	0.1	0.7
SDDSC138	419.3	420.1	0.8	0.3	0.1	0.5
SDDSC138	420.1	420.4	0.3	2.3	1.7	5.6
SDDSC138	420.4	420.5	0.1	6.6	6.7	19.3
SDDSC138	420.5	420.9	0.4	1.0	1.4	3.7
SDDSC138	420.9	421.8	0.9	0.8	0.1	1.0
SDDSC138	421.8	421.9	0.1	6.7	11.2	27.8
SDDSC138	421.9	422.3	0.4	0.4	0.2	0.8
SDDSC138	422.3	422.7	0.4	6.6	4.5	15.1
SDDSC138	422.7	423.4	0.7	6.5	1.5	9.4
SDDSC138	423.4	423.9	0.5	1.2	0.8	2.7
SDDSC138	423.9	424.4	0.6	0.3	0.1	0.4
SDDSC138	424.4	424.5	0.1	15.9	6.9	28.8
SDDSC138	424.5	425.5	1.0	0.1	0.1	0.2
SDDSC138	426.7	427.6	0.9	0.1	0.0	0.1
SDDSC138	427.6	427.7	0.1	79.2	6.2	90.9
SDDSC138	427.7	427.9	0.3	0.4	0.1	0.5
SDDSC138	427.9	428.5	0.5	3.6	0.3	4.1
SDDSC138	428.5	428.6	0.2	25.6	11.3	46.8
SDDSC138	428.6	429.2	0.6	0.2	0.0	0.3
SDDSC138	429.2	430.2	0.9	0.3	0.1	0.4
SDDSC138	430.2	431.0	0.8	0.1	0.1	0.2
SDDSC138	433.0	434.0	1.0	0.2	0.0	0.2
SDDSC138	434.0	434.4	0.4	0.6	0.0	0.6
SDDSC138	434.4	434.6	0.2	1.4	0.0	1.4
SDDSC138	434.6	435.1	0.6	0.2	0.0	0.2
SDDSC138	435.1	435.2	0.1	0.9	11.1	21.7
SDDSC138	435.2	436.3	1.1	0.1	0.3	0.6
SDDSC138	439.3	440.0	0.7	1.5	0.1	1.7
SDDSC138	441.0	441.2	0.2	1.6	0.3	2.0
SDDSC138	441.2	441.5	0.4	0.3	0.0	0.4
SDDSC138	442.2	442.8	0.6	0.1	2.6	5.0
SDDSC138	442.8	443.8	1.0	0.0	0.2	0.4
SDDSC138	445.0	445.2	0.2	36.6	0.1	36.7
SDDSC138	445.2	445.3	0.1	47.2	1.0	49.0
SDDSC138	445.3	446.0	0.7	1.5	0.2	1.8
SDDSC138	446.0	446.4	0.4	5.9	0.2	6.3
SDDSC138	446.4	446.7	0.3	183.0	10.8	203.3
SDDSC138	446.7	447.2	0.6	0.3	0.2	0.6
SDDSC138	447.2	448.2	0.9	0.1	0.0	0.1
SDDSC138	448.2	449.3	1.2	0.3	0.0	0.3

SDDSC138	449.3	450.3	1.0	0.1	0.1	0.2
SDDSC138	453.4	453.6	0.2	0.8	0.3	1.3
SDDSC138	453.6	453.7	0.1	0.4	0.4	1.1
SDDSC138	453.7	454.3	0.5	0.6	0.2	1.0
SDDSC138	454.3	455.2	0.9	0.6	0.1	0.7
SDDSC138	455.2	455.5	0.3	2.3	0.8	3.8
SDDSC138	455.5	456.7	1.3	0.2	0.0	0.2
SDDSC138	456.7	456.9	0.2	18.4	22.2	60.1
SDDSC138	456.9	457.1	0.2	0.3	0.1	0.5
SDDSC138	457.1	457.2	0.1	17.7	0.2	18.1
SDDSC138	457.2	457.8	0.5	2.6	0.9	4.3
SDDSC138	457.8	458.6	0.8	1.7	0.6	2.7
SDDSC138	458.6	458.8	0.3	2.3	17.2	34.6
SDDSC138	458.8	459.4	0.6	3.5	7.5	17.7
SDDSC138	459.4	460.1	0.7	0.8	0.0	0.9
SDDSC138	460.1	460.5	0.4	2.2	0.2	2.6
SDDSC138	460.5	461.0	0.6	0.5	0.0	0.6
SDDSC138	461.0	461.3	0.3	1.4	0.0	1.4
SDDSC138	461.3	461.7	0.4	0.1	0.0	0.2
SDDSC138	461.7	461.9	0.2	1.1	0.1	1.3
SDDSC138	462.9	464.0	1.1	0.3	0.0	0.3
SDDSC138	466.7	466.9	0.2	0.1	0.0	0.1
SDDSC138	468.1	469.1	1.0	0.1	0.0	0.2
SDDSC138	469.1	470.1	1.0	0.0	0.0	0.1
SDDSC138	470.1	470.5	0.4	0.1	0.1	0.3
SDDSC138	470.5	471.7	1.2	0.4	0.0	0.5
SDDSC138	471.7	471.8	0.1	0.5	1.0	2.4
Hole number	From (m)	To (m)	Length (m)	Au ppm	Sb%	AuEq (g/t)
SDDSC132	34.4	35.6	1.2	0.17	0.0	0.2
SDDSC132	123.95	124.63	0.68	0.15	0.0	0.2
SDDSC132	124.63	125.25	0.62	0.22	0.0	0.2
SDDSC132	125.25	125.98	0.73	0.17	0.0	0.2
SDDSC132	125.98	126.8	0.82	6.46	0.0	6.5
SDDSC132	126.8	127.33	0.53	0.16	0.0	0.2
SDDSC132	127.33	127.86	0.53	0.09	0.0	0.1
SDDSC132	127.86	128.38	0.52	0.66	0.0	0.7
SDDSC132	140.8	141.24	0.44	0.1	0.0	0.1
SDDSC132	145.78	146.22	0.44	0.86	0.0	0.9
SDDSC132	146.22	146.42	0.2	3.94	0.1	4.2
SDDSC132	146.42	146.67	0.25	77	17.6	110.1
SDDSC132	146.67	146.88	0.21	0.66	0.0	0.7
SDDSC132	146.88	147.36	0.48	0.25	0.0	0.3

SDDSC132	148.04	148.46	0.42	20.9	0.0	21.0
SDDSC132	148.46	148.6	0.14	0.12	0.0	0.1
SDDSC132	148.6	149.05	0.45	0.13	0.0	0.2
SDDSC132	149.05	149.45	0.4	0.34	0.0	0.4
SDDSC132	149.45	150	0.55	0.1	0.0	0.1
SDDSC132	151.17	151.62	0.45	1.04	0.0	1.1
SDDSC132	151.62	152	0.38	1.07	0.0	1.1
SDDSC132	152	152.77	0.77	0.18	0.0	0.2
SDDSC132	152.77	153.23	0.46	0.14	0.0	0.2
SDDSC132	153.23	153.4	0.17	1.86	0.6	3.0
SDDSC132	153.4	154	0.6	0.1	0.0	0.1
SDDSC132	154	154.38	0.38	1.42	0.4	2.1
SDDSC132	154.38	154.49	0.11	2.16	6.6	14.6
SDDSC132	154.49	155.02	0.53	0.75	0.1	1.0
SDDSC132	155.02	156.2	1.18	0.16	0.0	0.2
SDDSC132	156.2	156.4	0.2	0.52	0.0	0.5
SDDSC132	156.4	157.14	0.74	0.17	0.0	0.2
SDDSC132	157.14	157.52	0.38	0.94	0.0	1.0
SDDSC132	157.52	158.51	0.99	0.12	0.0	0.1
SDDSC132	158.51	159.53	1.02	0.17	0.0	0.2
SDDSC132	159.53	160.49	0.96	0.39	0.0	0.4
SDDSC132	160.49	161.3	0.81	0.43	0.0	0.4
SDDSC132	161.3	161.71	0.41	0.57	0.0	0.6
SDDSC132	161.71	162.06	0.35	0.81	0.0	0.8
SDDSC132	162.06	162.18	0.12	2.23	0.0	2.2
SDDSC132	162.18	162.6	0.42	0.53	0.0	0.5
SDDSC132	162.6	163.19	0.59	1.95	0.0	2.0
SDDSC132	163.19	163.34	0.15	4.38	0.0	4.4
SDDSC132	163.34	163.83	0.49	3.61	0.0	3.6
SDDSC132	166	166.56	0.56	0.27	0.0	0.3
SDDSC132	166.56	166.88	0.32	1.26	0.0	1.3
SDDSC132	166.88	167.15	0.27	2.39	0.0	2.4
SDDSC132	167.15	167.55	0.4	0.77	0.0	0.8
SDDSC132	167.55	168.37	0.82	0.21	0.0	0.2
SDDSC132	170	170.8	0.8	0.08	0.0	0.1
SDDSC132	170.8	170.98	0.18	0.95	0.5	1.9
SDDSC132	171.7	172.07	0.37	0.36	0.0	0.4
SDDSC132	172.07	172.38	0.31	15.3	0.6	16.5
SDDSC132	172.38	173.29	0.91	0.19	0.0	0.2
SDDSC132	176.49	176.62	0.13	0.71	0.1	0.9
SDDSC132	176.62	176.85	0.23	7.13	0.3	7.7
SDDSC132	177.68	178.35	0.67	0.1	0.0	0.1
SDDSC132	178.35	178.71	0.36	0.52	0.0	0.5

SDDSC132	178.71	179.3	0.59	0.34	0.0	0.4
SDDSC132	180.3	180.61	0.31	0.86	0.0	0.9
SDDSC132	184.51	184.99	0.48	0.22	0.0	0.2
SDDSC132	185.37	185.98	0.61	0.15	0.0	0.2
SDDSC132	186.61	186.75	0.14	28.5	15.6	57.8
SDDSC132	186.75	187.67	0.92	0.17	0.0	0.3
SDDSC132	187.67	188.15	0.48	0.28	0.0	0.3
SDDSC132	188.15	189	0.85	4.2	0.0	4.2
SDDSC132	189	190.14	1.14	1.7	0.1	1.8
SDDSC132	193.17	193.35	0.18	1.08	0.0	1.1
SDDSC132	193.35	193.9	0.55	0.37	0.0	0.4
SDDSC132	194.7	195.16	0.46	0.28	0.0	0.3
SDDSC132	195.16	195.74	0.58	0.11	0.0	0.1
SDDSC132	196.9	197.3	0.4	3.65	0.0	3.7
SDDSC132	460.19	460.79	0.6	0.59	0.0	0.6
SDDSC132	460.79	461.53	0.74	0.1	0.0	0.1
SDDSC132	461.53	461.87	0.34	0.14	0.0	0.2
SDDSC132	461.87	462.31	0.44	0.2	0.1	0.3
SDDSC132	475.04	475.22	0.18	0.11	0.0	0.1
SDDSC132	493	493.62	0.62	0.14	0.0	0.2
SDDSC132	515.91	516.63	0.72	0.18	0.0	0.2
SDDSC132	516.63	516.83	0.2	0.03	1.0	1.9
SDDSC132	532.66	533.34	0.68	0.26	0.0	0.3
SDDSC132	533.34	533.78	0.44	0.25	0.1	0.5
SDDSC132	533.78	534.26	0.48	0.12	0.3	0.6
SDDSC132	534.26	534.99	0.73	2.43	0.2	2.8
SDDSC132	534.99	535.15	0.16	4.53	1.1	6.5
SDDSC132	535.15	536	0.85	0.93	0.1	1.2
SDDSC132	536	537.08	1.08	0.24	0.0	0.3
SDDSC132	538.08	538.21	0.13	2.39	0.4	3.2
SDDSC132	538.21	538.59	0.38	0.12	0.0	0.2
SDDSC132	538.59	538.74	0.15	0.73	0.3	1.3
SDDSC132	539.84	540.25	0.41	0.17	0.1	0.4
SDDSC132	540.25	540.42	0.17	0.3	0.2	0.6
SDDSC132	540.42	541.26	0.84	0.39	0.0	0.4
SDDSC132	541.89	542.41	0.52	0.54	0.3	1.1
SDDSC132	542.41	543.18	0.77	0.15	0.0	0.2
SDDSC132	543.18	543.29	0.11	28.7	0.0	28.8
SDDSC132	543.29	543.79	0.5	0.19	0.0	0.2
SDDSC132	543.79	544.19	0.4	8.7	0.3	9.3
SDDSC132	544.19	544.37	0.18	2.45	0.2	2.8
SDDSC132	544.37	545.2	0.83	0.68	0.2	1.1
SDDSC132	545.2	545.36	0.16	61.2	0.2	61.6

SDDSC132	545.36	545.81	0.45	1.11	10.4	20.7
SDDSC132	545.81	546.58	0.77	0.27	0.1	0.4
SDDSC132	546.58	547.17	0.59	0.11	0.1	0.2
SDDSC132	547.17	547.46	0.29	0.57	0.4	1.4
SDDSC132	547.46	548.02	0.56	0.05	0.0	0.1
SDDSC132	548.02	548.37	0.35	0.91	1.2	3.1
SDDSC132	548.37	549	0.63	0.11	0.1	0.3
SDDSC132	549	549.94	0.94	0.2	0.4	1.0
SDDSC132	549.94	550.8	0.86	0.05	0.0	0.1
SDDSC132	550.8	550.9	0.1	3.11	1.4	5.7
SDDSC132	550.9	551.54	0.64	0.33	0.4	1.0
SDDSC132	551.54	551.94	0.4	2.4	1.7	5.5
SDDSC132	551.94	552.4	0.46	5.16	0.8	6.6
SDDSC132	552.4	552.56	0.16	7.12	0.7	8.4
SDDSC132	552.56	553.22	0.66	0.05	0.1	0.2
SDDSC132	553.22	554.01	0.79	0.22	0.1	0.4
SDDSC132	554.01	554.19	0.18	18.3	0.1	18.6
SDDSC132	554.19	554.35	0.16	13.3	0.2	13.7
SDDSC132	554.35	555.12	0.77	0.23	0.1	0.4
SDDSC132	555.12	556.32	1.2	0.03	0.1	0.1
SDDSC132	556.32	557.13	0.81	0.1	0.0	0.1
SDDSC132	565.1	565.75	0.65	0.3	0.0	0.3
SDDSC132	565.75	566.04	0.29	2.87	0.0	2.9
SDDSC132	566.04	567.2	1.16	0.3	0.0	0.3
SDDSC132	570.18	570.51	0.33	1.24	0.1	1.4
SDDSC132	570.51	571.27	0.76	0.13	0.0	0.1
SDDSC132	571.27	571.64	0.37	0.13	0.0	0.2
SDDSC132	571.64	572.01	0.37	1.2	1.0	3.1
SDDSC132	572.01	572.49	0.48	0.9	0.0	1.0
SDDSC132	572.49	572.68	0.19	1.35	0.1	1.5
SDDSC132	572.68	573.33	0.65	0.32	0.0	0.4
SDDSC132	573.33	573.82	0.49	0.98	0.4	1.8
SDDSC132	573.82	574.44	0.62	0.32	0.0	0.3
SDDSC132	574.44	574.56	0.12	0.74	0.0	0.8
SDDSC132	577.15	578.16	1.01	0.5	0.1	0.6
SDDSC132	579.23	580.22	0.99	0.15	0.0	0.2
SDDSC132	580.22	580.44	0.22	0.56	0.9	2.3
SDDSC132	584.31	584.42	0.11	0.96	0.5	1.9
SDDSC132	584.42	584.95	0.53	0.09	0.0	0.1
SDDSC132	584.95	585.93	0.98	0.31	0.2	0.7
SDDSC132	585.93	586.41	0.48	0.12	0.0	0.2
SDDSC132	586.41	587.06	0.65	0.52	0.1	0.6
SDDSC132	587.06	587.38	0.32	0.39	0.2	0.8

SDDSC132	587.38	587.65	0.27	0.47	0.1	0.6
SDDSC132	587.65	588.53	0.88	0.11	0.2	0.5
SDDSC132	588.53	588.7	0.17	0.96	6.5	13.2
SDDSC132	588.7	589.69	0.99	0.12	0.0	0.2
SDDSC132	589.69	589.92	0.23	0.74	0.8	2.3
SDDSC132	591.8	592.04	0.24	0.13	0.0	0.2
SDDSC132	592.04	592.57	0.53	0.51	0.1	0.6
SDDSC132	592.57	593.46	0.89	0.45	0.0	0.5
SDDSC132	606.8	607.1	0.3	0.2	0.4	0.9
SDDSC132	609	609.85	0.85	0.13	0.0	0.2
SDDSC132	609.85	610.29	0.44	0.55	0.2	0.8
SDDSC132	610.29	610.98	0.69	1.71	0.6	2.9
SDDSC132	610.98	611.3	0.32	0.45	0.1	0.6
SDDSC132	611.3	611.88	0.58	0.09	0.0	0.2
SDDSC132	611.88	612.7	0.82	0.04	0.2	0.4
SDDSC132	613.75	614.17	0.42	0.06	0.1	0.2
SDDSC132	616.43	617	0.57	1.54	0.0	1.6
SDDSC132	617.67	618.06	0.39	0.15	0.0	0.2
SDDSC132	618.06	618.53	0.47	0.12	0.1	0.4
SDDSC132	618.53	618.74	0.21	0.1	0.1	0.2
SDDSC132	618.74	619.8	1.06	0.21	0.0	0.3
SDDSC132	628.55	628.99	0.44	0.07	0.0	0.1
SDDSC132	628.99	630	1.01	0.03	0.0	0.1
SDDSC132	633.47	633.63	0.16	0.51	0.4	1.2
SDDSC132	634.86	635	0.14	1.75	0.2	2.0
SDDSC132	635	635.59	0.59	0.18	0.2	0.5
SDDSC132	636.35	637.07	0.72	0.14	0.0	0.2
SDDSC132	638.24	639.1	0.86	0.13	0.0	0.2
SDDSC132	650.17	650.33	0.16	1.3	0.0	1.3
SDDSC138	39.93	40.8	0.87	0.33	0.0	0.3
SDDSC138	40.8	41.79	0.99	0.24	0.0	0.3
SDDSC138	41.79	43.08	1.29	0.15	0.0	0.2
SDDSC138	54.13	55.12	0.99	0.24	0.0	0.2
SDDSC138	73.75	74.75	1	0.1	0.0	0.1
SDDSC138	74.75	75.49	0.74	0.17	0.0	0.2
SDDSC138	79.86	80.9	1.04	0.11	0.0	0.1
SDDSC138	131.75	131.93	0.18	0.23	0.2	0.5
SDDSC138	131.93	132.03	0.1	77.5	23.8	122.2
SDDSC138	132.03	132.26	0.23	1.75	0.1	1.9
SDDSC138	132.26	132.95	0.69	0.37	0.0	0.4
SDDSC138	132.95	133.87	0.92	0.81	0.0	0.9
SDDSC138	133.87	134.12	0.25	0.11	0.0	0.1
SDDSC138	134.52	135.28	0.76	0.39	0.0	0.4

SDDSC138	135.28	135.6	0.32	0.97	0.3	1.5
SDDSC138	135.6	135.88	0.28	2.56	0.0	2.6
SDDSC138	135.88	135.98	0.1	1.27	0.0	1.3
SDDSC138	135.98	136.48	0.5	0.33	0.0	0.3
SDDSC138	136.48	137	0.52	0.17	0.0	0.2
SDDSC138	138.04	138.91	0.87	0.13	0.0	0.2
SDDSC138	138.91	139.07	0.16	0.75	0.2	1.2
SDDSC138	139.07	139.53	0.46	0.2	0.0	0.2
SDDSC138	139.53	139.89	0.36	0.19	0.1	0.3
SDDSC138	142.95	143.18	0.23	0.13	0.0	0.1
SDDSC138	143.18	143.3	0.12	0.6	7.1	14.0
SDDSC138	143.3	143.64	0.34	0.4	0.0	0.4
SDDSC138	143.64	144.68	1.04	0.24	0.0	0.3
SDDSC138	144.68	145.1	0.42	1.99	1.1	4.0
SDDSC138	145.1	145.77	0.67	0.38	0.0	0.4
SDDSC138	148.61	148.84	0.23	0.34	0.0	0.4
SDDSC138	267.73	269	1.27	0.34	0.0	0.3
SDDSC138	271.56	272.76	1.2	0.26	0.0	0.3
SDDSC138	278.98	279.75	0.77	0.38	0.0	0.4
SDDSC138	279.75	281	1.25	0.16	0.0	0.2
SDDSC138	281	281.77	0.77	0.21	0.0	0.2
SDDSC138	284.71	285	0.29	0.38	0.1	0.6
SDDSC138	285	285.85	0.85	0.1	0.0	0.1
SDDSC138	285.85	286.39	0.54	5.29	0.0	5.4
SDDSC138	286.39	286.55	0.16	6.54	0.4	7.2
SDDSC138	286.55	287.09	0.54	11.7	0.0	11.8
SDDSC138	287.09	288.22	1.13	0.35	0.0	0.4
SDDSC138	288.22	288.8	0.58	0.17	0.0	0.2
SDDSC138	294.61	294.93	0.32	180	26.3	229.4
SDDSC138	294.93	295.47	0.54	2.76	1.1	4.8
SDDSC138	295.47	295.8	0.33	62.6	23.0	105.8
SDDSC138	295.8	296.31	0.51	0.7	0.3	1.3
SDDSC138	296.31	296.41	0.1	5.59	0.0	5.6
SDDSC138	296.41	297.11	0.7	0.65	0.0	0.7
SDDSC138	297.11	297.62	0.51	0.28	0.0	0.3
SDDSC138	297.62	297.95	0.33	2.95	0.0	3.0
SDDSC138	297.95	298.63	0.68	0.41	0.0	0.4
SDDSC138	298.63	299.45	0.82	0.1	0.0	0.1
SDDSC138	302.48	303.19	0.71	0.72	1.6	3.7
SDDSC138	303.19	303.52	0.33	0.68	0.2	1.0
SDDSC138	303.52	303.68	0.16	0.15	0.4	1.0
SDDSC138	306.68	306.82	0.14	0.5	0.0	0.6
SDDSC138	306.82	307.58	0.76	0.17	0.0	0.2

SDDSC138	308.54	309.82	1.28	0.15	0.0	0.2
SDDSC138	309.82	310.32	0.5	0.38	0.0	0.4
SDDSC138	310.32	311	0.68	0.06	0.0	0.1
SDDSC138	311	311.35	0.35	16.4	2.1	20.4
SDDSC138	311.35	312.09	0.74	0.37	0.1	0.5
SDDSC138	312.95	313.09	0.14	62.4	8.7	78.7
SDDSC138	313.09	314.03	0.94	0.29	0.0	0.4
SDDSC138	314.03	314.19	0.16	2.25	4.4	10.5
SDDSC138	314.19	314.4	0.21	4.37	1.5	7.1
SDDSC138	314.4	314.52	0.12	17.8	9.0	34.8
SDDSC138	314.52	315.03	0.51	2.67	0.4	3.4
SDDSC138	315.03	315.6	0.57	1.19	0.6	2.2
SDDSC138	315.6	315.83	0.23	1.87	0.9	3.5
SDDSC138	315.83	316.46	0.63	0.17	0.2	0.6
SDDSC138	316.46	316.94	0.48	0.24	0.4	1.1
SDDSC138	316.94	317.17	0.23	44.8	33.8	108.3
SDDSC138	317.17	317.58	0.41	3.52	3.6	10.3
SDDSC138	317.58	317.77	0.19	60.6	9.2	77.9
SDDSC138	317.77	318.39	0.62	0.55	0.2	1.0
SDDSC138	318.39	318.98	0.59	3.76	1.5	6.6
SDDSC138	318.98	319.11	0.13	51.1	10.6	71.0
SDDSC138	319.11	319.22	0.11	3.52	2.3	7.9
SDDSC138	319.22	319.62	0.4	0.17	0.1	0.4
SDDSC138	319.62	320	0.38	4.07	2.1	8.0
SDDSC138	320	320.33	0.33	0.74	0.3	1.4
SDDSC138	320.33	320.66	0.33	0.1	0.0	0.2
SDDSC138	320.66	321.75	1.09	0.15	0.0	0.2
SDDSC138	321.75	322.8	1.05	1.17	0.1	1.3
SDDSC138	322.8	322.91	0.11	0.88	3.3	7.0
SDDSC138	323.6	323.92	0.32	0.74	0.3	1.3
SDDSC138	324.82	325.05	0.23	0.11	0.0	0.1
SDDSC138	326.3	327.3	1	0.12	0.0	0.1
SDDSC138	328.06	328.51	0.45	1.79	0.5	2.7
SDDSC138	328.51	328.89	0.38	0.36	0.1	0.6
SDDSC138	329.51	330	0.49	0.28	0.0	0.3
SDDSC138	332.28	332.42	0.14	0.29	0.0	0.3
SDDSC138	335	335.25	0.25	0.34	0.0	0.4
SDDSC138	336.23	336.93	0.7	0.65	0.5	1.6
SDDSC138	336.93	337.69	0.76	0.23	0.1	0.5
SDDSC138	337.69	338.64	0.95	5.23	0.1	5.5
SDDSC138	338.64	339.22	0.58	4.65	0.0	4.7
SDDSC138	339.22	340	0.78	0.55	0.0	0.6
SDDSC138	340	341	1	0.17	0.1	0.3

SDDSC138	341	342.06	1.06	0.3	0.1	0.4
SDDSC138	342.06	342.3	0.24	0.36	0.6	1.4
SDDSC138	342.3	343.25	0.95	0.11	0.0	0.2
SDDSC138	345.55	345.94	0.39	0.92	0.1	1.2
SDDSC138	347.24	347.44	0.2	0.28	0.1	0.4
SDDSC138	348.47	348.66	0.19	2.3	0.0	2.3
SDDSC138	350	350.31	0.31	0.24	0.2	0.6
SDDSC138	350.31	351.34	1.03	0.19	0.0	0.2
SDDSC138	351.34	351.59	0.25	0.38	0.2	0.7
SDDSC138	351.59	352.55	0.96	1.14	0.5	2.1
SDDSC138	352.55	352.95	0.4	6.04	1.8	9.4
SDDSC138	352.95	353.6	0.65	1.94	0.4	2.7
SDDSC138	353.6	354	0.4	1.83	1.3	4.3
SDDSC138	354	354.71	0.71	3.66	1.4	6.2
SDDSC138	354.71	355.42	0.71	1.92	0.2	2.4
SDDSC138	355.42	355.7	0.28	2.82	0.8	4.3
SDDSC138	355.7	356	0.3	10.6	0.3	11.2
SDDSC138	356	356.62	0.62	0.53	0.3	1.1
SDDSC138	356.62	357.32	0.7	0.94	0.3	1.6
SDDSC138	357.32	358.33	1.01	0.09	0.0	0.1
SDDSC138	358.33	358.5	0.17	0.82	0.3	1.4
SDDSC138	358.5	359.4	0.9	0.25	0.1	0.4
SDDSC138	360.62	361	0.38	0.7	0.1	0.8
SDDSC138	361	361.5	0.5	0.62	0.0	0.7
SDDSC138	361.5	362.1	0.6	0.41	0.3	0.9
SDDSC138	362.1	362.65	0.55	0.87	0.2	1.2
SDDSC138	362.65	362.94	0.29	1.01	0.2	1.4
SDDSC138	362.94	364.06	1.12	0.27	0.4	1.0
SDDSC138	366.16	367.13	0.97	0.34	0.0	0.4
SDDSC138	367.13	367.45	0.32	0.39	0.2	0.7
SDDSC138	367.45	367.88	0.43	0.6	0.3	1.2
SDDSC138	367.88	367.98	0.1	13.9	0.8	15.5
SDDSC138	368.59	369.5	0.91	0.14	0.0	0.2
SDDSC138	369.5	370.22	0.72	2.86	0.3	3.4
SDDSC138	371.91	372.17	0.26	1.5	0.0	1.6
SDDSC138	372.17	373.21	1.04	0.11	0.0	0.1
SDDSC138	373.21	374.2	0.99	0.15	0.0	0.2
SDDSC138	375.84	376.52	0.68	0.25	0.0	0.3
SDDSC138	376.52	376.68	0.16	1.83	0.1	2.0
SDDSC138	376.68	377	0.32	2	0.1	2.2
SDDSC138	377.46	378.29	0.83	0.51	0.0	0.6
SDDSC138	378.29	379.24	0.95	0.28	0.1	0.4
SDDSC138	379.24	380	0.76	0.54	0.0	0.6

SDDSC138	380	380.64	0.64	0.3	0.4	1.0
SDDSC138	380.64	380.89	0.25	0.82	0.1	1.0
SDDSC138	380.89	381.6	0.71	1.11	1.4	3.7
SDDSC138	386.05	386.86	0.81	0.72	0.3	1.3
SDDSC138	386.86	387.62	0.76	0.33	0.0	0.4
SDDSC138	387.62	387.72	0.1	9.08	3.6	15.8
SDDSC138	387.72	388.49	0.77	1.12	0.2	1.5
SDDSC138	388.49	388.92	0.43	0.17	0.0	0.2
SDDSC138	392	392.97	0.97	0.23	0.0	0.3
SDDSC138	392.97	394.06	1.09	0.11	0.0	0.1
SDDSC138	395.18	396.27	1.09	0.25	0.0	0.3
SDDSC138	397.03	397.62	0.59	0.27	0.0	0.3
SDDSC138	397.62	398.33	0.71	0.58	0.0	0.6
SDDSC138	398.33	398.82	0.49	6.19	0.3	6.7
SDDSC138	398.82	399.23	0.41	0.97	0.2	1.3
SDDSC138	399.23	399.75	0.52	1.33	0.8	2.8
SDDSC138	400	400.1	0.1	0.37	0.0	0.4
SDDSC138	400.1	400.32	0.22	0.64	0.2	0.9
SDDSC138	400.32	401.29	0.97	0.31	0.1	0.4
SDDSC138	401.29	402.33	1.04	0.25	0.0	0.3
SDDSC138	402.33	402.87	0.54	3.21	0.4	3.9
SDDSC138	402.87	402.97	0.1	1.21	0.5	2.2
SDDSC138	402.97	403.38	0.41	0.32	0.0	0.4
SDDSC138	404.03	404.27	0.24	0.43	0.1	0.6
SDDSC138	404.27	405.21	0.94	0.12	0.0	0.2
SDDSC138	405.21	405.62	0.41	2.33	0.2	2.7
SDDSC138	405.62	405.99	0.37	1.12	1.4	3.8
SDDSC138	406.47	407.46	0.99	0.38	0.2	0.7
SDDSC138	407.46	408.23	0.77	0.8	0.2	1.2
SDDSC138	408.23	408.4	0.17	35.6	1.2	37.9
SDDSC138	408.4	408.69	0.29	0.84	0.4	1.6
SDDSC138	408.69	409.27	0.58	0.1	0.0	0.2
SDDSC138	409.27	409.37	0.1	49.5	1.8	52.8
SDDSC138	409.37	409.69	0.32	1.48	1.0	3.3
SDDSC138	409.69	410.23	0.54	0.06	0.0	0.1
SDDSC138	410.23	410.68	0.45	0.17	0.1	0.3
SDDSC138	410.68	411.56	0.88	0.64	0.0	0.7
SDDSC138	413.26	414	0.74	0.07	0.0	0.1
SDDSC138	414	414.38	0.38	17.4	1.4	20.1
SDDSC138	414.38	414.62	0.24	4.52	0.4	5.4
SDDSC138	414.62	415.07	0.45	2.73	0.9	4.5
SDDSC138	415.07	415.37	0.3	7.15	5.2	16.9
SDDSC138	415.37	415.68	0.31	1.76	0.1	2.0

SDDSC138	415.68	415.78	0.1	2.56	1.9	6.2
SDDSC138	415.78	416.3	0.52	0.97	0.6	2.0
SDDSC138	416.3	416.64	0.34	2.51	0.3	3.1
SDDSC138	416.64	416.96	0.32	0.79	0.1	1.0
SDDSC138	416.96	417.06	0.1	141	1.6	144.1
SDDSC138	417.06	417.16	0.1	15.4	0.4	16.1
SDDSC138	417.16	418	0.84	0.21	0.0	0.3
SDDSC138	418	418.23	0.23	0.41	0.1	0.6
SDDSC138	418.23	418.37	0.14	1.71	0.9	3.3
SDDSC138	418.37	419.26	0.89	0.56	0.1	0.7
SDDSC138	419.26	420.06	0.8	0.31	0.1	0.5
SDDSC138	420.06	420.39	0.33	2.32	1.7	5.6
SDDSC138	420.39	420.53	0.14	6.62	6.7	19.3
SDDSC138	420.53	420.91	0.38	1.02	1.4	3.7
SDDSC138	420.91	421.8	0.89	0.75	0.1	1.0
SDDSC138	421.8	421.9	0.1	6.74	11.2	27.8
SDDSC138	421.9	422.26	0.36	0.43	0.2	0.8
SDDSC138	422.26	422.67	0.41	6.63	4.5	15.1
SDDSC138	422.67	423.39	0.72	6.47	1.5	9.4
SDDSC138	423.39	423.85	0.46	1.23	0.8	2.7
SDDSC138	423.85	424.4	0.55	0.27	0.1	0.4
SDDSC138	424.4	424.5	0.1	15.9	6.9	28.8
SDDSC138	424.5	425.54	1.04	0.06	0.1	0.2
SDDSC138	426.68	427.55	0.87	0.06	0.0	0.1
SDDSC138	427.55	427.65	0.1	79.2	6.2	90.9
SDDSC138	427.65	427.94	0.29	0.44	0.1	0.5
SDDSC138	427.94	428.48	0.54	3.64	0.3	4.1
SDDSC138	428.48	428.64	0.16	25.6	11.3	46.8
SDDSC138	428.64	429.23	0.59	0.18	0.0	0.3
SDDSC138	429.23	430.16	0.93	0.33	0.1	0.4
SDDSC138	430.16	431	0.84	0.12	0.1	0.2
SDDSC138	433	434	1	0.15	0.0	0.2
SDDSC138	434	434.4	0.4	0.58	0.0	0.6
SDDSC138	434.4	434.57	0.17	1.35	0.0	1.4
SDDSC138	434.57	435.14	0.57	0.18	0.0	0.2
SDDSC138	435.14	435.24	0.1	0.85	11.1	21.7
SDDSC138	435.24	436.3	1.06	0.08	0.3	0.6
SDDSC138	439.32	440.02	0.7	1.46	0.1	1.7
SDDSC138	441	441.15	0.15	1.55	0.3	2.0
SDDSC138	441.15	441.53	0.38	0.31	0.0	0.4
SDDSC138	442.23	442.79	0.56	0.14	2.6	5.0
SDDSC138	442.79	443.81	1.02	-0.01	0.2	0.4
SDDSC138	445	445.24	0.24	36.6	0.1	36.7

SDDSC138	445.24	445.34	0.1	47.2	1.0	49.0
SDDSC138	445.34	446	0.66	1.53	0.2	1.8
SDDSC138	446	446.43	0.43	5.93	0.2	6.3
SDDSC138	446.43	446.69	0.26	183	10.8	203.3
SDDSC138	446.69	447.24	0.55	0.28	0.2	0.6
SDDSC138	447.24	448.15	0.91	0.12	0.0	0.1
SDDSC138	448.15	449.3	1.15	0.25	0.0	0.3
SDDSC138	449.3	450.31	1.01	0.13	0.1	0.2
SDDSC138	453.4	453.61	0.21	0.77	0.3	1.3
SDDSC138	453.61	453.71	0.1	0.43	0.4	1.1
SDDSC138	453.71	454.25	0.54	0.62	0.2	1.0
SDDSC138	454.25	455.16	0.91	0.59	0.1	0.7
SDDSC138	455.16	455.46	0.3	2.28	0.8	3.8
SDDSC138	455.46	456.73	1.27	0.18	0.0	0.2
SDDSC138	456.73	456.88	0.15	18.4	22.2	60.1
SDDSC138	456.88	457.12	0.24	0.26	0.1	0.5
SDDSC138	457.12	457.24	0.12	17.7	0.2	18.1
SDDSC138	457.24	457.77	0.53	2.55	0.9	4.3
SDDSC138	457.77	458.55	0.78	1.68	0.6	2.7
SDDSC138	458.55	458.81	0.26	2.28	17.2	34.6
SDDSC138	458.81	459.42	0.61	3.53	7.5	17.7
SDDSC138	459.42	460.11	0.69	0.78	0.0	0.9
SDDSC138	460.11	460.46	0.35	2.16	0.2	2.6
SDDSC138	460.46	461.02	0.56	0.52	0.0	0.6
SDDSC138	461.02	461.32	0.3	1.37	0.0	1.4
SDDSC138	461.32	461.71	0.39	0.13	0.0	0.2
SDDSC138	461.71	461.9	0.19	1.07	0.1	1.3
SDDSC138	462.9	464	1.1	0.25	0.0	0.3
SDDSC138	466.74	466.9	0.16	0.1	0.0	0.1
SDDSC138	468.1	469.12	1.02	0.13	0.0	0.2
SDDSC138	469.12	470.1	0.98	0.04	0.0	0.1
SDDSC138	470.1	470.5	0.4	0.13	0.1	0.3
SDDSC138	470.5	471.68	1.18	0.44	0.0	0.5
SDDSC138	471.68	471.82	0.14	0.52	1.0	2.4

JORC Table 1

Section 1 Sampling Techniques and Data

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (e.g. cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc.). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (e.g. 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (e.g. submarine nodules) may warrant disclosure of detailed information. 	<ul style="list-style-type: none"> Sampling has been conducted on drill core (half core for >90% and quarter core for check samples), grab samples (field samples of in-situ bedrock and boulders; including duplicate samples), trench samples (rock chips, including duplicates) and soil samples (including duplicate samples). Locations of field samples were obtained by using a GPS, generally to an accuracy of within 5 metres. Drill hole and trench locations have been confirmed to <1 metre using a differential GPS. Samples locations have also been verified by plotting locations on the high-resolution Lidar maps Drill core is marked for cutting and cut using an automated diamond saw used by Company staff in Kilmore. Samples are bagged at the core saw and transported to the Bendigo On Site Laboratory for assay. At On Site samples are crushed using a jaw crusher combined with a rotary splitter and a 1 kg split is separated for pulverizing (LM5) and assay. Standard fire assay techniques are used for gold assay on a 30 g charge by experienced staff (used to dealing with high sulphide and stibnite-rich charges). On Site gold method by fire assay code PE01S. Screen fire assay is used to understand gold grain-size distribution where coarse gold is evident. ICP-OES is used to analyse the aqua regia digested pulp for an additional 12 elements (method BM011) and over-range antimony is measured using flame AAS (method known as B050). Soil samples were sieved in the field and an 80 mesh sample bagged and transported to ALS Global laboratories in Brisbane for super-low level gold analysis on a 50 g samples by method ST44 (using aqua regia and ICP-MS). Grab and rock chip samples are generally submitted to On Site Laboratories for standard fire assay and 12 element ICP-OES as described above.
Drilling techniques	<ul style="list-style-type: none"> Drill type (e.g. core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc.) and details (e.g. core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc.). 	<ul style="list-style-type: none"> HQ diameter diamond drill core, oriented using Boart Longyear TruCore orientation tool with the orientation line marked on the base of the drill core by the driller/offsider. A standard 3 metre core barrel has been found to be most effective in both the hard and soft rocks in the project.
Drill sample recovery	<ul style="list-style-type: none"> Method of recording and assessing core and chip sample recoveries and results assessed. 	<ul style="list-style-type: none"> Core recoveries were maximised using HQ diamond drill core with careful control over water pressure to maintain soft-rock integrity and prevent loss of

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> Measures taken to maximise sample recovery and ensure representative nature of the samples. Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material. 	<p>finer from soft drill core. Recoveries are determined on a metre-by-metre basis in the core shed using a tape measure against marked up drill core checking against driller's core blocks.</p> <ul style="list-style-type: none"> Plots of grade versus recovery and RQD (described below) show no trends relating to loss of drill core, or fines.
Logging	<ul style="list-style-type: none"> Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies. Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc.) photography. The total length and percentage of the relevant intersections logged. 	<ul style="list-style-type: none"> Geotechnical logging of the drill core takes place on racks in the company core shed. Core orientations marked at the drill rig are checked for consistency, and base of core orientation lines are marked on core where two or more orientations match within 10 degrees. Core recoveries are measured for each metre RQD measurements (cumulative quantity of core sticks > 10 cm in a metre) are made on a metre-by-metre basis. Each tray of drill core is photographed (wet and dry) after it is fully marked up for sampling and cutting. The ½ core cutting line is placed approximately 10 degrees above the orientation line so the orientation line is retained in the core tray for future work. Geological logging of drill core includes the following parameters: Rock types, lithology Alteration Structural information (orientations of veins, bedding, fractures using standard alpha-beta measurements from orientation line; or, in the case of un-oriented parts of the core, the alpha angles are measured) Veining (quartz, carbonate, stibnite) Key minerals (visible under hand lens, e.g. gold, stibnite) 100% of drill core is logged for all components described above into the company MX logging database. Logging is fully quantitative, although the description of lithology and alteration relies on visible observations by trained geologists. Each tray of drill core is photographed (wet and dry) after it is fully marked up for sampling and cutting. Logging is considered to be at an appropriate quantitative standard to use in future studies.
Sub-sampling techniques and sample preparation	<ul style="list-style-type: none"> If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc. and whether sampled wet or dry. For all sample types, the nature, quality and appropriateness of the sample preparation technique. Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples. 	<ul style="list-style-type: none"> Drill core is typically half-core sampled using an Almonte core saw. The drill core orientation line is retained. Quarter core is used when taking sampling duplicates (termed FDUP in the database). Sampling representivity is maximised by always taking the same side of the drill core (whenever oriented), and consistently drawing a cut line on the core where orientation is not possible. The field technician draws these lines.

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. Whether sample sizes are appropriate to the grain size of the material being sampled. 	<ul style="list-style-type: none"> Sample sizes are maximised for coarse gold by using half core, and using quarter core and half core splits (laboratory duplicates) allows an estimation of nugget effect. In mineralised rock the company uses approximately 10% of ¼ core duplicates, certified reference materials (suitable OREAS materials), laboratory sample duplicates and instrument repeats. In the soil sampling program duplicates were obtained every 20th sample and the laboratory inserted low-level gold standards regularly into the sample flow.
Quality of assay data and laboratory tests	<ul style="list-style-type: none"> The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc., the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc. Nature of quality control procedures adopted (e.g. standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (i.e. lack of bias) and precision have been established. 	<ul style="list-style-type: none"> The fire assay technique for gold used by On Site is a globally recognised method, and over-range follow-ups including gravimetric finish and screen fire assay are standard. Of significance at the On Site laboratory is the presence of fire assay personnel who are experienced in dealing with high sulphide charges (especially those with high stibnite contents) – this substantially reduces the risk of in accurate reporting in complex sulphide-gold charges. The ICP-OES technique is a standard analytical technique for assessing elemental concentrations. The digest used (aqua regia) is excellent for the dissolution of sulphides (in this case generally stibnite, pyrite and trace arsenopyrite), but other silicate-hosted elements, in particular vanadium (V), may only be partially dissolved. These silicate-hosted elements are not important in the determination of the quantity of gold, antimony, arsenic or sulphur. A portable XRF has been used in a qualitative manner on drill core to ensure appropriate core samples have been taken (no pXRF data are reported or included in the MX database). Acceptable levels of accuracy and precision have been established using the following methods <ul style="list-style-type: none"> <i>¼ duplicates</i> – half core is split into quarters and given separate sample numbers (commonly in mineralised core) – low to medium gold grades indicate strong correlation, dropping as the gold grade increases over 40 g/t Au. <i>Blanks</i> – blanks are inserted after visible gold and in strongly mineralised rocks to confirm that the crushing and pulping are not affected by gold smearing onto the crusher and LM5 swing mill surfaces. Results are excellent, generally below detection limit and a single sample at 0.03 g/t Au. <i>Certified Reference Materials</i> – OREAS CRMs have been used throughout the project including blanks, low (<1 g/t Au), medium (up to 5 g/t Au) and high-grade gold samples (> 5 g/t Au). Results are automatically checked on data import into the MX database to fall within 2 standard deviations of the expected value. <i>Laboratory splits</i> – On Site conducts splits of both coarse crush and pulp

Criteria	JORC Code explanation	Commentary
		<p>duplicates as quality control and reports all data. In particular, high Au samples have the most repeats.</p> <p><i>Laboratory CRMs</i> – On Site regularly inserts their own CRM materials into the process flow and reports all data</p> <p><i>Laboratory precision</i> – duplicate measurements of solutions (both Au from fire assay and other elements from the aqua regia digests) are made regularly by the laboratory and reported.</p> <ul style="list-style-type: none"> • <i>Accuracy and precision</i> have been determined carefully by using the sampling and measurement techniques described above during the sampling (accuracy) and laboratory (accuracy and precision) stages of the analysis. • <i>Soil sample</i> company duplicates and laboratory certified reference materials all fall within expected ranges.
<p>Verification of sampling and assaying</p>	<ul style="list-style-type: none"> • <i>The verification of significant intersections by either independent or alternative company personnel.</i> • <i>The use of twinned holes.</i> • <i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i> • <i>Discuss any adjustment to assay data.</i> 	<ul style="list-style-type: none"> • The Independent Geologist has visited Sunday Creek drill sites and inspected drill core held at the Kilmore core shed. • Visual inspection of drill intersections matches both the geological descriptions in the database and the expected assay data (for example, gold and stibnite visible in drill core is matched by high Au and Sb results in assays). • In addition, on receipt of results Company geologists assess the gold, antimony and arsenic results to verify that the intersections returned expected data. • The electronic data storage in the MX database is of a high standard. Primary logging data are entered directly by the geologists and field technicians and the assay data are electronically matched against sample number on return from the laboratory. • Certified reference materials, ¼ core field duplicates (FDUP), laboratory splits and duplicates and instrument repeats are all recorded in the database. • Exports of data include all primary data, from hole SDDSC077B onwards after discussion with SRK Consulting. Prior to this gold was averaged across primary, field and lab duplicates. • Adjustments to assay data are recorded by MX, and none are present (or required). • Twinned drill holes are not available at this stage of the project.
<p>Location of data points</p>	<ul style="list-style-type: none"> • <i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i> • <i>Specification of the grid system used.</i> • <i>Quality and adequacy of topographic control.</i> 	<ul style="list-style-type: none"> • Differential GPS used to locate drill collars, trenches and some workings • Standard GPS for some field locations (grab and soils samples), verified against Lidar data. • The grid system used throughout is Geocentric datum of Australia 1994; Map Grid Zone 55 (GDA94_Z55), also referred to as ELSG 28355. • Topographic control is excellent owing to sub 10 cm accuracy from Lidar data.

Criteria	JORC Code explanation	Commentary
Data spacing and distribution	<ul style="list-style-type: none"> • <i>Data spacing for reporting of Exploration Results.</i> • <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i> • <i>Whether sample compositing has been applied.</i> 	<ul style="list-style-type: none"> • The data spacing is suitable for reporting of exploration results – evidence for this is based on the improving predictability of high-grade gold-antimony intersections. • At this time, the data spacing and distribution are not sufficient for the reporting of Mineral Resource Estimates. This however may change as knowledge of grade controls increase with future drill programs. • Sample compositing has not been applied to the reporting of any drill results.
Orientation of data in relation to geological structure	<ul style="list-style-type: none"> • <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i> • <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i> 	<ul style="list-style-type: none"> • The true thickness of the mineralised intervals reported are interpreted to be approximately 60-70% of the sampled thickness. • Drilling is oriented in an optimum direction when considering the combination of host rock orientation and apparent vein control on gold and antimony grade. The steep nature of some of the veins may give increases in apparent thickness of some intersections, but more drilling is required to quantify. • A sampling bias is not evident from the data collected to date (drill holes cut across mineralised structures at a moderate angle).
Sample security	<ul style="list-style-type: none"> • <i>The measures taken to ensure sample security.</i> 	<ul style="list-style-type: none"> • Drill core is delivered to the Kilmore core logging shed by either the drill contractor or company field staff. Samples are marked up and cut by company staff at the Kilmore core shed, in an automated diamond saw and bagged before loaded onto strapped secured pallets and trucked by commercial transport to Bendigo for submission to the laboratory. There is no evidence in any stage of the process, or in the data for any sample security issues.
Audits or reviews	<ul style="list-style-type: none"> • <i>The results of any audits or reviews of sampling techniques and data.</i> 	<ul style="list-style-type: none"> • Continuous monitoring of CRM results, blanks and duplicates is undertaken by geologists and the company data geologist. Mr Michael Hudson for SXG has the orientation, logging and assay data.

Section 2 Reporting of Exploration Results

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	<ul style="list-style-type: none"> Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	<ul style="list-style-type: none"> The Sunday Creek Goldfield, containing the Clonbinane Project, is covered by the Retention Licence RL 6040 and is surrounded by Exploration Licence EL6163 and Exploration Licence EL7232. All the licences are 100% held by Clonbinane Goldfield Pty Ltd, a wholly owned subsidiary company of Southern Cross Gold Ltd.
Exploration done by other parties	<ul style="list-style-type: none"> Acknowledgment and appraisal of exploration by other parties. 	<ul style="list-style-type: none"> The main historical prospect within the Sunday Creek project is the Clonbinane prospect, a high level orogenic (or epizonal) Fosterville-style deposit. Small scale mining has been undertaken in the project area since the 1880s continuing through to the early 1900s. Historical production occurred with multiple small shafts and alluvial workings across the Clonbinane Goldfield permits. Production of note occurred at the Clonbinane area with total production being reported as 41,000 oz gold at a grade of 33 g/t gold (Leggo and Holdsworth, 2013) Work in and nearby to the Sunday Creek Project area by previous explorers typically focused on finding bulk, shallow deposits. Beadell Resources were the first to drill deeper targets and Southern Cross have continued their work in the Sunday Creek Project area. EL54 - Eastern Prospectors Pty Ltd Rock chip sampling around Christina, Apollo and Golden Dyke mines. Rock chip sampling down the Christina mine shaft. Resistivity survey over the Golden Dyke. Five diamond drill holes around Christina, two of which have assays. ELs 872 & 975 - CRA Exploration Pty Ltd Exploration focused on finding low grade, high tonnage deposits. The tenements were relinquished after the area was found to be prospective but not economic. Stream sediment samples around the Golden Dyke and Reedy Creek areas. Results were better around the Golden Dyke. 45 dump samples around Golden Dyke old workings showed good correlation between gold, arsenic and antimony. Soil samples over the Golden Dyke to define boundaries of dyke and mineralisation. Two costeans parallel to the Golden Dyke targeting soil anomalies. Costeans since rehabilitated by SXG. ELs 827 & 1520 - BHP Minerals Ltd Exploration targeting open cut gold mineralisation peripheral to SXG tenements. ELs 1534, 1603 & 3129 - Ausminde Holdings Pty Ltd

Criteria	JORC Code explanation	Commentary
		<p>Targeting shallow, low grade gold. Trenching around the Golden Dyke prospect and results interpreted along with CRAs costeans. 29 RC/Aircore holes totalling 959 m sunk into the Apollo, Rising Sun and Golden Dyke target areas.</p> <p>ELs 4460 & 4987 - Beadell Resources Ltd</p> <ul style="list-style-type: none"> • ELs 4460 & 4987 - Beadell Resources Ltd ELs 4460 and 4497 were granted to Beadell Resources in November 2007. Beadell successfully drilled 30 RC holes, including second diamond tail holes in the Golden Dyke/Apollo target areas. • Both tenements were 100% acquired by Auminco Goldfields Pty Ltd in late 2012 and combined into one tenement EL4987. • Nagambie Resources Ltd purchased Auminco Goldfields in July 2014. EL4987 expired late 2015, during which time Nagambie Resources applied for a retention licence (RL6040) covering three square kilometres over the Sunday Creek Goldfield. RL6040 was granted July 2017. • Clonbinane Gold Field Pty Ltd was purchased by Mawson Gold Ltd in February 2020. Mawson drilled 30 holes for 6,928 m and made the first discoveries to depth.
Geology	<ul style="list-style-type: none"> • <i>Deposit type, geological setting and style of mineralisation.</i> 	<ul style="list-style-type: none"> • Refer to the description in the main body of the release.
Drill hole Information	<ul style="list-style-type: none"> • <i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> <ul style="list-style-type: none"> ○ <i>easting and northing of the drill hole collar</i> ○ <i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> ○ <i>dip and azimuth of the hole</i> ○ <i>down hole length and interception depth</i> ○ <i>hole length.</i> • <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i> 	<ul style="list-style-type: none"> • Refer to appendices
Data aggregation methods	<ul style="list-style-type: none"> • <i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high-grades) and cut-off grades are usually Material and should be stated.</i> • <i>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for</i> 	<ul style="list-style-type: none"> • See “Further Information” and “Metal Equivalent Calculation” in main text of press release.

Criteria	JORC Code explanation	Commentary																		
	<p>such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</p> <ul style="list-style-type: none"> The assumptions used for any reporting of metal equivalent values should be clearly stated. 																			
Relationship between mineralisation widths and intercept lengths	<ul style="list-style-type: none"> These relationships are particularly important in the reporting of Exploration Results. If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported. If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (e.g 'down hole length, true width not known'). 	<ul style="list-style-type: none"> See reporting of true widths in the body of the press release. 																		
Diagrams	<ul style="list-style-type: none"> Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views. 	<ul style="list-style-type: none"> The results of the diamond drilling are displayed in the figures in the announcement. 																		
Balanced reporting	<ul style="list-style-type: none"> Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high-grades and/or widths should be practiced to avoid misleading reporting of Exploration Results. 	<ul style="list-style-type: none"> All results above 0.1 g/t Au have been tabulated in this announcement. The results are considered representative with no intended bias. Core loss, where material, is disclosed in tabulated drill intersections. 																		
Other substantive exploration data	<ul style="list-style-type: none"> Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances. 	<ul style="list-style-type: none"> Previously reported diamond drill results are displayed in plans, cross sections and long sections and discussed in the text and in the Competent Person's statement. Preliminary testing (AMML Report 1801-1) has demonstrated the viability of recovering gold and antimony values to high value products by industry standard processing methods. The program was completed by AMML, an established mineral and metallurgical testing laboratory specialising in flotation, hydrometallurgy, gravity and comminution testwork at their testing facilities in Gosford, NSW. The program was supervised by Craig Brown of Resources Engineering & Management, who was engaged to develop plans for initial sighter flotation testing of samples from drilling of the Sunday Creek deposit. Two quarter core intercepts were selected for metallurgical test work (Table 1). A split of each was subjected to assay analysis. The table below shows samples selected for metallurgical test work: <table border="1"> <thead> <tr> <th>Sample Location</th> <th>Sample Name</th> <th>Weight (kg)</th> <th>Drill hole</th> <th>from (m)</th> <th>to (m)</th> </tr> </thead> <tbody> <tr> <td>Rising Sun</td> <td>RS01</td> <td>22.8</td> <td>MDDSC025</td> <td>275.9</td> <td>289.3</td> </tr> <tr> <td>Apollo</td> <td>AP01</td> <td>16.6</td> <td>SDDSC031</td> <td>220.4</td> <td>229.9</td> </tr> </tbody> </table>	Sample Location	Sample Name	Weight (kg)	Drill hole	from (m)	to (m)	Rising Sun	RS01	22.8	MDDSC025	275.9	289.3	Apollo	AP01	16.6	SDDSC031	220.4	229.9
Sample Location	Sample Name	Weight (kg)	Drill hole	from (m)	to (m)															
Rising Sun	RS01	22.8	MDDSC025	275.9	289.3															
Apollo	AP01	16.6	SDDSC031	220.4	229.9															

Criteria	JORC Code explanation	Commentary
		<p>The metallurgical characterisation test work included:</p> <ul style="list-style-type: none"> • Diagnostic LeachWELL testing. • Gravity recovery by Knelson concentrator and hand panning. • Timed flotation of combined gravity tails. • Rougher-Cleaner flotation (without gravity separation), with sizing of products, to produce samples for mineralogical investigation. • Mineral elemental concentrations and gold department was investigated using Laser Ablation examination by University of Tasmania. • QXRD Mineralogical assessment were used to estimate mineral contents for the test products, and, from this, to assess performance in terms of minerals as well as elements, including contributions to gold department. For both test samples, observations and calculations indicated a high proportion of native ('free') gold: 84.0% in RS01 and 82.1% in AP01. • Samples of size fractions of the three sulphide and gold containing flotation products from the Rougher-Cleaner test series were sent to MODA Microscopy for optical mineralogical assessment. Key observations were: <ul style="list-style-type: none"> ○ The highest gold grade samples from each test series found multiple grains of visible gold which were generally liberated, with minor association with stibnite (antimony sulphide). ○ Stibnite was highly liberated and was very 'clean' – 71.7% Sb, 28.3% S. ○ Arsenopyrite was also highly liberated indicating potential for separation. ○ Pyrite was largely free but exhibited some association with gangue minerals.
<p>Further work</p>	<ul style="list-style-type: none"> • <i>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> • <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i> 	<ul style="list-style-type: none"> • The Company drilled 30,000 m in 2023 and plans to continue drilling with 5 diamond drill rigs. The Company has stated it will drill 60,000 m from 2023 to Q4 2025. The company remains in an exploration stage to expand the mineralisation along strike and to depth. • See diagrams in presentation which highlight current and future drill plans.